



Supporting Information

Table: Results of EDAX analysis for $M_{0.5}Bi_3P_2O_{10}$

	M%	Bi%	P%
0.5M : 3Bi : 2P	9.1	54.5	36.4
$Ca_{0.5}Bi_3P_2O_{10}$	8.5	57.5	34.0
$Sr_{0.5}Bi_3P_2O_{10}$	9.0	54.0	35.2
$Ba_{0.5}Bi_3P_2O_{10}$	9.0	54.0	37.0
$Pb_{0.5}Bi_3P_2O_{10}$	10.5	53.5	36.0



ORTEP of $\text{Ca}_{0.5}\text{Bi}_3\text{P}_2\text{O}_{10}$ (50% probability)



ORTEP of $\text{Sr}_{0.5}\text{Bi}_3\text{P}_2\text{O}_{10}$ (50% probability)

