

Supplementary Material

Structural parameters for $\text{Ga}_2\text{O}_3(\text{ZnO})_6$.

	x	y	z	$U_{\text{iso}}/U_{\text{eq}}$	Occ. ($<_1$)
M_1	o	0.00986(5)	0.06901(4)	0.0121(2)	
M_2	o	0.13506(5)	0.61698(4)	0.0102(2)	
M_3	o	0.12576(7)	0.75	0.0085(3)	
M_4	o	0.38720(4)	0.00459(4)	0.01131(17)	
M_5	o	0.36650(5)	0.62690(5)	0.0157(2)	
M_6	o	0.51297(4)	0.68246(4)	0.00981(18)	
M_7	o	0.36488(12)	0.75	0.0111(6)	0.528(4)
M_8	o	0.10969(19)	0.2564(4)	0.0311(19)	0.236(2)
M_9	o	0.24094(4)	0.05420(4)	0.01102(19)	
M_{10}	o	0.25526(5)	0.18559(4)	0.0103(2)	
O_1	o	0.4363(3)	0.5721(3)	0.0163(13)	
O_2	o	0.4327(4)	0.25	0.0105(16)	
O_3	o	0.0409(2)	0.8579(2)	0.0121(11)	
O_4	o	0.0698(3)	0.5254(3)	0.030(2)	
O_5	0.066(3)	0.4167(4)	0.8083(3)	0.025(2)	0.5
O_6	o	0.3322(3)	0.0831(2)	0.0178(14)	
O_7	o	0.1990(4)	0.25	0.020(2)	
O_8	o	0.1901(3)	0.1255(2)	0.0128(12)	
O_9	o	0.2979(2)	0.5265(3)	0.0198(15)	
O_{10}	o	0.1888(2)	0.6871(2)	0.0094(12)	