




JOURNAL OF  
APPLIED  
CRYSTALLOGRAPHY

**Volume 52 (2019)**

**Supporting information for article:**

**An Electrochemical Cell for *Operando* Bench-Top X-Ray Diffraction**

**Jonas Sottmann, Valérie Pralong, Nicolas Barrier and Christine Martin**



- 1** Results of Rietveld fit of pristine  $\text{LiMn}_2\text{O}_4$  [ $a = 8.2429(4)$  Å, space group  $Fd-3m$ ] in the *operando* cell with glassy carbon (Sigradur-G) window ( $R_p = 2.49\%$ ,  $R_{wp} = 3.30\%$ ,  $R_{exp} = 3.61\%$ ).