



JOURNAL OF
APPLIED
CRYSTALLOGRAPHY

Volume 55 (2022)

Supporting information for article:

Structure analysis of a buried interface between organic and porous inorganic layers using spin-contrast-variation neutron reflectivity

Takayuki Kumada, Daisuke Miura, Kazuhiro Akutsu, Kazuki Ohishi, Toshiaki Morikawa, Yukihiro Kawamura, Jun-ichi Suzuki, Takayuki Oku and Naoya Torikai

Supporting information

Table S1 Thickness, SLD, and surface and interface roughness for the MOTOFIT

simulation in Fig. 1.

	Thickness (nm)	SLD ($\times 10^{10} \text{ cm}^{-2}$)			Roughness (nm)
		UNR	PNR	NNR	
Liq. He			0.72		
Resin	198.0	1.20	3.50	-1.13	0.5
MePDS	63.7	1.46	2.50	0.48	1.8
SiO ₂	0.641		3.47		0.85
Si			2.07		0.85

Table S2 Thickness, SLD, and surface and interface roughness for the MOTOFIT

simulation in Fig. 4.

	Thickness (nm)	SLD ($\times 10^{10} \text{ cm}^{-2}$)			Roughness (nm)
		UNR	PNR	NNR	
Liq. He			0.72		
Resin	198.0	1.20	3.50	-1.13	1.2
* ¹ MePDS	2.5	0.95	1.63	0.34	0.3
MePDS	65.4	1.46	2.50	0.48	1.2
SiO ₂	0.391		3.47		0.3
Si	-		2.07		0.3

*¹ Near the interface with the resin layer