



Fig. S2. Variable-temperature powder X-ray diffractograms for the transformation of the zinc glycine ionic complex tetraaquabis(glycine-*O*)zinc(II) hexaaquazinc(II) bis(sulfate) to the zinc form of complex (I) at *ca* 343 K, followed by the transformation to the zinc form of complex (II) at *ca* 393 K.