Study on the Formation of Cs-U-O from the Reaction between Cs₂O and UO₂†

JONG-GOO KIM*, EUNSIL JANG, YANG-SOON PARK, YEONG-KEONG HA and KYUSEOK SONG

Nuclear Chemistry Research Division, Korea Atomic Energy Research Institute, Daedeok-daero 989-111, Yuseong-gu, Daejeon 305-353, Republic of Korea

*Corresponding author: Fax: +82 42 868 8148; E-mail: njgkim@kaeri.re.kr

AJC-13634

Reactions between UO₂ and Cs₂O in various Cs/U compounds (atom ratios: 0.5~3.0) were investigated in a temperature range of 30 to 1100 °C using a thermogravimetric analyzer and differential scanning calorimeter. The formation of Cs-U-O was determined by the appearance of exothermic peaks at 186 °C and 240 °C in differential scanning calorimeter and weight loss depending on the Cs/U ratio from 200 °C to 250 °C and from 610 °C to 710 °C when using a TGA. By chemical analysis, it was determined that the formation of Cs-U-O increased linearly with the Cs/U ratio. From X-ray diffractometer measurements, diffraction patterns of Cs₂UO₄ and Cs₂U₂O₇ were observed when heated to 500 °C and 1100 °C, respectively.

Key Words: UO₂, Cs₂O, Formation of Cs-U-O, TGA-DSC, XRD.

INTRODUCTION

Cs-U-O compounds (cesium uranates) have been observed at the periphery of irradiated nuclear fuels by scanning electron microscopy and electron probe micro analysis mapping of Cs and U¹. Cs-U-O compounds were generally found at the region where local burnup increased strongly. Furthermore, the fuel chemistry of Cs-U-O has become a matter of concern because of the current trend of high burnup operations of power plants. According to a report concerning the chemistry of the fuel periphery of UO₂, Cs₂UO₄ was synthesized to investigate the properties of Cs-U-O through reactions between cesium oxides or carbonate and U₃O₈ or UO₃, where the oxidation state of U was high². In this work, as a different trial, reactions using UO₂ as a reactant against Cs₂O were traced for samples of various Cs/U compounds (atom ratio) by measuring the weight variance and heat flow using TGA and DSC. Through chemical analysis and XRD measurements, the extent of the formation of Cs-U-O and the patterns of phases for the samples from the reactions were obtained.

EXPERIMENTAL

Preparation of the samples for the reaction between Cs₂O and UO₂: UO₂ powder, which was ground well with an agate mortar, was used and particle sizes of the UO₂ powder were observed to be within the range of 2 to 5 μm by SEM.

Cs₂O was a product of the supplier (Aldrich, metallic impurities < 1 %). The calculated amounts of Cs₂O and UO₂ were ground and blended thoroughly in an agate mortar to give a certain Cs/U (atom ratio) value in which the Cs/U compounds ranged from 0.5 to 3. Because of the high hygroscopic property of Cs₂O, the above works were all conducted in a glove box and the humidity was controlled at 0 %.

Measurement of the reaction between Cs₂O and UO₂:

The thermal properties, *i.e.*, the weight variance and heat flow during heating from 30 to 1100 °C, for the blended samples of various Cs/U compounds (0.5, 1.0, 1.5, 2.0, 2.5 and 3.0), which were prepared as described above, were measured using TGA-DSC (Scinco 1500) in a continuous argon flow and at a heating rate of 5 °C/min.

Determination of the formation extent of Cs-U-O by chemical analysis: Cs-U-O compounds dissolve well in an aqueous solution of approximately pH 2. However, UO₂ does not dissolve as well in this type of solution. The samples that were heated during the TGA-DSC measurement were treated using a pH-2 solution to dissolve and separate the U ions from unreacted UO₂. Additionally, the concentrations of uranium ion that were dissolved in the pH-2 solution were determined using an inductively coupled plasma-atomic emission spectrometer (ICP-AES) and corresponded to the extent of the formation of Cs-U-O that was produced through the reaction between Cs₂O and UO₂.

†Presented to the 4th International Symposium on Applications of Chemical and Analytical Technologies in Nuclear Industries, Daejeon, Korea

Phase characterization: To obtain phase information on the Cs-U-O that was formed through the reaction, the sample of Cs/U=2 that was heated during the TG-DSC was measured using a Siemens D5000 X-ray diffractometer with a scanning step of 0.02° for 10 s at each count in the range of 15° to 90° .

RESULTS AND DISCUSSION

Measurement of the reaction between Cs_2O and UO_2 :

The heat flow curves from DSC for the blended samples of various Cs/U compounds are shown in Fig. 1 and they include those for each of the individual reactants, Cs_2O and UO_2 , for a comparison with the blended samples. In Fig. 1, a common exothermic peak near 186°C for all blended samples and an exothermic peak near 240°C for the samples with higher Cs/U ratios than 2 are shown. However, only the endothermic peaks at 186°C and 244°C for the Cs_2O sample disappear. The disappearance of the peaks at 186°C and 244°C (for only the Cs_2O sample) and the appearance of the peaks near 186°C and 240°C (for all blended samples) in Fig. 1 could be evidence for the formation of Cs-U-O through the reaction between Cs_2O and UO_2 . However, the exact interpretation for each individual peak in connection with the reaction process of Cs_2O and UO_2 is not simple because the reaction between Cs_2O and UO_2 is not currently well understood.

Fig. 1. Heat flow curves of DSC measurements for the reaction between Cs_2O and UO_2

Fig. 2 shows thermogravimetric curves for the blended samples of various Cs/U compounds and for each of the individual reactants, Cs_2O and UO_2 . The first interesting aspect in Fig. 2 is the curve for only Cs_2O . This curve shows a slight weight loss in the region from 200 to 300°C and remarkable weight loss from 610 to 710°C . According to previous literature³, the first, slight weight loss should be caused by evaporation of Cs_2O and the cause of the large weight loss should be evaporation of Cs_2O_2 (b.p., 650°C) and Cs (b.p., 669.3°C), which are the decomposed products of Cs_2O through the equation, $2\text{Cs}_2\text{O} \rightarrow 2\text{Cs} + \text{Cs}_2\text{O}_2$ at temperatures above 400°C . The thermogravimetric curves for the blended samples show comparable shapes in some aspects to that for only Cs_2O . First, the slight weight loss for the blended samples occurs

from 200 to 250°C , which is a shorter temperature interval compared to that for only Cs_2O , which ranges from 200 to 300°C . Additionally, if the temperature interval from 200 to 250°C for slight weight loss, as seen in Fig. 2, is considered with the exothermic peaks at 186°C and 240°C for the blended samples in Fig. 1, the slight weight loss for the blended samples in that temperature interval could be connected to the formation of Cs-U-O through the reaction between Cs_2O and UO_2 . Secondly, in Fig. 2, unlike Cs_2O , the curves for the blended samples do not show any weight loss at 610°C . Meanwhile, a small amount of weight loss appears in the cases with Cs/U ratios that are higher than 2. It can be inferred from the lack of weight loss for the blended samples, which are mixtures of Cs_2O and UO_2 , that Cs_2O in the blended samples is consumed by the reaction with UO_2 and no additional Cs_2O is decomposed. The weight loss for the blended samples with Cs/U ratios that are higher than 2 is thought to be caused by an excess amount of Cs_2O to that of UO_2 in the reaction between those two reactants. The curve for only UO_2 does not show any weight gain by oxygen, despite UO_2 being easily oxidized by oxygen at temperatures near 150°C ⁴ and from this result, it is confirmed that the oxygen content in the heating environment of the instrument (TGA-DSC) is sufficiently low even at high temperatures of up to 1100°C and do not interfere with the oxygen oxidation reaction of Cs_2O and UO_2 .

Fig. 2. Thermogravimetric measurements for the reaction between Cs_2O and UO_2

Formation extent of Cs-U-O depending on the Cs/U that is added: The formation extent of Cs-U-O, which was obtained by the chemical analysis of the U concentration as described before was plotted against the Cs/U ratio (Fig. 3), where the formation extent was $U_{\text{dissolved}}/U_{\text{Initial}}$ ($U_{\text{dissolved}}$: the total amount of U that was dissolved by the pH-2 solution; U_{Initial} : the total amount of U that was initially added to the blended samples). Fig. 3 shows a linear relationship between the Cs/U ratio and the extent of formation of Cs-U-O, which means that the formation of Cs-U-O increased linearly with the Cs/U ratio. In Fig. 3, the extent of formation reached near 100 % when Cs/U was 3. This result suggests the possibility that Cs_3UO_x is the formula of cesium uranate that is formed through

the reaction. However, any cesium uranate of $\text{Cs}/\text{U} = 3$ in the formula has not been reported in the literature and it is difficult to determine the possibility of the formula of Cs_3UO_x with only the present result. Regarding the above results, it can be assumed that some portion of the total added amount of Cs_2O into the blended samples would be consumed through other paths other than it reacting with UO_2 . Therefore, more Cs_2O would be needed to complete (meaning 100 % of the extent of formation) of the reaction with UO_2 and, consequently, could give a higher Cs/U value than the real state when calculating the formula of Cs-U-O that is formed.

Fig. 3. Formation extent of Cs-U-O depending on the Cs/U ratio of the blended samples

Phase characterization: From the XRD measurements for the samples that were heated at 500 °C and 1100 °C as shown in Fig. 4, the diffraction patterns of Cs_2UO_4 at 500 °C and $\text{Cs}_2\text{U}_2\text{O}_7$ at 1100 °C were observed. It was found that Cs_2O could react with UO_2 to produce Cs_2UO_4 , which is a well-known cesium uranate, when heated to 500 °C. The phase $\text{Cs}_2\text{U}_2\text{O}_7$ at 1100 °C is thought to result from the reported reaction²:

Fig. 4. XRD patterns for the reaction products of Cs_2O and UO_2

Conclusion

The appearance of exothermic peaks at 186 and 240 °C from DSC and the weight loss depending on the Cs/U ratio from 200 to 250 °C and from 610 to 710 °C from TGA could be evidence for the formation of Cs-U-O resulting from the reaction between Cs_2O and UO_2 . Through chemical analysis, it was determined that the formation of Cs-U-O increased linearly with the Cs/U ratio. From diffraction patterns, it was shown that Cs_2UO_4 was produced when the blended sample of $\text{Cs}/\text{U}=2$ was heated to 500 °C and $\text{Cs}_2\text{U}_2\text{O}_7$ was produced from the same sample, when it was heated to 1100 °C.

ACKNOWLEDGEMENTS

This work was supported by the National Research Foundation of Korea (NRF) grant funded by the Korea Government.

REFERENCES

1. S. van den Berghe, A. Leenaers, B. Vos, L. Sannen and M. Verwerft, Observation of a Pellet-cladding Bonding layer in High-power Fuel, Seminar Proceedings, Pellet-clad Interaction in Water Reactor Fuels, Aix-en-Provence, France, March 9-11, OECD-NEA No.60042004, pp. 265-272 (2005).
2. Chemistry of the UO_2 Fuel Periphery-Properties of Cs-U-O Compounds, Institute for Transuranium Elements Annual Report, EUR15154EN, 124 (1992).
3. Caesium, DOE Scientific and Technical information, Office of Scientific and Technical Information, U.S. Department of Energy (2009).
4. J.-G. Kim, Y.-K. Ha, S.-D. Park, K.-Y. Jee and W.-H. Kim, *J. Nucl. Mater.*, **297**, 327 (2001).