Effect of Phase Transitions Between α -Tricalcium Phosphate and β -Tricalcium Phosphate on the Setting Properties of Novel Strontium-Containing Bioactive Bone Cement

ZHAOYAO SUN^{1,†}, YUANFEI FU^{2,†} and DEMIN CHEN^{1,*}

¹Shanghai Biomaterials Research & Testing Center, Shanghai Key Laboratory of Stomatology, Ninth People's Hospital, Shanghai Jiaotong University School of Medicine, No. 427, Ju-men Road, Shanghai 200023, P.R. China

²Department of Prosthodontics, School of Stomatology, Ninth People's Hospital, School of Medicine, Shanghai Jiao Tong University, No. 639 Zhizaoju Road, Shanghai 200011, P.R. China

*Corresponding author: Fax: +86 21 63011643; Tel: +86 21 63034903; E-mail: chendemin9999@163.com

†The two authors made equal contribution to the paper

(Received: 31 January 2012;

Accepted: 12 December 2012)

AJC-12525

In this study, the influence of series of strontium substitutions on bioactive polymeric calcium phosphate cements has been evaluated in the present work. The cements were derived from a liquids that consisted of polycarboxylic acid (PCA), citric acid, potassium citrate and a calcium phosphate cement (CPC) powder that consisted of strontium-containing tricalcium phosphate (TCP) and hydroxyapatite (HA) which is proved by the XRD and FTIR. A series of strontium-containing α -TCP/HA biphasic cement is prepared successfully. But the cement powder group of 20 atom % strontium amount was composition of β -TCP/HA biphasic and did not set with the liquids.

Key Words: α -Tricalcium Phosphate, β -Tricalcium Phosphate, Strontium, Bioactive bone cement, Phase transition setting.

INTRODUCTION

Calcium phosphate cements (CPCs) have been developed with good biocompatibility and bioactivity, which has received much attention in recently years¹. All kinds of cements with different compositions have been prepared in order to conquer the disadvantages of traditional used polymethyl methacrylate (PMMA) bone cements, because of its non-degradable and non-resorbable properties, fast exothermic reaction, cardio-pulmonary complications and aseptic loosening induced by its lack of adhesiveness to bone tissue^{2,3,4}. On the other hand, the beneficial effect of strontium element by reduction of bone resorption and stimulation of bone formation has been recognized in the treatment of osteoporosis, especially senile⁵. In human tissue, strontium ion shares the similar physiological pathway as calcium ion and the substitution of calcium by strontium in apatite will cause lattice expansion due to the larger atomic radius of Sr than that of Ca, which alters the physicochemical property and biocompatibility of the bioactive bone cement^{6,7}. Recent developments have focused on injectable calcium phosphate cements for various applications in treatment of vertebral compression fractures or bone defects, but most of these bone cement have weak mechanical properties. Polymeric calcium phosphate cement having good mechanical properties (compressive strengths 50-80 MPa)

similar to zinc polycarboxylate cements which would be worthy of further investigation⁸.

In the present study, the effect of various additives, citric acid, potassium citrate, strontium carbonate on the properties of the polycarboxylic acid-calcium phosphate cement bone cement were investigated in the hope of obtaining polyacid-calcium phosphate cements with more suitable bioactive and mechanical properties. Containing strontium 0, 5, 10, 15 and 20 atom % bioactive bone cement were prepared. But there was an interesting phenomena *i.e.*, the setting of the cement pastes occurred in several minutes except the 20 atom % Sr/(Sr + Ca) sample which did not set even in 6 h. Therefore, the main goal of the present study was to investigate the influence of Sr-substitutions on the setting of the bioactive bone cement. The presence of the foreign ions can alter a series of structural and physico-chemical properties of bioactive bone cement, such as lattice constants, crystal sizes and thermal stability. The effects of Sr content on the structure and vibrational modes of tricalcium phosphate/hydroxy apatite were also discussed.

EXPERIMENTAL

Preparation of the powder of cement: Stoichiometric amounts of $\text{CaHPO}_4 \cdot 2\text{H}_2\text{O}$ (Fourth Reagent Plant Shanghai, China), CaCO_3 (Si Lian Chemical Co. Ltd. Shanghai, China) and SrCO_3 (THE First Reagent Plant Shanghai, China) were

used to reach the respective compositions of 0, 5, 10, 15 and 20 atom % of Sr replacing Ca in composition. The mixture were grinded by a QM-IF ball mill (Nanjing University Instrument Factory, China) at a low rotation speed (400 rpm) and heated at 1450 °C for 5 h and cooled slowly. The calcined cakes were milled and through a 200 mesh sieved and then were used as cement powders.

Preparation of the liquids of cement: Poly(acrylic acid-co-itaconic acid) was synthesized as previously reported. Twenty five wt % citric acid, 5 wt % potassium citrate, 70 wt % poly(acrylic acid-co-itaconic acid (poly(AA-co-IA)) copolymer were mixed and dissolved⁹. Liquids to powder rates (LPR): 1.8:1 g/g. Five kinds of cement were prepared by mixing the the powder of 0, 5, 10, 15 and 20 atom % and the liquids were mixed in the liquid/powder = 1:1.8.

The powder and cements were analyzed by X-ray diffraction (XRD, D/MAX 2550 VB/PC, Rigaku, Japan) using CuK α radiation from 2 θ = 10–80°, with a 2 θ -step of 0.02°. XRD patterns were recorded in an automatic diffractometer crystallographic identification of the phases of synthesized powders and the cement was accomplished by comparing the experimental XRD patterns with standards compiled by the Joint Committee on Powder Diffraction Standards (JCPDS). (HA, card#09-432; α -TCP, #29-359; β -TCP, #09-169).

The liquids, the powder and the cement were scanned by Fourier transform infrared spectroscopy apparatus. FTIR were measured on a Nicolet 5700 FT-IR spectroscope. All samples were taken from KBr pellets and with 0.09 cm⁻¹ resolution. IR measurements were carried out at room temperature using the KBr pellet technique or liquid film method.

RESULTS AND DISCUSSION

Fig. 1 show the X-ray diffraction patterns of the five group of bioactive cement powders. Fig. 1a-d show the biphasic of α -TCP/HA. The diffraction patterns of the cement powders were slightly and continuously shift to lower diffraction angles as increasing strontium amounts till to 15 atom % indicating that the changes in lattice parameters turned up because of the substitution of Sr for Ca in TCP/HA. But Fig. 1e show the characteristic biphasic of β -TCP/HA when strontium amount got to 20 atom %. The presence of foreign ions strontium can replace calcium in TCP/HA biphasic structure, while the relative variations of the cell parameters and the phase of TCP are quite different. Strontium can enter into the α -TCP by substitution for calcium up to 15 atom % Sr/(Sr + Ca), causing a linear enlargement of the lattice constants. But when strontium content got to 20 atom % Sr/(Sr + Ca), the XRD patterns indicate that the phase of β -TCP emerged and the phase of α -TCP disappeared. On the other hand, the phase of HA maintain stability while its cell parameters enlarged. The results confirm the formation of Sr-substituted TCP/HA biphasic powders. the reaction may be represented by equation given below:

β -TCP represents the form of tricalcium phosphate stable at temperatures lower than 1120 °C and its crystallizes are in the rhombohedral space group R3c. In present study, β -TCP phase may be formed at low temperature while phase transition from β -TCP into α -TCP may take place at higher temperature.

Fig. 1. X-Ray diffraction patterns of (a) 0 atom % Sr/(Sr + Ca), (b) 5 atom % Sr/(Sr + Ca), (c) 10 atom % Sr/(Sr + Ca), (d) 15 atom % Sr/(Sr + Ca), (e) 20 atom % Sr/(Sr + Ca) cement powders

According the results of the XRD, the transformation from β -TCP phase to α -TCP may be occurred, even a series of Sr (0, 5, 10 and 15 %) are incorporated into it at high temperature. Strontium may enlarge the unit cell because strontium ion radius (1.13 Å) is bigger than that of calcium (0.99 Å). But, up to 20 atom % Sr/(Sr + Ca), the rhombohedral space group R3c of β -TCP does not transform to the monoclinic space group P21/a(14) of α -TCP at the temperature of 1450 °C, which suggests that strontium incorporation does not provoke a remarkable rearrangement of the unit cell of β -TCP even in higher temperature than 1120 °C. So strontium substitution for calcium may change the thermal stabilization of β -TCP.

At the same time, strontium can substitute for calcium in the hexagonal space group P63/m (176) of HA which is confirmed by Fig. 1. The diffraction patterns of the HA phase were also slightly and continuously shift to lower diffraction angles when mounting Sr amounts were introduced.

Figs. 2 and 3 show the variation of the lattice dimensions and the lattice volume of α -(Sr, Ca)TCP and (Sr, Ca)HA with increasing Sr amounts. Rietveld refinement analyses performed on the powder data revealed an almost linear evolution of the lattice parameters. With the increase of Sr content, the lattice dimensions and lattice volume of α -(Sr, Ca)TCP and (Sr, Ca)HA increased. It is clear that the incorporation of Sr in α -TCP has led to a significant expansion in all the a, b and c axis. The cell parameters (a, b, c, V) of HA vary nearly linearly with a series of strontium content including 20 atom % Sr/(Sr + Ca). The present method that Sr/(Sr + Ca), (Sr + Ca)/P ratio can be controlled by proportionate weighing while common homogenization methods can be applied. The crystallinity of TCP/HA biphasic bioactive cement powders is excellent as shown in Fig. 1.

Fig. 2. Variation of the lattice of α -(Sr,Ca) TCP with increasing Sr content

Fig. 3. Variation of the lattice of (Sr, Ca) HA with increasing Sr content

Figs. 4 and 5 show the FTIR spectra of the cement powder with different content of strontium. The assignment of FTIR of cement powders is listed in Table-1^{10,11}.

FTIR spectra of the Sr series (0, 5, 10 and 15 %) cement powder were assigned to the α -TCP/HA. The spectra of 20 % cement powder clearly shows the presence of bands at 1112, 1082, 1037 and 1015 cm^{-1} can be assigned to PO_4^{3-} bend (ν_3) of β -TCP. PO_4^{3-} bend (ν_1) disappeared or weakened because wavenumber 962 cm^{-1} (HA PO_4^{3-} bend (ν_1)); 972 and 945 cm^{-1} (β -TCP PO_4^{3-} bend (ν_1)) were too close to merge together.

The assignment of FTIR of cement liquid, the reactive products of 0, 10 and 20 % cement powder is listed in Table-2¹²⁻¹⁵.

accord with the peaks of corresponding powder except the intensity became weaker because of the impact of the polycarboxylate, which also show that β -TCP has no character of hydration.

The polymeric calcium phosphate cements set as the result of two reactions, the typical acid-base reaction and a polymerization reaction of polymer monomers¹⁶. The reaction product, that is the polysalt derived from the reaction of poly(AA-co-IA) copolymer and citric acid, with the α -TCP/HA powder, forms a cement matrix analogous to that formed in polycarboxylate zinc cement⁸. But β -TCP has no self-hardening property although it is finally dried¹⁷. The manipulation of the setting times of bioactive bone cement is significant as they should meet the requirements of surgical procedures. So it can not be put into practical clinic use because the set time is too long.

Conclusion

Strontium containing α -TCP/HA biphasic bioactive bone cement powders could be prepared at 1450 °C. 20 % atom Sr/(Sr + Ca) powder of β -TCP/HA was not suit for preparing bioactive bone cement.

ACKNOWLEDGEMENTS

This work was supported by grants from National Natural Science Foundation of China (No. 30470480) and Shanghai Leading Academic Discipline Project (No. S30206, T0202).

REFERENCES

1. B.W. Brown and L.C. Chow, Dental Resorative Cement Pastes, US Patent 4518430 (1985).
2. G. Dagang, X. Dagang and L. Yaxiong, *Mater. Med.*, **21**, 1927 (2010).
3. M.P. Ginebra, M. Espanol, E.B. Montufar, R.A. Perez and G. Mestres, *Acta Biomater.*, **6**, 2863 (2010).
4. I.H. Lieberman, D. Togawa and M.M. Kayanja, *Spine J. Official J. North Am. Spine Soc.*, **5**, 305S (2005).
5. P.J. Marie, *Bone*, **38**, S10 (2006).
6. S. Pors Nielsen, *Bone*, **35**, 583 (1985).
7. X. Wang and J. Ye, *Mater. Med.*, **19**, 1183 (2008).
8. Y. Matsuya, J.M. Antonucci, S. Matsuya, S. Takagi and L.C. Chow, *Dental Mater. Official Pub. Acad. Dental Mater.*, **12**, 2 (1996).
9. D.M. Chen, *Chin. J. Dental Mater. Devices*, **8**, 118 (1999).
10. I. Manjubala, *Mater. Chem. Phys.*, **71**, 272 (2001).
11. Y. Li, F. Kong and W. Weng, *J. Biomed. Mater. Res. B Appl. Biomater.*, **89B**, 508 (2009).
12. J.-S. Weng, S.-C. Liou and S.-Y. Chen, *Biomaterials*, **25**, 3155 (2004).
13. Y. Park, S. Ryu, S. Yoon, R. Stevens and H. Park, *Mater. Chem. Phys.*, **109**, 440 (2008).
14. J. Pena and M. Vallet-Regi, *ChemInform*, **34**, 1687 (2003).
15. S. Meejoo, W. Maneeprakorn and P. Winotai, *Thermochim. Acta*, **447**, 115 (2006).
16. R.M. Khashaba, M. Moussa, C. Koch, A.R. Jurgensen, D.M. Missimer, R.L. Rutherford, N.B. Chutkan and J.L. Borke, *Int. J. Biomater.*, **2010**, 467641 (2010).
17. T. Shiotsu, Surgical Cement Containing α -Tricalcium phosphate, Poly(carboxylic acid) and Water, US Patent 4677140 (1987).