NOTE

3-Dimensional 4-Connected Metal-Organic Frameworks of Zinc(II) Built from 5-Aminotetrazole

ZHIQIANG JIANG

Biology and Chemistry Engineering College of Panzhuhua University, Sichuan 617000, P.R. China

Corresponding author: E-mail: myjiangzq@163.com

(Received: 17 March 2012;

Accepted: 31 October 2012)

AJC-12357

A novel metal-organic frameworks, [compound **1**, $\text{Zn}(\text{ATZ})_2$, ATZ = 5-aminotetrazole], has been synthesized by the solvothermal reaction of zinc nitrate and 5-aminotetrazole. Compound **1** displays a unique three-dimensional four-connected dia topological network.

Key Words: Metal-organic frameworks, Zinc, 5-Aminotetrazole.

Current interest in the synthesis of crystalline 4-connected zeolite-like materials is rapidly expanding owing to their intriguing architectures and potential applications¹⁻⁴. Imidazole and its derivative with various interesting coordination chemistry and a strong networking ability have been extensively used as organic linkers for construction of novel 4-connected zeolitic imidazolate frameworks (ZIF)^{5,6}. Because they have highest content of nitrogen among the organic substances and show surprisingly high thermal stabilities, 5-aminotetrazole are prospective materials for the generation of gases, such as blowing agents, solid propellants and other combustible and thermally decomposing systems^{7,8}. In this work, we report a novel metal-organic frameworks, $[\text{Zn}(\text{ATZ})_2]$, ATZ = 5-aminotetrazole].

All reagents and solvents employed were commercially available and used as received without further purification.

Preparation of compound: A mixture of $\text{Zn}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ (0.1499 g, 0.51 mmol), pyrazine (0.0300 g 0.37 mmol), 5-aminotetrazole (ATZ , 0.0935 g, 1.1 mmol), 2,6-naphthalenedicarboxylic acid (2,6-ntd, 0.0512 g 0.24 mmol), tetramethylammonium bromide (0.0300 g 0.20 mmol), 2-imidazolidinone (1.9903 g, 20 mmol), methanol (3.0 mL) and *N,N*-dimethylacetamide (DMA, 3.0 mL) in a 23 mL teflon-lined stainless steel vessel was heated at 120 °C for 96 h and then cooled to room temperature. The resulting colourless transparent crystals were obtained, washed using acetone and dried at room temperature.

X-crystallography: Suitable single crystals of $[\text{Zn}(\text{ATZ})_2]$ were carefully selected under an optical microscope and glued to thin glass fibers. Whereafter, single-crystal X-ray diffraction analyses were performed on a computer-controlled XCalibur E CCD diffractometer with graphite-monochromated $\text{MoK}\alpha$

radiation ($\lambda_{\text{MoK}\alpha} = 0.71073 \text{ \AA}$) at $T = 293.2 \text{ K}$. Empirical absorption corrections were made using the SADABS program⁹. The structures were solved using the direct method and refined by full-matrix least-squares methods on F^2 by using the SHELX-97 program package¹⁰. All non-hydrogen atoms were refined anisotropically and hydrogen atoms attached to carbon or nitrogen atoms were fixed at their ideal positions.

Structure description: Single-crystal X-ray analysis revealed that the asymmetric unit of compound **1** contains one Zn^{2+} cation, two independent anionic ATZ^- ligands (Fig. 1a). Each ATZ^- anion serves as μ_2 -bridge linking two Zn atoms and each Zn atom is surrounded by four ATZ^- ligands, where the four-coordinated Zn atom adopts a tetrahedral geometry (Fig. 1b). Interestingly, there are a cage comprising twelve ATZ ligands and these cages constructed three-dimensional frameworks (Fig. 1c). A better insight into the nature of this intricate framework can be achieved by the application of a topological approach. As shown in Fig. 1d and 1e, if every Zn atom acts as a nodal point, each nodal point was further linked to result in four-connected frameworks, which can be abstracted as a uninodal 4-connected typical dia topological net. The result of topological analysis indicates this network has extended point symbol of $6(2).6(2).6(2).6(2).6(2).6(2)$.

REFERENCES

1. G. Ferey, C. Mellot-Draznieks, C. Serre and F. Millange, *Acc. Chem. Res.*, **38**, 217 (2005).
2. A. Vimont, A. Travert, P. Bazin, J.-C. Lavalley, M. Daturi, C. Serre, G. Ferey, S. Bourrelly and P.L. Llewellyn, *Chem. Commun.*, 3291 (2007).
3. Y.L. Lai, K.-H. Lii and S.L. Wang, *J. Am. Chem. Soc.*, **129**, 5350 (2007).
4. G. Cao, M.E. Garcia, M. Alcala, L.F. Burgess and T.E. Mallouk, *J. Am. Chem. Soc.*, **114**, 7574 (1992).

Fig. 1. (a) and (b) Coordination environment around the zinc(II) atoms and ATZ ligands in compound **1**; (c) The units of cage in compound **1**; (d) The topology of compound **1**; (e) The dia topology in the topology of compound **1**

- R. Banerjee, H. Furukawa, D. Britt, C. Knobler, M. O'Keeffe and O.M. Yaghi, *J. Am. Chem. Soc.*, **131**, 3875 (2009).
- W. Morris, B. Leung, H. Furukawa, O.K. Yaghi, N. He, H. Hayashi, Y. Houndonougbo, M. Asta, B.B. Laird and O.M. Yaghi, *J. Am. Chem. Soc.*, **132**, 11006 (2010).
- A.I. Lesnikovich, O.A. Ivashkevich, S.V. Levchik, A.I. Balabanovich, P.N. Gaponik and A.A. Kulak, *Thermochim. Acta*, **388**, 233 (2002).
- X.W. Wang, J.Z. Chen and J.H. Liu, *Cryst. Growth Design*, **7**, 1227 (2007).
- G.M. Sheldrick, SADABS, Program for Area Detector Adsorption Correction; Institute for Inorganic Chemistry, University of Göttingen: Göttingen, Germany (1996).
- G.M. Sheldrick, SHELXL-97, Program for Solution of Crystal Structures; University of Göttingen: Göttingen, Germany (1997).