Sol-Gel Synthesis and Luminescence Properties of $\text{ZnMoO}_4\text{:Tb}^{3+}$ Nano-Structural Materials

JIANFU ZHANG*, HUI ZHANG, HU YANG and ZHEN LING WANG

Department of Chemistry, Zhoukou Normal University, Zhoukou 466001, P.R. China

*Corresponding author: Fax: +86 394 8178238; Tel: +863948178238; E-mail: jianfuok@163.com

(Received: 12 April 2012;

Accepted: 23 January 2013)

AJC-12744

The ultraviolet excitation molybdates-based green phosphors were synthesized by sol-gel method and characterized by X-ray powder diffraction, photoluminescence spectrum, UV-visible absorption spectrum and scanning electron microscopy. A systematic study about the effects of calcinations temperature on the composition and luminescent properties of the phosphors has also been undertaken. The result of XRD reveals that the $\text{ZnMoO}_4\text{:Tb}^{3+}$ phosphors have triclinic structure of bulk ZnMoO_4 . Under the excitation of 275 nm, the emission intensity of the self-activation phosphor MoO_4^{2-} is weakened greatly, while that of $\text{Tb}^{3+} {}^5\text{D}_4 \rightarrow {}^7\text{F}_5$ transition at 543 nm (green light) is significantly enhanced. These observed luminescent properties of this phosphor demonstrate it has potential applications as luminescent material in lighting, display, etc.

Key Words: Sol-gel Method, ZnMoO_4 , Rare earth ion, Photoluminescence.

INTRODUCTION

Recently, the exploration of novel materials and energies attracts much attention in P.R. China, especially molybdates- or tungstates-based phosphors with Eu^{3+} doped have been investigated^{1,2} due to their high stability and high emission efficiency. However, most of the studies focused on red phosphors, rarely on other colour³. It's known that molybdates intrinsically show blue-green fluorescence under the excitation by UV light and Tb^{3+} emits green light. Therefore, we can get green phosphors *via* doping appropriate amounts of Tb^{3+} to molybdates or tungstates⁴⁻⁷.

Molybdates- or tungstates-based phosphors mostly prepared by the conventional solid-state reaction. The size distribution of particles obtained by this method is irregular and this method is also high power consumption, these disadvantages can be overcome by sol-gel method which having the advantages of benign reaction conditions and good homogeneity etc.

ZnMoO_4 phosphors are triclinic structure and self-luminescence fluorescence chromophores, can easily forming complex ion luminescence center with closed shell electron configuration. MoO_4^{2-} has tetrahedral structure, showing green emission under the excitation by UV light (250-310 nm)^{8,9}. Herein, we present a novel green phosphor, ZnMoO_4 doping Tb^{3+} prepared by sol-gel method. Under the excitation of 275 nm, the emission intensity of the activation self-luminescent MoO_4^{2-} is weakened greatly, while that of $\text{Tb}^{3+} {}^5\text{D}_4 \rightarrow {}^7\text{F}_5$ transition at 543 nm (green emission) is significantly enhanced.

EXPERIMENTAL

0.1 mol L⁻¹ $\text{Tb}(\text{NO}_3)_3$ solution, $\text{Na}_2\text{MoO}_4 \cdot 2\text{H}_2\text{O}$, analytical pure, bought from Beijing Chemical Plant; ZnCl_2 , analytical pure, bought from Xi'an Chemical Reagent Factory; $\text{HO}(\text{CH}_2\text{CH}_2\text{O})_n\text{H}$, 6000-7500, Guangdong XiLong Chemical.

Measurement: X-ray diffraction (D₈ Advance, Bruker); scanning electron microscope (Quanta 200, FEI); UV-VIS spectroscopy (Perkin Elmer, USA); LS55 Luminescence spectrometer (Perkin Elmer, USA).

Firstly, 2.4228 g $\text{Na}_2\text{MoO}_4 \cdot 2\text{H}_2\text{O}$ and 1.3629 g ZnCl_2 were dissolved in deionized water under continuous stirring at room temperature until forming homogeneous solution. The transparent gel was formed after stirred at 80 °C for half an hour and filtrated. Secondly, the gel was transferred into a surface plate and maintained at 140 °C in drying oven for 2 h to form white gel and then divided into three parts. Finally, the samples were obtained after placing in Muffle furnace at 500 °C, 700 °C, 900 °C calcined for 4 h, respectively.

Firstly, 1 mL, 3 mL, 5 mL, 7 mL of 0.1 mol L⁻¹ $\text{Tb}(\text{NO}_3)_3$ were added to beakers which contain four equal parts of 2.4512 g $\text{Na}_2\text{MoO}_4 \cdot 2\text{H}_2\text{O}$, 1.9370 g ZnCl_2 and 0.4413 g polyethylene glycol respectively and then add 20 mL deionized water. The transparent gel was formed after stirred at 80 °C for 0.5 h and filtrated. Secondly, the gel was transferred onto a surface plate and maintained at 140 °C in drying oven for 2 h to form a white gel. Finally, the samples were obtained after placing in Muffle furnace at 900 °C calcined for 4 h.

The structure of samples was characterized by X-ray powder diffraction (XRD, D₈ Advance, Bruker). The morphology of nanoparticle was obtained by SEM (Quanta 200, FEI). UV-visible diffuse reflectance spectrum was measured on a UV-visible spectrophotometers (UV-VIS Perkin Elmer Lambda35 equipped with an integrating sphere, BaSO₄ was used for the reflection-background contrast). The excitation and emission spectra were recorded using an FLS920P Edinburgh Analytical Instrument apparatus equipped with a 450 W Xenon lamp as the excitation source.

RESULTS AND DISCUSSION

Fig. 1 shows the XRD patterns of ZnMoO_4 prepared by sol-gel method with different calcining temperature (500 °C, 700 °C, 900 °C) for 4 h. As shown in Fig. 1, the sample still has amorphous structure under the 500 °C and the structure of crystal is not very good, yet the single crystalline phase of triclinic structure has been formed and the XRD patterns are consistent with that given in JCPDS No. 35-0765. When the temperature rises to 700 °C, the ZnMoO_4 sample was obtained completely with mixed phase appearing. With the increasing of the calcining temperature, the relative intensity of diffraction peak is increased while the width reduced, which shows that the single crystalline phase of ZnMoO_4 sample is becoming well; meanwhile, the sample has stable structure and composition at above 700 °C and ZnMoO_4 is the host which has the strongest diffraction at $2\theta = 30.054^\circ$ and the disappearance of part diffraction peak due to the high temperature destroying the phase partly.

Fig. 1. XRD patterns of the samples obtained at different calcining temperature

Fig. 2 is X-ray diffraction patterns of the precursor without and with Tb^{3+} doping calcined at 900 °C for 4 h. It is obviously that the relative intensity of diffraction peak increased and the width reduced with Tb^{3+} doping and the crystalline is approximately consistent with standard spectra. Moreover, the appearance of the strongest diffraction at $2\theta = 26.633^\circ$ and the crystallographic plane at (-220) , $d = 0.3344$ nm.

Fig. 2. XRD patterns of the samples without and with Tb^{3+} doping

The SEM images of ZnMoO_4 prepared by the sol-gel method under different calcining temperatures are shown in Fig. 3. The sample which calcined at 500 °C has granular and less rod-like shape owing to lower temperature reducing the crystallization. With the increasing of calcining temperature, in Fig. 3(b), the rod-like shape material is increased and the surface of the rods have become relatively more smooth with the appearance of irregular crystals. It is observed that regular small cubic crystals are formed in Fig. 3 (c) with $2.210 \mu\text{m}$ rod-like material appearing, which indicates that the crystallization of the sample is completed. In Fig. 3 (d), more uniform cubic crystal can be observed, with apart of defects on the surface owing to the high temperature destroying the structure partly.

Fig. 3. SEM image of ZnMoO_4 fired at 500 °C (a), 700 °C (b, c), 900 °C (d) for 4 h

Fig. 4 demonstrates the ZnMoO_4 has strong absorption at 275 nm no matter whether it calcined at 900 °C for 4 h with Tb^{3+} doping or not, the intensity of undoped sample is stronger. Therefore, we can study their luminescent properties *via* the emission spectrum of sample excited by 275 nm.

Fig. 4. UV-visible absorption spectra of ZnMoO_4 obtained before and after Tb^{3+} doping

Fig. 5 shows the emission spectra of ZnMoO_4 with 5 % Tb^{3+} doping under the excitation at 275 nm. We chose ZnMoO_4 with 5 % Tb^{3+} doping to investigate luminescent properties as they have the strongest green light emission by ultraviolet light excitation. The main emission is the $^5\text{D}_4 \rightarrow ^7\text{F}_5$ transition of Tb^{3+} at 543 nm. Other $f-f$ transitions of Tb^{3+} are weak, such as $^5\text{D}_4 \rightarrow ^7\text{F}_6$ at 489 nm and $^5\text{D}_4 \rightarrow ^7\text{F}_4$ transitions at 583 nm. Under 583 nm, the $^5\text{D}_4 \rightarrow ^7\text{F}_4$ transition having split demonstrates that $\text{ZnMoO}_4:\text{Tb}^{3+}$ has MoO_4^{2-} and Tb^{3+} two luminescent centers. For the sample of ZnMoO_4 doped with 5 % Tb^{3+} , the emission intensity of the activation self-luminescent MoO_4^{2-} is weakened greatly, while that of Tb^{3+} $^5\text{D}_4 \rightarrow ^7\text{F}_5$ transition at 543 nm (green emission) is significantly enhanced. This phosphor has the potential application value as luminescent material.

Fig. 5. Emission spectra of ZnMoO_4 with 5 % Tb^{3+} doping

Conclusion

We investigated the effect of temperature to the composition and structure of the ZnMoO_4 and $\text{ZnMoO}_4:\text{Tb}^{3+}$ phosphors prepared by the sol-gel method. The strong diffraction peaks in XRD spectra are consistent with the standard spectra when they calcined at 700 °C. It is concluded that the single crystalline phase of triclinic structure has been formed completely in the light of this evidence. The morphology of samples observed by SEM show that they have triclinic crystal structure. We also investigated the luminescent properties of $\text{ZnMoO}_4:\text{Tb}^{3+}$ according to emission spectrum, it has strong green light emission when calcined at 900 °C. In summary, we can prepare the ultraviolet photoexcitation molybdic acid salt base green phosphors by adjusting the percent of Tb^{3+} .

ACKNOWLEDGEMENTS

This work was supported by the Program for Science and Technology Innovation Talents in University of Henan Province (2011HASTIT030), Foundation for University Key Teacher by the Henan Province (2009GGJS-119) and the Key Discipline of Applied Chemistry of Zhoukou Normal University.

REFERENCES

1. X. Li and Z. Zhang, *Chinese J. Rare Earth*, **12**, 69 (2008).
2. X. Li, Y. Yang, Z.P. Yang, L. Guan and C. Liu, *Chinese J. Luminescence*, **29**, 93 (2008).
3. C.F. Guo and T. Chen, *J. Func. Mater.*, **38**, 200 (2007).
4. J. Lin, Q. Su, *Chinese J. Rare Earth*, **2**, 42 (1994).
5. J.B. Yu, X.M. Yuan and J.Z. Chen, *Mater. Rev.*, **15**, 30 (2001).
6. L.D. Zhang and J.M. Mu, *Beijing Sci. Technol. Press*, 135 (2001).
7. Y.S. Yang, J.X. Qi and M.S. Zhang, *J. Inorg. Mater.*, **14**, 20 (1999).
8. Y. Liao, W. Zhu, X.M. Li, Y.Q. Mo, X.G. Hao and X.Q. Ma, *Mater. Rev.*, **21**, 321 (2007).
9. F. Auzel, *Chem. Rev.*, **104**, 139 (2004).