NOTE

A Novel Quaternary Metal Chalcogenide $\text{HgZn}_2\text{I}_4\text{Cl}_2$: Solid-State Synthesis and Structure

HUA-LONG CHEN, HAN-MAO KUANG and WEN-TONG CHEN*

Institute of Applied Chemistry, School of Chemistry and Chemical Engineering, Jinggangshan University, Ji'an 343009, Jiangxi, P.R. China

*Corresponding author: E-mail: wtchen_2000@yahoo.cn

(Received: 29 September 2012;

Accepted: 12 August 2013)

AJC-13914

An unprecedented quaternary metal chalcogenide $\text{HgZn}_2\text{I}_4\text{Cl}_2$ (**1**) was synthesized by a solid-state reaction and structurally characterized by single crystal X-ray diffraction. Compound **1** is characterized by a one-dimensional (1-D) infinite chain-like structure, which is constructed from the interconnected 9-membered $\text{HgZn}_2\text{I}_4\text{Cl}_2$ quadrangles.

Key Words: Chalcogenide, $\text{HgZn}_2\text{I}_4\text{Cl}_2$, Synthesis, Structure.

Metal chalcogenides usually exhibit abundant structural chemistry and interesting physical or chemical properties for potential applications in different fields such as ferroelectrics¹, solar energy conversion², *etc.* To our best of knowledge, a lot of ternary metal chalcogenides - as a branch of metal chalcogenides, have been synthesized and broadly used in military areas. Among which, the most famous is probably $\text{Hg}_{1-x}\text{Cd}_x\text{Te}$ (MCT) and CuInSe_2 , whose important application is found in photoelectric devices of infrared detection^{2,3}. Up to date, most of the ternary metal chalcogenides are A-M-Q (A = alkali/alkaline-earth metals, M = *p*-block metals, Q = chalcogen = S/Se/Te) compounds, while IIB-Q-X (IIB = Zn/Cd/Hg, X = F/Cl/Br/I) compounds are still relatively rare. Furthermore, quaternary IIB-Q-X metal chalcogenides (only containing IIB, Q and X) are much more scarce, although lots of other quaternary metal chalcogenides (not only containing IIB, Q and X) like CuHgSeCl_4 and $\text{Cd}_{13}\text{P}_4\text{S}_{22}\text{I}_2$ ⁵, have been reported. Our recent efforts in preparing novel IIB-based compounds are mainly focusing on the systems containing both chalcogenide and halide elements. We herein report the solid-state synthesis and crystal structure of a novel quaternary metal chalcogenide $\text{HgZn}_2\text{I}_4\text{Cl}_2$ (**1**) with an infinite chain-like structure.

Synthesis: The chalcogenide $\text{HgZn}_2\text{I}_4\text{Cl}_2$ was synthesized from the reaction of HgCl_2 (1 mmol, 272 mg) and ZnI_2 (2 mmol, 638 mg). The starting materials were loaded into a silica tube, which was flame-sealed under a 10^{-3} Torr atmosphere and subsequently placed into a furnace. The tube was heated to 523 K in 6 h from room temperature and kept there for 2 days, then heated to 723 K in 12 h and kept for 15 days, followed by cooling to 373 K at a rate of 5 K/h to promote

crystal growth, then cooled down to room temperature and power off. Yield: 29 %.

Single-crystal X-ray diffraction experiment: X-Ray diffraction data set was collected on a Rigaku Mercury CCD X-ray diffractometer with graphite monochromated MoK_α radiation ($\lambda = 0.71073 \text{ \AA}$) using an ω scan technique. Crystal Clear software was used for data reduction and empirical absorption correction. The structure was solved by the direct methods using the Siemens SHELXTLTM Version 5 package of crystallographic software. The difference Fourier maps based on the atomic positions yield all atoms. The structure was refined using a full-matrix least-squares refinement on F^2 . All atoms were refined anisotropically. The summary of crystallographic data and structure analysis is given in Table-1. The selected bond lengths and bond angles are listed in Table-2.

Compound **1** was obtained from the reaction of HgCl_2 and ZnI_2 by solid-state reactions at an intermediate temperature. X-Ray diffraction analyses reveal that compound **1** is characteristic of a 1-D infinite chain-like structure. An ORTEP diagram of **1** together with the atomic numbering scheme is shown in Fig. 1. The Hg(II) ion coordinates to four iodine ions with the bond distances of Hg-I being of 2.661(2) and 2.8069(19) $\text{\AA}$, as shown in Fig. 2 and Table-2. The bond lengths of Hg-I are normal and comparable with the counterparts documented previously⁶. The Zn(II) ion binds to two iodine ions with the bond lengths of Zn-I being of 2.666(3) and 2.775(3) $\text{\AA}$, respectively, which are normal and comparable with those reported in the literature⁷. Additionally, each zinc ion connects to a neighboring one with the $\text{Zn}\cdots\text{Zn}$ distance being of

TABLE-1
CRYSTAL DATA OF 1

Empirical formula	Cl ₂ HgI ₄ Zn ₂
Formula weight	909.83
Crystal system	Monoclinic
Space group	C2/c
Unit cell dimensions	a = 9.798(3) Å, b = 14.779(5) Å, c = 12.318(4) Å, β = 110.556(4)°
Z	4
V	1670.1(10) Å ³
D _c	3.618 Mg/m ³
Absorption coefficient	19.686 mm ⁻¹
Crystal size	0.08 mm × 0.06 mm × 0.05 mm
No. of reflections collected/unique	2888/945 [R _(int) = 0.0270]
Goodness-of-fit on F ²	0.932
Final R indices	R ₁ = 0.0891, wR ₂ = 0.2032
R indices (all data)	R ₁ = 0.1258, wR ₂ = 0.2388
(Δσ) _{max}	0.001

TABLE-2

SELECTED BOND LENGTHS (Å) AND BOND ANGLES (°)

Hg(1)-I(1)#1	2.661(2)	I(1)-Hg(1)-I(2)	90.21(6)
Hg(1)-I(1)	2.661(2)	I(1)#1-Hg(1)-I(1)	177.90(8)
Hg(1)-I(2)	2.8069(19)	I(1)#1-Hg(1)-I(2)	89.75(6)
Hg(1)-I(2)#1	2.8069(19)	I(1)#1-Hg(1)-I(2)#1	90.21(6)
Zn(1)-I(1)#1	2.775(3)	I(1)-Hg(1)-I(2)#1	89.75(6)
Zn(1)-I(2)	2.666(3)	I(2)-Zn(1)-I(1)#1	90.35(10)
Zn(1)-Zn(1)#2	2.452(6)	I(2)-Hg(1)-I(2)#1	177.84(7)

Symmetry codes: #1 -x+1, y, -z+3/2; #2 -x+2, y, -z+3/2.

Fig. 1. An ORTEP drawing of 1 with 50 % thermal ellipsoids

2.452(6) Å which is comparable with those documented before⁸. One mercury, two zinc, two chlorine and four iodine atoms interconnect together to form a 9-membered HgZn₂I₄Cl₂ quadrangle. The HgZn₂I₄Cl₂ quadrangles interlink together *via* zinc atoms to give a 1-D infinite chain-like structure running along the a axis, as shown in Fig. 2. The 1-D infinite chains stack together to give a crystal packing motif, as shown in Fig. 3.

Fig. 2. A chain-like structure of 1 running along the a axis

Fig. 3. Packing diagram of 1 viewed down along the b axis

In summary, a novel quaternary metal chalcogenide HgZn₂I₄Cl₂ has been obtained *via* a solid-state reaction. Its crystal structure is characteristic of a one-dimensional infinite chain-like structure, which is constructed from the interconnected 9-membered HgZn₂I₄Cl₂ quadrangles.

ACKNOWLEDGEMENTS

The authors thank the support of the National Science and Technology Support Program of the Ministry of Science and Technology of P.R. China (2012BAC11B01).

REFERENCES

1. M. Tampier and D. Johrendt, *J. Solid State Chem.*, **158**, 343 (2001).
2. J.M. Steward, W.S. Chen, W.E. Deveny, R.A. Mickelson, S.K. Deb and A. Zunger, Materials Research Society: Pittsburgh, PA, p. 59 (1987).
3. K. Zweibel and R. Michell, CuInSe₂ and CdTe: Scale-Up for Manufacturing; SERI Publication, prepared for US DOE under Contract No. DE-AC02-83CH10093 (1989).
4. M. Guillo, B. Mercey, P.H. Labbe and A. Deschanvres, *Acta Crystallogr. B*, **36**, 2520 (1980).
5. A. Bubenzer, R. Nitsche and E. Grieshaber, *Acta Crystallogr. B*, **32**, 2825 (1976).
6. K.K. Sarker, B.G. Chand, K. Suwa, J. Cheng, T.-H. Lu, J. Otsuki and C. Sinha, *Inorg. Chem.*, **46**, 670 (2007).
7. M. Rademeyer, C. Tsouris, D.G. Billing, A. Lemmerer and J. Charmant, *Cryst. Eng. Commun.*, **13**, 3485 (2011).
8. M. Carrasco, R. Peloso, I. Resa, A. Rodríguez, L. Sanchez, E. Alvarez, C. Maya, R. Andreu, J.J. Calvente, A. Galindo and E. Carmona, *Inorg. Chem.*, **50**, 6361 (2011).