A Solvothermal Process to Synthesize Calcium Metastannate Nanoparticles Assisted by Microwave Irradiation

CHANG SUNG LIM

Department of Advanced Materials Science & Engineering, Hanseo University, Seosan 356-706, South Korea

Corresponding author: Tel/Fax: +82 41 6601445; E-mail: cslim@hanseo.ac.kr

(Received: 27 December 2011;

Accepted: 7 November 2012)

AJC-12371

Calcium metastannates (CaSnO_3) nanoparticles were synthesized successfully using a facile microwave solvothermal route followed by further heat-treatment. Well-crystallized CaSnO_3 nanoparticles were formed after heat-treatment at 800 °C for 3 h showing a fine and homogeneous morphology with particle sizes of 20-40 nm. The synthesized CaSnO_3 nanoparticles were characterized by X-ray diffraction, Fourier transform infrared spectroscopy, scanning electron microscopy, energy-dispersive X-ray spectroscopy and transmission electron microscopy.

Key Words: Calcium metastannates, Microwave irradiation, Solvothermal process, Nanoparticles.

INTRODUCTION

Alkaline earth metal metastannates, with structures closely related to the perovskite one, are of particular interest due to their unusual dielectric and semiconducting properties, leading to various applications such as thermally stable capacitors, ceramic dielectric bodies, gas and humidity sensors and battery electrode materials¹⁻⁵. Numerous non-conventional soft chemical synthetic routes have been employed to synthesize alkaline earth metastannates by a range of processes, such as a solid-state reaction⁶, a co-precipitation method⁷, sol-gel⁸, a combustion method⁹, a precursor route^{10,11}, a microwave synthesis¹², a polymerized complex method¹³, molten salt synthesis¹⁴, a pulsed laser deposition¹⁵, a self-heat-sustained method^{16,17}.

Generally conventional solid-state ceramic route was used for the preparation of metastannates based compounds. It requires prolonged calcinations at *ca.* 1200 °C for several hours along with intermediate processes in order to obtain reasonable phase purity. To coarse-grained powders synthesized using the conventional solid-state route has disadvantages of larger particle sizes, high temperature processing and lower phase purity. Microwave synthesis has the advantages of a very short reaction time, a small particle size, a narrow particle size distribution and is a high purity method for preparing polycrystalline samples. Microwave energy is delivered directly to the material through molecular interactions with an electromagnetic field¹⁸. Hydrothermal process is an efficient low temperature method that allows the formation of particles with

high degree of crystallinity and easy dispersion in an aqueous medium. The use of microwave energy in hydrothermal system promotes the development of a rapid heating to the required temperature with rapid rates of crystallization^{19,20}.

The microwave solvothermal process is adjusted to heat the metal metastannates uniformly resulting in fine particles with a controlled morphology and to fabricate the product in a green manner without the generation of solvent waste. Recently, microwave solvothermal processes have been reported the use of a facile and fast method in preparing nanocrystalline particles of metal tungstates with unique and enhanced properties^{21,22}. The solvothermal synthesis proceeds the reactions in a hot ethylene glycol solution as a polar solvent above a boiling point of 197 °C. When the microwave radiation is supplied to the ethylene glycol under a sealed pressure above boiling point, the components dissolving in the ethylene glycol are charged and vibrated in electric field interdependently.

In this study, the calcium metastannate (CaSnO_3) nanoparticles were synthesized using a facile solvothermal route assisted by the microwave irradiation. The characteristics of the synthesized calcium metastannate nanoparticles are discussed based on the microwave solvothermal reaction in ethylene glycol under the high sealed pressure. The synthesized CaSnO_3 nanoparticles were characterized by X-ray diffraction, Fourier transform infrared spectroscopy, scanning electron microscopy and transmission electron microscopy.

EXPERIMENTAL

Fig. 1 shows a flow chart for the synthesis of CaSnO_3 nanoparticles by the cyclic microwave solvothermal process. CaCl_2 , $\text{Na}_2\text{SnO}_3 \cdot 3\text{H}_2\text{O}$ and ethylene glycol of analytic reagent grade were used to prepare the CaSnO_3 compound. Each of 0.01 mol CaCl_2 and 0.01 mol $\text{Na}_2\text{SnO}_3 \cdot 3\text{H}_2\text{O}$ for CaSnO_3 was dissolved in 30 mL ethylene glycol. The solutions were mixed and adjusted at a pH 9.5 using NaOH. The aqueous solution was stirred in ultrasonic bath at room temperature. In the sequence, the mixture was transferred into a Teflon lined digestion vessel of 120 mL capacity. The Teflon vessel was placed into a microwave solvothermal autoclave (2.45 GHz, maximum power of 800 W). The microwave solvothermal conditions were kept at 200 °C for 0.5 h. After microwave solvothermal process, the microwave autoclave was cooled room temperature. The resulting solutions were treated with ultrasonic radiation and washed many times with distilled hot water. The white precipitates were corrected and dried at 100 °C in a dry oven. The final products were heat-treated at 800 °C for 3 h.

Fig. 1. Flow chart for the synthesis of calcium metastannate nanoparticles by the microwave solvothermal process

The existing phases of the calcium metastannate particles after the microwave solvothermal process were identified by powder XRD ($\text{CuK}\alpha$, Rigaku D/MAX 2200, Japan). FTIR (Nicolet IR 200, Thermo Electron Corporation, USA) was used to examine the absorption behaviour of the synthesized CaSnO_3 particles over the frequency range, 4000–400 cm^{-1} . The microstructure, particle morphology and qualitative compositions of the CaSnO_3 particles were observed by SEM (JSM-5600, JEOL, Japan) and TEM (JEM 2000-FX, 250 kV, Japan).

RESULTS AND DISCUSSION

Fig. 2 shows XRD patterns of the CaSnO_3 nanoparticles synthesized by the microwave solvothermal process after heat-treatment at 800 °C for 3 h. All XRD peaks could be assigned to a cubic structure of CaSnO_3 (space group: $\text{P}2_12_12_1$, JCPDS 31-0312)¹⁰. It suggests that microwave solvothermal synthesis is suitable for the growth of CaSnO_3 crystallites with the strongest major intensity peaks from the (020), (121) and (202) planes with some preferred orientation.

Fig. 2. XRD patterns of the CaSnO_3 nanoparticles synthesized by the microwave solvothermal process

Fig. 3 shows FT-IR spectra of the CaSnO_3 nanoparticles synthesized by the microwave solvothermal process in the wavenumber range, 4000–480 cm^{-1} . The very strong absorbable peak at 629 cm^{-1} reveals typical characteristics of a strong Sn-O stretching mode. The strong Sn-O stretching modes are contributed to the uniform regular SnO_6 octahedra of the metal stannates¹². The bands at 856 and 1050 cm^{-1} are due to the presence of carbonates. The band at 1450 cm^{-1} is assumed that the samples prepared contain a small amount of surface-adsorbed water and alcohol⁹.

Fig. 3. FT-IR spectrum of the CaSnO_3 nanoparticles synthesized by the microwave solvothermal process

Fig. 4 shows a SEM image (a) and a TEM image (b) of the CaSnO_3 nanoparticles synthesized by the microwave solvothermal process. The SEM image of CaSnO_3 in Fig. 4(a) shows a well-defined and homogeneous morphology, while the TEM image of CaSnO_3 in Fig. 4(b) shows the particle sizes

Fig. 4. A SEM image (a) and a TEM image (b) of the CaSnO_3 nanoparticles synthesized by the microwave solvothermal process

of 20–40 nm. The solvothermal synthesis proceeds the reactions between CaCl_2 and $\text{Na}_2\text{SnO}_3 \cdot 3\text{H}_2\text{O}$ in a hot ethylene glycol solution as a polar solvent above a boiling point of 197 °C. The microwave solvothermal process of metal stannates occurs in accordance with the reaction:

When the microwave radiation is supplied to the ethylene glycol under a sealed pressure above boiling point, the components dissolving in the ethylene glycol are charged and vibrated in electric field interdependently. The microwave solvothermal process is adjusted to heat the metal stannates uniformly resulting in fine particles with a controlled morphology and to fabricate the product in a green manner without the generation of solvent waste. The microwave-assisted solvothermal reaction involves the exchange of atomic/ionic species, where the driving force is the exothermic reaction in ethylene glycol accompanying the formation of NaCl with a high lattice energy. The microwave exothermic reaction occurs so rapidly that the temperature and the pressure of the ethylene glycol increases so quickly that the reaction products are essentially heated up. The microwave-assisted solvothermal reactions provide a facile route for the synthesis of CaSnO_3 nanoparticles, which were obtained in the form of loosely connected nano-sized particles at considerably lower temperatures with a high pressure than those usually employed for their synthesis. The well-defined CaSnO_3 nanoparticles features synthesized by the microwave-assisted solvothermal process have a control over the morphology of the fine particles and can be used for technological applications.

Conclusion

Calcium metastannates nanoparticles were synthesized successfully by the microwave solvothermal processes between CaCl_2 and $\text{Na}_2\text{SnO}_3 \cdot 3\text{H}_2\text{O}$ in a hot ethylene glycol solution as a polar solvent. The microwave solvothermal reactions occurred so rapidly that the exothermic reaction was essentially used to heat up the metal metastannates. Well-crystallized CaSnO_3

nanoparticles were formed after heat-treatment at 800 °C for 3 h showing a fine and homogeneous morphology with particle sizes of 20–40 nm. The very strong absorbable peak at 629 cm^{-1} was typical characteristics of a strong Sn–O stretching mode.

ACKNOWLEDGEMENTS

This study was supported by Basic Science Research Program through the National Research Foundation of Korea (NRF) funded by the Ministry of Education, Science and Technology (2012-0007858).

REFERENCES

1. A. Kumar, R.N.P. Choudhary, B.P. Singh and A.K. Thakur, *Ceram. Int.*, **32**, 73 (2006).
2. A. Aydi, H. Khemakhem, A. Simon, D. Michau and R. von der Muehl, *J. Alloys Comp.*, **484**, 356 (2009).
3. W. Yude, S. Xiaodan, L. Yanfeng, Z. Zhenlai and W. Xinghui, *Solid State Elect.*, **44**, 2009 (2000).
4. A. Kumar, B.P. Singh, R.N.P. Choudhary and A.K. Thakur, *J. Alloys Comp.*, **394**, 292 (2005).
5. A.M. Azad, L.J. Min and M.A. Alim, *Ceram. Int.*, **27**, 335 (2001).
6. S. Upadhyay, O. Parkash and D. Kurmar, *J. Mater. Sci. Lett.*, **16**, 1330 (1997).
7. M.M. Rashad and H. El-Shall, *Powder Technol.*, **183**, 161 (2008).
8. A. M. Azad, M. Hashim, S. Baptist, A. Badri and A.U. Haq, *J. Mater. Sci.*, **35**, 5475 (2000).
9. A.S. Deepa, S. Vidya, P.C. Manu, S. Solomon, A. John and J.K. Thomas, *J. Alloys Comp.*, **509**, 1830 (2010).
10. C. Fan, X. Song, H. Yu, Z. Yin, H. Xu, G. Cao, D. Zheng and S. Sun, *Mater. Lett.*, **61**, 1591 (2007).
11. R. Koeferstein, L. Jaeger, M. Zenker and S.G. Ebbinghaus, *J. Eur. Ceram. Soc.*, **29**, 2324 (2009).
12. J. Bohemann, R. Libanori, M.L. Moreira and E. Longo, *Chem. Eng. J.*, **155**, 905 (2009).
13. C.P. Udawatte, M. Kakihana and M. Yoshimura, *Solid State Ionics*, **128**, 217 (2000).
14. B. Ramdas and R. Vijayaraghavan, *Bull. Mater. Sci.*, **33**, 75 (2010).
15. M.C.F. Alves, S. Boursicot, S. Ollivier, V. Bouquet, S. Deputier, A. Perrin, I.T. Weber, A.G. Souza, I.M.G. Santos and M. Guilloux-Viry, *Thin Solid Films*, **519**, 614 (2010).
16. A.M. Azad, L.L.W. Shyan, T.Y. Pang and C.H. Nee, *Ceram. Int.*, **26**, 685 (2000).
17. A.M. Azad, L.L.W. Shyan and P.T. Yen, *J. Alloys Comp.*, **282**, 109 (1999).
18. S. Das, A.K. Mukhopadhyay, S. Datta and D. Basu, *Bull. Mater. Sci.*, **32**, 1 (2009).
19. K.P.F. Siqueira, R.L. Moreira, M. Valadares and A. Dias, *J. Mater. Sci.*, **45**, 6083 (2010).
20. J.C. Sczancoski, L.S. Cavalcante, M.R. Joya, J.a. Varela, P.S. Pizani and E. Longo, *Chem. Eng. J.*, **140**, 632 (2008).
21. J. Bi, L. Wu, Z. Li, Z. Ding, X. Wang and X. Fu, *J. Alloys Comp.*, **480**, 684 (2009).
22. T. Thongtem, A. Phuruangrart and S. Thongtem, *Curr. Appl. Phys.*, **8**, 189 (2008).