Effect of Flux NH_4F on Structure and Luminescence Properties of $\text{SrMoO}_4\text{:Tb}^{3+}$ Phosphors Synthesized by Microwave Radiation Method

YONG-QING ZHAI^{1,*}, RUI-FANG LI¹, YAO-XUAN CUI¹, SHAN-SHAN SONG¹ and JIA QIAO²

¹College of Chemistry and Environmental Science, Hebei University, Baoding 071002, P.R. China

²College of Mechanical and Electrical Engineering, Agricultural University of Hebei, Baoding 071002, P.R. China

*Corresponding author: E-mail: zhaiyongqinghbu@163.com

Received: 21 October 2013;

Accepted: 21 January 2014;

Published online: 30 September 2014;

AJC-16098

$\text{SrMoO}_4\text{:Tb}^{3+}$ green-emitting phosphors were prepared by microwave radiation method at medium-high power (560 W) for 0.5 h using active carbon as microwave absorbent and NH_4F as the flux. The effect of flux NH_4F on crystal structure, morphology and luminescent properties of samples were investigated by X-ray powder diffraction, scanning electron microscope and fluorescence spectrophotometer respectively. The results show that NH_4F -added samples are Scheelite-type tetragonal phase SrMoO_4 with space group $I4_1/a$. The particles of $\text{SrMoO}_4\text{:Tb}^{3+}$ phosphors prepared with flux NH_4F have smooth surface and are larger than that of sample with no flux. With the increase of NH_4F dosage, the location and shape of the excitation and emission spectra have no obvious change, but the luminescent intensity strongly depends on the dosage of NH_4F . When the dosage of NH_4F is 4 wt %, the emission intensity reaches to the maximum. Compared with the sample without flux, the intensity is enhanced about 58 %.

Keywords: Microwave radiation method, $\text{SrMoO}_4\text{:Tb}^{3+}$, Green phosphors, Flux, NH_4F , Luminescence.

INTRODUCTION

Recently, white light emitting diodes (WLEDs) with small size, high luminous reliability, long lifetime, low energy consumption and environment-friendly characteristics^{1,2} have attracted much attention due to its widespread technological applications, such as backlighting for liquid crystal displays, incandescent and auto lamps, the landscape lighting and other emerging areas³⁻⁶.

It is well known that there are two approaches to generating white light in light emitting diodes. One is to mix different color lights emitted directly by tricolor chips; the other is to mix different colors obtained by converting the emission of blue or ultraviolet LED chip to longer-wavelength light using phosphors^{4,7}. Considered the feasibility, practicability, commercialization and other aspects, the latter is the main development direction of WLEDs in the future. Therefore, to develop tricolor phosphors with high conversion efficiency under UV excitation has important significance and has become research emphasis in solid-state lighting at present. On one hand, green-emitting phosphors can be used for the preparation of pure green LEDs and on the other hand, it can be used to form the green part in the three primary colors of WLEDs⁸.

Luminescence properties of phosphors strongly depend on the crystallization degree, particle size and morphology. Usually, the fluxes have a great influence on the ionic diffusions,

crystallization and the formation of the target in high temperature solid reaction⁹. Proper fluxing agent is added into the system to decrease melting point and improve the diffusion rate and the rate of solid reaction. For luminescent materials, it is beneficial to the formation of the matrix, the doped ions entering into matrix lattice easily and improving luminescence intensity of product^{10,11}.

In the present work, green-emitting phosphors $\text{SrMoO}_4\text{:Tb}^{3+}$ were prepared by microwave radiation method. This method has a lot of advantages, such as fast and efficient, simple operation and good heating uniformity. It provides a new idea for saving energy and reducing energy consumption. The influences of fluxing agent NH_4F on the crystal structure, morphology and luminescent properties of the obtained samples were investigated. The obtained samples exhibits excellent luminescent properties and can be excited effectively by UV at about 287 nm and show strong green emitting. Therefore, as-synthesized $\text{SrMoO}_4\text{:Tb}^{3+}$ shows good prospect for green phosphors of WLEDs.

EXPERIMENTAL

The powder samples of $\text{SrMoO}_4\text{:Tb}^{3+}$ were prepared by microwave radiation method. The starting materials were Tb_4O_7 , MoO_3 and SrCO_3 , with purity of 99.9, 99.9999 and 99.9 %, respectively. The other materials used in this study

include NH_4F (A.R.) as flux and active carbon (A.R.) as microwave absorbent.

The preparation process of $\text{SrMoO}_4:\text{Tb}^{3+}$ is as follows. According to the stoichiometric composition of $\text{SrMoO}_4:\text{Tb}^{3+}$, starting materials Tb_4O_7 , MoO_3 and SrCO_3 were mixed together with a certain amount of NH_4F and ground in a porcelain mortar for 0.5 h to ensure homogeneity and fine particle size. The mixture was placed in a corundum crucible inside a large covered ceramic crucible. The space between the corundum and the ceramic crucible was filled with active carbon as microwave absorbent or heating medium. Then, the crucibles were placed into a Galanz WG700SL2011 -KG microwave oven and heated for 0.5 h under the middle-high power (560 W). Subsequently, the samples were cooled to room temperature in air and ground into powder in a porcelain mortar to obtain the desired products.

Characterization: The crystal structure and the phase purity of the samples were examined by X-ray powder diffraction (XRD) using $\text{CuK}\alpha$ radiation (30 kV $\times$ 20 mA and a scanning speed 0.06 $^\circ/\text{s}$). The particle size and morphology of the samples were characterized with a scanning electron microscopy (SEM). The excitation and emission spectra of the samples were recorded on an F-380 fluorescence spectrophotometer. All measurements were carried out at room temperature.

RESULTS AND DISCUSSION

In order to investigate the influence of flux NH_4F dosage on the crystal structure and phase purity of samples, a series of samples have been prepared with different dosage of NH_4F varying between 0 and 10 wt %. The XRD patterns of the as-synthesized samples are shown in Fig. 1. It can be seen that the sample synthesized without flux exhibits SrMoO_4 phase together with a little amount of raw materials MoO_3 , which indicates that the reaction proceeded incompletely. When NH_4F is introduced as the flux, the peaks of MoO_3 phase become weak. When the dosage of NH_4F is increased to 4 wt %, the MoO_3 phase disappears and the XRD pattern is in good agreement with JCPDS card (No. 85-0809). So, the sample is pure Scheelite-type tetragonal structure SrMoO_4 with space group

Fig. 1. XRD patterns of samples obtained under different dosage of flux NH_4F

$\text{I4}_{1/a}$. No peaks of Tb compounds can be observed, which suggests that Tb^{3+} ions have been uniformly incorporated into the host lattice of SrMoO_4 . The sharp and narrow XRD peaks indicate that as-synthesized $\text{SrMoO}_4:\text{Tb}^{3+}$ phosphors have high crystallinity. When the amount of NH_4F is over 4 wt %, new phase SrF_2 appears and the intensity of diffraction peaks of SrF_2 increases slightly with the increase of NH_4F dosage.

SEM analysis: The effects of flux NH_4F on the morphology and particle size of $\text{SrMoO}_4:\text{Tb}^{3+}$ phosphors have been studied. Fig. 2 illustrates SEM images of phosphors prepared with no flux and 4 wt % NH_4F . It can be seen that the particles of $\text{SrMoO}_4:\text{Tb}^{3+}$ phosphors prepared with the addition of NH_4F have larger size and clearer interface compared with the sample without flux, which suggests that the introduction of flux NH_4F promotes the growth of $\text{SrMoO}_4:\text{Tb}^{3+}$ particles, enhance the crystallization degree and decrease surface defect.

Fig. 2. SEM images of $\text{SrMoO}_4:\text{Tb}^{3+}$ phosphor synthesized with different dosage of NH_4F , (a) 0 wt %, (b) 4 wt %

Luminescent properties: In order to investigate the influence of flux NH_4F dosage on the photoluminescence properties of the $\text{SrMoO}_4:\text{Tb}^{3+}$ powders, the as-synthesized samples were characterized by the photoluminescence excitation and emission spectra.

Excited by 287 nm, the emission spectra of samples were measured and shown in Fig. 3. It can be seen that the dosage of NH_4F has little effect on the shape and position of emission spectra. All the emission spectra are composed of a group of narrow peaks at about 490, 544, 586 and 621 nm, which can be ascribed to $^5\text{D}_4\text{-}^7\text{F}_j$ ($J = 6, 5, 4, 3$) electronic transition of Tb^{3+} , respectively⁹. The main emission peak at 544 nm due to

Fig. 3. Emission spectra of $\text{SrMoO}_4:\text{Tb}^{3+}$ with different dosage of NH_4F

$^5\text{D}_4-^7\text{F}_5$ transition of Tb^{3+} . It is worth noting that the dosage of NH_4F has great effect on the luminescent intensity. The intensity of emission peak at 544 nm first increases with the increase of NH_4F dosage, then decreases when NH_4F dosage exceeds 4 wt % (as shown in the inset in Fig. 3). The intensity of emission peak at 544 nm of as-prepared $\text{SrMoO}_4:\text{Tb}^{3+}$ phosphor with 4 wt % NH_4F reaches the maximum, which is 1.58 times of the sample with no flux. Therefore, it can be known that the appropriate doping amount of flux NH_4F can improve luminescent intensity of the sample significantly.

Fig. 4 shows the excitation spectra of $\text{SrMoO}_4:\text{Tb}^{3+}$ samples, which was obtained by monitoring the $^5\text{D}_4-^7\text{F}_5$ transition emission of Tb^{3+} at 544 nm. It can be seen that the shape of excitation spectra is similar and all of them consist of a broad band between 200 and 350 nm with a main peak at about 287 nm and some weak peaks between 350 nm and 500 nm. The broad band is ascribed to the charge-transfer band of Mo-O and $4f^8-4f^7 5d^1$ transition of Tb^{3+} . The weak peaks belong to $4f-4f$ transition of Tb^{3+12} . The dosage of NH_4F has little effect on the shape and position of the excitation spectra. But, the peak intensity of excitation spectra strongly depends on the dosage of NH_4F , it has the same trend as that of the emission spectra along with the dosage of NH_4F (as shown in the inset in Fig. 4).

The possible reason for above results is as follows. Luminescence properties have a lot to do with the phase purity and crystallinity of the sample. The more pure, more complete crystal phase is, the better luminescence properties perform. By the addition of flux agent at low concentration level in a phosphor material, the crystallinity of host lattice is improved by assisting ionic diffusion during high temperature processing and when the flux dosage is over a certain range, the excessive amount of liquid phase has an impact on the crystallization, destroy the luminescence center and the host structure to some extent and make the luminescent performance become poor, because of liquid viscosity increasing, the deposition of extra flux, crystal reunion and agglomeration between the particles in the process of cooling¹³. When NH_4F dosage exceeds 4 wt %, the generation of new phase SrF_2 (Fig. 1) as impurity makes the luminescence efficiency of Tb^{3+} decrease, at the same time, transparent vitreous material was observed in the process of experiment. Comprehensive consideration of the crystal

Fig. 4. Excitation spectra of $\text{SrMoO}_4:\text{Tb}^{3+}$ with different dosage of NH_4F

structure, phase purity and luminescence properties, the optimum dosage of NH_4F is 4 wt %.

Conclusion

In the present work, green phosphors $\text{SrMoO}_4:\text{Tb}^{3+}$ has been synthesized by microwave radiation method, in which NH_4F were used as the flux. The results show that the introduction of flux NH_4F is conducive to the improvement of phase purity and crystallinity of $\text{SrMoO}_4:\text{Tb}^{3+}$. Meanwhile, flux NH_4F is helpful to increase the particle size and decrease surface defect. The luminescent intensity of $\text{SrMoO}_4:\text{Tb}^{3+}$ can be enhanced obviously by adding proper amount of NH_4F and reaches the maximum when the dosage of NH_4F is 4 wt %. Compared with the sample with no flux, the intensity is enhanced about 58 %. Therefore, the obtained $\text{SrMoO}_4:\text{Tb}^{3+}$ powders exhibit good prospect for green phosphors of white light emitting diodes because of their excellent luminescence performance.

ACKNOWLEDGEMENTS

This study was supported by National Natural Science Foundation of China (No. 20675023).

REFERENCES

- Y.Q. Zhai, Z.J. You, Y.H. Liu, Y.P. Sun and Q.Q. Ji, *J. Rare Earths*, **30**, 114 (2012).
- A. Xie, X.M. Yuan, F.X. Wang, Y. Shi, J. Li, L. Liu and Z.F. Mu, *J. Alloys Comp.*, **501**, 124 (2010).
- X.H. He, J. Zhou, N. Lian, J.H. Sun and M.Y. Guan, *J. Lumin.*, **130**, 743 (2010).
- Z.L. Wang, H.B. Liang, M.L. Gong and Q. Su, *J. Alloys Comp.*, **432**, 308 (2007).
- Md. Haque, H. I. Lee and D. K. Kim, *J. Alloys Comp.*, **481**, 792 (2009).
- P.L. Li, Z.J. Wang, Z.P. Yang, Q.L. Guo and X. Li, *J. Lumin.*, **130**, 222 (2010).
- X. Li, Z.P. Yang, L. Guan and Q.L. Guo, *Mater. Lett.*, **63**, 1096 (2009).
- S.X. Cao, T. Han and M.J. Tu, *Mater. Rev.*, **25**, 65 (2011).
- N. Niu, P.P. Yang, W.X. Wang, F. He, S.L. Gai, D. Wang and J. Lin, *Mater. Res. Bull.*, **46**, 333 (2011).
- D.M. Yang, H.X. Ji, L.M. Xie, L. Wei and W.Y. Hu, *J. Chin. Ceram. Soc.*, **39**, 1239 (2011).
- S.Q. Xu, L.Z. Sun, Y. Zhang, H.D. Ju, S.L. Zhao, D.G. Deng, H.P. Wang and B.L. Wang, *J. Rare Earths*, **27**, 327 (2009).
- A.P.A. Marques, F.V. Motta, M.A. Cruz, J.A. Varela, E. Longo and I.L.V. Rosa, *Solid State Ion.*, **202**, 54 (2011).
- Z.Y. Feng, W.D. Zhuang, X.W. Huang, X.F. Wen and Y.S. Hu, *J. Rare Earths*, **28**, 351 (2010).