Ionic Liquid [Bmim]PF₆ Plasticize Poly(lactic Acid)†

ZHOUFENG WANG^{1,*}, PENG CHEN¹, ZHICHONG CHEN¹ and ZHIXIANG YU²

¹School of Materials Science and Engineering, Anhui University of Science and Technology, Huainan 232001, P.R. China

²Shangyu Shaofeng Chemical Co. Ltd., Shangyu 312375, China

*Corresponding author: Fax: +86 531 6668649; E-mail: zfwang@aust.edu.cn

Published online: 10 March 2014;

AJC-14883

Room temperature ionic liquid 1-butyl-3-methylimidazolium hexafluorophosphate ([Bmim]PF₆) was studied as novel plasticizers for poly(lactic acid). The mixture process was carried out in molten state. [Bmim]PF₆ were found to be excellent plasticizers for poly(lactic acid), with improved thermal stability and plasticity. The microstructure indicated that novel plasticizer make agglomeration of CaCO₃ particles and phase separation easy, which might be due to the reduction of melt viscosity and the [Bmim]PF₆ concentration on the CaCO₃ particles.

Keywords: Ionic liquid, Poly(lactic acid), Mechanical properties, Thermal stability.

INTRODUCTION

Poly(lactic acid) (PLA) is one of the most studied biodegradable polymers mainly because of its high mechanical properties and easy production from its monomer. At present, the monomer of PLA is produced by fermentation from agricultural products. Poly(lactic acid) is eco-friendly and exhibits interesting physical properties, which can be further modulated by simply blending with selected additives in the molten state. In spite of all these advantages, its range of application is still limited by high production cost, brittleness and low thermal stability¹.

Plasticizers are added to polymer formulations to reduce glass transition temperature and impart flexibility to materials under conditions where they are normally used. Dioctyl phthalate (DOP) is the most widely used plasticizer, as it is highly compatible with polymers². Dioctyl phthalate is being questioned worldwide because of their potential toxicity to humans and the environment, so it is a huge challenge to develop new plasticized materials that have better performance in harsh environments, longer lifetimes and reduced toxicity. In this context, ionic liquids (ILs) are currently being presented as interesting alternatives to replace plasticizers¹⁻⁶. The general properties of ionic liquids, such as negligible vapor pressure, non-flammability, chemical and thermal stability, enable their use as solvents, thermal fluids, lubricants, dispersants and surfactants, antimicrobial agents and so on. Moreover, ionic

liquids have already been proved to be an efficient plasticizers for both synthetic¹⁻⁷ and natural-based polymers⁸.

In this study, ionic liquids 1-butyl-3-methylimidazolium hexafluorophosphate ([Bmim]PF₆) was used as plasticizer of PLA. The effect of [Bmim]PF₆ dosage on mechanical properties, processing performance and thermal stability have been evaluated by tensile and impact strength test, TGA/DTA and SEM.

EXPERIMENTAL

Poly(lactic acid) (PLA706) was purchased from Zhejiang Hisun Biomaterials Co., Ltd. [Bmim]PF₆ was purchased from Lanzhou Institute of Chemical Physics. Poly(lactic acid) was dried at 60 °C for 24 h before use. Reagents were used as received without further purification. Direct addition of [Bmim]PF₆ into the molten PLA in the mixing process. The concentrations of ionic liquids was 0, 0.4, 0.8, 1.2 and 2 %, respectively. Melt-kneading continued 6 min at 130 °C. The blends of PLA/[Bmim]PF₆ was forming a sheet of 4 mm after melt-kneading.

Techniques used to analyze the plasticized polymer samples included Impact Tester (Tanhor, TCJ-25J, CHN), Universal Testing Machine (Kaiqiangli, WDW-50, CHN), Melt Indexer (Tanhor, RZY-400, CHN), Thermogravimetric Analysis (TA, SDT2960, USA) and Scanning Electron Microscopy (Hitachi, S-3000N, JPN). Mechanical properties was tested according to GB/T 1040-1992 and GB/T 1043-1992.

†Presented at The 7th International Conference on Multi-functional Materials and Applications, held on 22-24 November 2013, Anhui University of Science & Technology, Huainan, Anhui Province, P.R. China

Melt Indexer was tested according to GB/T 3682-2000. TG was conducted using a thermal ramp rate of 10 K/min from 30–400 °C.

RESULTS AND DISCUSSION

Poly(lactic acid) materials are stiff, brittle and limited extendibility, [Bmim]PF₆ modified PLA substantially improved the ductile mechanical properties, as shown in Fig. 1. The prepared new ductile materials showed higher impact strength with the dosage of ionic liquids, but lower tensile strength. For the PLA modified with 2 % [Bmim]PF₆, impact strength was increased from 15.97 to 36.31 KJ/m², tensile strength was decreased from 53.0 to 41.8 MPa. Mechanical properties and the amount of ionic liquids showed linear trend in our experiments.

Fig. 1. Mechanical properties of [Bmim]PF₆ modified PLA materials

We evaluated the thermal stability of polylactic acid based on the TG/DTG. The thermal decomposition temperatures at 20 % (A point) and 50 % (B point) weight loss was connected with a line, which crossed with the baseline at C point. The temperature of C point was named as decomposition temperature of the PLA samples. The peak of DTG curve (D point) was the maximum weight lose rate temperature. In previous studies of ductile PLA, general plasticizers improved the ductility of PLA, but reduced the thermal properties of PLA. In contrast, the addition of [Bmim]PF₆ maintained the good thermal stability of PLA (Fig. 2) while improving the ductile mechanical properties of PLA (Fig. 1). the PLA/[Bmim]PF₆ showed much better thermal stability than pristine PLA. The decomposition temperature raise 10–36 °C and the maximum weight lose rate temperature raise 16–20 °C, which can be attributed to the high temperature stability of ionic liquids.

The morphology was elucidated by SEM to investigate the microstructure of modified materials. In Fig. 3a, pristine PLA showed a smooth and dense morphology. The white particles in the images was CaCO₃ particles which was mixed in the PLA in their produce process. When PLA was modified with [Bmim]BF₆ to prepare the ductile polymer material, the morphology of the fracture surface changed substantially. The CaCO₃ particles agglomerated and phase separation between PLA and CaCO₃ particles became difficult. The agglomeration

Fig. 2. TGA scan of PLA/[Bmim]PF₆ samples, A: 0 % [Bmim]PF₆; B: 0.4 % [Bmim]PF₆; C: 1.2 % [Bmim]PF₆; D: 2.0 % [Bmim]PF₆;

Fig. 3. SEM morphology of the samples fracture surface, A: 0 % [Bmim]PF₆; B: 0.4 % [Bmim]PF₆; C: 1.2 % [Bmim]PF₆

of CaCO₃ particles occurred in the course of plasticizing, the melt viscosity of PLA caused a strong reduction after the addition of [Bmim]PF₆, that had been proved based on strong increase of melt indexer (Fig. 1). That might make CaCO₃ particles agglomerate easy. The phase separation between PLA and CaCO₃ Particles might due to ionic liquids trend to concentrate on CaCO₃ Particles.

Conclusion

Ionic liquid [Bmim]PF₆ modified PLA demonstrated markedly improved ductile mechanical properties. The thermal stability of PLA became better, the decomposition temperature raise 10-36 °C and the maximum weight lose rate temperature raise 16-20 °C. Agglomeration of CaCO₃ particles and phase separation were found at samples fracture surface, which might due to the reduction of melt viscosity and the [Bmim]PF₆ concentration on the CaCO₃ particles. Ionic liquids as plasticizers may revolutionize the usage of flexible polymers at high temperatures, without brittleness or loss of mechanical strength. However, the ionic liquids is still expensive compared general plasticizers and limit its widespread application, the potential threat of ionic liquids to human and environment is still not clear.

ACKNOWLEDGEMENTS

This work is financially supported by Young Teacher Research Fund of Anhui University of Science and Technology (2012QNZ03).

REFERENCES

1. P. Xu, H.-G. Gui and Y.-S. Ding, *Ionics*, **19**, 1579 (2013).
2. M. Rahman, H.W. Shoff and C.S. Brazel, Ionic Liquids as Alternative Plasticizers for Poly(vinyl chloride): Flexibility and Stability in Thermal, Leaching and UV Environments, in *Ionic Liquids in Polymer Systems*, American Chemical Society, pp. 103-118 (2005).
3. A.M.A. Dias, S. Marceneiro, M.E.M. Braga, J.F.J. Coelho, A.G.M. Ferreira, P.N. Simões, H.I.M. Veiga, L.C. Tomé, I.M. Marrucho, J.M.S.S. Esperança, A.A. Matias, C.M.M. Duarte, L.P.N. Rebelo and H.C. de Sousa, *Acta Biomater.*, **8**, 1366 (2012).
4. M.P. Scott, M.G. Benton, M. Rahman and C.S. Brazel, Plasticizing Effects of Imidazolium Salts in PMMA: High-Temperature Stable Flexible Engineering Materials, in *Ionic Liquids as Green Solvents*, American Chemical Society, pp. 468-477 (2003).
5. F.-F. Tong, H. Xu, J. Yu, L.-X. Wen, J. Zhang and J.-S. He, *Ind. Eng. Chem. Res.*, **51**, 12329 (2012).
6. J. Zhu, J. Zhai, X. Li and Y. Qin, *Sens. Actuators B*, **159**, 256 (2011).
7. L. Guo, Y. Liu, C. Zhang and J. Chen, *J. Membr. Sci.*, **372**, 314 (2011).
8. K. Wilpiszewska and T. Szychaj, *Carbohydr. Polym.*, **86**, 424 (2011).