IR, EPR and Optical Absorption Studies of $x\text{CuO}-(1-x)\text{Bi}_2\text{O}_3$ Glasses

RAJESH KUMAR SHARMA* and V. ILAMATHI

Department of Chemistry, Kanchi Mamunivar Centre for Postgraduate Studies, Pondicherry-605 008, India

*Corresponding author: E-mail: rksepr@gmail.com

Received: 6 October 2017;

Accepted: 29 January 2018;

Published online: 28 February 2018;

AJC-18797

Glasses with composition $x\text{CuO}-(1-x)\text{Bi}_2\text{O}_3$ have been synthesized over the range $0.6 \leq x \leq 0.8$ mol % by sol-gel method. The IR studies show that the glassy system contains $[\text{BiO}_6]$ octahedral and $[\text{BiO}_3]$ pyramidal units. The X-band electron paramagnetic resonance and optical absorption studies were carried out to understand the nature of bonding, symmetry and local structure around Cu^{2+} ions in the glasses. The spin-Hamiltonian parameters have been calculated. The trends in g-values $g_{\parallel} > g_{\perp} > g_e$ (2.0023), calculated from the observed EPR spectra show that Cu^{2+} ions are coordinated with six ligand atoms in a distorted octahedron elongated along z-axis and the ground state of the Cu^{2+} is $d_{x^2-y^2}$ orbital ($^2B_{1g}$ state) having D_{4h} symmetry. The optical absorption spectra of all the glass samples show a broad band corresponding to $^2B_{1g} \rightarrow ^2B_{2g}$ transition of Cu^{2+} ion. By correlating the EPR and optical absorption spectral data, the molecular orbital coefficients, α^2 and β_1^2 have been evaluated.

Keywords: Glasses, IR, Electron paramagnetic resonance, Bonding parameters, Optical absorption.

INTRODUCTION

CuO -containing glasses draw special attention because of their different electrical conductivity [1] and structure-property behaviour [2,3] compared to the glasses containing V_2O_5 [4] and MoO_3 [5]. In the case of CuO , during the reduction process by citric acid for gel formation [6], Cu^+ ($3d^{10}$) ions are formed. The Cu^{2+} ($3d^9$) ion is an interesting paramagnetic site to study the nature of bonding and site symmetry [7] by electron paramagnetic resonance (EPR) spectroscopy. Electron paramagnetic resonance investigations of Cu^{2+} ions in glasses are interesting and have received a considerable attention due to the sensitivity of parameters to local symmetry and have been studied in wide variety of glasses [8]. Furthermore, in the case of Bi_2O_3 -containing glasses, the structural complications involving the different units in the network, makes it interesting to study the structural-property relations in such systems. Unconventional glasses containing Bi_2O_3 as glass former are of great interest because of their potential applications in industry and many allied areas [9]. By correlating the electron paramagnetic resonance and optical absorption spectra, we obtain information regarding the bond parameters that determine the metal-ligand bond nature in the glasses. In this paper we study the changes in IR, electron paramagnetic resonance and optical absorption parameters as a result of the variation in glass composition.

EXPERIMENTAL

In the present study, three glass samples of compositions $x\text{CuO}-(1-x)\text{Bi}_2\text{O}_3$ ($0.6 \leq x \leq 0.8$) were prepared by sol-gel method via nitrate-citrate gel route using reagent grade chemicals $[\text{Bi}(\text{NO}_3)_3]$, $[\text{Cu}(\text{NO}_3)_2]$ and citric acid. Three samples were labeled as A1, A2 and A3. Calculated amounts of $[\text{Cu}(\text{NO}_3)_2]$ and $[\text{Bi}(\text{NO}_3)_3]$ were dissolved in dil. HNO_3 to prepare 0.05 M solutions. These solutions were then mixed with 2 M citric acid solution to prepare the sol. The resulting sol was air dried by heating at about 60°C to prepare the gel which was then decomposed at $\sim 120^\circ\text{C}$. Finally, the samples were prepared by melting them in alumina crucibles in the range 1073-1133 K. The melt was air quenched by pressing between two ice cold aluminum plates to prepare the glass. The glass formation was confirmed by powder X-ray diffraction recorded with a Phillips type PW 1050 diffractometer using $\text{CuK}\alpha$ radiation. The IR spectra of the samples at room temperature were recorded in the range $4000-400\text{ cm}^{-1}$ by a Shimadzu FTIR-8700 spectrometer using KBr pellet technique. The EPR spectra were recorded on an EPR spectrometer (JEOL-FE-1X) operating in the X-band frequency ($H \approx 9.200\text{ GHz}$) with a field modulation frequency of 100 kHz. A powdered glass sample of 100 mg was placed in a quartz tube for EPR measurements. The optical absorption spectra of the glasses were recorded using a UV-visible spectrophotometer in the wavelength region 500-900 nm.

RESULTS AND DISCUSSION

The X-ray diffraction (XRD) spectra of glass samples are shown in Fig. 1. A broad peak around 30° in 2θ vanishing at higher diffraction angles is characteristic of a glass. The absence of sharp peaks in XRD patterns exhibit that the glass samples do not possess long range periodic lattice arrangement of a crystal. A broad hump observed in the XRD patterns further confirms that the samples show amorphous nature. In Fig. 2 we show the room temperature IR spectra of glasses A1-A3 in the range $4000\text{--}400\text{ cm}^{-1}$.

Fig. 1 XRD patterns of $x\text{CuO}-(1-x)\text{Bi}_2\text{O}_3$ ($0.6 \leq x \leq 0.8$) glasses

Fig. 2. FTIR spectra of $x\text{CuO}-(1-x)\text{Bi}_2\text{O}_3$ ($0.6 \leq x \leq 0.8$) glasses

In copper phosphate glasses, it is reported in literature [1] that copper exists as Cu^+ and Cu^{2+} ions and the environment of Cu^{2+} ion is tetragonally distorted octahedron, $[\text{O}_{1/2}\text{--CuO}_{4/2}\text{--O}_{1/2}]$ [10]. It is also reported in literature [11] that Bi_2O_3 cannot form glasses by itself, in the presence of conditional glass

formers such as V_2O_5 , CuO , *etc.* or a strong polarizing cation such as Si^{4+} , it reduces its coordination number from six in the $[\text{BiO}_6]$ octahedral to three in $[\text{BiO}_3]$ pyramidal units and forms the glass network. The sharp and intense peak in the range $883\text{--}874\text{ cm}^{-1}$ in A1-A3 is due to the symmetric stretching [11] vibration mode of $[\text{CuO}_6]$ octahedral unit and has approximately the same intensity for A1-A3. The weak peak in the range $457\text{--}465\text{ cm}^{-1}$ in A1-A3 is ascribed to the symmetric bending mode [12] of $[\text{BiO}_3]$ pyramidal units. The peak at 668 cm^{-1} in A1-A5 is due to the symmetric stretching mode [13] of $[\text{BiO}_6]$ octahedral unit in the matrices.

The room temperature X-band EPR spectra of the present glasses are shown in Fig. 3. Cu^{2+} ions with $S = 1/2$ have a nuclear spin of $I = 3/2$ for both ^{63}Cu (natural abundance 69 %) and ^{65}Cu (natural abundance 31 %). For Cu^{2+} ions, a regular octahedral site may not exist, as the cubic symmetry is disturbed by the electronic hole in the degenerate $d_{x^2-y^2}$ orbital and this produces the tetragonal distortion. The EPR spectra of Cu^{2+} ions in glasses can be analyzed by using an axial spin-Hamiltonian of the form:

$$H = \beta_e g_{\parallel} B_z S_z + \beta_e g_{\perp} (B_x S_x + B_y S_y) + A_{\parallel} I_z S_z + A_{\perp} (S_x I_x + S_y I_y) \quad (1)$$

where the symbols have their usual meaning [14]. The nuclear quadrupole and nuclear Zeeman interaction terms are ignored due to their negligible contribution. From the Fig. 3 it is observed that the absorption spectra are asymmetric, characteristic of Cu^{2+} ($3d^9$) ions in axially distorted octahedral symmetric sites. It is observed that the EPR lineshapes in the compositional range ($0.6 \leq x \leq 0.8$) exhibit high structural stability of the glassy matrix. The spectra show the hyperfine structure due to the interaction of the unpaired electron spin with the nuclear one, $I = 3/2$, characteristic of Cu^{2+} . The hyperfine structure shows poorly resolved parallel band of the spectra and unresolved perpendicular line typical of ^{63}Cu or ^{65}Cu system. Three

Fig. 3. EPR spectra of $x\text{CuO}-(1-x)\text{Bi}_2\text{O}_3$ ($0.6 \leq x \leq 0.8$) glasses

hyperfine lines are observed on the parallel features of the spectrum. The hyperfine lines are not observed on the perpendicular features of the spectrum as a result of individual line broadening which is due to the increased dipolar interactions with the ligand field fluctuations around the paramagnetic ion. The values of spin-Hamiltonian parameters $g_{\parallel}$, $g_{\perp}$, $A_{\parallel}$ and $A_{\perp}$ were estimated from the spectra and are given in Table-1.

TABLE-1
EPR AND OPTICAL PARAMETERS OF THE
GLASS SYSTEM $x\text{CuO}-(1-x)\text{Bi}_2\text{O}_3$

Parameters	$x = 0.6$	$x = 0.7$	$x = 0.8$
$g_{\parallel}$	2.367	2.354	2.355
$g_{\perp}$	2.055	2.056	2.056
$A_{\parallel} \times 10^{-4} (\text{cm}^{-1})$	147	146	147
$A_{\perp} \times 10^{-4} (\text{cm}^{-1})$	33	33	33
$\lambda (\text{nm})$	690	690	700
$\Delta E_{xy} (\text{cm}^{-1})$	14493	14493	14286
α^2	0.836	0.820	0.824
β_1^2	0.95	0.94	0.92
$\Gamma_{\sigma} (\%)$	36	39	38
$\Gamma_{\pi} (\%)$	10	12	16

The change in spin Hamiltonian parameters with composition can be attributed to the variation of ligand field around Cu^{2+} . The observed values of $g_{\parallel}$ and $g_{\perp}$ suggest that the Cu^{2+} ions in the glasses are coordinated by six ligands that form an octahedron elongated along the Z-axis [15,16]. As $g_{\parallel} > g_{\perp} > g_e (= 2.0023)$, it is confirmed that ground state for Cu^{2+} ions is $d_{x^2-y^2}$ orbital ($^2B_{1g}$ state), the Cu^{2+} ion being located in distorted octahedral site (D_{4h}) elongated along the Z-axis. The optical absorption spectra of glassy system are shown in Fig. 4. A single absorption band in near-infrared region is observed in all samples, which are attributed to $d-d$ transition band due to Cu^{2+} ions [17]. Cu^{2+} undergoes a Jahn-Teller distortion, which leads to the splitting of energy levels in terms of ligand field theory [18]. It is observed that the elongated structures are usually more energetically favoured than the compressed ones [19]. Hence, in the present study, the observed broad and asymmetric band for the samples (A1-A3) is due to overlap of $^2B_{1g} \rightarrow ^2A_{1g}$ and $^2B_{1g} \rightarrow ^2B_{2g}$ transitions. The optical absorption spectra of all the samples (A1-A3) are similar, showing one strong band as a result of the transition $^2B_{1g} \rightarrow ^2B_{2g}$ at 14286 cm^{-1} . Most of the authors [20,21] assigned the observed optical peak to the $^2B_{1g} \rightarrow ^2B_{2g}$ transition and have used this value in the evaluation of the bonding parameters. The intensity of absorption band is maximum in A3 ($x = 0.8$). The transition $^2B_{1g} \rightarrow ^2B_{2g}$ is a measure of $10 Dq$. The observed absorption bands obtained in the present work are in good agreement with those reported by earlier workers [22-24]. We determine the bonding coefficients of Cu^{2+} from the absorption frequencies of optical absorption bands. By correlating EPR and optical absorption data, we evaluate the bonding coefficients of Cu^{2+} . The bonding between the Cu^{2+} ion and its ligands can be described in terms of the covalency parameters α^2 and β_1^2 ; where α^2 describes the in-plane σ bonding with the copper $d_{x^2-y^2}$ orbital and the β_1^2 is a measure of the in-plane π bonding with the d_{xy} orbital. The values of α^2 lie between 0.5 and 1, the limits of pure covalent and pure ionic bonding, respectively.

Fig. 4. Optical absorption spectra of $x\text{CuO}-(1-x)\text{Bi}_2\text{O}_3$ ($0.6 \leq x \leq 0.8$) glasses

The bonding parameters were evaluated using the equations [25] given below:

$$\alpha^2 = (g_{\parallel} - g_e) + 3/7(g_{\perp} - g_e) - A_{\parallel}/0.036 + 0.04 \quad (2)$$

where P , the dipolar hyperfine coupling parameter = 0.036 cm^{-1} and $A = (1/3 A_{\parallel} + 2/3 A_{\perp})$.

The bonding coefficients of Cu^{2+} are evaluated using the following equations [26] by correlating EPR and optical absorption data.

$$g_{\parallel} = 2.0023 \left(1 - \frac{4\lambda\alpha^2\beta_1^2}{\Delta E_{xy}} \right) \quad (3)$$

ΔE_{xy} is the energy corresponding to the transitions $^2B_{1g} \rightarrow ^2B_{2g}$ and λ is the spin-orbit coupling constant ($= -828 \text{ cm}^{-1}$) [27]. In the present work, values of α^2 and β_1^2 are similar in A1-A3 in the composition range ($0.6 \leq x \leq 0.8$). The calculated values of the parameter α^2 and β_1^2 given in Table-1, show an ionic nature for the Cu (II)-O in-plane σ bonding and the in-plane π bonding. From the calculated values of α^2 and β_1^2 , two more variables that give an idea about the basicity of the oxide ion can be calculated. The normalized covalency of the Cu(II)-O in-plane bonding of σ and π symmetry is expressed [28] in terms of bonding coefficients α^2 and β_1^2 .

$$\Gamma_{\sigma} (\%) = 200 (1-S) (1-\alpha^2)/(1-2S) \quad (4)$$

$$\Gamma_{\pi} (\%) = 200 (1-\beta_1^2) \quad (5)$$

where S is the overlapping integral ($S_{\text{oxygen}} = 0.076$). The normalized covalency (Γ_{π}) of Cu(II)-O bonding of π symmetry indicates the basicity of the oxide ion. We observe that the covalency of the in-plane σ bonding (Γ_{σ}) is constant whereas the covalency of in-plane π bonding (Γ_{π}) increases.

Conclusion

The IR spectral analysis confirms the presence of [BiO₆] octahedral and [BiO₃] pyramidal units in the glass. From the spin-Hamiltonian parameters of EPR and optical absorption data, it is observed that Cu²⁺ ions in all the samples have occupied tetragonally distorted octahedral sites elongated along z-axis with d_{x²-y²} orbital (²B_{1g} state) as the ground state. The optical absorption spectra of the glasses show a single broad band due to ²B_{1g}→²B_{2g} transition of Cu²⁺ ions in axially elongated octahedral sites. The values of the molecular orbital bonding parameters show that in-plane σ bonding and the in-plane π bonding are ionic in nature. The covalency of in-plane σ bonding (Γ_σ) is constant, whereas the covalency of in-plane π bonding (Γ_π) increases.

REFERENCES

1. A. Duran, J.R. Jurado and J.M. Fernandez Navarro, *J. Non-Cryst. Solids*, **79**, 333 (1986); [https://doi.org/10.1016/0022-3093\(86\)90232-2](https://doi.org/10.1016/0022-3093(86)90232-2).
2. A. Murali and J.L. Rao, *J. Phys. Condens. Matter*, **11**, 7921 (1999); <https://doi.org/10.1088/0953-8984/11/40/316>.
3. R.P.S. Chakradhar, K.P. Ramesh, J.L. Rao and J. Ramakrishna, *J. Phys. Condens. Matter*, **15**, 1469 (2003); <https://doi.org/10.1088/0953-8984/15/9/311>.
4. M. Sayer and A. Mansingh, *Phys. Rev. B*, **6**, 4629 (1972); <https://doi.org/10.1103/PhysRevB.6.4629>.
5. U. Selvaraj and K.J. Rao, *J. Non-Cryst. Solids*, **72**, 315 (1985); [https://doi.org/10.1016/0022-3093\(85\)90187-5](https://doi.org/10.1016/0022-3093(85)90187-5).
6. B.B. Das and R. Ambika, *Chem. Phys. Lett.*, **370**, 670 (2003); [https://doi.org/10.1016/S0009-2614\(03\)00077-0](https://doi.org/10.1016/S0009-2614(03)00077-0).
7. D.L. Griscom and R.E. Griscom, *J. Chem. Phys.*, **47**, 2711 (1967); <https://doi.org/10.1063/1.1712288>.
8. I. Ardelean, M. Peteanu, R. Ciceo-Lucacel and I. Bratu, *J. Mater. Sci.: Mater. Electr.*, **11**, 11 (2000); <https://doi.org/10.1023/A:1008943901463>.
9. S. Bale, M. Purnima, C.H. Srinivasu and S. Rahman, *J. Alloys Compd.*, **457**, 545 (2008); <https://doi.org/10.1016/j.jallcom.2007.03.100>.
10. V.A. Kolesova, *Fiz. Khim. Stekla*, **12**, 4 (1986).
11. A. Bishay and C. Maghrabi, *Phys. Chem. Glasses*, **10**, 1 (1969).
12. K. Nakamoto, *Infrared and Raman Spectra of Inorganic and Coordination Compounds*, John Wiley & Sons, New York, p. 118 (1986).
13. S. Hazra, S. Mandal and A. Ghosh, *J. Chem. Phys.*, **104**, 10041 (1996); <https://doi.org/10.1063/1.471748>.
14. B. Bleaney, K.D. Bowers and D.J.E. Ingram, *Proc. Royal Soc. Lond. A Math. Phys. Sci.*, **228**, 147 (1955); <https://doi.org/10.1098/rspa.1955.0039>.
15. I. Ardelean, M. Peteanu, R. Ciceo-Lucacel and I. Bratu, *J. Mater. Sci. Mater. Electron.*, **11**, 11 (2000); <https://doi.org/10.1023/A:1008943901463>.
16. T. Taoufik, M. Haddad, A. Nadiri, R. Brochu and R. Berger, *J. Phys. Chem. Solids*, **60**, 701 (1999); [https://doi.org/10.1016/S0022-3697\(98\)00067-5](https://doi.org/10.1016/S0022-3697(98)00067-5).
17. I. Siegel and J.A. Lorenc, *J. Chem. Phys.*, **45**, 2315 (1966); <https://doi.org/10.1063/1.1727927>.
18. A.A. Ahmed, A.F. Abbas and F.A. Moustafa, *Phys. Chem. Glasses*, **24**, 43 (1983).
19. C.K. Jorgensen, L.H. Smith, G. Hanshoff and H. Prydz, *Acta Chem. Scand.*, **9**, 1362 (1955); <https://doi.org/10.3891/acta.chem.scand.09-1362>.
20. A.H. Dietzel, *Phys. Chem. Glasses*, **24**, 172 (1983);
21. B.V. Raghavaiah, C. Laxmikanth and N. Veeraiah, *Opt. Commun.*, **235**, 341 (2004); <https://doi.org/10.1016/j.optcom.2004.02.082>.
22. G. van Veen, *J. Magn. Reson.*, **30**, 91 (1969); [https://doi.org/10.1016/0022-2364\(78\)90228-7](https://doi.org/10.1016/0022-2364(78)90228-7).
23. H.G. Hetch and T.S. Johnston, *J. Chem. Phys.*, **46**, 23 (1967); <https://doi.org/10.1063/1.1840378>.
24. V. Kamalaker, G. Upender, M. Prasad and V. Chandra Mouli, *Indian J. Pure Appl. Phys.*, **48**, 709 (2010).
25. H.A. Kuska, M.T. Rogers and R.E. Drullinger, *J. Phys. Chem.*, **71**, 109 (1967); <https://doi.org/10.1021/j100860a015>.
26. D. Kivelson and R. Neiman, *J. Chem. Phys.*, **35**, 149 (1961); <https://doi.org/10.1063/1.1731880>.
27. F.M. Mabbs and D.J. Machin, *Magnetism and Transition Metal Complexes*, Chapman and Hall: London, p. 154 (1973).
28. A. Yadav, V.P. Seth and P. Chand, *J. Mater. Sci. Lett.*, **6**, 468 (1987); <https://doi.org/10.1007/BF01756801>.