Stress Analysis and Failure Prediction of Adhesively Bonded Single-lap Laminates Joints Subjected to the Tensile Loading

Yinhuan Yang

*School of Energy and Civil Engineering, Harbin University of Commerce, Harbin
150028, China
yangyh80@163.com*

Abstract

On the basis of the existing experimental results and considering five kinds of failure modes, failure prediction of adhesively bonded single-lap laminates joints with adherend thickness 3mm, adherend thickness 2mm and defect in the adhesive layer under uniaxial tensile loading is performed by progressive failure analysis method. The numerical analysis of composites adhesive joints is implemented in ANSYS Parametric Design Language (APDL) with commercial finite element codes ANSYS. The error of computational and experimental failure loads is 3.0%. Evolution of adhesive progressive damage is simulated effectively and the initial position and reason of damage is discovered. Furthermore, a finite element simulation is carried out to analyze the stress distributions in the mid-surface of the adhesive layer and the bonding interface. It is found that stress concentration is all emerged near by 1.25mm on the overlap zone ends, that is the initial point of damage, and it is the main factor that the joint strength is affected by peel/shear stress concentrations at overlap zone ends. The computational results are in good agreement with the experimental values.

Keywords: *single-lap; laminates joints; progressive failure analysis; stress distribution*

1. Introduction

Advanced composites are being increasingly used in structural applications especially in industries such as aeronautics and automotive. Failure analysis of the adhesively bonded joints is the critical problem to be settled [1, 2]. The basic steps of progressive failure analysis are summarized by Ochoa and Reddy [3]. The finite element method is prior applied to analyze failure process of composites by Lee [4]. Progressive failure analysis of composites adhesive joints is presented by the references [5-7]. According to the references, progressive failure analysis have not been reported on T700/EPOXY unidirectional laminates single-lap adhesive joints with adherend thickness 3mm, adherend thickness 2mm and defect in the adhesive layer under tensile loading.

Therefore, failure prediction of the three kinds of joints uniaxial tensile loading is performed by progressive failure analysis method in this paper. The numerical analysis of laminates adhesive joints is implemented in ANSYS Parametric Design Language (APDL) to compile Shokrieh's improving failure criterion and maximum stress criterion. Five kinds of failure modes including matrix tensile failure, fibre fracture failure, matrix-fiber shear-out, delamination in tension and adhesive failure are considered. A sudden degradation model is proposed to reduce material properties. And then numerical results are compared with the experimental results [8, 9]. By the three kinds of laminates single-lap adhesive joints, failure mechanisms, modes and strengths is analyzed and compared with the experiment results using progressive failure analysis method. Finally, stress distributions are simulated in the mid-surface and interface of the adhesive layer.

2. Progressive Failure Analysis Model

A modified form of Hashin's failure criterion by Shokrieh [10] and maximum stress criterion are used to detect the laminate failure and adhesives failure, respectively, and five failure modes are considered as follows:

Adhesive failure:

$$\sigma_{11} < X_T, \quad \sigma_{22} < Y_T, \quad |\tau_{12}| < S; \quad (1)$$

where, X_T (Y_T)—adhesive tension strength, S — adhesive shear strength.

Fibre fracture failure:

$$\left(\frac{\sigma_{11}}{X_T}\right)^2 + \left(\frac{\tau_{12}}{S_{12}}\right)^2 + \left(\frac{\tau_{13}}{S_{13}}\right)^2 \geq 1 \quad (\sigma_{11} > 0) \quad (2)$$

Matrix tensile failure:

$$\left(\frac{\sigma_{22}}{Y_T}\right)^2 + \left(\frac{\tau_{12}}{S_{12}}\right)^2 + \left(\frac{\tau_{23}}{S_{23}}\right)^2 \geq 1 \quad (\sigma_{22} > 0) \quad (3)$$

Matrix-fiber shear-out:

$$\left(\frac{\sigma_{11}}{X_C}\right)^2 + \left(\frac{\tau_{12}}{S_{12}}\right)^2 + \left(\frac{\tau_{13}}{S_{13}}\right)^2 \geq 1 \quad (\sigma_{11} < 0) \quad (4)$$

Delamination in tension:

$$\left(\frac{\sigma_{33}}{Z_T}\right)^2 + \left(\frac{\tau_{13}}{S_{13}}\right)^2 + \left(\frac{\tau_{23}}{S_{23}}\right)^2 \geq 1 \quad (\sigma_{33} > 0) \quad (5)$$

where, X_T (X_C), Y_T , Z_T —tension(compression) strength; S_{12} , S_{13} , S_{23} —shear strength.

Matrix tensile failure, fiber fracture failure, matrix-fiber shear-out, delamination in tension and adhesive failure are considered and a sudden degradation model is used to reduce engineering material constants in Table 1. Accordingly, entire failure is taken for this element and all degradation engineering material constants are 0.

Table 1. Degradation Engineering Material Constants

Failure mode	E_{11}	E_{22}	E_{33}	G_{23}	G_{13}	G_{12}	ν_{12}	ν_{23}	ν_{13}
Matrix	1	0.2	1	0.2	1	0.2	0	1	1
Fibre	0	0	0	0	0	0	0	0	0
Matrix and fibre	1	1	1	1	1	0	0	1	1
Delamination	1	1	0	0	0	1	1	0	0
Adhesive	1	1	0.2	1	1	1	1	1	0

Displacement load is imposed on composite laminates and acquired force P_i is compared with P_{i-1} . If $\Delta P = |P_i| - |P_{i-1}| < 0$ and $|\Delta P| \geq 0.2 \cdot |P_{i-1}|$, the ultimate failure is happened for composite laminates.

3. Proposed Problem

A typical configuration of single-lap adhesive joint with adherend thickness 3mm and 2mm is shown in Figure 1. Geometry dimensions are shown in reference [8, 9]. Mechanical properties of laminates and adhesives are shown in Table 2 and Table 3, respectively.

Figure 1. T700/EPOXY Unidirectional Laminates Single-lap Adhesive Joints with Adherend Thickness 3mm (lap length 20mm, width 25mm, Adhesive Thickness 0.3mm)

Table 2. Mechanical Properties of Unidirectional Laminates (T700/EPOXY)

E_1/GPa	$E_2/E_3/\text{GPa}$	γ_{12}	γ_{13}	γ_{23}	G_{12}/GPa	G_{13}/GPa	G_{23}/GPa
134	9.6	0.29	0.29	0.3	4.8	4.8	5
X_T/MPa	X_C/MPa	Y_T/MPa	S_{12}/MPa	S_{13}/MPa	S_{23}/MPa	Z_T/MPa	Z_C/MPa
2097	1258	42.0	119	119	83.7	94	290

Table 3. Mechanical Properties of Adhesives

Type	E_1/GPa	γ	S/Mpa	$X_1/Y_1/\text{Mpa}$
J-272	2.87	0.4	25	45

The 3D FEM model and meshes are built up based on the ANSYS10.0 software. Cohesive element inter205 is applied in the adherends-adhesive interfaces. Both the adherends and adhesive layer are treated using Solid 45 element. Meshes of whole and local model are shown in Figure 2, and the maximum and minimum element dimensions are 1 and 0.15 mm, respectively. Boundary and loads conditions are shown in Figure 3.

Figure 2. Mesh of Whole and Local Models

Figure 3. Constrained Displacement and Application of Load

4. Failure Prediction

4.1. Strength Prediction

Numerical and experimental load-displacement curves of adhesively bonded laminates single-lap joints with adherend thickness 3mm under tensile loading are shown in Figure 4.

Figure 4. Load & Displacement Curves of Single-lap Adhesive Joints with Adherend Thickness 3mm ($t=0.3$ mm, $L=20$ mm)

In scope of displacement 0.46mm, load-displacement curve is linear and simulation curve is well fitted with the experimental curves. According to the experimental and simulation results, experimental and numerical failure load is 12.3kN and 12.67kN, respectively, and the error is 3.0%. Simulation results are in agreement with experiment results, which demonstrate the validity of the finite element analysis model.

4.2. Progressive Failure Analysis

According to the experiment results [8, 9], adhesive failure is the main failure mode. By the following three kinds of laminates single-lap adhesive joints, failure mechanisms and modes is analyzed and compared with the experiment results using progressive failure analysis method.

4.2.1 Joint with Adherend Thickness 3 mm: Evolution of adhesive damage on laminates single-lap adhesive joint with adherend thickness 3mm is shown in Figure 5. The initiation of adhesive failure is appeared from 1.46 mm on both ends of the overlap region and at the edge position of the width direction at the applied loading 10.56 kN. Adhesive failure is propagated gradually to two sides along the lap-length direction with the increasing load until the final failure is emerged. Therefore, it is demonstrated that stress concentrations is existed obviously in the overlap ends. The model has been validated and agreed well with experimental results [8].

Figure 5. Evolution of Adhesive Damage on Laminates Single-lap Adhesive Joint with Adherend Thickness 3 mm

4.2.1 Joint with Adherend Thickness 2 mm: Evolution of adhesive damage on laminates single-lap adhesive joint with adherend thickness 2 mm is shown in Figure 6. Shear failure is occurred in the bonding interface at the applied loading 9.07 kN. The starting point of damage is located from 1.25 mm on both ends of the overlap zone and at the edge position of the width direction. Interfacial shear failure by the overlap ends position is extended progressively to two sides with the increasing load until the ultimate failure is emerged. Thereby, it is demonstrated that stress concentrations is existed obviously in the overlap ends. The numerical results are in good agreement with the experimental results [9].

Figure 6. Evolution of Adhesive Interface Damage of SLJ with Adherend Thickness 2 mm

4.2.1 Joint with Defect in the Adhesive Layer: Evolution of adhesive damage on laminates single-lap adhesive joint with defect in the adhesive layer is shown in Figure 7. According to the simulating results, the initiation of damage is appeared at interface around the defect at the applied loading 8.25 kN. Interface fairlure around the defect is expanded relatively slow with the increasing load. As the applied load is arrived to 8.5 kN, shear interfacial failure is occurred at the overlap ends. The initiation of interfacial shear failure is appeared from 1.67 mm on both ends of the overlap region and at the edge position of the width direction, and is expanded progressively to two sides. At the same time, interface damage around the defect is expanded gradually to all around and interface damage around the defect is propagated faster along the lap-length direction than along the width direction. As the applied loading increases, damage area around the defect connected with interface damage by the overlap end lead to the eventual failure. it is found that stress concentrations is appeared obviously in the overlap ends and around the defect. The model are in good accordance with the experimental results [9].

Figure 7. Evolution of Adhesive Interface Damage of SLJ with Defect in the Adhesive

5. Stress Analysis

The load is imposed by the application of an uniaxial tension force of 9 kN, and will be uniformly distributed along the normal surface. mesh of the local model is shown in Figure 2.

5.1. Stress Distributions in the Mid-surface of the Adhesive Layer

In-plane stress $\sigma_x, \sigma_y, \tau_{xy}$ and out-of-plane stress $\sigma_z, \tau_{xz}, \tau_{yz}$ distributions on lanimates single-lap adhesive joint with adherend thickness 2 mm in the mid-surface of the adhesive layer are shown in Figure 8. It is found that shear stress τ_{xz} and peel stress σ_z concentrations is generated obviously in the overlap ends and shear/peel stress distributions are symmetrical along the lap length direction, nevertheless, peel stress is less than shear stress. For this reason, shear stress is the main factor to affect joint strengths.

Figure 8. Stress Distributions in the Mid-surface of the Adhesive Layer of Single-lap Adhesive Joint (Adhesive Thickness 0.3 mm, Lap Length 20 mm, Adherend Thickness 2 mm)

5.2. Stress Distributions in the Bonding Interface

In-plane stress $\sigma_x, \sigma_y, \tau_{xy}$ and out-of-plane stress $\sigma_z, \tau_{xz}, \tau_{yz}$ distributions on laminates single-lap adhesive joint with adherend thickness 2 mm in the bonding interface are shown in Figure 9. Compared with the stress values in the mid-surface of the adhesive layer, it is clear that stress values in the bonding interface is much greater than them in the mid-surface of the adhesive layer except for out-of-plane stress τ_{xz} and τ_{yz} . Consequently, it is easier relatively that interface failure is occurred. Compared with both stress distributions, stress concentration is all located from 1.25mm on the overlap zone ends, further, it is proved the position from 1.25mm on the overlap zone ends is the initial point of damage.

Figure 9. Stress Distributions in the Bonding Interface of Single-lap Adhesive Joint (Adhesive Thickness 0.3 mm, Lap Length 20 mm, Adherend Thickness 2 mm)

5. Conclusions

T700/EPOXY unidirectional laminates adhesively bonded single-lap joints with adherend thickness 3 mm, adherend thickness 2 mm and defect in the adhesive layer under the tensile loading have been investigated by progressive failure analysis method on the basis of the experimental results [8, 9]. According to a modified form of Hashin's failure criterion by Shokrieh and maximum stress criterion, a sudden degradation model is proposed to reduce engineering material constants. Mechanical behavior and failure mechanism of three kinds of joints is analyzed and stress distributions in the mid-surface of the adhesive layer and bonding interface is simulated, and the conclusions are as follows:

Using the interfacial element and progressive failure analysis model can well predict the failure strength of the joints with adherend thickness 3mm and the error of simulation and experimental failure load is 3.0%. Simulation results are in good agreement with experiment results, which demonstrate the validity of the model.

The initiation of adhesive failure and interfacial shear failure is discovered in both ends for joints with adherend thickness 3 mm and 2 mm, adhesive failure is expanded fast along the lap-length direction with the increasing load until ultimate failure is emerged.

The initiation of damage for the joint with defect in the adhesive layer is broken out around the defect, and damage area around the defect connected with interface damage by the overlap end lead to the eventual failure.

Stress values in the bonding interface is much greater than them in the mid-surface of the adhesive layer except for out-of-plane stress τ_{xz} and τ_{yz} . It is easier relatively that interface failure is occurred. further, it is found that stress concentration is all emerged near by 1.25mm on the overlap zone ends, that is the initial point of damage.

Acknowledgments

Fundation item: Dr. Start-up fund of Harbin university of commerce (13DL008).

References

- [1] L. F. M. Da Silva, P. J. C. Neves and R. D. Adam, “Analytical models of adhesively bonded joints—Part I: literature survey”, *International Journal of Adhesion & Adhesives*, vol. 29, **(2009)**, pp. 319-330.
- [2] T. Zeng and L. Jiangi, “Development of investigation into mechanical properties of 3D braided composites”, *Journal of Harbin University of Science and Technology*, vol. 16, **(2011)**, pp. 34-41, 47.
- [3] O. Ochoa and J. N. Reddy, “Finite Element Analysis of Composite Laminates. Kluwer Academic Publishers”, **(1992)**.
- [4] J. D. Lee, “Three Dimensional Finite Element Analysis of Damage Accumulation in Composite Laminate”, *Computers and Structures*, vol. 15, **(1982)**, pp. 335-350.
- [5] J. H. Oh, “Strength Prediction of Tubular Composite Adhesive Joints under Torsion, *Composites Science and Technology*”, vol. 67, **(2007)**, pp. 1340-1347.
- [6] Z. Chen, R. D. Adams and L. F. M. Da Silva, “Prediction of Crack Initiation and Propagation of Adhesive Lap Joints Using An Energy Failure Criterion”, *Engineering Fracture Mechanics*, vol. 78, **(2011)**, pp. 990-1007.
- [7] Y. Yang, “Progressive failure analysis of adhesively bonded laminates joints with spew fillets”, *Proceedings of the 4th International Conference on Manufacturing Science and Engineering*, **(2013)**.
- [8] Y. H. Yang, L. Z. Wu, Y. Guo and Z. G. Zhou, “Effect of adherent thickness on strength of single-lap adhesive composites joints”, *3rd International Conference on Heterogeneous Material Mechanics*, Shanghai, China, **(2011)**.
- [9] Y. Yang, Z. Zhou, Y. Guo and L. Wu, “Acta Materiae Compositae Sinica, Effect of defects in the adhesive layer on strength of adhesively bonded single-lap composites joints”, vol. 5, no. 29, **(2012)**, pp. 157-163.
- [10] W. J. Peng and J. Q. Chen, “Numerical Evaluation of Ultimate Strengths of Composites Considering both In-plane Damage and Delamination Key Engineering Materials”, **(2006)**, pp. 771-774.