Crystallization paths in $\text{SiO}_2\text{-Al}_2\text{O}_3\text{-CaO}$ system as a genotype of silicate materials

VASILY LUTSYK ■ Institute of Physical Materials Science (Siberian Branch of Russian Academy of Sciences), Ulan-Ude, Russian Federation ■ E-mail: vluts@ipms.bscnet.ru

ANNA ZELENAYA ■ Institute of Physical Materials Science (Siberian Branch of Russian Academy of Sciences), Ulan-Ude, Russian Federation ■ E-mail: zel_ann@mail.ru

Érkezett: 2013. 08. 25. ■ Received: 08. 25. 2013. ■ <http://dx.doi.org/10.14382/epitoanyag-jsbcm.2013.7>

Abstract

The phases trajectories in the fields of primary crystallization of cristobalite (SiO_2^{cr}), tridymite (SiO_2^{tr}), mullite ($3\text{Al}_2\text{O}_3 \cdot 2\text{SiO}_2$) and in a field of liquid immiscibility are analyzed on a basis of computer model for T-x-y diagram of $\text{SiO}_2\text{-Al}_2\text{O}_3\text{-CaO}$ system. The concentration fields with unique set of microconstituents and the fields without individual crystallization schemes and microconstituents are revealed.

Keywords: phase diagram, crystallisation path, $\text{SiO}_2\text{-Al}_2\text{O}_3\text{-CaO}$ system, computer model

1. Introduction

A phase diagram of system $\text{SiO}_2\text{-Al}_2\text{O}_3\text{-CaO}$ (S-A-C) has wide applications and can be used in the cement industry to describe the properties of Portland and aluminous cements [1-3], and in studies of refractories and alkali-free glass [4]. To extend the capabilities of research and examine the processes of crystallization for S-A-C system allows its computer model [5-6]. Analysis of concentration fields obtained by the projection of phase regions onto Gibbs triangle allows to establish the boundaries of phase regions (located above the considered fields), the sequence of phase transformations and microstructural elements in crystallized initial melt at the equilibrium condition. Based on this technology, the research identifies fields with coinciding sets of crystallization scheme and microconstituents and the fields with individual characteristics.

2. T-x-y diagram model for $\text{SiO}_2\text{-Al}_2\text{O}_3\text{-CaO}$ (S-A-C) system

The experimental data about the structure of S-A-C presented in the literature is usually confined to the surface of the primary crystallization (figure 1a) and triangles of coexistent phases [1-2, 7-9]. The spatial scheme of mono and invariant equilibria permits to restore the full construction of phase diagram. In the first stage a position of invariant planes are reproduced (figure 1b). Then the ruled surfaces of three-phase region borders are formed.

Let's consider the fragment of scheme adjoining to the component SiO_2 (figure 1c). The plane of four-phase regrouping of phases $\text{L}_U + \text{SiO}_2^{\text{cr}} \rightleftharpoons \text{R}_5 + \text{SiO}_2^{\text{tr}}$ has a degenerated structure $\text{U-R}_5\text{-S}_1\text{-U}$ ($\text{S}_1 = \text{SiO}_2^{\text{cr}}$ and $\text{S}_2 = \text{SiO}_2^{\text{tr, cr}}$ – cristobalite, $^{\text{tr}}$ – tridymite), because the points S_1U and S_2U coincide together. Two ruled surfaces $\text{S}_1\text{E}_4\text{-E}_4\text{-U-S}_1\text{U}$ and $\text{R}_5\text{E}_4\text{-E}_4\text{-U-R}_5\text{U}$ bounding the phase region $\text{L+S}_1+\text{R}_5$ fit to the plane. The plane of ternary eutectic point E_4 : $\text{L}^{\text{E}_4} \rightarrow \text{S}_2^{\text{E}_4} + \text{R}_5^{\text{E}_4} + \text{R}_{12}^{\text{E}_4}$ ($\text{S}_2^{\text{E}_4} = \text{R}_5^{\text{E}_4} = \text{R}_{12}^{\text{E}_4}$) is arranged below. Three pairs of ruled surfaces ($\text{S}_2\text{U-U-E}_5\text{-S}_2^{\text{E}_5}$, $\text{R}_5\text{U-U-E}_5\text{-R}_5^{\text{E}_5}$; $\text{S}_2\text{E}_4\text{-E}_4\text{-[E}_4\text{,E}_5\text{]-S}_2^{\text{E}_4\text{E}_5}$, $\text{R}_{12}\text{E}_4\text{-E}_4\text{-[E}_4\text{,E}_5\text{]-R}_{12}^{\text{E}_4\text{E}_5}$) are bounded the phase regions $\text{L+S}_2+\text{R}_5$, $\text{L+S}_2+\text{R}_{12}$, $\text{L+R}_5+\text{R}_{12}$. The ruled surfaces $\text{S}_2\text{E}_4\text{-E}_4\text{-[E}_4\text{,E}_5\text{]-S}_2^{\text{E}_4\text{E}_5}$, $\text{R}_{12}\text{E}_4\text{-E}_4\text{-[E}_4\text{,E}_5\text{]-R}_{12}^{\text{E}_4\text{E}_5}$ are formed from the maximum point $[\text{E}_4\text{,E}_5]$ on monovariant curve E_4E_5 . Three-phase region $\text{S}_2+\text{R}_5+\text{R}_{12}$ situates below the simplex $\text{S}_2^{\text{E}_5}\text{-R}_5^{\text{E}_5}\text{-R}_{12}^{\text{E}_5}$.

Step-by-step restoring of phase regions boundaries permits to obtain the complete model of phase diagram (figure 1d). The projection of phase regions of system S-A-C divides the Gibbs triangle onto 117 two-dimensional, 163 one-dimensional and 45 zero-dimensional concentration fields. It is previously found that the projection of primary crystallization fields CaO , C_3S and C_3A are divided onto 52 concentration fields (19 two-, 21 one- and 12 zero-dimensional), among which 18 fields (12 one- and 6 zero-dimensional) haven't unique set of microconstituents [10].

Let's consider the fragment of phase diagram adjoining to component SiO_2 and carry out the analysis of concentration fields under the surfaces of primary crystallization cristobalite (SiO_2^{cr}), tridymite (SiO_2^{tr}), mullite (A_3S_2) and a cupola of melt immiscibility (i).

3. Structure of phase diagram adjacent to component SiO_2

There are 18 ruled surfaces, 4 horizontal planes at the temperatures of invariant points (E_4 , E_5 , Q_8 , U), 4 vertical triangulation planes under the fields of primary crystallization SiO_2^{cr} (surface Q_{S_1} with the contour $\text{mknp}_3\text{Ue}_4\text{S}$), SiO_2^{tr} ($\text{Q}_{\text{S}_2} = \text{e}_3\text{E}_4[\text{E}_4\text{,E}_5]\text{E}_5\text{Up}_3$), A_3S_2 ($\text{Q}_{\text{A}_3\text{S}_2} = \text{e}_4\text{UE}_5\text{Q}_8\text{e}_5\text{R}_5$) and the surface of immiscibility melt (i – $\text{k}^0\text{nk}^0\text{m}$) (figure 2, table 1). The following designations are used: e and p – binary eutectic and peritectic points, m and n – binary points of monotectic segment, E and Q – ternary eutectic and quasiperitectic points, U – point of the four-phase regrouping with participation of two polymorphous modifications SiO_2^{cr} and SiO_2^{tr} , $[\text{E}_4\text{,E}_5]$ – maximum point on the monovariant curve E_4E_5 .

Vasily LUTSYK

Doct. Sci. (chemistry), Head of computer-aided materials design sector at the Institute of Physical Materials Science (Siberian Branch of the Russian Academy of Sciences). Research interests: functional ceramics, silicate systems for advanced technologies of building materials, pyrometallurgy, synthesis of refractory borides, silicides and intermetallics, metallic systems for lead-free solders.

Anna ZELENAYA

Cand. Sci. (phys.-math.), Senior Scientist at the Institute of Physical Materials Science (Siberian Branch of the Russian Academy of Sciences). Research interests: computer models of three-five phase diagram with different topology for microstructures design of heterogeneous materials, analysis of crystallization stages and identification the concentration fields with individual set of micro-constituents, simulation of phase diagram for ceramics, salt and metal systems.

Fig. 1. XY projection of primary crystallization surfaces (a); 3D scheme of invariant planes arrangement (b) and three-phase regions of diagram fragment adjoining to the component S (c); XY projection of all phase regions (d) ($R_1=C_3S$, $R_2=C_2S$, $R_3=C_3S$, $R_4=CS$, $R_5=A_3S_2$, $R_6=C_2A$, $R_7=C_{12}A_2$, $R_8=CA$, $R_9=CA_2$, $R_{10}=CA_3$, $R_{11}=C_2AS$, $R_{12}=CAS_2$)

1. ábra Elsődleges kristályosodási felületek XY vetülete (a); invariáns síkok elhelyezkedésének 3D sémája (b); háromfázisú diagramszakaszok az S-fázishoz tartozóan (c); az összes fázisrész XY vetülete (d) ($R_1=C_3S$, $R_2=C_2S$, $R_3=C_3S$, $R_4=CS$, $R_5=A_3S_2$, $R_6=C_2A$, $R_7=C_{12}A_2$, $R_8=CA$, $R_9=CA_2$, $R_{10}=CA_3$, $R_{11}=C_2AS$, $R_{12}=CAS_2$)

Fig. 2. XY projection (a) and 3D model (b) of fragment of system S-A-C phase diagram

2. ábra Az S-A-C fázisdiagram egy töredékének XY vetülete (a) és 3D modellje (b)

16 phase regions are located under the considered fields of primary crystallization: L_1+L_2 , $L+S_1$, $L+S_2$, $L+A_3S_2$, $S+CAS_2$, $A+CAS_2$, $CS+CAS_2$, $A_3S_2+CAS_2$, $L_1+L_2+S_1$, $L+S_1+S_2$, $L+S_2+CS$, $L+S_2+CAS_2$, $L+A_3S_2+CAS_2$, $S_2+CS+CAS_2$, $A+A_3S_2+CAS_2$, $S+A_3S_2+CAS_2$ (table 2). The phase region $L+S_1+S_2$ is degenerated into line and the corresponding phase reaction proceeds at one temperature.

Symbol	Contour	Symbol	Contour
$Q_{e4_A3S2}^r$	$A_3S_{2(E4)}-e_4-U-A_3S_{2(U)}$	$Q_{E4E5_R12}^r$	$CAS_{2(E4)}-E_4-[E_4^-,E_5^-]-CAS_{2(E4,E5)}$
$Q_{E5U_A3S2}^r$	$A_3S_{2(U)}-U-E_5-A_3S_{2(E5)}$	$Q_{E5E4_R12}^r$	$CAS_{2(E5)}-E_5-[E_4^-,E_5^-]-CAS_{2(E4,E5)}$
$Q_{Q8E5_A3S2}^r$	$A_3S_{2(Q8)}-Q_8-E_5-A_3S_{2(E5)}$	i^r	m-k-n
$Q_{e5_A3S2}^r$	$A_3S_{2(E5)}-e_5-Q_8-A_3S_{2(Q8)}$	i_m^r	$S_{1(mn)}-m-k-S_{1(k)}$
$Q_{e4_S}^r$	$S_{1(E4)}-e_4-U-S_{1(U)}$	i_n^r	$S_{1(mn)}-n-k-S_{1(k)}$
$Q_{E5U_S}^r$	$S_{2(U)}-U-E_5-S_{2(E5)}$	H_{E4}	$S_{2(E4)}-CS_{E4}-CAS_{2(E4)}$
$Q_{e5_A}^r$	$A_{(E5)}-e_5-Q_8-A_{(Q8)}$	H_{E5}	$S_{2(E5)}-A_3S_{2(E5)}-CAS_{2(E5)}$
$Q_{Q8E5_CAS2}^r$	$CAS_{2(Q8)}-Q_8-E_5-CAS_{2(E5)}$	H_{Q8}	$Q_8-A_3S_{2(Q8)}-A-CAS_{2(Q8)}$
$Q_{e3_S}^r$	$S_{2(E3)}-e_3-E_4-S_{2(E4)}$	H_U	$U-A_3S_{2(U)}-S_{1(U)}-S_{2(U)}$
$Q_{p3_S}^r$	$S_{1(U)}-p_3-U$	V_{S-CAS2}	$S_{2(E4,E5)}-CAS_{2(E4,E5)}-CAS_{2^0}S_{2^0}$
$Q_{E4E5_S}^r$	$S_{2(E4)}-E_4-[E_4^-,E_5^-]-S_{2(E4,E5)}$	V_{A-CAS2}	$A_{Q8}-CAS_{2(Q8)}-CAS_{2^0}A_3S_{2^0}$
$Q_{E5E4_S}^r$	$S_{2(E5)}-E_5-[E_4^-,E_5^-]-S_{2(E4,E5)}$	$V_{R5-CAS2}$	$A_3S_{2(Q8)}-CAS_{2(Q8)}-CAS_{2^0}A_3S_{2^0}$
$Q_{e3_CS}^r$	$E_3-E_4-CS_{E4}-CS_{e3}$	$V_{R4-CAS2}$	$CS_{(E4)}-CAS_{2(E4)}-CAS_{2^0}CS^0$

Table 1. Contours of ruled surfaces (Q^r , i^r), horizontal (H) and vertical (V) planes
1. táblázat Az irányított felületek (Q^r , i^r) kontúrjai, vízszintes (H) és függőleges (V) síkok

4. Analysis of the concentration fields

At projection the surfaces Q_{S1} , Q_{S2} , Q_{A3S2} and i are divided onto 15 two-, 28 one- and 9 zero-dimensional concentration fields. Thirteen (2 two-, 8 one- and 3 zero-dimensional) fields coincide with neighbouring fields by the set of microconstituents.

The microconstituents of concentration fields corresponding to the regions of immiscibility melt (m-n-k, SiO_2 -m-k, SiO_2 -k, n-k, m-k, k) coincide with the of field p_3 -1- SiO_2 -k-n. Meanwhile the fields m-n-k, SiO_2 -m-k and m-k differ from field p_3 -1- SiO_2 -k-n by intersected surfaces, phase regions and crystallization scheme (table 3). The phase region $L+S_1$ and phase region of immiscibility melt $L+S_1+S_2$ are located under the field SiO_2 -m-k. At that the phase region $L+S_1$ is twice crossed for this field. So the field is characterized by two primary

crystallization reactions $L^1 \rightarrow S_1^1$ between which the monotectic reaction $L_1^m \rightarrow L_2^m + S_1^m$ takes place. Field m-n-k arranges under the surface of immiscibility melt (i) and intersects the phase regions L_1+L_2 and $L_1+L_2+S_1$, where the phase reaction $L_1^1 \rightarrow L_2^1$ and $L_1^m \rightarrow L_2^m + S_1^m$ occur.

Since the process of melt immiscibility ends in the phase region $L_1+L_2+B_1$, then the reaction products L_2^1 and L_2^m doesn't influence on the microconstituents forming. The crystals B_1 are not present in the microconstituents, because they are fully disappeared in the reactions $L^p, B_1 \rightarrow B_2^p$ and $L^u, S_1 \rightarrow S_2^u + A_3S_2^u$ and in the subsequent phase transformations there are only B_2 crystals. The reactions $L^p, S_1 \rightarrow S_2^p$ and $L^u, S_1 \rightarrow S_2^u + A_3S_2^u$ have degenerated form as the result of degeneration of phase regions $L+S_1+S_2$ in horizontal line and four-phase plane in the triangle $U-A_3S_{2(U)}-S_{1(U)}-S_{2(U)}$ [11].

The fields SiO_2 -k, n-k and k coincide with field p_3 -1- SiO_2 -k-n by the list of phase reactions and the microconstituents.

Fig. 3. Diagram of material balance for the concentration field p_3 -1- SiO_2 -k-n
3. ábra p_3 -1- SiO_2 -k-n koncentráció mező anyag egyensúlyi diagramja

Let's consider the diagram of mass balances for composition given in the field p_3 -1- SiO_2 -k-n (figure 3). After the reaction of primary crystallization $L^1 \rightarrow S_1^1$ in the phase region $L+S_1$ the composition falls into phase region $L+S_1+S_2$ (degenerated into line) where the crystals S_1 is fully disappeared as the result of reactions $L^p, S_1 \rightarrow S_2^p$ and $L^u, S_1 \rightarrow S_2^u + A_3S_2^u$. Then the composition moves into the phase region $L+S_2$ where the post-peritectical primary crystallization $L^{1p} \rightarrow S_2^{1p}$ takes place with the increasing of phase part S_2 . In the phase region $L+S_2+CS$ the part of phase L is decreased and parts of phases S_2 and CS are increased: $(L^{ep} \rightarrow S_2^{ep(CS)} + CS^{ep(B2)})$. The phase L is fully disappeared as the result of reaction $L^{E4} \rightarrow S_2^{E4} + CS^{E4} + CAS_2^{E4}$

Symbol	Bounding surfaces	Symbol	Bounding surfaces
L_1+L_2	i, i^r	$L+A_3S_2+CAS_2$	$Q_{Q8E5_A3S2}^r, Q_{Q8E5_CAS2}^r, H_{Q8}, H_{E5}, V_{A3S2-CAS2}$
$L+S_1$	$Q_{S1}^r, i^r, Q_{e4_S}^r, Q_{p3_S}^r$	$S_2+CS+CAS_2$	$V_{S-CAS2}, V_{CS-CAS2}, H_{E4}$
$L+S_2$	$Q_{S2}^r, Q_{e3_S}^r, Q_{p3_S}^r, Q_{E5U_S}^r, Q_{E4E5_S}^r, Q_{E5E4_S}^r$	$A_3S_2+CAS_2+A$	$H_{Q8}, V_{A-CAS2}, V_{A3S2-CAS2}$
$L+A_3S_2$	$Q_{A3S2}^r, Q_{e4_A3S2}^r, Q_{E5U_A3S2}^r, Q_{Q8E5_A3S2}^r, Q_{e5_A3S2}^r$	$S_2+A_3S_2+CAS_2$	$V_{A3S2-CAS2}, V_{S-CAS2}, H_{E5}$
$L_1+L_2+S_1$	i^r, i_n^r, i_m^r	S_2+CAS_2	V_{S-CAS2}
$L+S_1+S_2$	$Q_{p3_S}^r$	$A+CAS_2$	V_{A-CAS2}
$L+S_2+CS$	$Q_{e3_CS}^r, Q_{e3_S}^r, H_{E4}$	$A_3S_2+CAS_2$	$V_{A3S2-CAS2}$
$L+S_2+CAS_2$	$Q_{E4E5_S}^r, Q_{E5E4_S}^r, Q_{E5E4_CAS2}^r, Q_{E4E5_CAS2}^r, H_{E4}, H_{E5}, V_{S-CAS2}$	$CS+CAS_2$	$V_{CS-CAS2}$

Table 2. Phase regions structure
2. táblázat Fázis területek szerkezete

Concentration fields	Intersected surfaces	Intersected phase regions	Crystallization scheme	Microconstituents
p₃-1-SiO₂-k-n	$Q_{S1'}$ $Q_{p3-S'}$ $Q_{e3-S'}$ H_{E4}	$L+S_1'$ $L+S_1+S_2'$ $L+S_2'$ $L+S_2+CS_2$ $B_2+CS+CAS_2$	$L^1 \rightarrow S_1^1$ $L^p+S_1^1 \rightarrow S_2^p$ $L^{1p} \rightarrow S_2^{1p}$ $L^{ep} \rightarrow S_2^{ep(CS)}+CS_2^{ep(B2)}$ $L^{E4} \rightarrow S_2^{E4}+CS_2^{E4}+CAS_2^{E4}$	S_2^p S_2^{1p} $S_2^{ep(CS)}, CS_2^{ep(B2)}$ $S_2^{E4}, CS_2^{E4}, CAS_2^{E4}$
SiO₂-m-k	$Q_{S1'}$ $i_{r'm'}$ $i_{r'n'}$ $Q_{p3-S'}$ $Q_{e3-S'}$ H_{E4}	$L+S_1'$ $L_1+L_2+S_1'$ $L+S_1'$ $L+S_1+S_2'$ $L+S_2'$ $L+S_2+CS_2$ $S_2+R_4+CAS_2$	$L^1 \rightarrow S_1^1$ $L_1^m \rightarrow L_2^m+S_1^m$ $L^1 \rightarrow S_1^1$ $L^p+S_1^{1p} \rightarrow S_2^p$ $L^{1p} \rightarrow S_2^{1p}$ $L^{ep} \rightarrow S_2^{ep(CS)}+CS_2^{ep(B2)}$ $L^{E4} \rightarrow S_2^{E4}+CS_2^{E4}+CAS_2^{E4}$	S_2^p S_2^{1p} $S_2^{ep(CS)}, CS_2^{ep(B2)}$ $S_2^{E4}, CS_2^{E4}, CAS_2^{E4}$
m-n-k	i i_r $i_{r'n'}$ $Q_{p3-S'}$ $Q_{e3-S'}$ H_{E4}	L_1+L_2' $L_1+L_2+S_1'$ $L+S_1'$ $L+S_1+S_2'$ $L+S_2'$ $L+S_2+CS_2$ $S_2+CS+CAS_2$	$L_1^1 \rightarrow L_2^1$ $L_1^m \rightarrow L_2^m+S_1^m$ $L^1 \rightarrow S_1^1$ $L^p+S_1^1 \rightarrow S_2^p$ $L^{1p} \rightarrow S_2^{1p}$ $L^{ep} \rightarrow S_2^{ep(CS)}+CS_2^{ep(B2)}$ $L^{E4} \rightarrow S_2^{E4}+CS_2^{E4}+CAS_2^{E4}$	S_2^p S_2^{1p} $S_2^{ep(CS)}, CS_2^{ep(B2)}$ $S_2^{E4}, CS_2^{E4}, CAS_2^{E4}$
SiO₂-k	$Q_{S1'}$ $Q_{p3-S'}$ $Q_{e3-S'}$ H_{E4}	$L+S_1'$ $L+S_1+S_2'$ $L+S_2'$ $L+S_2+CS_2$ $S_2+R_4+CAS_2$	$L^1 \rightarrow S_1^1$ $L^p+S_1^1 \rightarrow S_2^p$ $L^{1p} \rightarrow S_2^{1p}$ $L^{ep} \rightarrow S_2^{ep(CS)}+CS_2^{ep(B2)}$ $L^{E4} \rightarrow S_2^{E4}+CS_2^{E4}+CAS_2^{E4}$	S_2^p S_2^{1p} $S_2^{ep(CS)}, CS_2^{ep(B2)}$ $S_2^{E4}, CS_2^{E4}, CAS_2^{E4}$
n-k	$Q_{S1'}$ $Q_{p3-S'}$ $Q_{e3-S'}$ H_{E4}	$L+S_1'$ $L+S_1+S_2'$ $L+S_2'$ $L+S_2+CS_2$ $B_2+R_4+CAS_2$	$L^1 \rightarrow S_1^1$ $L^p+S_1^1 \rightarrow S_2^p$ $L^{1p} \rightarrow S_2^{1p}$ $L^{ep} \rightarrow S_2^{ep(CS)}+CS_2^{ep(B2)}$ $L^{E4} \rightarrow S_2^{E4}+CS_2^{E4}+CAS_2^{E4}$	S_2^p S_2^{1p} $S_2^{ep(CS)}, CS_2^{ep(B2)}$ $S_2^{E4}, CS_2^{E4}, CAS_2^{E4}$
m-k	$Q_{S1'}$ $i_{r'm'}$ $i_{r'n'}$ $Q_{p3-B'}$ $Q_{e3-B'}$ H_{E4}	$L+S_1'$ $L_1+L_2+S_1'$ $L+S_1'$ $L+S_1+S_2'$ $L+S_2'$ $L+S_2+CS_2$ $S_2+R_4+CAS_2$	$L^1 \rightarrow S_1^1$ $L_1^m \rightarrow L_2^m+S_1^m$ $L^1 \rightarrow S_1^1$ $L^p+S_1^{1p} \rightarrow S_2^p$ $L^{1p} \rightarrow S_2^{1p}$ $L^{ep} \rightarrow S_2^{ep(CS)}+CS_2^{ep(B2)}$ $L^{E4} \rightarrow S_2^{E4}+CS_2^{E4}+CAS_2^{E4}$	S_2^p S_2^{1p} $S_2^{ep(CS)}, CS_2^{ep(B2)}$ $S_2^{E4}, CS_2^{E4}, CAS_2^{E4}$

* 1 – primary crystallization $L^1 \rightarrow S_1^1$; e – monovariant eutectic reaction $L^e \rightarrow L^e + J^e$; p – monovariant peritectic reaction $L^p + A^p \rightarrow R^p$; m – monovariant monotectic reaction $L_1^m \rightarrow L_2^m + R^m$; E – invariant eutectic crystallization $L^E \rightarrow B^E + C^E + R^E$; Q – invariant quasiperitectic regrouping of masses $L^Q + A^Q \rightarrow B^Q + R^Q$; 1p – post-peritectic primary crystallization $L^{1p} \rightarrow R^{1p}$; ep – post-peritectic monovariant crystallization $L^{ep} \rightarrow R^{ep} + J^{ep}$ ($J=B, C$)

Table 3. Crystallization scheme and microconstituents for surface of immiscibility i and the fragment of primary crystallization surface Q_{S1} of high-temperature modification SiO_2 ($S1$)*
3. táblázat Kristályosodási séma és mikro-összetevők az i oldhatatlansági felülethez és a Q_{S1} elsődleges kristályosodási felület töredéke a SiO_2 ($S1$)* módosulására magas hőmérsékleten

on the plane at the temperature of ternary eutectic points E_4 . Below the plane the composition gets to the solid-phase region $S_2+CS+CAS_2$.

The concentration fields e_4 -U and U coincide with fields SiO_2 -U- e_4 and SiO_2 -U by the microconstituents, but differ the crystallization scheme. Fields e_4 -U and U haven't the reaction of primary crystallization $L^1 \rightarrow B_1^1$. The concentration fields p_3 -1 and 2 differ from fields e_3 - E_4 -1- p_3 and 2-4 by intersected surfaces. The fields E_5 -3, A_3S_2 -U and A_3S_2 - Q_8 are identical with E_5 -U-3, U- E_5 - A_3S_2 and E_5 - Q_8 - A_3S_2 by the microconstituents and crystallization scheme correspondently.

5. Conclusion

Computer model of PD gives the possibility to analyze the crystallization stages for any composition and to find the concentration fields both with individual set of microstructure elements and the fields at which the crystallization scheme and microconstituents of phases assemblage coincide with those in the adjoining fields. It is used as an important tool to investigate

multicomponent system, to correct its constitutional diagram, to design the microstructures of heterogeneous material, to decipher the genotype of heterogeneous material [12]. One more reason for the microstructures variety is the competition of crystals with different dispersity, when a field of invariant reaction is divided into the fragments with the tiny eutectical crystals, with more large primary crystals and with the both type of these crystals [13].

Acknowledgements

The paper was presented as Plenary Lecture and was published with the permission of ic-cmtp2, the 2nd International Conference on Competitive Materials and Technology Processes, 8-12 October 2012, Miskolc-Lillafüred, Hungary.

References

- [1] Taylor, H. F. W.: *Cement Chemistry*. Thomas Telford, London, 1997, 459 p.
- [2] Lea, F.: *Lea's Chemistry of Cement and Concrete*. P.C. Hewlett, London, 1998, 1092 p.

- [3] De Noirfontaine, M. N. – Tusseau-Nenez, S. – Girod-Labianca, C. – Pontikis, V.: *CALPHAD formalism for Portland clinker: thermodynamic models and databases*. Journal of Material Science 47(3), February 2012, pp 1471-1479, <http://dx.doi.org/10.1007/s10853-011-5932-7>
- [4] Pashchenko, A. A. – Aleksenko, N. V. et al: *Physical Chemistry of Silicates*. Edited by Pashchenko, A. A., Vysshaya Shkola, Kiev, 1977, 368 p. (in Russian)
- [5] Lutsyk, V. I. – Zelenaya, A. E. – Savinov, V. V.: *Melt solidification in the ceramic system $\text{CaO-Al}_2\text{O}_3\text{-SiO}_2$. ICC3: Symposium 8: Glass-Science & Technology and Photonic Applications*. IOP Conference Series: Materials Science and Engineering. 18(2001) 112005, IOP Publishing, <http://dx.doi.org/10.1088/1757-899X/18/11/112005>
- [6] Lutsyk, V. I. – Zelenaya, A. E. – Savinov, V. V.: *Phase trajectories in $\text{CaO-Al}_2\text{O}_3\text{-SiO}_2$ melts*. Crystallography Reports. 57(7), December 2012, pp. 943-947., <http://dx.doi.org/10.1134/S1063774512070176>
- [7] Gentile, A. L. – Foster, W. R.: *Calcium Hexaluminate and Its Stability Relations in the System $\text{CaO-Al}_2\text{O}_3\text{-SiO}_2$* . Journal of the American Ceramic Society. 46(2), February 1963, pp. 74-76., <http://dx.doi.org/10.1111/j.1151-2916.1963.tb11679.x>
- [8] Levin, E. M. – Robbins, C. R. – McMurdie, H. F.: *Phase Diagrams for Ceramists*. American Ceramic Society, Ohio, 1964, 395 p.
- [9] Toropov, N. A. – Bazarkovsky, V. P. – Lapshin, V. V. et al.: *Diagrams of Silicate Systems*. vol 3. Ternary Silicate Systems, Nauka, Leningrad, 1972, pp. 184-190 (in Russian)
- [10] Lutsyk, V. I. – Zelenaya, A.: *Crystallization paths and microstructures in ternary oxide systems with stoichiometric compounds*. Proc. Int. Conf. Oxide Materials for Electronic Engineering (Lviv, Ukraine), 3-7 Sept. 2012, pp. 133-134., <http://dx.doi.org/10.1109/OMEE.2012.6464817>
- [11] Lukas, H. L. – Hengl, E. T. – Petzow, G.: *Zeitschrift für Metallkunde*. 77, pp. 360, 1986
- [12] Lutsyk, V. I.: *Bulletin of Buryat Scientific Centre (SB RAS)* no 1(5), 78 p., 2012 (in Russian)
- [13] Lutsyk, V. I. – Nasrulin, E. R.: *Competition of primary and eutectic crystals in invariant and univariant reactions*. Crystallography Reports. 57(7), December 2012, pp. 979-983., <http://dx.doi.org/10.1134/S1063774512070152>

Ref.:

Vasily **Lutsyk** – Anna **Zelenaya**: *Crystallization paths in $\text{SiO}_2\text{-Al}_2\text{O}_3\text{-CaO}$ system as a genotype of silicate materials*.
Építőanyag, 65. évf. 2. szám (2013), 34–38. p.
<http://dx.doi.org/10.14382/epitoanyag-jbcm.2013.7>

Kristályosodási folyamatok a $\text{SiO}_2\text{-Al}_2\text{O}_3\text{-CaO}$ anyagrendszerben, mint a szilikát anyagok genotípusában

A $\text{SiO}_2\text{-Al}_2\text{O}_3\text{-CaO}$ anyagrendszerben a nem elegyedő folyadékfázisok mezőjéből kiindulva a krisztobalit (SiO_2 cr), a tridimit (SiO_2 tr) és a mullit ($3\text{Al}_2\text{O}_3 \times 2\text{SiO}_2$) fázisátalakulása – kristályosodása – kerül a szerzők által bemutatásra a T-x-y koordináta rendszerben számítógépes modellezés segítségével. Az elvégzett számítógépes modellezés és elemzés eredményeként feltárulnak azok a hőmérséklettől és összetételtől függő unikális mikro-szerkezettel bíró terek és mezők, amelyekben a szilikát anyagok genotípusát alkotó anyagrendszerben az egyes komponensek kristályosodási folyamata nem önállóan megy végbe.

Kulcsszavak: fázisdiagram, kristályosodás, $\text{SiO}_2\text{-Al}_2\text{O}_3\text{-CaO}$ rendszer, számítógépes modellezés

NIISK, the Ukrainian state agency “Research Institute of Building Constructions” celebrates its 70th anniversary in 2013

The Institute was founded in 1943 by the Council of People's Commissars of the USSR on October 26, 1943 and received the name “Ukrainian Research Institute facilities (UkrNDIS)” from the temporary location of the Institute in Moscow. The main purpose of the institute was the development and implementation of advanced building science and technology, conduct research on housing and civil engineering and technical assistance to construction companies. The main activity of the Institute was to address a number of issues in the construction industry, contributing to the implementation of the program of construction of recovery in short term construction projects destroyed during the 2nd World War and find the most efficient design, saving in building materials and replacement techniques. The UkrNDIS was transferred to Kyiv in March 1944.

During the years of its history NIISK solve complex scientific and technical issues concerning the construction of many buildings in Ukraine and other former Soviet republics. Numerous research and development institute were used in our country and abroad. Scientists and engineers have created a unique institute of technology and building construction in the Ukraine and other former Soviet republics and make several housing estates in difficult

geological conditions. NIISK is now a large research centre known not only in Ukraine but also abroad. The work of the institute has been recognized by international prizes and honours.

Over 500 specialists are currently working for the institute, which has branches and branch laboratories in several regions of Ukraine. Main Technical Committees of NIISK: Energy Efficiency of buildings; Building construction; Protection of buildings. In addition to scientific departments, the institute has design departments and experimental bases developing projects and technologies for new structural designs and producing structures for experimental construction.

The institute issues the scientific collection “Building structures” as well as the scientific journal “Geotechnical world”.

The institute carries out work in the following areas: building structures, geotechnics and foundation engineering, seismic resistance construction, energy effectiveness and acoustics, reliability and effectiveness of technical decisions, test methods for building structures and scientific support for large structures.

Among other honours, the Institute was awarded with the International Prize for Commercial Prestige – The New Millennium Prize in 2002, and The World Quality Award XXI Century – World of Marketing award in 2003.