Raman shift of silicon rubber-nano titania PMNC

Sabah Mohammed Milkat Al Mutoki

is an Assist. Prof. at Al-Furat Al-Awsat Technical University, Iraq. He is the dean of Al Samawah Technical Institute since 2014. He got his PhD from Lancaster University, UK, 2012, in the field of condensed materials nano-technology. Interest in: nano-materials, nano-composites, electronic applications of nano-materials.

Baydaa Abul Hassan Khalaf Al Ghazawi

is a lecturer at Al Samawah Technical Institute, Al-Furat Al-Awsat Technical University. She has her Master degree in ceramic technology from Baghdad Technical College, The Middle Technical University at 2007, currently she is a PhD student.

Samir M. Abdulalmohsin

is an Asst. Prof. at University of Thi Qar, Faculty of Science, Department Of Physics, Iraq; University ; He has received his Ph.D. from University of Arkansas at Little Rock (UALR) in 2014. Main fields of interest: Applied Physics, Opto Electronics, Nanostructure Materials, Solar Cells. He has more than 20 papers with citation about 78.

Emad Abbas Jaffar Al-Mulla

is an Asst. Prof. College of Health and Medical Techniques, Al-Furat Al-Awsat Technical University, Iraq; He has received his PhD from Universiti Putra Malaysia, Malaysia in 2010, He was a Postdoctoral researcher at the same University from April 2012 to April 2013; main fields of interest: bioorganic synthesis, nano-materials, biopolymer nano-composites; He has more than 50 papers in Scopus and ISI journals; his H-Index = 14 according to Scopus database.

SABAH MOHAMMED MLKAT AL MUTOKI ▪ Electrical Department, Al-Furat Al-Awsat University, Technical Institute of Samawa ▪ asabah_sh2003@yahoo.com

BAYDAA ABDUL-HASSAN KHALAF AL-GHZAWI ▪ Mechanical Department, Al-Furat Al-Awsat University, Technical Institute of Samawa ▪ baydaafawz@gmail.com

SAMIR M. ABDUL AMOHSIN ▪ Physical Department, Faculty of Science, Thi Qar University ▪ samir.mahdi75@gmail.com

EMAD A. JAFFAR AL-MULLA ▪ College of Health and Medical Techniques, Al-Furat Al-Awsat Technical University ▪ emadalmulla@atu.edu.iq

Érkezett: 2016. 12. 14. ▪ Received: 14. 12. 2016. ▪ <http://dx.doi.org/10.14382/epitoanyag-jsbcm.2017.4>

Abstract

Raman shift, FTIR spectra and SEM were used to detect the percolation threshold of nano titania filler ceramic nTiO₂ dispersed in a silicon rubber matrix SR8100 by hot vibrate dispersion. It has been found that an additional frequencies, and stock lines appears in Raman shift when nTiO₂ reach (5)wt% which mean a change in polarity of the SR8100/nTiO₂ PMNC polarity.

Keywords: PMNC, nano ceramic oxide fillers, nTiO₂, Raman shift

1. Introduction

It is increasingly being recognized that new applications for materials require functions and properties that are not achievable with single materials. In this sense, composites formed by a polymer matrix and a conductive nano second phase are very interesting materials [1], these conducting polymer matrix nano composites PMNCs are capable of dissipating electrostatic charges and shielding devices from electromagnetic radiation [2]. Dielectric property of PMNCs with different conductivity fillers, such as carbon nano tube (CNT), copper (Cu) and nickel (Ni) powders was investigated by several researchers [2-5]. Dependence of the dielectric property of the PMNC composites on frequency and volume fraction of fillers was also studied [6,7]. With gradually increasing the conducting filler content, composites undergo a percolation transition where the electrical conductivity of the composite jumps up several orders of magnitudes and its nature changes from an insulator to a conductor. This behavior is attributed to the formation of conducting network through the insulating matrix material when the filler content is at or above the percolation threshold [8,9]. The critical content of any filler that characterizes a drastic increase in conductivity is commonly termed as the electrical percolation threshold (EPT) [10]. On the other hand the use of nano ceramic oxides as a filler in several polymer matrixes can be viewed as one of the most promising area driven towards electronic applications [11]. Among all the ceramic oxide nano fillers nTiO₂ is documented to have the highest effect on the PMNCs, especially on the electrical and thermal properties. The

improvement in these properties observed for nTiO₂ filled polymers could be due to one and/or more of the following factors (i) the large surface area of nano particles which creates a large interaction zone or region of altered polymer behavior, (ii) change in the polymer morphology due to the surfaces of nano particles, (iii) a reduction in the internal field caused by the decrease in the size of the particles, (iv) change in the space charge distribution, (v) scattering mechanism [12-17]. Aim of this research was to determine the percolation threshold of a new PMNC composed of SR8100 and nTiO₂ ceramic filler fabricated by hot vibrate dispersion (HVD).

2. Experiments

2.1 Materials

SR8100 polymer containing resin and hardener from (SICOMEN, USA), and (99.9%), and (10 nm) TiO₂ from (HORIBA, Germany).

2.2 Method

Polymer matrix discs were prepared using mould with 1cm diameter and 1cm height, the ratio of resin and hardener was 1:3. They were stirred by a magnetic stirrer for 5 min, then it was poured into the mould leaving for 24 hrs. After solidification the polymer discs were put in 1×1 cm cylindrical mould with a moving base with TiO₂ nano powder. The mould was then heated up to 80 °C and vibrate ultrasonically for 1 hr to ensure a uniform disperse for TiO₂ nano particles in SR8100 polymer matrix. Then it was left to cool down at room temperature.

Fig. 1 FTIR of SR8100/nTiO₂ PMNCs
1. ábra SR8100/nTiO₂ PMNC FTIR spektruma

Fig. 2 Raman Shift of SR8100/nTiO₂ PMNCs
2. ábra SR8100/nTiO₂ PMNC Raman eltolódása

Specimens were tested by Raman shift, FTIR, and SEM to detect their properties.

3. Results and discussion

In the present work we succeeded to change polarity of silicon rubber (SR8100) by the addition of nano titania filler with 10 nm particle size using hot vibrate dispersion technique to prepare a polymer matrix nano composite material (PMNC) with high electrical conductivity. Both heating and vibrating used in PMNC preparation stimulate molecules and give it the energy it need to vibrate and spin creating a large change in the polarity of the polymer matrix as we shall see from Raman shift of the SR8100/nTiO₂ PMNC specimen. Fig. 1 illustrates FTIR of SR8100/TiO₂ PMNC specimen peaks at (1472.32,1635.64) refers to phases where SR8100 epoxy is the dominant, while peaks at (3587.60, 3525.88, 3464.15) are places where nTiO₂ concentrate [20].

Fig. 2 illustrates the Raman shift of SR8100 1-5 wt% nTiO₂. It is easy to notice the additional frequencies in Raman shift related to the internal energy of the SR8100/nTiO₂ PMNC especially when nTiO₂ weight percent is 5% as can be seen from Fig. 1, where stock lines has also appeared which is a very interesting result that we shall relay for our future work. From Fig. 1 we may see the large similarity between Raman shift for the 1-4 wt% nTiO₂ PMNC specimen, while the 5 wt% nTiO₂ has much different peaks which may refer to a percolation threshold phenomena. According to this fact we may distinguish two types of Raman shift peaks; (i) the repeated peaks that appear in SR8100/nTiO₂ PMNC specimen with 1-4 wt% nTiO₂, which are as follow, peak at (100) which is related to symmetric stretching of C=O, (275,267 and 278) peaks indicate the stretching mode of C-H bond, (333,336) refer to a combination of C-O stretching and O-H deformation, peaks at 437,438 refer to nTiO₂, and/or stretching mode of saturated C-O, it may also refer to a slight entrance between SR8100 polymer matrix and nTiO₂ filler. Peaks (488,489,490) all refer to the presence of nTiO₂ phase, while (552,581,582,585) peaks indicate the deformation of C-H and C-O-H, ring deformation of polymer matrix and nTiO₂ presence [18,19]. Raman shift of 5 wt% nTiO₂ shows completely different

peaks than the other SR8100/nTiO₂ PMNC specimens. In this specimen nTiO₂ is more obvious in the peaks (256,267,288), peak (349) refer to combination of C-O stretching and C=H deformation, peak (393) refers to nTiO₂ [20,21], and/or combination of C-O stretching and O-H deformation. Peak (435) indicates stock line that is not defined as polymer or nTiO₂; it may indicate percolation threshold and tunneling effect [18] that may take place within SR8100/nTiO₂ PMNC. Finally (585) peak refers to nTiO₂ and/or deformation of C-C and C-O [19,22,23]. The Raman shift results of this work are in agreement with FTIR results shown in Fig. 1.

Fig. 3 illustrates SEM of SR8100/nTiO₂ (PMNCs). We can see the good dispersion and high interaction between polymer matrix and nano reinforcing particles; this may lead us to conclude that there is, we may notice that at ultra low nTiO₂ concentration 1-3 wt% nTiO₂ there is no obvious pattern for dispersion of nTiO₂ in SR8100 matrix, hence no percolation is expected. But this regular pattern starts to appear at 4% nTiO₂ and continue with the same regular dispersion especially at 5% nTiO₂ which gives a very regular dispersion of nTiO₂ phase through the SR8100 matrix.

Fig. 3 SEM of SR8100/nTiO₂ PMNCs 1-5 wt% nTiO₂
3. ábra SR8100/nTiO₂ PMNC (1-5 wt% nTiO₂) pásztázó elektronmikroszkóp felvételei

Values of electrical resistivity, and thermal conductivity of the SR8100/nTiO₂ are listed in Table 1. From the table we may notice that addition of nTiO₂ effects on both electrical resistivity, and thermal conductivity when concentration of nano titania filler exceed 3%.

4. Conclusions

Raman shift, FTIR spectra and SEM were used to detect the percolation threshold of nano titania filler ceramic nTiO₂ dispersed in a silicon rubber matrix SR8100 by hot vibrate dispersion. It has been found that an additional frequencies, and stock lines appears in Raman shift when nTiO₂ reach (5) wt% which mean a change in polarity of the SR8100/nTiO₂ PMNC polarity.

Specimen Composition	Electrical Resistivity (Ω.cm)	Thermal Conductivity (W/m.k)
SR8100	1.0×10 ¹³	0.120
SR8100+1%nTiO ₂	0.821×10 ¹³	0.416
SR8100+2%nTiO ₂	3.07×10 ¹²	1.002
SR8100+3%nTiO ₂	5.48×10 ¹⁰	2.714
SR8100+4%nTiO ₂	2.36×10 ¹⁰	5.227
SR8100+5%nTiO ₂	4.65×10 ⁸	7.186

Table 1..Electrical Resistivity and Thermal Conductivity of SR8100/nTiO₂
1. táblázat SR8100/nTiO₂ elektromos ellenállása és hővezetési tényezője

References

- [1] Yan, T. – Shen, Z. G. – Zhang, W. W. – Chen, J. F. (2006): Size dependence on the ferroelectric transition of nanosized BaTiO₃ particles. *Materials Chemistry and Physics*, Vol. 98, pp. 450-455. <https://doi.org/10.1016/j.matchemphys.2005.09.058>
- [2] Wada, S. – Hoshina, T. – Yasuno, H. – Ohishi, M. M. – Kakemoto, H. – Tsurumi, T. – Yashima M. (2013): Size effect of dielectric properties for barium titanate particles and its model. *Key Engineering Materials*, Vol. 301, pp. 27-30. <https://doi.org/10.4028/www.scientific.net/KEM.301.27>
- [3] Caseri, W. R. (2006): Nanocomposites of polymers and inorganic particles: preparation, structure and properties. *Materials Science and Technology*, Vol. 22, pp. 807-817. <https://doi.org/10.1179/174328406X101256>
- [4] Jing Li – Peng Cheng Ma – Chow Wing Sze – To Chi Kai – Ben Zhong Tang – Jang-Kyo Kim (2007): Percolation Threshold of Polymer Nnnocomposites Containing Graphite Nano Platelets and Carbon Nanotubes, *16th International Conference on Composite Materials*, Kyoto-Japan, 2007.
- [5] B. H. Kim – J. H. Ahn – J. H. Jeong – Y. S. Jeon – K. O. Jeon – K. S. Hwang (2006): Preparation of TiO₂ Thin Film on SiO₂ Glass by a Spin Coating—Pyrolysis Process, *Ceramics International*, Vol. 32, pp. 223-225. <https://doi.org/10.1016/j.ceramint.2005.01.016>
- [6] Salahuddin Sayeef, Datta, D. – Srivastava, P. – Datta Supriyo (2007): Quantum Transport Simulation of Tunneling Based Spin Torque Transfer (STT) Devices: Design Trade offs and Torque Efficiency, *Electron Devices Meeting*, 2007. IEDM 2007. IEEE International, pp.121-124.
- [7] Moya, J. S. – Lopez-Esteban, S. – Pecharroman, C. (2007): The challenge of ceramic/metal microcomposites and nanocomposites. *Progress in Materials Science*. Vol. 52, pp. 1017-1090. <https://doi.org/10.1016/j.pmatsci.2006.09.003>
- [8] Al-Shemmari, F. A. – Rabah, A. A. A. – Al-Mulla, E. A. J. (2014): Comparative study of different Msurfactants for natural rubber clay nanocomposite preparation. *Rendiconti Lincei Scienze Fisiche e Naturali*, Vol. 25, pp. 409-413.
- [9] Fahrenholtz, W. G. – Ellerby, D. T. – Loehman, R. E. (2000): Al₂O₃-Ni Composites with high strength and fracture toughness. *Journal of the American Ceramic Society*. Vol. 83, pp. 1279-1280. <https://doi.org/10.1111/j.1151-2916.2000.tb01368.x>
- [10] Tuan, W. H. – Wu, H. H. – Yang, T. J. (1995): The preparation of Al₂O₃/Ni composites by a powder coating technique. *Journal of Materials Science*. Vol. 30, pp. 855-859. <https://doi.org/10.1007/BF01178417>

- [11] Wang, X. – Padture, N. P. – Tanaka, H. (2004): Contact-damage-resistant ceramic/single-wall carbon nanotubes and ceramic/graphite composites. *Nature Materials*. Vol. 3, pp. 539-544. <https://doi.org/10.1038/nmat1161>
- [12] Cho, J. – Boccaccini, A. R. – Shaffer, M. S. P. (2009): Ceramic matrix composites containing carbon nanotubes. *Journal of Materials Science*. Vol. 44, pp. 1934-1951. <https://doi.org/10.1007/s10853-009-3262-9>
- [13] Efros, A. L. – Shklovskii, B. I. (1976): Critical behaviour of conductivity and dielectric constant near the metal-non-metal transition threshold. *Physica Status Solidi B*. Vol. 76, pp. 475-485. <https://doi.org/10.1002/pssb.2220760205>
- [14] Nan, C. W. – Shen, Y. – Ma, J. (2010): Physical properties of composites near percolation. *Annual Review of Materials Research*. Vol. 40, pp. 131-151. <https://doi.org/10.1146/annurev-matsci-070909-104529>
- [15] Bauhofer, W. – Kovacs, J. Z. (2009): A review and analysis of electrical percolation in carbon nanotube polymer composites. *Composites Science and Technology*. Vol. 69, pp. 1486-1498. <https://doi.org/10.1016/j.compscitech.2008.06.018>
- [16] S. F. Chen – J. P. Li – K. Qian – W. P. Xu – Y. Lu – W. X. Huang – S. H. Yu (2010): Large Scale Photochemical Synthesis of M@TiO₂ Nanocomposites (M = Ag, Pd, Au, Pt) and Their Optical Properties, CO Oxidation Performance, and Antibacterial Effect, *Nano Research*, Vol. 3, pp. 244-255. <https://doi.org/10.1007/s12274-010-1027-z>
- [17] Kim, H. J. – Lee, S. M. – Oh, Y. S. – Yang, Y. H. – Lim, Y. S. – Yoon, D. H. (2014): Unoxidized graphene/alumina nanocomposite: fracture and wear-resistance effects of graphene on alumina matrix. *Scientific Reports*. Vol. 4, Article number 5176. <https://doi.org/10.1038/srep05176>
- [18] Fan, Y. C. – Jiang, W. – Kawasaki, A. (2012): Highly conductive few-layer graphene/Al₂O₃ nanocomposites with tunable charge carrier type. *Advanced Functional Materials*. Vol. 22, pp. 3882-3889. <https://doi.org/10.1002/adfm.201200632>
- [19] Wang, D. – Zhou, T. – Zha, J. W. – Zhao, J. – Shi, C. Y. – Dang, Z. M. (2013): Functionalized graphene–BaTiO₃/ferroelectric polymer nanodielectric composites with high permittivity, low dielectric loss, and low percolation threshold. *Journal of Materials Chemistry A*. Vol. 1, pp. 6162-6168. <https://doi.org/10.1039/C3TA10460E>
- [20] Lucía Fernández-García – Marta Suárez – José Luis Menéndez – Carlos Pecharrormán – Rosa Menéndez – Ricardo Santamaría (2015): Dielectric behavior of ceramic–graphene composites around the percolation threshold. *Nanoscale Research Letters*. Vol. 10, pp. 216-223. <https://doi.org/10.1186/s11671-015-0921-4>
- [21] Al-Mutoki, S. M. M. – Al-Ghzawi, B. A. H. K. – Al-Mulla, E. A. J. – AbdulAmohsin, S. (2016): Enhancement of Mechanical Properties of Polyamide Hexaglycol by Dispersion of TiO₂ Nanofiller. *Nano Biomedicine and Engineering*, Vol. 8, pp. 55-59. <https://doi.org/10.5101/nbe.v8i2.p55-59>
- [22] Al-Mutoki, S. M. M. – Wadday, A. G. – Abdullah, A. A. Al-Ghzawi, B. A. K. – Al-Mulla, E. A. J. (2016): Effect of nanoTiO₂ dopant on electrical properties of SR8100/nanoTiO₂ PMNC. *Results in Physics*, Vol. 6, pp. 551-553. <https://doi.org/10.1016/j.rinp.2015.12.006>
- [23] Al-Mutoki, S. M. M. – Al-Ghzawi, B. A. H. K. – Abdullah, A. A. – AlAmmar, A. I. R. – Al-Mulla, E. A. J. (2015): Synthesis and characterization of new epoxy/titanium dioxide nanocomposite. *Nano Biomedicine and Engineering*, Vol. 7, pp. 135-138. <https://doi.org/10.5101/nbe.v7i4.p135-138>

Ref.:

Al Mutoki, Sabah Mohammed Mlkat – Al-Ghzawi, Baydaa Abdul-Hassan Khalaf – Abdul Amohsin, Samir M. – Al-Mulla, Emad A. Jaffar: *Raman shift of silicon rubber-nano titania PMNC* Építőanyag – Journal of Silicate Based and Composite Materials, Vol. 69, No. 1 (2017), 20-23. p. <http://dx.doi.org/10.14382/epitoanyag-jsbcm.2017.4>

Szilikon gumi-nano titándioxid PMNC Raman eltolódása

A szerzők nanoszemcsés TiO₂ töltőanyagot alkalmaztak SR8100 szilikon gumi ágyazóanyagban. A kialakuló struktúrát és az anyagjellemzőket pásztázó elektronmikroszkóppal, Raman spektroszkópiával és Fourier-transzformációs infravörös spektroszkópiával vizsgálták, és meghatározták az FTIR spektrumokat és a Raman eltolódást a perkolációs határ azonosítása érdekében. Az eredmények rámutattak, hogy 5 m% TiO₂ töltőanyag tartalom felett megváltozik a kompozit polaritása és Raman eltolódása.

Kulcsszavak: PMNC, nano kerámia oxid töltőanyag, nTiO₂, Raman eltolódás

EUROMAT 2017

FEMS THE FIRST 30 YEARS

EUROPEAN CONGRESS AND EXHIBITION ON ADVANCED MATERIALS AND PROCESSES

17-22 SEPTEMBER 2017 THESSALONIKI, GREECE www.euromat2017.fems.eu

SMAR 2017

13-15 September 2017, Zurich, Switzerland

The fourth International Conference on Smart Monitoring, Assessment and Rehabilitation of Civil Structures

www.smar2017.org