Rheological characterization of the curing process for a water-based epoxy added with polythiol crosslinking agent

Maria Myrelle S. QUIAMBAO

Design and Development (D&D) specialist,
Chemrez Technologies Inc., Quezon City,
Philippines

Danilo D. LAPLANA

Design and Development (D&D) technologist,
Chemrez Technologies Inc., Quezon City,
Philippines

Ibarra Miguel D. ABOBO

MS Chemistry graduate of De La Salle University,
Manila, Philippines

Angelica G. JANCON

Design and Development (D&D) manager,
Chemrez Technologies Inc., Quezon City,
Philippines

Sonia D. SALVADOR

Consultant, D&L Industries, Inc., Quezon City,
Philippines

Henry C. SIY

General Manager, Chemrez Product Solutions
Inc., Quezon City, Philippines

David P. PENALOZA JR.

Associate professor in the Chemistry
Department, College of Science, De La Salle
University, Manila, Philippines. His research
interests focus on self-assembled systems and
nanostructured materials.

MARIA MYRELLE S. QUIAMBAO ▪ Chemrez Technologies Inc., Quezon City, Philippines

DANILO D. LAPLANA ▪ Chemrez Technologies Inc., Quezon City, Philippines

MIGUEL IBARRA D. ABOBO ▪ Chemrez Product Solutions Inc., Quezon City, Philippines
▪ Chemistry Department, College of Science, De La Salle University, Manila, Philippines

ANGELICA G. JANCON ▪ Chemrez Technologies Inc., Quezon City, Philippines

SONIA D. SALVADOR ▪ D&L Industries Inc., Quezon City, Philippines

HENRY C. SIY ▪ Chemrez Product Solutions Inc., Quezon City, Philippines

DAVID P. PENALOZA JR. ▪ D&L Industries Inc., Quezon City, Philippines ▪ Chemistry Department,
College of Science, De La Salle University, Manila, Philippines ▪ david.penalaza.jr@dlsu.edu.ph

Érkezett: 2019. 09. 04. ▪ Received: 04. 09. 2019. ▪ <https://doi.org/10.14382/epitoanyag-jsbcm.2019.28>

Abstract

This work presents a rheological investigation of the curing process of a water-based epoxy system by characterizing the efficiency of polythiols as crosslinking agents. Measurements using an oscillatory rheometer equipped with a parallel geometry determined that the rheological profiles (e.g. storage modulus and sol-gel transition - aka gelation, etc.) of the epoxy resins were affected by the number of thiols and the concentration of the added crosslinking agents. A strong correlation between the number of thiols and the storage modulus of the epoxy material was observed. These results enable improvement in epoxy curing process by providing a thorough understanding of the interrelationship of these variables.

Keywords: rheology, curing, epoxy, gel time

Kulcsszavak: reológia, utókezelés, epoxi, gélesedési idő

1. Introduction

Network materials based on crosslinked polymers (thermosets) are specific materials of interest from both basic and applied points of view. A common example of thermosets is epoxies [1-5]. We usually know epoxies as adhesives. A usual chemistry would involve the reaction of 1 mole of amine with 2 moles of epoxides. This will form three-dimensional crosslinks, and the degree of crosslinking determines the curing process (Fig. 1).

Usually comprised of a group of crosslinkable resin (epoxide) that when reacted with a curing agent - sometimes referred to as the hardener - resulted in a cured thermoset [6-11]. Combining the epoxy resin and hardener initiates a chemical reaction that converts the initially low molecular weight liquid resin into its thermoset form (solid) characterized by highly crosslinked network structure. This is process is called curing [12-15]. The time it takes for this conversion from liquid to solid is called gel time [4, 16-18]. Understanding the curing reaction is very important in the safe and efficient utilization of epoxies as commercial and technological products.

Introduced in the 1940s, the combination of valuable properties of epoxies such as high toughness [19-23], good adhesion to many substrates [24-29] and remarkable chemical resistance [30-33] and low shrinkage [34-37] and their good processing characteristics had led to their wide utilization in the coatings industry. They are extensively used in plant maintenance, automotive primers, can and drum coatings, appliance finishes, pipe coatings and trade-sales paints [38-48].

A good majority of epoxy materials require high temperature conditions to effect curing. If epoxies are not heated enough, chemical, mechanical and heat-resistance properties of which epoxies are known for consequently suffer [49-52]. It is therefore desired to achieve ease with which the curing process can be fine tuned to suit the fabricating process.

In this work, we used rheology to characterize the curing reaction of an epoxy-amine system modified with polythiol agents. The rheological properties as affected by change in the number of thiol groups as well as varying concentrations were investigated.

2. Experimental methods

Our material of interest is a two-part water-based epoxy system provided by Chemrez, Inc. We decided to add polythiols into the system to give an opportunity to have more crosslinking points that may significantly affect the curing process. Polythiol crosslinking agents having (a) three thiol groups, represented here as $R(SH)_3$; (b) four thiols, $R(SH)_4$ and (c) six thiols, $R(SH)_6$ were used. These thiols are commercially available and hence, from an industrial point of view, are more practical to be used. Thiols were chosen because they are known to react with a lot of functional groups like epoxides inducing a curing reaction [53-57], and we can use a rheometer to follow this curing behaviour [58-63] (Fig. 2).

Fig. 1 An illustration of the formation of a network system from the crosslinking reaction involving an epoxy-amine system
1. ábra Epoxi-amin rendszert tartalmazó térhálósodási reakcióból létrejövő hálózati rendszer kialakulásának illusztrációja

Fig. 2 Rheological study of the curing process of a water-based epoxy with polythiol additives using a rheometer
2. ábra Víz alapú epoxi politiol-adalékanyagokkal való kezelési folyamatának reológiai vizsgálata reométer segítségével

Fig. 3 Plot of viscosity (η), in Pa-s, vs time, in s, of the epoxy samples at different temperature conditions

3. ábra Az epoxi minták viszkozitása (η) [Pa-s] az idő [s] függvényében különböző hőmérsékleteken

Fig. 4 Plot of storage modulus (G'), in Pa, vs time, in s, of the epoxy samples at different temperature conditions

4. ábra Az epoxi minták tárolási modulusa G' [Pa] az idő [s] függvényében különböző hőmérsékleteken

Basically, we sandwiched the samples in between two plates. The samples were then subjected to oscillations and mechanical responses during this process were obtained using TA AR3 Hybrid Rheometer. From these measurements, mechanical properties such as viscosity (η) and storage (G') and loss (G'') moduli were extracted. In utilizing rheology to follow the curing process, we rely on the change of these viscoelastic parameters: G' , G'' and η when the material of interest is subjected to oscillations. η is the ability of the epoxy to resist flow, in a way reflects the fluidity of the epoxy material [64-65]. G' represents the elastic character (solid-like behavior) of the epoxy material and is a measure of the energy that can be recovered. On the other hand, G'' reflects energy loss by the material through dissipation and represents the viscous part (liquid-like behavior) of the epoxy [4, 16, 66-69].

3. Results and discussion

To characterize the curing reaction of the epoxy material, a sinusoidal shear strain or stress is applied to the sample sandwiched between two parallel plates and the response is monitored and finally recorded: viscosity (η) and storage (G') and loss (G'') moduli. We initially monitored the effect of different temperature conditions: 25, 30, 40 and 50°C on the η values of the two-part epoxy system over a period of time. As shown in Fig. 3, higher temperature results in a faster gelation as reflected in higher η values recorded over a shorter period of time. A case in point for instance is the higher slope of the η vs. time plot observed at 50°C than at 25°C.

Plotting G' against time – instead of η (Fig. 4) shows that the solid-like property of the material increases with increasing temperature. The change in these rheological parameters reflects the progress of the epoxy curing reaction: at the early stage, the epoxy resin behaves like a liquid. As the curing progresses, a crosslinking reaction occurs and this initiates network formation. This is known as the gel point [70]. During this time, epoxy behavior changes from being liquid-like to solid-like and is characterized by a significant change in η (gelation) denoting the formation of a highly crosslinked system [70]. This has a great impact on the application process of the epoxy material. However, in actual applications, increasing the temperature to hasten the curing is not very practical especially when in very wide spaces. So we came up with a solution to employ polythiol additives, in lieu of heating the epoxy to induce epoxy curing – and investigate its effect on the curing process.

At 1 %wt loading, different types of polythiol additives namely: (a) three thiol groups, represented here as $R(SH)_3$; (b) four thiols, $R(SH)_4$ and (c) six thiols, $R(SH)_6$ were used as shown in Fig. 5. A negative control – without $R(SH)_n$ – was also included for comparison. The polythiol with the most number of thiol reactive sites, $R(SH)_6$, exhibited the highest G' values, suggesting faster curing rate than the other polythiols used. Obviously, more reactive sites for the epoxides to crosslink offer the fastest gelation behavior the treatments considered.

Fig. 5 Plot of storage modulus (G'), in Pa, vs time, in s, of the epoxy samples having different types of polythiol additives - $R(SH)_n$ where $n=3,4,6$ at 1 wt% loading - as compared to control (no additive)

5. ábra Az epoxi minták tárolási modulusa G' [Pa] az idő [s] függvényében különböző típusú politiol adalékszerekkel - $R(SH)_n$, ahol $n=0,3,4,6$

After identifying the polythiol additive that can provide the highest increase in G' at the shortest time, here in this case, $R(SH)_6$ – we varied the additive loading concentration: 1, 2, 3, 5 and 10 %wt. Increasing the concentration also results in a faster gelation, as observed in the significant change in G' values in much shorter time periods (Fig. 6).

Fig. 6 Plot of storage modulus (G'), in Pa, vs time, in s, of the epoxy samples having different concentrations of $R(SH)_6$ additive as compared to control (no additive)

6. ábra Az epoxi minták tárolási modulusa G' [Pa] az idő [s] függvényében különböző koncentrációjú $R(SH)_6$ adalékszerekkel

We also determine the gel point. To do this, plot of G' and G'' versus time, the time correlating to the crossover point of G' and G'' corresponds to the gel point as shown in Fig. 7. During the initial cure period, the loss modulus is greater than storage modulus. What this means is during this stage, the liquid-like (viscous) behavior of the epoxy dominates over the solid-like (elastic) character. The crossover point is when $G'=G''$, suggesting that a crosslinking reaction between the epoxy resin and the hardener had initiated. This is known as the gel point. This is also characterized by a significant jump in η values. In the final cure stage, G' is much greater than G'' meaning the epoxy had become mostly an elastic solid.

Fig. 7 Gel point is determined as the crossover point of G' and G'' in the plot of these moduli values against time

7. ábra A gelpont meghatározása a G' és G'' keresztezési pontjaként az idő függvényében

Getting the gel point which is the crossover points of the G' and G'' at various concentrations of the $R(SH)_6$ added to the epoxy matrix tells us that increasing the additive concentration led to faster gelation (shorter gel point) as shown in Table 1.

Crosslinking agent	Gel point, seconds
Without (control)	4.3×10^3
Added with 1 %wt $R(SH)_6$ crosslinking agent	4.7×10^3
Added with 5 %wt $R(SH)_6$ crosslinking agent	2.2×10^3
Added with 10 %wt $R(SH)_6$ crosslinking agent	0.7×10^3

Table 1 Gel points in case of different amount of crosslinking agents

1. táblázat Gelpontok kialakulási időpontja különböző térhálósító szerek esetén

4. Conclusions

In this study, we investigated the curing of a water-based two-part epoxy system modified with polythiol additives. As shown, the curing process can be effectively characterized using rheology. By varying the type of thiol agents as well as the concentration, rheological properties such as viscosity (η), storage modulus (G'), loss modulus (G'') and gel point can be fine tuned. Increasing the thiol functional groups for the added crosslinking agent and its concentration result in a faster gelation, as observed in the significant change in G' values in much shorter time periods. Also, getting the gel point which is the crossover points of the G' and G'' at various concentrations of the $R(SH)_6$ added to the epoxy matrix tells us that increasing the additive concentration led to faster gelation (shorter gel point). Understanding the interrelationship of these variables is vital in epoxy formulation efforts.

Acknowledgment

We would like to acknowledge the financial grant and technical assistance provided by Chemrez, Inc. and D&L Industries, Inc.

References

- [1] Enns, J.B. – Gillham, J.K. (1983): Time-temperature-transformation (TTT) cure diagram: Modeling the cure behavior of thermosets. *Journal of Applied Polymer Science* Vol. 28, No. 8, pp. 2567-2591. <https://doi.org/10.1002/app.1983.070280810>
- [2] Kamal, M.R. – Sourour, S. – Ryan, M. (2017): Integrated thermorheological analysis of the cure of thermosets. *SPE Technical Paper* Vol. 19, pp. 187-191.
- [3] Plazek, D.J. – Frund, Z.N. (1990): Epoxy resins (DGEBA): The curing and physical aging process. *Journal of Polymer Science Part B: Polymer Physics* Vol. 28, No. 4, pp. 431-448. <https://doi.org/10.1002/polb.1990.090280401>
- [4] Tung, C.M. – Dynes, P.J. (1982): Relationship between viscoelastic properties and gelation in thermosetting systems. *Journal of Applied Polymer Science* Vol. 27, No. 2, pp. 569-574. <https://doi.org/10.1002/app.1982.070270220>
- [5] Varshney, V. – Patnaik, S.S. – Roy, A.K. – Farmer, B.L. (2008): A molecular dynamics study of epoxy-based networks: Cross-linking procedure and prediction of molecular and material properties. *Macromolecules* Vol. 41, No. 18, pp. 6837-6842. <https://doi.org/10.1021/ma801153e>
- [6] Chern, C.S. – Poehlein, G.W. (1987): A kinetic model for curing reactions of epoxides with amines. *Polymer Engineering and Science* Vol. 27, No. 11, pp. 788-795. <https://doi.org/10.1002/pen.760271104>
- [7] Dušek, K. – Bleha, M. – Luňák, S. (1977): Curing of epoxide resins: model reactions of curing with amines. *Journal of Polymer Science: Polymer Chemistry Edition* Vol. 15, No. 10, pp. 2393-2400. <https://doi.org/10.1002/pol.1977.170151009>
- [8] Karkanias, P.I. – Partridge, I.K. – Attwood, D. (1996): Modelling the cure of a commercial epoxy resin for applications in resin transfer moulding. *Polymer International* Vol. 41, No. 2, pp. 183-191. [https://doi.org/10.1002/\(SICI\)1097-0126\(199610\)41:2<183::AID-PI621>3.0.CO;2-F](https://doi.org/10.1002/(SICI)1097-0126(199610)41:2<183::AID-PI621>3.0.CO;2-F)
- [9] Mangion, M.B.M. – Johari, G.P. (1990): Relaxations in thermosets. 7. Dielectric effects during the curing and postcuring of an epoxide by mixed amines. *Macromolecules* Vol. 23, No. 15, pp. 3687-3695. <https://doi.org/10.1021/ma00217a024>
- [10] Matějka, L. (2000): Amine cured epoxide networks: Formation, structure, and properties. *Macromolecules* Vol. 33, No. 10, pp. 3611-3619. <https://doi.org/10.1021/ma991831w>
- [11] Ochi, M. – Okazaki, M. – Shimbo, M. (1982): Mechanical relaxation mechanism of epoxide resins cured with aliphatic diamines. *Journal of Polymer Science: Polymer Physics Edition* Vol. 20, No. 4, pp. 689-699. <https://doi.org/10.1002/pol.1982.180200411>
- [12] Brewis, D.M. – Comyn, J. – Fowler, J.R. (1979): Heat distortion temperatures, glass transition temperatures and extent of chemical cure of some amine-hardened epoxide resins. *Polymer* Vol. 20, No. 12, pp. 1548-1552. [https://doi.org/10.1016/0032-3861\(79\)90023-5](https://doi.org/10.1016/0032-3861(79)90023-5)
- [13] Lin, R.H. – Hsu, J.H. (2001): In situ FT-IR and DSC investigation on the cure reaction of the dicyanate/diepoxy/diamine system. *Polymer International* Vol. 50, No. 10, pp. 1073-1081. <https://doi.org/10.1002/pi.747>
- [14] Montserrat, S. – Roman, F. – Colomer, P. (2003): Vittrification and dielectric relaxation during the isothermal curing of an epoxy-amine resin. *Polymer* Vol. 44, No. 1, pp. 101-114. [https://doi.org/10.1016/S0032-3861\(02\)00745-0](https://doi.org/10.1016/S0032-3861(02)00745-0)
- [15] Skladanyuk, R.V. – Zakordonskii, V.P. (2005): Influence of physical structuring on the kinetics of the epoxy-amine reaction in filled systems. *Polymer Science Series A* Vol. 47, No. 1, pp. 24-31.
- [16] Chambon, F. – Winter, H.H. (1987): Linear viscoelasticity at the gel point of a crosslinking PDMS with imbalanced stoichiometry. *Journal of Rheology* Vol. 31, No. 8, pp. 683-697. <https://doi.org/10.1122/1.549955>
- [17] Michon, C. – Cuvelier, G. – Launay, B. (1993): Concentration dependence of the critical viscoelastic properties of gelatin at the gel point. *Rheologica Acta* Vol. 32, No. 1, pp. 94-103. <https://doi.org/10.1007/BF00396681>
- [18] Winter, H.H. (1987): Can the gel point of a cross-linking polymer be detected by the $G' - G''$ crossover? *Polymer Engineering and Science* Vol. 27, No. 22, pp. 1698-1702. <https://doi.org/10.1002/pen.760272209>
- [19] Benzeggagh, M.L. – Kenane, M. (1996): Measurement of mixed-mode delamination fracture toughness of unidirectional glass/epoxy composites with mixed-mode bending apparatus. *Composites Science and Technology* Vol. 56, No. 4, pp. 439-449. [https://doi.org/10.1016/0266-3538\(96\)00005-X](https://doi.org/10.1016/0266-3538(96)00005-X)

- [20] Garg, A.C. – Mai, Y.W. (1988): Failure mechanisms in toughened epoxy resins – A review. *Composites Science and Technology* Vol. 31, No. 3, pp. 179-223. [https://doi.org/10.1016/0266-3538\(88\)90009-7](https://doi.org/10.1016/0266-3538(88)90009-7)
- [21] Gojny, F.H. – Wichmann, M.H.G. – Fiedler, B. – Schulte, K. (2005): Influence of different carbon nanotubes on the mechanical properties of epoxy matrix composites – A comparative study. *Composites Science and Technology* Vol. 65, No. 15-16, pp. 2300-2313. <https://doi.org/10.1016/j.compscitech.2005.04.021>
- [22] Johnsen, B.B. – Kinloch, A.J. – Mohammed, R.D. – Taylor, A.C. – Sprenger, S. (2007): Toughening mechanisms of nanoparticle-modified epoxy polymers. *Polymer* Vol. 48, No. 2, pp. 530-541. <https://doi.org/10.1016/j.polymer.2006.11.038>
- [23] Rafiee, M.A. – Rafiee, J. – Wang, Z. – Song, H. – Yu, Z.Z. – Koratkar, N. (2009): Enhanced mechanical properties of nanocomposites at low graphene content. *ACS Nano* Vol. 3, No. 12, pp. 3884-3890. <https://doi.org/10.1021/nn9010472>
- [24] Armelin, E. – Pla, R. – Liesa, F. – Ramis, X. – Iribarren, J.I. – Alemán, C. (2008): Corrosion protection with polyaniline and polypyrrole as anticorrosive additives for epoxy paint. *Corrosion Science* Vol. 50, No. 3, pp. 721-728. <https://doi.org/10.1016/j.corsci.2007.10.006>
- [25] Dilsiz, N. – Wightman, J.P. (2000): Effect of acid-base properties of unsized and sized carbon fibers on fiber/epoxy matrix adhesion. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* Vol. 164, No. 2-3, pp. 325-336. [https://doi.org/10.1016/S0927-7757\(99\)00400-8](https://doi.org/10.1016/S0927-7757(99)00400-8)
- [26] Drzal, L.T. – Madhukar, M. (1993): Fibre-matrix adhesion and its relationship to composite mechanical properties. *Journal of Materials Science* Vol. 28, No. 3, pp. 569-610. <https://doi.org/10.1007/BF01151234>
- [27] Ma, P.C. – Mo, S.Y. – Tang, B.Z. – Kim, J.K. (2010): Dispersion, interfacial interaction and re-agglomeration of functionalized carbon nanotubes in epoxy composites. *Carbon* Vol. 48, No. 6, pp. 1824-1834. <https://doi.org/10.1016/j.carbon.2010.01.028>
- [28] Ochi, M. – Takahashi, R. – Terauchi, A. (2001): Phase structure and mechanical and adhesion properties of epoxy/silica hybrids. *Polymer* Vol. 42, No. 12, pp. 5151-5158. [https://doi.org/10.1016/S0032-3861\(00\)00935-6](https://doi.org/10.1016/S0032-3861(00)00935-6)
- [29] Prolongo, S.G. – Del Rosario, G. – Ureña, A. (2006): Comparative study on the adhesive properties of different epoxy resins. *International Journal of Adhesion and Adhesives* Vol. 26, No. 3, pp. 125-132. <https://doi.org/10.1016/j.ijadhadh.2005.02.004>
- [30] Ahmad, S. – Gupta, A.P. – Sharmin, E. – Alam, M. – Pandey, S.K. (2005): Synthesis, characterization and development of high performance siloxane-modified epoxy paints. *Progress in Organic Coatings* Vol. 54, No. 3, pp. 248-255. <https://doi.org/10.1016/j.porgcoat.2005.06.013>
- [31] Mostafaei, A. – Nasirpour, F. (2014): Epoxy/polyaniline-ZnO nanorods hybrid nanocomposite coatings: Synthesis, characterization and corrosion protection performance of conducting paints. *Progress in Organic Coatings* Vol. 77, No. 1, pp. 146-159. <https://doi.org/10.1016/j.porgcoat.2013.08.015>
- [32] Woo, R.S.C. – Chen, Y. – Zhu, H. – Li, J. – Kim, J.K. – Leung, C.K.Y. (2007): Environmental degradation of epoxy-organoclay nanocomposites due to UV exposure. Part I: Photo-degradation. *Composites Science and Technology* Vol. 67, No. 15-16, pp. 3448-3456. <https://doi.org/10.1016/j.compscitech.2007.03.004>
- [33] Zhang, Z. – Breidt, C. – Chang, L. – Hauptert, F. – Friedrich, K. (2004): Enhancement of the wear resistance of epoxy: short carbon fibre, graphite, PTFE and nano-TiO₂. *Composites Part A: Applied Science and Manufacturing* Vol. 35, No. 12, pp. 1385-1392. <https://doi.org/10.1016/j.compositesa.2004.05.005>
- [34] Chen, M.H. – Chen, C.R. – Hsu, S.H. – Sun, S.P. – Su, W.F. (2006): Low shrinkage light curable nanocomposite for dental restorative material. *Dental Materials* Vol. 22, No. 2, pp. 138-145. <https://doi.org/10.1016/j.dental.2005.02.012>
- [35] Ilie, N. – Jelen, E. – Clementino-Luedemann, T. – Hickel, R. (2007): Low-shrinkage composite for dental application. *Dental Materials Journal* Vol. 26, No. 2, pp. 149-155. <https://doi.org/10.4012/dmj.26.149>
- [36] Ishida, H. – Allen, D.J. (1996): Physical and mechanical characterization of near-zero shrinkage polybenzoxazines. *Journal of Polymer Science Part B: Polymer Physics* Vol. 34, No. 6, pp. 1019-1030. [https://doi.org/10.1002/\(SICI\)1099-0488\(19960430\)34:6<1019::AID-POLB1>3.0.CO;2-T](https://doi.org/10.1002/(SICI)1099-0488(19960430)34:6<1019::AID-POLB1>3.0.CO;2-T)
- [37] Yarovsky, I. – Evans, E. (2001): Computer simulation of structure and properties of crosslinked polymers: application to epoxy resins. *Polymer* Vol. 43, No. 3, pp. 963-969. [https://doi.org/10.1016/S0032-3861\(01\)00634-6](https://doi.org/10.1016/S0032-3861(01)00634-6)
- [38] Azeez, A.A. – Rhee, K.Y. – Park, S.J. – Hui, D. (2013): Epoxy clay nanocomposites - processing, properties and applications: A review. *Composites Part B: Engineering* Vol. 45, No. 1, pp. 308-320. <https://doi.org/10.1016/j.compositesb.2012.04.012>
- [39] Bao, C. – Guo, Y. – Song, L. – Kan, Y. – Qian, X. – Hu, Y. (2011): In situ preparation of functionalized graphene oxide/epoxy nanocomposites with effective reinforcements. *Journal of Materials Chemistry* Vol. 21, No. 35, pp. 13290-13298. <https://doi.org/10.1039/C1JM11434D>
- [40] Chattopadhyay, D.K. – Panda, S.S. – Raju, K.V.S.N. (2005): Thermal and mechanical properties of epoxy acrylate/methacrylates UV cured coatings. *Progress in Organic Coatings* Vol. 54, No. 1, pp. 10-19. <https://doi.org/10.1016/j.porgcoat.2004.12.007>
- [41] Hughes, J.D.H. (1991): The carbon fibre/epoxy interface – A review. *Composites Science and Technology* Vol. 41, No. 1, pp. 13-45. [https://doi.org/10.1016/0266-3538\(91\)90050-Y](https://doi.org/10.1016/0266-3538(91)90050-Y)
- [42] Li, Y. – Wong, C.P. (2006): Recent advances of conductive adhesives as a lead-free alternative in electronic packaging: Materials, processing, reliability and applications. *Materials Science and Engineering: R: Reports* Vol. 51, No. 1-3, pp. 1-35. <https://doi.org/10.1016/j.mser.2006.01.001>
- [43] Lorenz, H. – Despont, M. – Fahrni, N. – Brugger, J. – Vettiger, P. – Renaud, P. (1998): High-aspect-ratio, ultrathick, negative-tone near-UV photoresist and its applications for MEMS. *Sensors and Actuators A: Physical* Vol. 64, No. 1, pp. 33-39. [https://doi.org/10.1016/S0924-4247\(98\)80055-1](https://doi.org/10.1016/S0924-4247(98)80055-1)
- [44] Rakotomalala, M. – Wagner, S. – Döring, M. (2010): Recent developments in halogen free flame retardants for epoxy resins for electrical and electronic applications. *Materials* Vol. 3, No. 8, pp. 4300-4327. <https://doi.org/10.3390/ma3084300>
- [45] Randall, J.P. – Meador, M.A.B. – Jana, S.C. (2011): Tailoring mechanical properties of aerogels for aerospace applications. *ACS Applied Materials and Interfaces* Vol. 3, No. 3, pp. 613-626. <https://doi.org/10.1021/am200007n>
- [46] Rao, Y. – Ogitan, S. – Kohl, P. – Wong, C.P. (2001): Novel polymer-ceramic nanocomposite based on high dielectric constant epoxy formula for embedded capacitor application. *Journal of Applied Polymer Science* Vol. 83, No. 5, pp. 1084-1090. <https://doi.org/10.1002/app.10082>
- [47] Toldy, A. – Szolnoki, B. – Marosi, G. (2011): Flame retardancy of fibre-reinforced epoxy resin composites for aerospace applications. *Polymer Degradation and Stability* Vol. 96, No. 3, pp. 371-376. <https://doi.org/10.1016/j.polymdegradstab.2010.03.021>
- [48] van Westing, E.P.M. – Ferrari, G.M. – de Wit, J.H.W. (1993): The determination of coating performance with impedance measurements-I. Coating polymer properties. *Corrosion Science* Vol. 34, No. 9, pp. 1511-1530. [https://doi.org/10.1016/0010-938X\(93\)90245-C](https://doi.org/10.1016/0010-938X(93)90245-C)
- [49] Esposito, L. – Sorrentino, L. – Penta, F. – Bellini, C. (2016): Effect of curing overheating on interlaminar shear strength and its modelling in thick FRP laminates. *The International Journal of Advanced Manufacturing Technology* Vol. 87, No. 5-8, 2213-2220. <https://doi.org/10.1007/s00170-016-8613-5>
- [50] Huang, Y. – Young, R.J. (1995): Interfacial behaviour in high temperature cured carbon fibre/epoxy resin model composite. *Composites* Vol. 26, No. 8, pp. 541-550. [https://doi.org/10.1016/0010-4361\(95\)92619-N](https://doi.org/10.1016/0010-4361(95)92619-N)
- [51] Kim, J. – Moon, T.J. – Howell, J.R. (2002): Cure kinetic model, heat of reaction, and glass transition temperature of AS4/3501-6 graphite-epoxy preregs. *Journal of Composite Materials* Vol. 36, No. 21, pp. 2479-2498. <https://doi.org/10.1177/0021998302036021712>
- [52] Kim, J. – Moon, T.J. – Howell, J.R. (2003): Transient thermal modeling of in-situ curing during tape winding of composite cylinders. *Journal of Heat Transfer* Vol. 125, No. 1, pp. 137-146. <https://doi.org/10.1115/1.1527912>
- [53] Gráz, V. – Abian, O. – Mateo, C. – Batista-Viera, F. – Fernández-Lafuente, R. – Guisán, J.M. (2003): Novel bifunctional epoxy/thiol-reactive support to immobilize thiol containing proteins by the epoxy chemistry. *Biomacromolecules* Vol. 4, No. 6, pp. 1495-1501. <https://doi.org/10.1021/bm034262f>
- [54] Jin, K. – Wilmot, N. – Heath, W.H. – Torkelson, J.M. (2016): Phase-separated thiol-epoxy-acrylate hybrid polymer networks with controlled cross-link density synthesized by simultaneous thiol-acrylate and thiol-

- epoxy click reactions. *Macromolecules* Vol. 49, No. 11, pp. 4115-4123. <https://doi.org/10.1021/acs.macromol.6b00141>
- [55] Stuparu, M.C. – Khan, A. (2016): Thiol-epoxy “click” chemistry: Application in preparation and postpolymerization modification of polymers. *Journal of Polymer Science Part A: Polymer Chemistry* Vol. 54, No. 19, pp. 3057-3070. <https://doi.org/10.1002/pola.28195>
- [56] Zhang, Y. – Li, H. – Dong, J.Y. – Hu, Y. (2014) Facile synthesis of chain end functionalized polyethylenes via epoxide ring-opening and thiol-ene addition click chemistry. *Polymer Chemistry* Vol. 5, No. 1, pp. 105-115. <https://doi.org/10.1039/C3PY00727H>
- [57] Zhu, D.Y. – Cao, G.S. – Qiu, W.L. – Rong, M.Z. – Zhang, M.Q. (2015): Self-healing polyvinyl chloride (PVC) based on microencapsulated nucleophilic thiol-click chemistry. *Polymer* Vol. 69, pp. 1-9. <https://doi.org/10.1016/j.polymer.2015.05.052>
- [58] Khoun, L. – Centea, T. – Hubert, P. (2010) Characterization methodology of thermoset resins for the processing of composite materials – Case study: CYCOM 890RTM Epoxy Resin. *Journal of Composite Materials* Vol. 44, No. 11, pp. 1397-1415. <https://doi.org/10.1177/0021998309353960>
- [59] Lange, J. – Altmann, N. – Kelly, C.T. – Halley, P.J. (2000): Understanding vitrification during cure of epoxy resins using dynamic scanning calorimetry and rheological techniques. *Polymer* Vol. 41, No. 15, pp. 5949-5955. [https://doi.org/10.1016/S0032-3861\(99\)00758-2](https://doi.org/10.1016/S0032-3861(99)00758-2)
- [60] Lapique, F. – Redford, K. (2002): Curing effects on viscosity and mechanical properties of a commercial epoxy resin adhesive. *International Journal of Adhesion and Adhesives* Vol. 22, No. 4, pp. 337-346. [https://doi.org/10.1016/S0143-7496\(02\)00013-1](https://doi.org/10.1016/S0143-7496(02)00013-1)
- [61] Le Pluart, L. – Duchet, J. – Sautereau, H. – Halley, P. – Gerard, J.F. (2004): Rheological properties of organoclay suspensions in epoxy network precursors. *Applied Clay Science* Vol. 25, No. 3-4, pp. 207-219. <https://doi.org/10.1016/j.clay.2003.11.004>
- [62] Martinez, I. – Martin, M.D. – Eceiza, A. – Oyanguren, P. – Mondragon, I. (2000): Phase separation in polysulfone-modified epoxy mixtures. Relationships between curing conditions, morphology and ultimate behavior. *Polymer* Vol. 41, No. 3, pp. 1027-1035. [https://doi.org/10.1016/S0032-3861\(99\)00238-4](https://doi.org/10.1016/S0032-3861(99)00238-4)
- [63] Roller, M.B. (1986): Rheology of curing thermosets: A review. *Polymer Engineering and Science* Vol. 26, No. 6, pp. 432-440. <https://doi.org/10.1002/pen.760260610>
- [64] Khayat, K.H. (1998): Viscosity-enhancing admixtures for cement-based materials - An overview. *Cement and Concrete Composites* Vol. 20, No. 2-3, pp. 171-188. [https://doi.org/10.1016/S0958-9465\(98\)80006-1](https://doi.org/10.1016/S0958-9465(98)80006-1)
- [65] Pries, A.R. – Secomb, T.W. – Sperandio, M.B. – Gross, J.F. – Gaetgens, P. (1994): Resistance to blood flow in microvessels in vivo. *Circulation Research* Vol. 75, No. 5, pp. 904-915. <https://doi.org/10.1161/01.RES.75.5.904>
- [66] Almdal, K. – Dyre, J. – Hvidt, S. – Kramer, O. (1993): Towards a phenomenological definition of the term ‘gel’. *Polymer Gels and Networks* Vol. 1, No. 1, pp. 5-17. [https://doi.org/10.1016/0966-7822\(93\)90020-1](https://doi.org/10.1016/0966-7822(93)90020-1)
- [67] Winter, H.H. – Chambon, F. (1986): Analysis of linear viscoelasticity of a crosslinking polymer at the gel point. *Journal of Rheology* Vol. 30, No. 2, pp. 367-382. <https://doi.org/10.1122/1.549853>
- [68] Hori, K. – Penaloza, D.P. – Shundo, A. – Tanaka, K. (2012): Time-dependent heterogeneity in viscoelastic properties of worm-like micelle solutions. *Soft Matter* Vol. 8 No. 28, 7361-7364. <https://doi.org/10.1039/C2SM25549A>
- [69] Shundo, A. – Penaloza Jr., D.P. – Tanaka, K. (2013): Microscopic heterogeneity in viscoelastic properties of molecular assembled systems. *Chinese Journal of Polymer Science (English Edition)* Vol. 31, No. 1, pp. 1-11. <https://doi.org/10.1007/s10118-013-1193-z>
- [70] Wang, X. – Gillham, J. K. (1993): T_g -temperature property (T_g TP) diagram for thermosetting systems: anomalous behavior of physical properties vs. extent of cure. *Journal of Applied Polymer Science* Vol. 47, No. 3, pp. 425-446

Ref.:

Quiambao, Maria Myrelle S. – Laplana, Danilo D. – Abobo, Miguel Ibarra D. – Jancon, Angelica G. – Salvador, Sonia D. – Siy, Henry C. – Penaloza, David P. Jr.: *Rheological characterization of the curing process for a water-based epoxy added with polythiol crosslinking agent*
Építőanyag – Journal of Silicate Based and Composite Materials, Vol. 71, No. 5 (2019), 162–167. p.
<https://doi.org/10.14382/epitoanyag-jsbcm.2019.28>

European Science Foundation (ESF)

Over four decades of setting science agendas for Europe

Based in Strasbourg, France, ESF was established in 1974 as an independent, non-governmental, non-profit organisation to provide a common platform for its Member Organisations to collaborate internationally on research programmes through its networking, funding and coordination activities. The launch of Science Connect, our new expert services division, marks the next phase of ESF's role, borne out of our deep understanding of the science landscape, funding context and needs of the research community at this critical juncture.

www.esf.org

Science Connect

Your partner in Science

Science Connect's mission is to partner with clients in leading successful projects and in facilitating informed decision-making through a broad range of science-support services including Peer Review, Evaluation, Career Tracking, Programme and Project Management and Administration, the hosting of Expert Boards and Virtual Institutes. Building on ESF's extensive network and experience, Science Connect delivers resources, tools and metrics to support the effective administration of science projects in both the private and public research sector.