Real-scale experimental analysis on the continuity effect of steel-concrete composite slabs subjected to fire conditions: state-of-the-art

Fabício L. Bolina^{1*}, Bernardo Tutikian², Matheus Dilly³ e João Paulo C. Rodrigues⁴

¹ Faculdade de Engenharia Civil/Unisinos, Brazil, fabriciolb@unisinos.br

² Faculdade de Engenharia Civil/Unisinos, Brazil, bftutikian@unisinos.br

³ Faculdade de Engenharia Civil/Unisinos, Brazil, mthsdilly@gmail.com

⁴ Escola de Eng. Civil/Universidade de Coimbra, Portugal, jpaulocr@dec.uc.pt

Análise em escala natural do efeito de continuidade de lajes mistas de aço e concreto em situação de incêndio: estado da arte

Abstract

Composite slabs are common solutions in steel structures. The profiled steel sheeting of the steel deck can remove the need for positive reinforcement. However, due to the slenderness of these sheets and their fragility at high temperatures, the occurrence of fires can undermine the safety of the structural system. In many cases, positive reinforcements have been added to increase resistance to fire. It is known that negative reinforcements have better thermal protection than positive ones and generate structural continuity to the slabs, increasing their negative bending moment while reducing the positive one. These factors result in greater effectiveness of the negative reinforcement when compared to the positive one, despite the scarcity of studies in this regard, which makes the subject incipient. This paper presents a state-of-the-art analysis on the continuity effect of composite slabs subjected to fire conditions by means of real scale experiments.

Keywords: *composite slabs, structure fire, fire safety design, membrane action effect.*

Resumo

As lajes mistas de aço e concreto são soluções frequentes em estruturas metálicas. A chapa perfilada do deck metálico pode eliminar a necessidade de armaduras positivas. Porém, devido a esbeltez dessas chapas e sua sensibilidade às altas temperaturas, a ocorrência de incêndios pode comprometer a segurança deste elemento. Em muitos casos, armaduras positivas têm sido incorporadas para aumentar sua resistência ao fogo. Sabe-se que armaduras negativas estão termicamente mais protegidas face às positivas e incorporam continuidade estrutural às lajes, aumentando seu momento resistente negativo e reduzindo os momentos positivos. Isto propõe maior efetividade das armaduras negativas face às positivas. Porém, pouco tem sido estudado neste sentido, tornando o assunto incipiente. Este artigo apresenta o estado da arte do efeito da continuidade de lajes mistas avaliadas experimentalmente em escala natural sob situação de incêndio, as proposições normativas existentes e as lacunas neste sentido.

Palavras-chave: *Lajes mistas; Incêndio em Estruturas; Projeto ao incêndio; Efeito de Membrana*

1. Introduction

The design of steel structures allows composite slabs to decrease steel consumption of floor joists and produce composite beams. While these slabs restrain the beams laterally, they mitigate global and local instabilities as they reduce the beams' height and weight, thereby promoting greater overall structural stability (Marimuthu et al., 2007). Composite slabs are composed of profiled steel sheets with a top layer of concrete. The profile sheets function as a continuous positive reinforcement over the slab midspan.

The cross-section of the profiled steel sheets can be trapezoidal (Figure 1a), re-entrant (Figure 1b), corrugated (Figure 1c) or rectangular (Figure 1d), available in three thicknesses: 0.80, 0.95 and 1.25 mm.

Figure 1 – (a) trapezoidal, (b) re-entrant, (c) corrugated and (d) rectangular cross sections (Souza, 2001)

The mechanical degradation steel sheets undergo at high temperatures can compromise the design criteria of beams and columns (Lasheenetal, 2016), which may provoke the progressive collapse of the building on fire (Jiang; Li, 2016) as the deck becomes brittle at high temperatures. The slenderness of the built-in profiled steel sheeting of the slabs can lead to collapse (Li; Zhang; Jiang, 2017), justifying the need to increase reinforcements to mitigate the effect (Bailey; Toh, 2007), mainly over the midspan, where hogging moments occur (Dahham; Baharom; Badaruzzaman, 2017).

Studies at room temperature by Gholamhoseini et al. (2014); Abas et al. (2013) and Lee, Quek and Ang (2001) have already demonstrated that slabs are fit for bending moment redistribution with negative reinforcements acting on midspan supports. However, few studies have evaluated experimentally how structural continuity behaves when subjected to fire conditions. The investigations of Li, Zhang and Jiang (2017) and Stadler (2012) are examples of that. Both focused on a single experimental model. The research by Bednár et al. (2013), despite having being applied to continuous slabs, focused on the

analysis of the membrane action effect, another mechanism that increases the resistance to fire of the slab, mainly the hyperstatic ones.

Other experimental studies regarding continuous composite slabs at high temperatures support this gap, such as Wellman et al. (2010), who sought to study the influence of thermal protection of intermediate beams and shear connectors on the resistance to fire of composite slabs. On the other hand, the full-scale study by the European Coal and Steel Community (2010) aimed at analyzing the membrane action in continuous slabs. This was the same goal of DAST, a German Research Project with the cooperation of German universities, who sought optimization mechanisms for structural designs in addition to taking notes on the effects of structural continuity of composite slabs along intermediate beams. The results demonstrated the need for negative reinforcement in the slabs' design, in the area of the thermally protected beams.

The recommendation, however, was based on only one experimental test and requires further investigation. As a matter of fact, regarding composite slabs without additional reinforcement, the collapse of the profiled steel sheeting under fire conditions may become the main problem given the slenderness and sensitivity of the material in this condition. From a numerical perspective, based on the equilibrium between internal and external stresses applied to the cross section (total plasticization of member section), and considering a loss of strength at high temperatures, the slab tends to behave just like a non-reinforced concrete piece. In such case, the compatibility equations would not be satisfied and the system would collapse. The former experimental tests did not confirm the theory though, as catenary and membrane action effects provide specific boundary conditions that increase the strength of the slabs. Therefore, this subject becomes more representative through experiments.

The experimental tests which aimed to understand the phenomenon showed some peculiarities. Cracks were observed on the concrete slab of thermally protected secondary beams, despite the presence of negative reinforcement. The reinforcements in those cases were broken and the continuity of the slab was compromised. Cardington's investigations conducted by the BRE in England; in Munich, by the German Steel Construction Association in Germany; and the integrated work between several European universities, under the responsibility of Czech Technical University in Prague,

Czech Republic, became references, as they evinced said cracking. These investigations are presented in Figure 2 and Figure 3, being discussed by Newman, Robinson and Baley (2006) and Stadler (2012).

Figure 2 – Continuous composite slab cracking: test in Cardington, England (Newman; Robinson; Bailey, 2006)

Figure 3 – Cracks on the continuous composite slab: test in Munich, Germany (Stadler,2012)

Although not addressed by Wald et al. (2010), the lack of structural continuity seems to have been, among others, the cause for the collapse of the slab sample used in the study from the Czech Technical University, University of Sheffield and Slovak Technical University. Due to the lack of continuity reinforcement in the thermally protected secondary beams that support the slabs and trigger membrane action, cracks such as those listed by Newman, Robinson and Baley (2006) and Stadler (2012) alter the staticity of the slab on fire, leading to the collapse of this and other structural elements, as noted by Wald et al. (2010).

Mensinger et al. (2012) and Stadler (2012) came up with an explanation for these cracks. During the heating of the slab, negative bending moments develop along the thermally protected intermediate beams. As a consequence, the sides of the slab are subjected to a strain state originated from restricted thermal expansion. When the tensile stresses exceed concrete strength, the first cracks occur precisely at the point of maximum negative bending moment, which appears along the intermediate beam. If there are no negative reinforcements enough to resist the stresses, more intense cracks will develop. However, as membrane action begins, which develops only on continuous slabs, the cracks may not necessarily trigger the collapse.

The composite slab's connections and continuity rate depend on several other factors. It is difficult to predict the behavior of the structure in that sense, especially at high

temperatures, given its physical and geometric non-linearity and the interaction between materials exposed to different temperatures, as explained by Javaheriafif (2017). This refers to the concept of semi-rigid connections, not yet addressed at high temperatures.

Therefore, it is necessary to understand the influence of the continuity effect of composite slabs subjected to fire conditions. This phenomenon can be attributed to the negative reinforcement, whose protective layer provides greater thermal protection than the positive one and can improve the performance of the composite slabs exposed to fire as well as yield a more cost-efficient design. Afterwards, the main standards and verification parameters for composite slabs under these exposure conditions will be listed, in addition to the main experimental works developed on the subject and their conclusions.

2. Standardized design criteria

The design standards hardly address the continuity effect of composite slabs. In the cases in which the standards are followed, some built-in simplifications do not seem to match the results of the experimental work already done or require experimental confirmation. The main inspiration of the design standards are EN 1994-1-2 (2011) and AISC 360-05 (2005), from which NBR 14323 (2013) and NZS 2327 (2017) derive. BS 5950-8 (2003) is the only standard that presents criteria regarding the continuity of the slabs, but does not address membrane action, which is presented only by NZS 2327 (2017).

With prescriptive analysis methods, the standards generally establish strength reduction factors as a function of the temperature of the materials, taking the criteria for room temperature design as reference. The most advanced methods even assess thermomechanical effects. Alternatively, the standards propose experimental tests based on the temperature curves of ASTM E 119 (2012) and ISO 834 (2002).

2.1 EN 1994-1-2 (2011)

The definition of the positive bending moment for fire design, for instance, depends on the fire-resistance rating sought. Subsequently, strength reduction factors for the slab and its constituent materials are defined as shown in Equation (1).

$$M_{fi,Rd}^+ = \sum_{i=1}^n A_i \cdot z_i \cdot k_{y,\theta,i} \cdot \left(\frac{f_{y,i}}{\gamma_{M,fi}} \right) + \alpha_{slab} \cdot \sum_{j=1}^m A_j \cdot z_j \cdot k_{c,\theta,j} \cdot \left(\frac{f_{c,j}}{\gamma_{M,fi,c}} \right) \quad (1)$$

Being z_i and z_j the distances of the plastic neutral axis to the gravity center of the profiled steel sheeting and concrete cross section areas A_i and A_j when calculating the positive bending moment, with a strength $f_{y,i}$ and $f_{c,j}$. The $k_{y,\theta,i}$ and $k_{c,\theta,j}$ coefficients refer to the strength reduction factors that correspond to the temperature of the cross section, both of which are tabulated by the standard. The α_{slab} coefficient stands for long term effects on concrete, equals 0.85. It should be noted that EN 1994-1-2 (2011) does not limit the amount of reinforcing bars, leaving this extrapolation to the designer.

Regarding the analysis of negative bending moments at high temperatures, EN 1994-1-2 (2011) states that the effects of the profiled steel sheeting and the positive reinforcement, which are usually continuous under the middle support, can be ignored. Moreover, the tensile stress provided by the negative reinforcement is equal to that of the material at room temperature. To calculate the negative bending moment, a reduced cross section may be used, with the cross section portion that exceeds the limiting temperature being neglected. The remainder of the cross section is regarded as room temperature. The limiting temperature of the cross section is presented in Equation (2).

$$\theta_{lim} = d_0 + d_1 \cdot N_s + d_2 \cdot \frac{A}{L_r} + d_3 \cdot \emptyset + d_4 \cdot \frac{1}{b_2} \quad (2)$$

Where d_0 , d_1 , d_2 , d_3 and d_4 are tabulated factors established by the standard, being a function of the required fire-resistance rating and concrete density. The isotherm for the limiting temperature is established through coordinates presented by the standard which vary with respect to the geometric characteristic of the profiled steel sheeting set in the slab. Therefore, the negative bending moment is obtained by a procedure similar to the one applied at room temperature, considering the negative reinforcement absolute participation as a tensile strength element of the cross section, and a reduced portion of the concrete layer – based on temperature – as a compressive strength element of the cross section. The strength of concrete was corrected in accordance with

its temperature. The continuity effect of the slab was disregarded, as it can only be adjusted through extrapolations made by the designer and their understanding of how positive and negative bending moments can act in an integrated way during a fire.

The simplified method of design of EN 1994-1-2 (2011) is limited to isolated structural elements. EN 1994-1-2 (2011) recognizes that the tabulated numbers are simplified and the results provided are conservative when compared to more advanced experimental or numerical studies. The tables defined by the standard come from a compilation of laboratory test results conducted between 1983 and 1991, performed on a series of flat concrete slabs, indicating the need for advancements in the area.

2.2 BS 5950-8 (2003)

BS 5950-8 (2003) affirms that moment redistribution affects continuous slabs in fire conditions and it improves their fire performance. Concerning continuous slabs, the standard states that the combined effect between positive and negative moment capacities of these slabs should be determined by Equation (3), or Equation (4) by simplification.

$$M_p + 0.50 \cdot M_n \cdot (1 - M_n/8 \cdot M_o) \geq M_o \quad (3)$$

$$M_p + M_n \geq M_o \quad (4)$$

Where M_p , M_n and M_o are, respectively, the positive moment capacity, the negative moment capacity and the load moment exerted during the fire, admitting a simple slab (not continuous). Regarding the negative bending moment, the standard states that the mechanical properties are not much affected and are practically the same as at room temperature. The standard does not present equations to estimate bending moments, whereas it considers the moment of total plasticization of the cross section moment for room temperature calculations applying strength reduction factors to the materials that vary according to the temperature, even so without using of a safety factor for each capacity.

2.3 AISC 360-05 (2005)

Even though AISC 360-05 (2005) follows design specification similar to those of EN 1994-1-2 (2011), it does not present intangible equations, and even sounds vague with regards

to this type of verification. The standard only shows that the structural verifications of composite slabs in fire conditions must follow the same equations as those at room temperature, but applying tabulated strength reduction factors that vary based on the temperature of the required by the fire rating. The continuity effect of composite slabs is not regarded by this standard.

2.4 NZS 2327 (2017)

NZS 2327 (2017) took inspiration from EN 1994-1-2 (2011). The standard presents both simple calculation methods that rely on tables and advanced methods based on finite elements or experimental analyses. It is the first design standard to have combined membrane action and design recommendations, though in a simplified manner that allows secondary beams to be designed without any thermal protection. This principle was drawn from the remarks of Cardington tests, out of which Clifton (2006) developed procedures that have just been included to this standard.

2.5 NBR 14323 (2013)

NBR 14323 (2013) was heavily inspired by the Eurocode, but it presents different criteria in specific cases, adapting the proposals of EN 1994-1-2 (2011) to a particular style of design. One of these particularities is in Annex C of this standard, which presents possible conditions of collapse for composite slabs according to the structural continuity. Concerning continuous slabs, the standard proposes verification criteria according to the load bore during the fire and positive and negative bending moments for a determined fire rating. The definition of these bending moments is based on the same equations as EN 1994-1-2 (2011), without admitting the behavior of concrete structures accounting for its long-term response, represented by the $\alpha=0.85$ factor, as proposed by NBR 15200 (2012).

2.6 Comparison of standards

Table 1 shows the comparison of standards. It is understood that the standard is objective if it presents clear methods and procedures, and subjective if it leaves to the designer to extrapolate the concepts, not showing conclusive and direct procedures. Membrane action, which is remarked for influencing the continuity effect as shown in experimental studies, is not covered by all standards.

Table 1 – Comparison between standards

Standard	Positive bending moment	Negative bending moment	Continuity	Membrane Action
EN 1994-1-2 (2011)	Objective	Objective	Subjective	No
BS 5950-8 (2003)	Subjective	Subjective	Objective	No
AISC 360-05 (2005)	Subjective	Subjective	Subjective	No
NBR 14323 (2013)	Objective	Subjective	Objective	No
AS/NZS 2327 (2017)	Objective	Objective	Subjective	Yes

The standards do not have a general agreement on the continuity effect. EN 1994-1-2 (2011), for example, presents the criteria for calculating both negative and positive bending moments in a clear and objective way, but leaves it to the designer to extrapolate the concepts in the analysis of the continuity effect, which can be done by comparing both effects and the boundary conditions of the slab, rendering it subjective in that regard. On the other hand, BS 5950-8 (2003) presents an increased resistance to fire for continuous slabs by means of objective calculation criteria that allow for positive and negative bending moments in the analysis, but without presenting them objectively, making it subjective in the latter case. AISC 360-05 (2005) is the most subjective standard since it addresses the calculation procedure only by concept, leaving the understanding of the criteria and its application on behalf of the designer, requiring a theoretical basis for its use.

3. Experimental analyses

A compilation of the researches developed is shown as follows.

3.1 Li, Zhang and Jiang (2017)

Developed at the Research Institute of Structural Engineering and Disaster Reduction at Tongji University, China, the authors investigated the thermal and mechanical behavior of composite slabs exposed to the standard ISO (ISO, 2014) temperature curve. The test was performed on four specimens of slabs measuring 5.2x3.7 m, two of which were evaluated continuously over an intermediate steel beam and the other two were tested without the intermediate beam. The steel sheeting used had a trapezoidal cross section. Moreover, an 8-mm welded wire mesh with 15 cm of wire spacing was added to each specimen. The profiled steel sheeting height was 76 mm with a 70-mm thick concrete layer on top, so the total depth of the slabs was 146 mm. Figure 4a and Figure 4b show,

respectively, the dimensions of the continuous composite slab specimen installed in the horizontal test furnace.

Figure 4 – Details: (a) specimen dimensions (mm) and (b) experimental test (Li; Zhang; Jiang, 2017)

Regarding the two simple-span specimens, the difference between them was the concrete cover of the welded wire mesh, being 21 mm and 30 mm, measured from the upper face of the slab (Figure 5). The research focused on the influence of the use of an intermediate beam on membrane action and the deformations presented by the composite slabs. As for the two continuous slabs, a comparison between the thicknesses of the concrete cover over the welded wire fabric was made. Both slabs were loaded with approximately 18 kN/m^2 . Deformations on the concrete and wire mesh were monitored, as well as cracks on the concrete surface, vertical displacements and temperatures at the wire mesh and thermal insulation.

Figure 5 – Specimen with concrete cover (a) 21 mm (b) 30 mm (Li; Zhang; Jiang, 2017)

The duration of the tests was 75 and 90 minutes for the specimens with a 21 mm and 30 mm concrete cover.

In the slabs without secondary beams, the cracks started near the corners of the slab. On the other hand, the continuous slabs presented cracks over the intermediate beams, due to the negative bending moment created. In the latter, the welded wire mesh (next to the upper surface of the slab) with the smaller concrete cover showed the lowest maximum temperatures. In the most critical condition, the temperature of the wire mesh with the highest concrete cover thickness was twice that of the one presented by the specimen with lower cover thickness. The vertical displacements could not be compared due to the variation in the loading procedure. However, the vertical displacement was next to 19cm at the end of the test, still without collapsing. The authors settled on membrane action when analyzing the stresses bore by the concrete and its reinforcement. It was concluded that the failure of the slabs did not occur due to the development of the mechanism, not meeting the current standard design criteria.

3.2 Bednár et al. (2013)

The study was developed at Czech Technical University in the Czech Republic. It aimed to evaluate the potential use of fiber-reinforced concrete in composite slabs exposed to high temperatures and at room temperature. The specimens' dimensions were 3000x4500 mm and were analyzed as simple and continuous spans. The continuous slabs were tested with secondary beams distributed along the smaller span of the slab, spaced every 1000 mm. Also, three specimens were analyzed at room temperature, as shown in Figure 6a, and two at high temperatures, as shown in Figure 6b, which portrays a slab that collapsed at the end of the test. The difference between the slabs consisted in the content and type of fiber used and in the influence of secondary beams.

(a)

(b)

Figure 6 - Specimen at (a) room temperature and (b) high temperatures (Stadler, 2012)

In the high temperatures tests, two slabs were tested: one without intermediate beam and one with intermediate beam. The first test had a duration of 195 min, as a result, the slab collapsed. The second specimen did not collapse, but the test had a duration of 125 min. According to the authors, membrane action led to the collapse of the specimen, submitting the shear connectors to excessive stress, causing them to fail. As for the slab specimen with intermediate beam, the intensity of the stresses developed by the membrane action was slighter, not leading to collapse. A noteworthy improvement of continuous composite slabs was therefore noticed, considering the possible stress redistribution.

3.3 Stadler (2012), by the German Steel Construction Association (DAST)

The publication is the result of an integrated research project called *Nutzung der Membranwirkung von Verbuntrager-Decken-Systemen in Brandfall* (Application of Membrane Action for the Design of Composite Slabs and Beams in Fire Conditions), reproduced by Technische Universitat Munchen and Leibniz Universitat Hannover, both from Germany. This study group aimed to include membrane action in the German structural design recommendations. Discussions such as the incorporation of thermally protected secondary beams upon two slab spans were part of the investigation. The study took as reference experimental analyses performed on two composite slab specimens tested in the city of Munich, with computer-aided extrapolations in Hanover. The aim of this study was to present a design method for composite slabs, considering membrane action and admitting the arrangement of secondary beams and slabs on the level of the building. The two specimens used for the experimental analysis are depicted in Figure 7a and Figure 7b.

Figure 7 – Plan view of (a) test 1 and (b) test 2 of the German study (Stalder, 2012)

Both test specimens were reinforced with welded wire mesh with a cross section area of $1.88 \text{ cm}^2/\text{m}$ in each direction and concrete cover of 2.5 cm. The positive reinforcement for test specimen 1 consisted of 8-mm bars, with a cross section area of $2.5 \text{ cm}^2/\text{m}$, whereas prototype 2 received no positive reinforcement. The detail of the fire loading used in the experimental analysis of the slabs is shown in Figure 8a, the overall view of the test during its execution is shown in Figure 8b and Figure 8c, and the overview of the lower surface of the specimen at the end of the test is at Figure 9d. The loading of the slabs was made with sandbags.

Figure 8c portrays a significant crack formed on the alignment of the thermally protected intermediate beam, developed 19 minutes after the start of the fire resistance test. According to the author, all the negative reinforcements were broken, being evident the loss of the integrity of the specimen despite it not having collapsed. This does not meet the current standard design criteria, such as EN 1994-1-2 (2011), NBR 14323 (2013) and

AISC 360-05 (2005), which require full integrity of the negative reinforcement during the analysis and/or structural requirements at high temperatures.

Figure 8 – Detail of the study performed by the German research group (Stadler, 2012)

3.4 Wald et al. (2010).

The study was developed in the Czech Republic by researchers from Czech Technical University, with the participation of the University of Sheffield and Slovak Technical University. It used an office building as its specimen and aimed to optimize designs of steel, composite steel and concrete in fire conditions, as well as to collect data on the systemic and integrated behavior of structural systems under these exposure conditions. The structure was formed by different types of steel beams, such as castellated, alveolar and sinusoidal, as well as six types of slabs such as steel deck. The detail of the specimen and the test in progress are shown in Figure 9a and Figure 9b respectively.

Figure 9 – Detail of the (a) specimen and (b) test in progress (Wald et al., 2010)

The profiled steel sheeting that composed the slab had trapezoidal cross section, with 60 mm of height and thickness of 0.75 mm. The total slab thickness was 120 mm. The concrete had compressive strength of 30 MPa. The slab had a built-in welded wire mesh with diameter of 5 mm and spacing of 100 mm, with a 20-mm concrete cover. The loading was simulated by sandbags that applied 2.6 kN/m². The detail of the specimen after the end of the test is shown in Figure 10a. The composite slab is shown in Figure 10b, in which the development of the membrane mechanism can be observed.

Figure 10 – Detail of the (a) building after the test and (b) surface of the slab (Wald et al., 2010)

According to the authors, the degradation of the composite slab began on the corners, near the columns. The slab presented loss of strength at 62 minutes of testing when it collapsed. The fact that the study focused on a single specimen made it not possible to isolate some of the variables in the investigation, yielding results that should be analyzed with caution. The collapse of the composite slab is an example. Membrane action had manifested while the supporting elements of the slab were still able to withstand the high temperatures. Its failure appears to have been triggered at the interface with the

thermally protected slab, as shown in Figure 10b. Although not reported by Wald et al. (2010), it may have developed a crack on that area, forming a pinned support through the contour of the slab. The results show that continuity of the building floor, provided by negative reinforcements set on the alignment of the beams, could improve its performance under this exposure condition.

3.5 Kirby (1998), by British Steel Construction Institute (SCI)

This integrated work is considered a reference in the study of steel, composite steel, and concrete structures subjected to fire conditions. The research was developed inside an abandoned zeppelin hangar in the town of Cardington, England, where an eight-story building was built for real-scale analysis. Supervised by the Building Research Establishment of England, the work was supported by the European Coal and Steel Community; British Steel Swinden Technology Center, of England; the TNO Building and Construction Research in the Netherlands, and France's Centre de la Construction Métallique (CTICM). From 1995 to 2003, a total of seven fire tests were performed on the specimen, out of which none suffered collapse, even with thermally unprotected secondary beams. During these tests, the increased load capacity of the composite slabs caused by membrane action was noticed for the first time, sparking curiosity from the scientific Community and motivating subsequent studies. The hangar and the building specimen are shown in Figure 11a and Figure 11b respectively.

(a)

(b)

Figure 11 – Detail (a) BRE hangar and (b) real-scale building (Newman et al., 2006)

This study is taken as a reference in this field. The research program sought to understand mechanisms and to develop design criteria capable of representing the global behavior of high-rise steel buildings. The results inspired extensive computational

and experimental investigations in the fields of steel, composite steel and concrete structures in fire conditions.

The specimen was built with a steel structure, using composite slabs and beams. The building had 8 floors, spans of 6 and 9 m and total built area of 945 m². The steel beams were attached to the composite slabs through shear connectors. The slabs had a total thickness of 13 cm, to which a welded wire mesh was added. The secondary beams, which support the slabs, did not receive thermal protection so they reached temperatures above 1000°C. At this heating stage, tensile strength of steel is about 5% when compared to that at room temperature, nullifying its structural contribution. In spite of that, the slabs did not collapse, which made the need for thermal protection of these beams questionable. The deformations of the slabs were about 230 mm at the most critical points.

The main explanation for the stability of the composite slabs at high temperatures, even with failure of the secondary beams, was attributed to the mobilization of the membrane action. The mechanism provided structural stability to the slab. The built-in welded fire mesh, which served as negative reinforcement providing the continuity of the slab, was one of the presumed justifications. After the results were published, the membrane action effect on composite slabs began to receive special interest from researchers. However, because it is noted in experimental tests and involves the structural continuity of the slabs, the factors that trigger the process are not yet fully comprehended, since they depend on horizontal furnaces and large-scale tests to be studied.

4. Research gaps

The structural continuity of composite slabs is influenced by a number of factors, such as the profiled steel sheeting and positive and negative reinforcements that usually follow over the internal supports of the slab. This fact refers to a semi-continuity concept not identified by any standard. The effect can improve the negative bending moment of the slab and reduce its positive bending moment, increasing its resistance to fire. However, due to the integrated behavior of these or other factors, the prediction of the continuity behavior of the slab becomes difficult as it requires the adoption of simplified calculation models for design purposes.

The experimental studies already conducted focus on the study of the membrane mechanism, or on the use of fibers as a substitution for reinforcement, for instance. It is noteworthy that, in contrast to what has already been developed at room temperature in other researches, there are no studies that seek to understand the continuity effect of the slab at high temperatures, or to analyze more carefully the variables that weigh in this issue.

It is notorious that the negative reinforcement has greater thermal protection than the positive one. However, the positive reinforcement has been used as a design alternative to increase the fire-resistance rating of composite slabs, probably due to the lack of knowledge on the effectiveness of this measure. The incorporation of negative reinforcement alters the static condition of the slabs, reducing positive bending moments and mitigating the need for profiled steel sheeting as positive reinforcement during the fire. However, the variation of the negative reinforcement rate must be counterweighed with the variation of the positive reinforcement rate. Only then will technical and economic viability be achieved.

The failure of the negative reinforcement observed in some experimental tests showed that they can fail even when thermally protected by the concrete, which is not admitted by the standards that correlate structural continuity with resistance to fire, as in the case of BS 5950-8 and NBR 14323. By analyzing the up-to-date experimental studies developed, it can be concluded that these standard recommendations were not assessed experimentally. The thermomechanical stresses created in the experimental analyses, while difficult to assess by computer-aided analyses, show that stress distribution in continuous slabs should be correlated with the reduction of the positive bending moment. The connections idealized in design, such as the fixed supports, may not be accurate, leading to higher positive bending moments than those allowed by standard design criteria. The failure of the negative reinforcement observed experimentally assumes that composite slabs are hung by these reinforcements, which break even at room temperature.

The standard design criteria are based on propositions extracted from alternative slab compositions and extrapolated to composite slabs, what is unacceptable. The continuity effect should be better evaluated and considered among design criteria as it promotes

cost reduction for passive protection applied to the design of composite slabs in fire conditions.

5. Conclusion

The up-to-date developed researches on the continuity effect of composite slabs in fire conditions is incipient. The standard design criteria for this exposure condition have not yet received support from experimental results, culminating in propositions that have not yet been evaluated in terms of safety. The use of negative reinforcement instead of positive reinforcement may offer more cost-efficient results to the design of these slabs in fire conditions, which is already accepted by some standards. On the other hand, experimental studies propose that the negative reinforcement ruptures abruptly even when thermally protected, which must be investigated. The efficiency of the negative reinforcements when compared to the positive reinforcements must be understood in a fire situation.

6. References

- Marimuthu V, Seetharaman S, Arul Jayachandran S, et al. **Experimental studies on composite deck slabs to determine the shear-bond characteristic ($m - k$) values of the embossed profiled steel sheeting**. Journal Constructional Steel Research 63:791–803, 2007.
- Souza AS. **Análise do comportamento e da resistência de um sistema de lajes mistas com ancoragem de extremidade com considerações sobre a fôrma de aço isolada e o atrito nos apoios**. Dissertation (Master's Degree in Structural Engineering), Universidade Federal de Minas Gerais, 2001.
- Lasheen M, Shaat A, Khalil A. **Behavior of lightweight concrete slabs acting compositely with I-sections**. Construction Building Materials 124:967–981, 2016.
- Jiang, J, Li GQ. **Fire-induced progressive collapse of 3d steel frames with concrete floors**. In: Structures in Fire - Conference Annals. DEStech Publications, Princeton, 2016.
- Li GQ, Zhang N, Jiang J. **Experimental investigation on thermal and mechanical behaviour of composite floors exposed to standard fire**. Fire Safety Journal 89:63–76, 2017.
- Bailey CG, Toh WS. **Behaviour of concrete floor slabs at ambient and elevated temperatures**. Fire Safety Journal 42:425–436, 2007.
- Dahham KW, Baharom S, Wan Badaruzzaman WH. **Behavior of continuous-span composite slab: A review**. International Journal Appl Eng Research 12:2387–2390, 2017.
- Gholamhoseini A, Gilbert RI, Bradford MA, Chang ZT. **Longitudinal shear stress and bond – slip relationships in composite concrete slabs**. Eng Struct 69:37–48, 2014.
- Abas FM, Gilbert RI, Foster SJ, Bradford M. **Strength and serviceability of continuous composite slabs with deep trapezoidal steel decking and steel fibre reinforced concrete**. Eng Struct J 49:866–875, 2013.

- Lee LH, Quek ST, Ang KK. **Negative moment behavior of cold-formed steel deck and concrete composite slabs.** J Constructional Steel Res 57:401–415, 2001.
- Stadler M. **Design of composite slab systems in case of fire using simplified finite element analyses.** Thesis, Technische Universität München, 2012.
- Bednár J, Wald F, Vodička J, Kohoutková A. **Experiments on membrane action of composite floors with steel fibre reinforced concrete slab exposed to fire.** Fire Saf J 59:111–121, 2013.
- Wellman E, Varma A, Fike R, Kodur V. **Experimental evaluation of composite floor assemblies under fire loading.** J Struct Eng., 2010.
- Wald F, Kallerová P, Chlouba P, et al. **Fire Test on an administrative building in Mokrsko: summary of the results from the fire experiment.** Printing House Česká Technika, Prague, 2010.
- Newman GM, Robinson JT, Bailey CG. **Fire safe design: a new approach to multi-storey steel framed buildings fire and steel construction,** 3rd edn. The Steel Construction Institute, Ascot, 2006.
- Mensinger M, Schaumann P, Stadler M, Sothmann J. **Nutzung der Membran-wirkung von Verbundträger-Decken-Systemen im Brandfall.** DAST-Forschungsbericht, 2012.
- Javaheriafif M. **A practical approach to modelling integrity failure of composite floors in fire.** Thesis, University of Sheffield, 2017.
- European Committee for Standardization. **EN 1994-1-2: Design of composite steel and concrete structures. Part 1.2 - Design rules,** structural fire design. Brussels, 2011.
- American Institute of Steel Construction. **ANSI/AISC 360-05: specification for structural steel building.** Chicago, 2005.
- Associação Brasileira De Normas Técnicas. **ABNT NBR 14323: Projeto de estruturas de aço e mistas de aço e concreto de edifícios em situação de incêndio.** Rio de Janeiro, 2013.
- Associação Brasileira De Normas Técnicas. **ABNT NBR 15200: Projeto de estruturas de concreto em situação de incêndio.** Rio de Janeiro, 2012.
- Australia Standard/New Zealand Standard. **AS/NZS 2327: Composite steel-concrete construction for buildings.** Sydney/Wellington, 2017.
- British Standard. **BS 5950-4: Structural use of steelwork in building. Code of practice for design of composite slabs with profiled steel sheeting.** London, 2003.
- American Society for Testing and Materials. **ASTM E 119: Standard test methods for fire tests of building construction and materials.** West Conshohocken, 2012.
- International Organization for Standardization. **ISO 834-8: Fire resistance tests -- Elements of building construction.** Geneva, 2002.
- Newman GM. **The fire resistance of composite floors with steel decking.** The Steel Construction Institute, Ascot, 1991.
- Clifton GC. **Slab Panel Method: Design of composite steel floor systems for severe fires.** In: HERA Report R4-131. New Zealand Heavy Engineering Research Association, New Zealand, 2006.
- Kirby BR **The behavior of a multi-storey steel framed building subjected to fire attack.** British Steel, London, 1998.