Synthesis of poly[ε-caprolacton-b-epichlorohydrin-b-ε-caprolactone]-g-poly(styrene) Block-Graft Copolymers via Cationic Ring Opening and Atom Transfer Radical Polymerization Transformations.

İsmail ÇAKMAK², Temel ÖZTÜRK³, Ümit YILDIKO¹, Abdulkadir YÖRÜK⁴

ABSTRACT: The poly[(ε-caprolacton-b-epichlorohydrin-b-ε-caprolactone)]-g-(polystyrene-) [(PCL-b-ECH-b-PCL)]-g-PS block-graft copolymers were prepared via cationic, ring opening (ROP) and atom transfer radical polymerization (ATRP) transformations. With this goal in the first, cationic ring-opening technique was used to polymerize the epichlorohydrin (ECH). The ring opening polymerisation (ROP) of ε-caprolactone (ε-CL) was carried out using poly (epichlorohydrin) (PECH) with hydroxyl functional groups acting as initiators at 110 °C to yield poly(ε-caprolacton-b-epichlorohydrin-b-ε-caprolactone) (PCL-PECH-PCL) block copolymer. Finally, in the atom transfer radical polymerisation (ATRP) of the styrene, chloromethyl groups of the PECH segment of PCL-PECH-PCL were used as the starting functional group. [PCL-b-PECH-b-CL] -g-PS graft copolymer block was obtained as a result of polymerization. The results of the analysis indicated that the molecular weights of the graft copolymers increased linearly with styrene polymerisation. Synthesized polymers were characterized by ¹H-NMR, GPC and DSC techniques.

Keywords: ATRP, ROP, block copolymer, block-graft copolymer, epichlorohydrin, ε-caprolacton.

Poli - [(ε-kaprolakton-b-epiklorohidrin-b-ε-kaprolakton)] - g- (polistiren-) [(PCL-b-ECH-b-PCL)] - g-PS Blok-aşı Kopolimerleri Katyonik, Halka Açıklma Polimerizasyonu (ROP) ve Atom Transfer Radikal Polimerizasyon (ATRP) Tekniklerinin Kombinasyonu ile Sentezi

ÖZET: Poli - [(ε-kaprolakton-b-epiklorohidrin-b-ε-kaprolakton)] - g- (polistiren -) [(PCL-b-ECH-b-PCL)] - g-PS blok-aşı kopolimerleri katyonik, halka açıklama polimerizasyonu (ROP) ve atom transfer radikal polimerizasyon (ATRP) tekniklerinin kombinasyonu ile sentezlenmiştir. Bu amaçla, epiklorohidrin (ECH) polimerize etmek için katyonik halka açma tekniği kullanılmıştır. Sentezlenen, Hidroksil fonksiyonel gruplu poli (epiklorohidrin) (PECH), ε-kaprolaktonun (ε-CL) 110 ° C’de halkalı açılma polimerizasyonunun (ROP) başlatıcısı olarak poli (ε-kaprolakton-b-epiklorohidrin- B-ε-kaprolakton) (PCL-PECH-PCL) blok kopolimerinin eldesinde kullanıldı. Son olarak, başlatıcı olarak PCL-PECH-PCL’nin PECH bloğunun klorometil gruplarını kullanarak gerçekleştirilen stirenin atom transfer radikal polimerizasyonu (ATRP), [PCL-b-PECH-b-CL] -g-PS-graft kopolimeri oluşumuyla sonuçlanmıştır. Elde edilen sonuçlar, graft kopolimerlerinin moleküler ağırlıklarının stiren dönüşümüyle arttığını gösterdi. Polimerler, ¹H-NMR, GPC ve DSC teknikleri ile karakterize edildi.

Anahtar Kelimeler: ATRP, ROP, blok kopolimer, blok-aşı kopolimer, epiklorohidrin, ε-kaprolakton.

¹ İğdır Üniversitesi, Tuzluca Meslek Yüksek Okulu, Tıbbi Hizmetler Ve Dökümantasyon, Iğdır, Türkiye

² Kafkas Üniversitesi, Fen Edebiyat Fakültesi, Kimya Bölümü, Kars, Türkiye

³ Giresun Üniversitesi, Fen Edebiyat Fakültesi, Kimya Bölümü, Giresun, Türkiye

⁴ Isparta Üniversitesi, Isparta Sağlık Hizmetleri Meslek Yüksekokulu, Tıbbi Hizmetler Ve Dökümantasyon, Isparta, Türkiye
Sorumlu yazar/Corresponding Author: Ümit YILDIKO, yildiko1@gmail.com

INTRODUCTION

Numerous monomers have been polymerized by this technique after Matyjaszewski (Wang et al., 1995a) reported the ATRP technique, which uses compounds of alkyl halides as initiators and a Cu (I) -ligand complex as a catalyst. (Kato et al., 1995; Percec et al., 1995; Muftuoglu et al., 2004; Coessens et al., 2001). ATRP is one of the most suitable controlled polymerization technique to polymerize styrene and acrylate derivatives, and a range of other monomers yielding polymers with low polydispersities (PD) (Okcu et al., 2010; Du et al., 2015). Comparing to the other living/controlled radical polymerizations techniques, the ATRP has drawn widespread attention because of its many advantages and great industrialization prospects (Wang et al., 1995b). ATRP method has served a very important purpose for the preparation of new different type functional copolymers with controlled molecular weights and low polydispersities (PDI) (Matyjaszewski 1998; Chen et al., 2015).

The complexes of transition metals like Cu(I), Ni(II), Ru(II), Fe(II) and Os(II) have been used as catalysts in ATRP for the preparation of block copolymers (Matyjaszewski 1998; Braunecker et al., 2007). Copper (II) based catalysts are the most convenient and cheapest in terms of cost as well. Copper(I)-catalyzed ATRP is one of the most important techniques for controlling radical polymerizations (Matyjaszewski 1998; Tsarevsky et al., 2006).

There are many attempts to prepare block and graft copolymers due to their various properties and applications (Alam et al., 2015; Cakmak et al., 2006; Cakmak et al., 2008; Szabó et al., 2015). One of those polymers called segmented copolymers have some advantages like incorporated at least two or more polymer blocks possessing different chemical properties into one polymer segment. A wide range of disjointed copolymer properties can be prepared and inserted into the copolymers by using different monomers (Okrasa et al., 2004). The most suitable materials for the different applications are the polymers contain a specific combination of block and graft copolymers (Stoeckel et al., 2002).

Ring-opening polymerization (ROP) is a very useful polymerization technique for controlled synthesis of aliphatic polyesters (Stridsberg et al., 2002; Yuan et al., 2008; Yang et al., 2008; Erdogan et al., 2005) such as polylactide, polyglycolide, polymandelide, polyvalerolactone, or poly(ϵ -caprolactone) (PCL). Cakmak et al. prepared PECH-PS, PECH-PMMA graft copolymers by the transformation of cationic, photopolymerization and ATRP process (Cakmak and Baykara, 2006; Cakmak et al., 2008). Preparation of PECH-b-St-gPMMA block-graft copolymers by the transformation of activated monomer, nitroxide mediated polymerization and ATRP techniques was described by Yagci et al. (Tasdelen et al., 2007). Cho synthesized various cyclic monomers having -CN, -CO₂R and -C₆H₅ groups and these monomers were polymerized via radical ring-opening mechanism to obtain high molecular weight polymers (Cho, 2000). Yao et al. prepared and characterized a sequence of new anilido-imine-Al complexes, and those complexes were used as initiators for the polymerization of 3-caprolactone via ring opening mechanism (Yao et al., 2008).

Chen et al. synthesized and characterized Fe(II)/heterocyclic carbene coordination compounds. These complexes were used for polymerization of ϵ -caprolactone via ring opening mechanism as a single component initiator (Chen et al., 2006). Messman et al. carried out the ring-opening polymerization (ROP) of L-lactide, used Poly(L-lactide) in ATRP to yield molecular weight controllable linear block copolymers (Messman et al., 2005). Gowda et al. used FeCl₃·6H₂O, RuCl₃·H₂O and FeCl₂·4H₂O catalysts for polymerization of ϵ -caprolactone, δ -valerolactone and β -butyrolactone by ring opening method (Gowda and Chakraborty, 2009).

In this research, we present the preparation and characterization of ABA block copolymer chains of poly(epichlorohydrin) (PECH) (A block) and mediated PCL (B block) using ROP. Then, using this poly(ϵ -caprolactone-b-epichlorohydrin-b- ϵ -caprolactone) [poly(ϵ -CL-b-ECH-b- ϵ -CL)] block copolymers, poly(ϵ -caprolactone-b-epichlorohydrin-g-polystyrene-

b- ϵ -caprolactone) [poly(ϵ -CL-b-ECH-g-PS-b- ϵ -CL)] block-graft copolymers were synthesized by ATRP. The bulk-ATRP of Styrene (S) was carried out using CuCl/2,2'-bipyridine (bpy) complex as catalyst.

MATERIALS AND METHODS

Copper (I) chloride (CuCl), ϵ -caprolactone (ϵ -CL), epichlorohydrin (ECH), stannous octoate ($\text{Sn}(\text{oct})_2$) and 2,2'-bipyridine (bpy) were supplied from Merck or Aldrich. The styrene was obtained from Merck Company and the extraction was carried out with 10% NaOH solution and purified by conventional procedure. The other materials were supplied from Aldrich or Fluka and used as purchased.

Cationic Polymerization of ECH: 30 ml of CH₂Cl₂ and 10 g of 57% HBF₄ were added to a flask and a magnetic stirrer was used for homogeneous mixing. The reaction was set so that nitrogen gas would pass through it. To the reaction vessel, 96 g of epichlorohydrin were added (3 hour periods).

The reaction contents were poured into 1 L of water to remove inorganic impurities and the organic phase was separated. After drying with MgSO₄ and evaporation of the organic phase, a viscous substance remained in the glass vessel. (23.0 g 36 % yield of ECH). M_n : 1611 g/mol M_w/M_n : 1.04, ¹H-NMR (ppm): 4.02-4.10 (HOCH₂), 3.69-3.60 (CHO), 3.97-3.83 (OCH₂Cl).

Ring-opening Polymerization of ϵ -CL: The general recipe for ROP of ϵ -CL with PECH as follows: to a Schlenk tube containing magnetic stirring bar, macroinitiator (PECH) and monomers with bulbed by nitrogen (ϵ -CL) were added.

The tube content were degassed by bulbing pure nitrogen again and placed in a thermostated silicon-oil bath at 110 °C. PCL-PECH-PCL block copolymers synthesized were precipitated in excess methanol to remove unreacted ϵ -caprolactone and the soluble small impurities. The synthesis conditions and the results can be seen in Table 1.

Table 1. ROP of ϵ -CL with PECH at 110°C

Code	Time (h)	ϵ -CL (g)	PECH (g)	Yield of polymer (%)	$\overline{M}_n$ GPC	$\overline{M}_w / \overline{M}_n$
FC-1	4	2.7074	0.7394	4.64	3500	1.41
FC-2	4	2.5965	0.8006	26.8	4300	1.60
FC-3	2	2.5300	0.7400	3.7	4500	1.51
FC-4	2	5.0160	0.7642	5.1	3400	1.44
FC-5	2.5	15.0021	3.0560	13.6	3000	1.45

Grafting by ATRP method: The Schlenk tubes dried with hot air which is containing the reaction mixture of monomer (S), poly(ϵ -CL-b-ECH-b- ϵ -CL) block copolymer, CuCl, and bipyridine were degassed by vacuum and nitrogen (to create an inert atmosphere), and sealed under vacuum. Then all the test tubes were placed in a silicone oil bath set at a temperature of 110 ° C. When the polymerization

completed, Schlenk tubes were cooled. The tubes' contents were diluted with ethyl acetate.

These Solvents were filtered and precipitated with methanol to separate the polymer products. The block-graft copolymers were dried at 40°C in a vacuum oven for three days. The conditions and data from which the polymerisation is obtained can be seen in Tables 2 and 3.

Table 2. ATRP of styrene with poly(ϵ -CL-b-ECH-b- ϵ -CL) block copolymer (FC-5 in Table 1) at 110°C . Time: 14 hours

Code	S/poly(ϵ -CL-b-ECH-b- ϵ -CL) (mol/mol)	poly(ϵ -CL-b-ECH-b- ϵ -CL) (g)	S (g)	CuCl (g)	bPy (g)	Yield of polymer (%)	$\overline{M}_n$ GPC	$\overline{M}_w / \overline{M}_n$
FAB-2	200/1	0.1442	1.0212	0.0048	0.0150	3,8	3100	1.44
FAB-3	50/1	0.5772	1.0179	0.0190	0.0600	25,5	3800	1.70
FAB-4	75/1	0.3848	1.0043	0.0127	0.0400	15,75	3200	1.58
FAB-5	100/1	0.2886	1.0424	0.0095	0.0300	12,5	3200	1.59

Table 3. ATRP of styrene with poly(ϵ -CL-b-ECH-b- ϵ -CL) block copolymer (FC-1 in Table 1) at 110°C. Poly(ϵ -CL-b-ECH-b- ϵ -CL) = 2.5×10^{-2} g (7.0×10^{-6} mol), CuCl = 7.0×10^{-4} g (7.0×10^{-6} mol), bpy = 2.2×10^{-3} g (1.4×10^{-5} mol), time: 22 hours

Code	S (g)	Yield of polymer (%)	$\overline{M}_n$ GPC	$\overline{M}_w / \overline{M}_n$
FT-1	0.5049	3,2	30000	3.60
FT-2	0.7651	37,5	51000	2.13
FT-4	1.2504	33,7	59000	1.88
FT-6	2.0146	42,11	62000	1.73

Characterization of the polymers: A Waters brand system consisting of a Waters 2414 refractive index detector, a Waters model 1515 isocratic pump and HR3, HR4E and HR4 stragrag columns was used as the GPC instrument. The ^1H -NMR spectra of the polymers were

obtained on a Varian/Mercury-200 (200 MHz) NMR spectrometer in CDCl_3 solution. Perkin Elmer Diamond differential calorimetry was used for differential scanning calorimetry (DSC) analyzes. (Under a nitrogen atmosphere, in the temperature range 20 - 250 °C)

RESULTS AND DISCUSSIONS

Synthesis of Poly(epichlorhydrin) (PECH):

According to scheme 1, PECH with chain end hydroxyl group was synthesized by cationic polymerization of ECH. HBF_4 was used as the catalyst in the reaction and the results were confirmed by ^1H -NMR and GPC measurements. According to the ^1H -NMR spectrum

of PECH in FIG. 1, It indicates characteristic signals of 4.07-3.60 ppm (broad) for the protons $-\text{OCH}_2$, CH_2 $-\text{CH}_2$ Cl and $-\text{CH}_2$ Cl of PECH.

Cationic polymerization of ECH was carried out by dropwise addition of ECH to the HBF_4 solution. The actively extending PECH chain was stopped with water and OH terminal PECH was obtained.

Figure 1. ^1H -NMR spectrum of PECH

Scheme 1. Cationic polymerization of epichlorohydrin (ECH).

Synthesis of PCL-PECH-PCL block copolymers: PCL- PECH- PCL block copolymers were synthesized by the ROP of ϵ -CL with PECH possessing two hydroxyl functional groups in different conditions according to Table 1. The synthesis of

block copolymers was performed in the presence of $\text{Sn}(\text{oct})_2$ (110°C). The polydispersities of the PCL-PECH-PCL block copolymers were determined between 1.41 and 1.60. The reaction pathway is represented in Scheme 2.

Scheme 2. ROP of ϵ -caprolactone with PECH.

Synthesis of [PCL-b-PECH-b-CL]-g-PS block-graft copolymers: The approach for the synthesis of block-graft copolymers is shown in scheme 3. Tables 2 and 3 include the results from several polymerizations

using poly(ϵ -CL-b-ECH-b- ϵ -CL) block copolymer as macroinitiator. The physical state of yielded block-graft copolymer was white solid.

Scheme 3. ATRP of styrene with poly(ϵ -CL-b-ECH-b- ϵ -CL)/CuCl/bpy initiating system.

Characterization of the Polymers: Yielded polymers can be undergone polymer films. The characterization of polymeric macromolecules with mostly transparent properties can be summarized as follows. When compared to Macro initiator, the determined increases in molecular weights will prove the formation of the block-graft copolymer of the products. The $^1\text{H-NMR}$, and GPC measurement

techniques were used for the characterization of block and block-graft copolymers. In Fig. 1, the characteristic signals of PECH at 4.00-3.40 ppm in $^1\text{H-NMR}$ analysis show PECH protons ($-\text{CH}_2-$, $-\text{CHO}-$, $-\text{CH}_2\text{Cl}$). The $-\text{OH}$ proton signals in the spectrum can be seen at 1.2 ppm. The structure of the PCL-b-PECH-b-PCL block copolymer was characterized by $^1\text{H-NMR}$ (see Figure 2).

Figure 2. $^1\text{H-NMR}$ spectrum of PCL-b-PECH-b-PCL block copolymer

As shown in Figure 2, signals are observed at 4.01-4.08 ppm (triplet), originating from methylene protons ($-\text{OCH}_2-$) of PCL chain, and a signal observed 3.63-3.70 ppm is assigned to the $-\text{OCH}_2-$ protons of PECH chain. Figure 3 shows $^1\text{H-NMR}$ spectrum of [(PCL-b-PECH-

b-PCL)]-g-PS block-graft copolymer, which exhibits signals at 6.59-7.26 ppm (aromatic $-\text{CH}$ for PS), 4.03-4.09 ppm ($-\text{OCH}_2-$ for PECH) and 2.27-2.34 ppm ($\text{O}=\text{CCH}_2-$ for PCL).

Figure 3. $^1\text{H-NMR}$ spectrum of [(PCL-b-PECH-b-PCL)]-g-PS block-graft copolymer

The molecular weight values (M_n) of the block and block-graft copolymer are determined by GPC as

shown in Figure 4.

Figure 4. GPC curves of (a) [ϵ -CL-b-ECH-b- ϵ -CL]-g-PS (Table 3- FT-4) M_n : 59346 g/mol (b) ϵ -CL-b-ECH-b- ϵ -CL M_n : 3529 g/mol (Table 1 FC-1).

Chromatograms show the increasing average molecular weight due to block graft copolymerization and narrow molecular weight distribution. According to the GPC results the block-graft copolymers have the polydispersity values in a range of 1,44-170. The low

polydispersity value of the block-graft copolymers is a result and evidence of ATRP. Narrow/low polydispersity values indicate that the polymer chains have similar molecular weights.

Figure 5. DSC curve of the PCL-b-PECH-b-PCL block copolymer.

Figure 6. DSC curve of the [(PCL-b-PECH-b-PCL)]-g-PS

The glass transition temperature (T_g) of PS is 100 °C. PECH was an amorphous polymer, exhibiting a T_g at -23 °C. The T_g 's of the PCL-b-PECH-b-PCL and [(PCL-b-PECH-b-PCL)]-g-PS are shown Figure 5 and Figure 6. Due to narrow polydispersities (1,44-1,70) of yielded block-graft copolymer ([PCL-b-PECH-b-PCL)]-g-PS is showing a higher T_g (104,35 °C) than styrene's homopolymer (100 °C). In addition, the obtained results indicate that T_g values of block and block-graft copolymers were different than those of their homopolymers. This is an evidence for the formation of block and block-graft copolymers.

CONCLUSION

The synthesis of block-graft copolymers has drawn an increasing attention of the researchers in recent years.

REFERENCES

- Alam BM, Aouak T, Alandis NM, Alam MM. Synthesis, Characterization, Drug Solubility Enhancement, and Drug Release Study of Poly(Methacrylic Acid-graft-Simvastatin). *Int. J. Polym. Mater. Polym. Biomater.* 2015;64:229–241.
- Braunecker WA, Brown WC, Morelli BC, Tang W, Poli R, Matyjaszewski K. Origin of Activity in Cu-, Ru-, and Os-Mediated Radical Polymerization *Macromolecules.* 2007;40:8576–8585.
- Cakmak I, Baykara H, Set B. Synthesis of poly(epichlorohydrin-g-methyl methacrylate) and poly(epichlorohydrin-g-styrene) graft copolymers by a combination of cationic and photopolymerization methods. *J. Appl. Polym. Sci.* 2008;107:1604–1608
- Cakmak I, Baykara H. Synthesis of poly(epichlorohydrin-g-methyl methacrylate) graft copolymers by the combination of cationic and atom transfer radical polymerization.) *J. Appl. Polym. Sci.* 2006;102:2725–2729.
- Chen G, Pei X, Wei H, Xu L, Fang X. Synthesis and characterization of sulfonated block copolyimides derived from 4,4'-sulfide-bis(naphthalic anhydride) for proton exchange membranes. *J. Appl. Polym. Sci.* 2015;132:41501.
- Chen M-Z, Sun H-M, Li W-F, Wang Z-G, Shen Q, Zhang Y. Synthesis, structure of functionalized N-heterocyclic carbene complexes of Fe(II) and their catalytic activity for ring-opening polymerization of ϵ -caprolactone. *J. Organomet. Chem.* 2006;691:2489–2494.
- Cho I. New ring-opening polymerizations for copolymers having controlled microstructures. *Prog. Polym. Sci.* 2000;25:1043–1087.
- Coessens V, Pintauer T, Matyjaszewski K. Functional polymers by atom transfer radical polymerization. *Prog. Polym. Sci.* 2001;26:337–377
- Erdogan T, Bernaerts KV, Van Renterghem LM, Du Prez FE, Goethals EJ. Preparation of star block co-polymers by combination of cationic ring opening polymerization and atom transfer radical polymerization. *Des. Monomers Polym.* 2005;8:705–714.
- Gowda RR, Chakraborty D. Environmentally benign process for bulk ring opening polymerization of lactones using iron and ruthenium chloride catalysts. *J. Mol. Catal. -Chem.* 2009;301:84–92.
- Kato M, Kamigaito M, Sawamoto M, Higashimura T. Polymerization of Methyl Methacrylate with the Carbon Tetrachloride / Dichlorotris- triphenylphosphine) ruthenium(II) / Methylaluminum Bis(2,6-di-tert-butylphenoxide) Initiating System: Possibility of Living Radical Polymerization. *Macromolecules.* 1995;28:1721–1723.
- Matyjaszewski K. Radical Nature of Cu-Catalyzed Controlled Radical Polymerizations (Atom Transfer Radical Polymerization) *Macromolecules.* 1998;31:4710–4717.
- Messman JM, Scheuer AD, Storey RF. Synthesis and characterization of A–B–A triblock copolymers derived from chloro-telechelic poly(L-lactide): combining ring-opening polymerization (ROP) and atom transfer radical polymerization (ATRP). *Polymer.* 2005;46:3628–3638.
- Muftuoglu A. E, Cianga I, Colak D, Yagci Y, Synthesis of A2B and A2B2 type miktoarm star co-polymers by combination of ATRP or ROP with photoinduced radical polymerization. *Designed Monomers and Polymers.* 2004;7:563–582.
- Nuyken O, Weidner R. Graft and block copolymers via polymeric azo initiators () *Adv. Polym. Sci.* 1986;73–74:145–199.
- Okcu SS, Durmaz YY, Yagci Y, Synthesis and Characterization of Telechelic Block Co-polymers by Combination of Atom Transfer Radical Polymerization and Click Chemistry Processes. *Designed Monomers and Polymers.* 2010;13:459–472.

This is because of the fact that block-graft copolymers are having special chemical structures yield unusual physical properties.

The [(PCL-b-PECH-b-PCL)]-g-PS block-graft copolymers were obtained by a subsequent three methods without any modification of the initiating site, using AMP, CRP and ATRP methods. In conclusion, poly(ϵ -CL-b-ECH-b- ϵ -CL) block copolymer were used as the macroinitiator for ATRP of styrene, resulting poly(ϵ -CL-b-ECH-g-PS-b- ϵ -CL) block-graft copolymers, succesfully.

Acknowledgement: This project was financially supported by The Scientific and Technological Research Council of Turkey (TUBITAK), no. 107T294 (TBAG-HD/283). The authors gratefully acknowledge TUBITAK for the financial support.

- Okrasa L, Pakula T, Inoue Y, Matyjaszewski K. Morphology and thermomechanical properties of well-defined polyethylene-graft-poly(n-butyl acrylate) prepared by atom transfer radical polymerization. *Colloid Polym. Sci.* 2004;282:844–853.
- Percec V, Barboiu B. “Living” Radical Polymerization of Styrene Initiated by Arenesulfonyl Chlorides and CuI(bpy)_nCl. *Macromolecules.* 1995;2823:7970–7972.
- Stoeckel N, Wieland PC, Nuyken O. New syntheses of graft copolymers using the DPE-technique: ATRP graft copolymerization. *Polym. Bull.* 2002;49:243–250.
- Stridsberg KM, Ryner M, Albertsson AC. Controlled Ring-Opening Polymerization: Polymers with designed Macromolecular Architecture. In *Degradable Aliphatic Polyesters*, ed AC Albertsson. 2002;157:41–65. Berlin: Springer-Verlag Berlin.
- Szabó Á, Wacha A, Thomann R, Szarka G, Bóta A, Iván B. Synthesis of Poly(methyl methacrylate)-poly(poly(ethylene glycol) methacrylate)-polyisobutylene ABCBA Pentablock Copolymers by Combining Quasiliving Carbocationic and Atom Transfer Radical Polymerizations and Characterization. *J. Macromol. Sci. Part A.* 2015;52:252–259.
- Tasdelen MA, Yagci Y, Demirel AL, Biedron T, Kubisa P. Synthesis and Characterization of Block-Graft Copolymers [poly(epichlorohydrin-b-styrene)-g-poly(methyl methacrylate)] by Combination of Activated Monomer Polymerization, NMP and ATRP). *Polym. Bull.* 2007;58:653–663.
- Tsarevsky NV, Braunecker WA, Tang W, Brooks SJ, Matyjaszewski K, et al. Copper-based ATRP catalysts of very high activity derived from dimethyl cross-bridged cyclam. *J. Mol. Catal. Chem.* 2006;257:132–140.
- Wang J, Matyjaszewski K. Controlled/“living” radical polymerization. atom transfer radical polymerization in the presence of transition-metal complexes. *J. Am. Chem. Soc.* 1995;117:5614–5615.
- Wang J, Matyjaszewski K. Controlled/“Living” Radical Polymerization. Halogen Atom Transfer Radical Polymerization Promoted by a Cu(I)/Cu(II) Redox Process. *Macromolecules.* 1995;28:7901–7910.
- Yang L, Zhou H, Shi G, Wang Y, Pan C-Y. Synthesis of ABCD 4-miktoarm star polymers by combination of RAFT, ROP, and “Click Chemistry”. *J. Polym. Sci. Part -Polym. Chem.* 2008;46:6641–6653.
- Yao W, Mu Y, Gao A, Su Q, Liu Y, Zhang Y. Efficient ring-opening polymerization of ϵ -caprolactone using anilido-imine-aluminum complexes in the presence of benzyl alcohol Polymer. 2008;49:2486–2491.
- Yuan W, Yuan J, Zhou M, Pan C. Synthesis, characterization, and fluorescence of pyrene-containing eight-arm star-shaped dendrimer-like copolymer with pentaerythritol core. *J. Polym. Sci. Part -Polym. Chem.* 2008;46:2788–2798.