iJRASET

International Journal For Research in
Applied Science and Engineering Technology

INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 5 Issue: VIII Month of publication: August 2017

DOI: <http://doi.org/10.22214/ijraset.2017.8099>

www.ijraset.com

Call: ☎ 08813907089

E-mail ID: ijraset@gmail.com

Effect of Reinforcement Profile On Creep Rates in a FG Disc

Sujata Goyal¹

¹Department of Mathematics, A. S. College, Khanna-141402

Abstract: In the present study, we have investigated effect of varying reinforcement profile on creep rates in a Functionally Graded (FG) Rotating Disc. The disc under observation is made of Al-SiC_p composite. The SiC_p particle content is decreasing radially for negative value of reinforcement gradation index (n) while it is increasing for the positive value of n . It is concluded that the creep rates in the FGM disc reduces significantly with decreasing value of reinforcement gradation index.

Key words: Creep, variable thickness, FGM

I. INTRODUCTION

FGMs are heterogeneous composite materials with variation of volume content continuously from one side to the other [1-2]. Rotating disc is very important due to its extensive use in engineering applications [3].

Singh and Ray [4] investigated steady state creep in a rotating isotropic FGM disc of constant thickness by using Norton's power law. Gupta et al. [3] extended the work to investigate the creep rates for a constant thickness rotating FGM disc operating under thermal gradient. Several authors investigated creep response in rotating FGM disc but using linear thickness profile [3, 5]. In the present study we have investigated effect of reinforcement profile on creep rates in rotating FGM disc.

II. DISC PROFILE AND DISTRIBUTION OF REINFORCEMENT

Let us consider a rotating disc ($a = 31.75 \text{ mm}$ and $b = 152.4 \text{ mm}$) rotating at 15000 rpm . The thickness of the disc is varying along radius (r) as given by,

$$h(r) = h_b \left(\frac{r}{b} \right)^k \quad (1)$$

where k ($= -0.5$) and h_b ($= 20.13 \text{ mm}$) are the gradation index and outer thickness respectively.

The SiC_p content in the FGM disc is assumed to vary with radial distance as,

$$V(r) = V_b \left(\frac{r}{b} \right)^n \quad (2)$$

where n is gradation index.

On equating equal SiC_p content in constant thickness and variable thickness FGM disc, we get the SiC_p content at the outer radius (V_o),

$$V_o = \frac{(2+k+n)b^n V_{avg} (b^{2+k} - a^{2+k})}{(2+k)(b^{2+k+n} - a^{2+k+n})}$$

The density of disc material is assumed to vary as given by,

$$\rho(r) = \rho_b \left(\frac{r}{b} \right)^{n_1} \quad (3)$$

The effective strain rate ($\dot{\epsilon}$) of the disc material is described by the threshold stress (σ_o) based law [5] as given by,

$$\dot{\epsilon} = [M(r) \{ \bar{\sigma} - \sigma_o(r) \}]^5 \quad (4)$$

where

$$M(r)=0.0288-\frac{0.0088}{P}-\frac{14.0267}{T}+\frac{0.0322}{V(r)} \quad (5)$$

$$\sigma_o(r)=-0.084 P-0.023 T+1.185 V(r)+22.207 \quad (6)$$

The constitutive equations between stresses (σ_r, σ_θ) and strain rates ($\dot{\epsilon}_r, \dot{\epsilon}_\theta$) for an isotropic disc under plane stress condition

are given by [3],

$$\dot{\epsilon}_r = \frac{\dot{\bar{\epsilon}}}{2\bar{\sigma}} [2\sigma_r - \sigma_\theta]$$

$$\dot{\epsilon}_\theta = \frac{\dot{\bar{\epsilon}}}{2\bar{\sigma}} [2\sigma_\theta - \sigma_r] \quad (7)$$

According to von Mises yield criterion, the effective stress ($\bar{\sigma}$) is given by,

$$\bar{\sigma} = \frac{1}{\sqrt{2}} [\sigma_\theta^2 + \sigma_r^2 + (\sigma_r - \sigma_\theta)^2]^{1/2} \quad (8)$$

Considering the equilibrium of forces acting on an element of a variable thickness disc, one may get the following equilibrium equation [6],

$$\frac{d}{dr} [r h(r) \sigma_r] - h(r) \sigma_\theta + \rho(r) r^2 h(r) \omega^2 = 0 \quad (9)$$

where $\rho(r)$ is the density of FGM disc at any radius r .

The disc is assumed to be operate under free-free boundary conditions [3],

$$\sigma_r = 0 \text{ at } r=a \text{ and } \sigma_r = 0 \text{ at } r=b$$

The equilibrium eq. (9) is solved along with set of constitutive eqs. (7) by following the procedure given in [5] to obtain the distribution of stresses and strain rates in the FGM disc.

III. RESULTS AND DISCUSSION

A code has been developed for the calculations. The effect of varying reinforcement gradation index (n) has been investigated on the creep response (Refer Table 1).

Table 1: Description of FGM discs

n	SiC _p Content (vol %)	
	V_a	V_b
0.5	11.51	25.22
0	20	20
-0.5	33.39	15.24

Fig. 1: Effect of particle gradient on creep rates radial and tangential strains.

It is clear above from Fig. 1 that radial strains in the FGM disc are lowest in FGM disc with lowest gradation index ($n = -0.5$) as compare FGM disc ($n = 0.5$) and composite disc ($n = 0$). The effect of increasing PG on the tangential strain in the FGM disc is similar to radial strain.

IV. CONCLUSIONS

The study has led to the following conclusions:

- A. The creep response of the FGM disc with decreasing SiC_p content along the radius is superior to a similar FGM disc with decreasing SiC_p content along the radius.
- B. The creep life can be significantly improved with decreasing SiC_p content along the radius.

REFERENCES

- [1] Neubrand A. and Rodel J. (1997) 'Gradient materials: An overview of a novel concept', Zeitschrift für Metallkunde, Vol. 88 No. 5, pp.358-371.
- [2] Bayat M.N., Saleem M., Sahari B.B., Hamouda A.M.S. and Mahdi E. (2007) 'Thermo elastic analysis of a functionally graded rotating disk with small and large deflections', Thin-Walled Structures, Vol. 45 Nos. 7-8, pp.677-691.
- [3] Gupta V.K., Singh S.B., Chandrawat H.N. and Ray S. (2005) 'Modeling of creep behavior of a rotating disc in the presence of both composition and thermal gradients', Journal of Engineering Materials and Technology, Vol. 127 No. 1, pp.97-105.
- [4] Singh S.B. and Ray S. (2001) 'Steady state creep behavior in an isotropic functionally graded material rotating disc of Al-SiC composite', Metallurgical and Materials Transactions A, Vol. 32 No. 7, pp.679-1685.
- [5] Garg M., Salaria B.S. and Gupta V.K. (2013) Effect of disc geometry on the steady state creep in a rotating disc made of functionally graded materials, Materials Science Forum, Vol. 736, pp. 183-191.
- [6] Timoshenko, S.P. and Goodier, J.N. (1970) Theory of Elasticity, McGraw-Hill, Singapore.

10.22214/IJRASET

45.98

IMPACT FACTOR:
7.129

IMPACT FACTOR:
7.429

INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 (24*7 Support on Whatsapp)