Simultaneous effect of surface roughness and passivity on corrosion resistance of metals

A. S. Toloei, V. Stoilov & D. O. Northwood
University of Windsor, Canada

Abstract

Unidirectional surface roughness of varying magnitudes was created on both nickel and mild steel by grinding on SiC papers with grit sizes from G60 (roughest) to G1200 (smoothest) and the corrosion resistance in 0.5 M H₂SO₄ solution was determined using a potentiodynamic polarization technique. A different trend of corrosion rate versus roughness was seen for the active-passive metal (nickel) and non-active-passive metal (mild steel). For nickel, there was an increase in corrosion rate with increasing roughness, whereas for mild steel the corrosion rate decreased with increasing surface roughness. Furthermore, through a detailed examination of the surface before and after corrosion using techniques including profilometry, scanning electron microscopy (SEM) and energy dispersive spectroscopy (EDS), it was established that different corrosion mechanisms were operative for nickel and mild steel. In the case of nickel, the higher roughness provided a greater contact area between the corrosive medium and metal and there was trapping of the corrosive ions in the deep grooves. Both of these factors would lead to an increase in corrosion rate. Also, for the smoother nickel surfaces, it is easier to form a stable passive film. For mild steel, which does not form a passive film, corrosion rates are generally much higher than for nickel. For the rougher surfaces with the deeper grooves, the corrosion product, FeSO₄, can fill the grooves thereby acting as a barrier to further ingress of the corrosive ions to the un-corroded metal.

Keywords: corrosion resistance, passivity, surface roughness, potentiodynamic polarization.

1 Introduction

In metallic materials the surface roughness has a major impact on both general corrosion and the localized nucleation of metastable pitting. In most metals and their alloys, the general trend is that a higher surface roughness results in higher corrosion rate. Such trend was observed for copper, nickel, aluminium, stainless steel, magnesium and titanium alloys [1–6]. Zuo *et al.* [7] investigated the metastable pitting behaviour of 316L stainless steel with various degrees of surface roughness and showed that, as surface roughness increased, the nucleation rate of metastable pits as well as the overall corrosion rate increased. In contrast, a range of materials such as mild steel [8] and AE44 magnesium alloy [9] show the reverse trend namely, as surface roughness increases, the corrosion rate decreases. Alvarez *et al.* [9] showed that the corrosion rate in AE44 from polished coupons (with lower roughness) was notably greater than the corrosion rate from the semi-polished coupons (with higher roughness). Similar behaviour was observed by Abosrra *et al.* [8] on mild steel in saline solution containing 1 and 3% NaCl. In his work Abosrra *et al.* [8] showed that the improvement of the surface finish led to a shift in the corrosion potential to more noble states and to an increase of the corrosion rate. The obvious difference between these two groups of materials is that materials such as aluminium, copper, nickel, stainless steel passivate quickly by developing stable oxide films whereas AE44 magnesium alloy and mild steel, unlike the first group, do not form a stable passive film. For the material group without stable passive film (mild steel, magnesium alloys etc.) the phenomenon of the decrease of the corrosion with the increase of the roughness (contact area) is not well understood. The main goal of this work is to provide a better insight into the effect of the roughness and the main corrosion mechanisms of non-active–passive metals (such as mild steel) in comparison to active–passive metal (such as nickel).

2 Experimental procedure

The mild steel and nickel specimens were prepared by cutting mild steel and nickel sheet using wire electrical discharge machining (EDM) to pieces of $15 \times 15 \times 1 \text{ mm}^3$. The sample surfaces were abraded with 60, 120, 180, 240, 320, 400, 600, 800 and 1200 grade SiC papers in a manner that produced unidirectional roughness, washed with double-distilled water, degreased with acetone and dried in warm air. A smaller grit number represents a rougher finish. The letter G, in the used notation (G60 to G1200), stands for grit. After drying, the specimens were placed in a desiccator and then used for experiment. The 0.5 M H_2SO_4 solution was prepared by dilution of analytical grade H_2SO_4 with double distilled water.

All electrochemical measurements were conducted in a thermostatic conventional three-electrode cell using a Solarton SI-1287 (electrochemical interface) instrument. Mild steel and nickel were used as the working electrode (WE). Only 1 cm^2 areas of the samples were exposed to the electrolyte. A saturated calomel electrode (SCE) and a platinum wire were also used as the reference and auxiliary electrodes, respectively. All experiments were carried out in 100 mL of

naturally aerated electrolyte maintained at 25°C. The scan rate of the experiments was 1.0 mV/s. In all experiments, the mild steel and nickel electrodes were allowed to reach their stable open-circuit potential (OCP), which occurred after 30 minutes. The surface morphology of the samples, both before and after corrosion, was studied using a JEOL 5800 SEM at an accelerating voltage of 20.0 kV. The EDS spectra were obtained both before and after corrosion to show the changes in the oxygen content in the surface layer. A profilometry technique was used to calculate different roughness parameters including R_a , R_q , R_z and R_t before and after corrosion using a Wyko Surface Profiling System NT-1100. The change in all parameters was calculated after corrosion and the relationship between each parameter and corrosion rate was determined.

3 Results

3.1 Potentiodynamic polarization technique

The three different curves for three different values of unidirectional roughness in Fig. 1 illustrate the potentiodynamic polarization test results for mild steel in 0.5 M H_2SO_4 solution at room temperature. The electrochemical parameters shown in Table 1, i.e. the open-circuit potential (OCP), the corrosion potential E_{corr} , the corrosion current density i_{corr} and the anodic β_a and cathodic β_c Tafel constants were collected from the plots using the extrapolation of the polarization curves. The corrosion current was determined by the intersection of the cathodic or the anodic Tafel line with the OCP (potential of zero current in the potentiodynamic curves or E_{corr}). This point determines the potential E_{corr} and current density i_{corr} for corrosion [10]. Polarization resistance R_p and corrosion rate CR were also determined using the equations [10]:

$$R_p = \frac{\beta_a \beta_c}{2.3 i_{corr} (\beta_a + \beta_c)} \quad (1)$$

$$CR = K i_{corr} \frac{EW}{\rho} \quad (2)$$

where K is a constant for converting units, i_{corr} the corrosion current density ($\mu A/cm^2$), ρ the alloy density (g/cm^3), EW the alloy equivalent weight ($g/equivalent$). The potentiodynamic polarization curves show that in the presence of surfaces with different roughness values, there is a decrease in anodic and cathodic current densities. The increase of the roughness (G1200 to G60) resulted in the curve shift toward lower corrosion current densities which meant lower corrosion rates. In addition, according to the data in Table 1, with the increase of the roughness values, the corrosion current density and corrosion rate decreased and polarization resistance increased.

On the other hand, the presence of unidirectional roughness only slightly modified the current densities of the anodic and cathodic curves and decreased corrosion. The same effect has already been observed in AE44 Mg alloy [9]. In both cases the metal has no ability to form a passive layer but in the case of other

metals which form a passive layer, a reverse trend was observed [1–6]. As shown in Fig. 1, the polarization curves rise to parallel and it is clear that both cathodic and anodic branches show a lower current density indicating that the hydrogen evolution reaction is activation controlled [11, 12]. Thus, creating the unidirectional roughness does not affect the mechanism of this process and has been able to affect the corrosion performance. In order to be sure about the consistency of the results, all the tests were performed five times. As seen in

Figure 1: Polarization curves for mild steel samples.

Table 1: Corrosion testing results for mild steel.

Sample	E_{corr} (V)	i_{corr} ($\mu\text{A}/\text{cm}^2$)	β_a (V)	β_c (V)	R_p (Ω/cm^2)	CR (mil/year)
G60	-0.968	4141	0.295	0.570	20.46	1886
G120	-0.971	4373	0.290	0.507	18.37	1991
G180	-0.973	4432	0.305	0.457	17.93	2018
G240	-0.974	4724	0.291	0.513	17.05	2151
G320	-0.973	5027	0.306	0.543	16.93	2289
G400	-0.974	6113	0.349	0.690	16.49	2784
G600	-0.974	6255	0.358	0.688	16.35	2848
G800	-0.973	7239	0.388	0.628	14.44	3297
G1200	-0.973	7499	0.374	0.740	14.41	3415

Fig. 2(a), by decreasing the roughness from sample G60 to G1200, i_{corr} and consequently CR are increased. In contrast, as can be seen in Fig. 2(b), a different corrosion behaviour and a reverse trend was observed in the case of nickel in 0.5 M H_2SO_4 solution on surfaces with different unidirectional roughness [6]. As can be seen in previous work carried out by the authors, by increasing the roughness of nickel surface from sample G1300 to G60, the polarization curves shifted toward higher corrosion current densities which meant higher corrosion rates [13].

Figure 2: Dependence of i_{corr} on surface finish of (a) mild steel and (b) nickel.

3.2 Scanning electron microscopy

Figs. 3(a)–(d) illustrates the SEM micrographs of the surface morphologies of mechanically polished mild steel electrodes with unidirectional roughness before and after corrosion. Samples G1200 and G60 are shown as examples of smooth and rough surfaces. It can be seen that the surfaces of electrodes became rougher before corrosion as the grain size of the applied SiC paper increased (higher roughness value). Fig. 3(a) presents the smoothest mild steel surface (G1200) with nano-size unidirectional roughness whereas Fig. 3(b) presents the sample G1200 surface after corrosion in 0.5 M H₂SO₄ solution. Fig. 3(c) shows sample G60 as the sample with the roughest surface and Fig. 3(d) presents this sample surface after corrosion in 0.5 M H₂SO₄ solution. It is clear from the images that the surface of mild steel has changed in both cases. In the case of sample G1200 the metal has been corroded completely and the surface was strongly damaged but there are still some grooves on sample G60, but in a larger scale. Other samples also showed the same trend i.e. on rougher samples more grooves are still visible which shows less degradation on rougher samples. The results obtained from SEM showed good agreement with the results obtained from potentiodynamic polarization technique. In Figs. 3(e)–(h), a reverse trend is observed for the nickel samples in 0.5 M H₂SO₄ solution namely more degradation on rougher samples and corrosion seemed to be concentrated along the grooves [13]. This trend in change of corrosion versus surface roughness for nickel as an active–passive metal was observed by researchers in the case of stainless steel and aluminium [3, 5] which showed poorer corrosion resistance and trapping the corrosive ions on rougher surfaces of active–passive metals.

3.3 EDS analysis

Energy dispersive spectroscopy (EDS) was used to characterize the surface and measure the oxygen content of the surface both before and after corrosion testing. Table 2 presents oxygen concentration both before and after corrosion on surfaces of mild steel with different roughness. All samples had similar oxygen contents before corrosion testing but the oxygen content increased for all samples after corrosion. Looking at the oxygen content increase of the surface, all samples show a significant increase. For the roughest samples (G60–G120) the increase in oxygen content is a little bit less compared to that for the other samples. As demonstrated by the electrochemical results, G60 and G120 exhibited the lowest corrosion rates, and the corrosion rate decreased with increasing roughness.

All the chemical composition analysis for mild steel before the corrosion testing had almost similar results which were as expected. After corrosion in all samples, specially samples G180 to G1200, there is a significant increase in oxygen content which is related to a severe general corrosion on the surface. The same thing has happened for rougher surfaces (G60 and G120) but with lower amounts of oxygen and less degree of corrosion. The results are in good agreement with SEM and potentiodynamic polarization tests.

In the case of metals such as aluminium and nickel, the lower corrosion rate was related to the formation of a stable passive film on smoother surfaces as

suggested by the authors [3, 13–16] but in the case of mild steel no stable passive film is formed and rougher surfaces showed less corrosion and lower oxygen content. Generally, more increase in the oxygen content was observed for mild steel indicating more oxides form on the surface.

Figure 3: SEM micrograph of mild steel sample G1200 (a) before corrosion, (b) after corrosion, G60 (c) before corrosion, (d) after corrosion and nickel samples G1200 (e) before corrosion, (f) after corrosion and G60 (g) before corrosion, (h) after corrosion.

Table 2: EDS results for oxygen contents on the surface of the mild steel samples before and after corrosion.

Sample	Oxygen wt% before corrosion	Oxygen wt% after corrosion	Oxygen wt% difference
G60	2.51	24.63	22.12
G120	2.92	20.36	17.44
G180	2.93	31.61	28.68
G240	2.55	30.49	27.94
G320	2.38	33.67	31.29
G400	2.35	26.28	23.93
G600	2.23	31.95	29.72
G800	2.63	26.95	24.32
G1200	2.37	28.85	26.48

3.4 Roughness measurement

Profilometry (Wyko Surface Profiling System NT-1100) was used to characterize the surface and measure the average surface roughness R_a , root-mean-squared roughness R_q , the average of the ten greatest peak-to-valley separations R_z and the peak-to-valley difference calculated over the entire measured array R_t both before and after corrosion testing. In all parameters, the roughness value for mild steel has increased after corrosion which is due to the formation of corrosion products on the surface. As an example, R_a values before and after corrosion testing are listed in Table 3. The last column in this table is a list of SiC particle size on grinding papers. Nickel also showed an increase in roughness parameters after corrosion which is an indication of the formation of deeper grooves (on rougher surfaces where there is more corrosion) and passive layer (on all surfaces especially smoother surfaces) [6, 13].

3.5 Relationship between corrosion rate and roughness

Figs. 4(a), (b) and 5(a), (b) show the variation of the corrosion rate as determined by potentiodynamic polarization tests versus the average surface roughness R_a and the average ten largest peak-to-valley separations R_z for mild steel and nickel, respectively.

By increasing the surface roughness of mild steel, corrosion rate decreased. These results are in agreement with results of previously reported studies which investigated the appearance, oxygen concentration and roughness parameters in SEM, EDS and profilometry tests, respectively. This is a general trend in corrosion of metals with no ability to form a passive layer [8, 9]. This trend is exactly the opposite to the one in nickel (Fig. 4(b)) and aluminium with ability to form a

protective passive film [3, 6]. A reverse trend was also reported by Li and Li [2] for Cu in a 3.5% NaCl solution which was expected. Looking at the general shape of the plot, it can be seen that after a limit, decreasing the surface roughness of mild steel dramatically increases the corrosion rate. The rate of change of corrosion rate with roughness decreases before this limit and, for the high roughness values, the corrosion rate appears to reach a plateau.

Table 3: R_a values before and after corrosion testing on mild steel.

Sample No	Roughness values		SiC particle size (μm)
	R_a (before corrosion testing) (nm)	R_a (after corrosion testing) (nm)	
G60	1446	1550	254
G120	916	1688	102
G180	819	1725	80
G240	401	1384	60
G320	272	1460	40
G400	217	1578	30
G600	185	1586	15
G800	171	1588	13
G1200	128	1254	9

4 Discussion

The result obtained in this work was that mild steel with smoothest polished surfaces (G1200) showed the highest corrosion rate compared to surfaces with higher roughness values. This can be attributed to the high rate of corrosion propagation after initiation. It is said that localized corrosion is controlled by the diffusion process and in this case once the corrosion started, it propagated at a fast rate due to the continuous diffusion process and the formation of acid media at the bottom of the grooves [8]. The results are in a good agreement with the observations of Alvarez on AE44 magnesium alloy which has similar characteristics as mild steel i.e. no ability to form a stable passive film [9]. These trends are opposite of the trends seen in the literature for aluminium, nickel, copper, titanium and stainless steel, which include the rough surfaces limiting diffusion out of the forming pits, more available active sites on the rough surfaces and fast formation of a stable oxide film on the smoother surfaces [3, 7].

Figure 4: Dependence of corrosion rate on R_a for (a) mild steel and (b) nickel.

Figure 5: Dependence of corrosion rate on R_z for (a) mild steel and (b) nickel.

On mild steel and also magnesium [9], since there is no stable protective passive film on both smooth and rough surfaces, the active sites would be equally available on both surfaces. But there are some grooves which are left from polishing process that act like active sites. These grooves exist more on the surfaces with higher roughness values. Corrosion products and corrosive ions are trapped in such grooves which will result in more corrosion on rough surfaces. But this is not the whole story, because the rough surface might still possess some of the corrosion products, which is said to be less reactive than the bulk of metals. The same thing could also occur on mild steel or magnesium. Therefore, the

possibility of corrosion will be decreased on rougher surfaces of mild steel because of the corrosion product layer that exists on the surface. But despite of having fewer places for corrosion nucleation, there would be more corrosion on smoother surfaces because there is no protection on the polished surface since the places for corrosion to occur would be more in contact with corrosive solution.

It is said that a rougher surface would prevent the diffusion of the corrosive ions out of the grooves and forming pits by trapping the ions [3], but simultaneously a rougher surface on mild steel surfaces could also prevent the diffusion of the corrosive ions into the grooves [7]. Thus, the limited diffusion of the aggressive ions into the grooves would reduce the corrosion on the rougher surface. But on smooth mild steel surface which has no corrosion product layer or a passive film, corrosion is dependent on the diffusion of the corrosive ions onto the surface because there would be nothing to prevent the corrosion [3]. In the case of metals with no ability to form a passive layer, no repassivation of the smooth surface will occur, unlike stainless steel, nickel or aluminium, but instead more corrosive ions will be in contact with the surface and help the occurrence of corrosion.

Thus, it is suggested that corrosion is dependent on both surface roughness and the ability of the material to form a protective passive film.

5 Conclusions

The surface roughness of mild steel as a metal with no ability to form a passive layer showed a significant effect on its corrosion resistance. A rougher surface has both a slight amount of corrosion product layer remaining, as well as a rougher topography that can prevent the corrosive ions from diffusing close to the surface to initiate corrosion but the smoother surface is corroded more quickly because the latter has nothing preventing corrosion in contrast to the rougher surface. For nickel, low surface roughness promotes the formation of a stable passive film and in rougher samples there is a greater contact area between the corrosive solution and metal together with trapping of corrosive ions in the deep grooves leading to processes such as pitting.

The potentiodynamic polarization technique was used to measure corrosion parameters related to samples with different roughness values. Less corrosion was observed on rougher samples of mild steel and by decreasing the roughness, corrosion rate increased. A reverse trend was observed for nickel.

SEM micrographs showed more degradation on smoother surface of mild steel but in the case of rougher surfaces some grooves are still visible in a larger scale. The micrograph for nickel showed that the corrosion pits were preferentially aligned along the grooves suggesting that the deep valleys on the ground surface were favourable sites for corrosion nucleation.

EDS analysis also measured oxygen content before and after corrosion and different elements were characterised from the peak analysis. Less increase in oxygen content was observed on rougher samples of mild steel. On nickel, however, the increases in oxygen content, especially on smoother surfaces, could be indicative of the formation of a stable passive film.

Profilometry was utilized to measure different roughness parameters to investigate corrosion. By increasing the roughness in mild steel, all roughness parameters had the same trend in corrosion rate (decreased and plateaued) and rougher samples showed less increase in roughness after corrosion. For nickel, by increasing the roughness, corrosion rate increased and plateaued.

References

- [1] Cabrini, M., Cigada, A., Rondell, G. & Vicentini, B., Effect of different surface finishing and of hydroxyapatite coatings on passive and corrosion current of Ti6Al4V alloy in simulated physiological solution. *Biomaterials*, **18(11)**, pp. 783–787, 1997.
- [2] Li, W. & Li, D.Y., Influence of surface morphology on corrosion and electronic behavior. *Acta Materialia*, **54(2)**, pp. 445–452, 2006.
- [3] Suter, T., Müller, Y., Schmutz, P. & von Trzebiatowski, O., Microelectrochemical studies of pit initiation on high purity and ultra high purity aluminum. *Advanced Engineering Materials*, **7(5)**, pp. 339–348, 2005.
- [4] Walter, R. & Kannan, M.B., Influence of surface roughness on the corrosion behaviour of magnesium alloy. *Materials & Design*, **32(4)**, pp. 2350–2354, 2011.
- [5] Burstein, G. & Vines, S., Repetitive nucleation of corrosion pits on stainless steel and the effects of surface roughness. *Journal of The Electrochemical Society*, **148(12)**, pp. B504–B516, 2001.
- [6] Toloei, A.S., Stoilov, V. & Northwood, D.O., The effect of different surface topographies on the corrosion behaviour of nickel. *WIT Transactions on Engineering Science*, **77**, pp. 193–204, 2013.
- [7] Zuo, Y., Wang, H. & Xiong, J., The aspect ratio of surface grooves and metastable pitting of stainless steel. *Corrosion Science*, **44(1)**, pp. 25–35, 2002.
- [8] Abosrra, L., Ashour, A.F., Mitchell, S.C. & Youseffi, M., Corrosion of mild steel and 316L austenitic stainless steel with different surface roughness in sodium chloride saline solutions. *WIT Transactions on Engineering Sciences*, **65**, pp. 161–172, 2009.
- [9] Alvarez, R.B., Martin, H.J., Horstemeyer, M.F., Chandler, M.Q., Williams, N., Wang, P.T. & Ruiz, A., Corrosion relationships as a function of time and surface roughness on a structural ae44 magnesium alloy. *Corrosion Science*, **52(5)**, pp. 1635–1648, 2010.
- [10] Roberge, P., *Corrosion Engineering Principles and Practice*, 1st ed., McGraw-Hill: New York, 2008.
- [11] Slepski, P., Gerengi, H., Jazdzewska, A., Orlikowski, J. & Darowicki, K., Simultaneous impedance and volumetric studies and additionally potentiodynamic polarization measurements of molasses as a carbon steel corrosion inhibitor in 1M hydrochloric acid solution. *Construction and Building Materials*, **52**, pp. 482–487, 2014.

- [12] Bouklah, K.O., Messali, M., Hammouti, B., Elidrissi, A. & Warad, I., A pyrrolidine phosphonate derivative as corrosion inhibitor for steel in H_2SO_4 solution. *Der Pharma Chemica*, **3(5)**, pp. 283–293, 2011.
- [13] Toloei, A.S., Stoilov, V. & Northwood, D.O., An electrochemical impedance spectroscopy and potentiodynamic polarization study of the effect of unidirectional roughness on the corrosion of nickel. *International Journal of Computational Methods and Experimental Measurements*, **2(3)**, pp. 243–254, 2014.
- [14] Toloei, A.S., Stoilov, V. & Northwood, D.O., A new approach to combating corrosion of metallic materials. *Applied Surface Science*, **284**, pp. 242–247, 2013.
- [15] Toloei, A., Stoilov, V. & Northwood, D.O., The effect of creating different size surface patterns on corrosion properties of nickel. *Proc. of ASME International Mechanical Engineering Congress & Exposition (IMECE2012)*, Houston, USA, 2012.
- [16] Toloei, A., Stoilov, V. & Northwood, D.O., The relationship between surface roughness and corrosion. *Proc. of ASME International Mechanical Engineering Congress & Exposition*, San Diego, California, USA, 65498, 2013.