Conference Article

Microstructure and Mechanical Properties of Joint Welds Formed by Linear Friction Welding in Al-Cu-Mg Alloy**S.K. Kiselyeva*, Vas.V. Astanin, L. Gareeva, V.M. Bychkov, A.Y. Medvedev, Musin F.F. and I.V. Alexandrov***Ufa State Aviation Technical University, Ufa, Russian Federation*

Received 10 September 2014; Accepted 22 September 2014

Abstract

The microstructure and mechanical properties of joint welds formed by linear friction welding (LFW) in Al-Cu-Mg alloy was investigated. Joint welds of two samples of rectangular shape do not possess any macroscopic defects and are characterized by high strength. The substantial transformation of the microstructure occurs in the weld zone as a result of plastic deformation and deformation heating during LFW.

Keywords: aluminum alloy, linear friction welding, microstructure

1. Introduction

Nowadays there are a few manufacturing processes which allow the joint of metals without melting at the weld interface. They involve such different types of friction welding like the rotary, the orbital and the linear one. The linear friction welding (LFW) is the advanced technology which is used in aviation engineering to produce integrally bladed disks (blisks). As such there is a growing interest in the last few years in the LFW process of heat-resisting Ti alloys and steels [1-5]. The successful application of LFW technology has already been shown as well as modeling blisks with the Russian Ti alloys VT6 and VT8M-1 [4,5].

Linear friction welding of Al alloys is also attracting a lot of interest. Although there are a number of works on using LFW [6] and modeling [7,8] the process, there are no papers on the microstructure and properties of LFW welds of Al alloys.

Therefore the aim of this work is the investigation of using the LFW process on microstructural changes and mechanical properties of the Russian aluminum alloy D16T.

2. Experimental

The deformable aluminum alloy D16T has been chosen as the material of investigation. Chemical composition of the alloy is shown in Table 1. The samples after the usual heat treatment for aluminum alloys, such as hardening with the following ageing, have been welded with LFW.

To describe and simulate the OFDM reception process, an appropriate receiver model and simulation resources must be used.

Table 1. Chemical composition (main alloying elements) of D16T.

Cu	Mg	Mn	Si	Fe	Cr	Zn	Ti
4.11	1.55	0.72	0.21	0.24	0.03	0.25	0.15

The samples were cut in rectangular sections with length of 40 mm and a cross section of 13×26 mm. The main welding parameters have been selected based on the LFW machine capabilities.

Metallographic samples for microstructure investigation were prepared in the central zone of the welded sample. To reveal the structure, the prepared metallographic samples were etched with hydrochloric, nitric and hydrofluoric acid solution in water. For the microstructure investigations the optical microscope «OLYMPUS GX-51» was used.

For microhardness testing a «Struers Duramin» machine was used with a 1 N load applied for 10 sec, along a line perpendicular to the welding interface at a pitch of 0.5 mm. Tensile tests were performed with flat samples with thickness 2 mm using the universal machine «Instron 5982» at the crosshead speed of 1 mm / min.

3. Results

Microstructure investigations did not reveal any defects such as discontinuities, incomplete penetration and pores in the welding interface.

The microstructure of the samples after welding in the contact zone of the two materials can be divided into three zones: 1 – the weld centre; 2 – the thermo-mechanically affected zone; 3 – the zone of the parent material. These zones can be seen in the panoramic photo of the weld and the adjusting zone (Fig. 1). These zones differ in their reaction to etchants, sizes and shape of the grains.

* E-mail address: nurieva_s@mail.ru

Fig. 1. Panoramic microstructure photo of D16T after LFW:
 1- the weld centre, 2 – the thermo-mechanically affected zone, 3 – the parent material zone

Fig 2. Microstructure of alloy D16T after linear friction welding a) the base metal, b) the thermo-mechanically affected zone, c) the weld centre

The parent material zone (Fig. 2a) is characterized by a well defined metallographic texture, produced after pressing.

The average aspect ratio of grains was $K=23\pm1$. Thus, both grains at both sides of the weld line are perpendicular to the welding interface. Grain boundaries are in a straight position, and in some cases a ripple effect of boundaries can be observed. Along the boundaries of the elongated grains there are some stroke precipitates of the primary intermetallic phases and smaller intermetallic phases, originating from cooling from the welding temperature. The volume fraction of the primary phases has been $15.0\pm0.5\%$.

Fig 3. The polished face of the sample after LFW a) the base metal, b) the weld centre.

The turn of the initial elongated grains towards the direction parallel to the weld plane is observed in the thermo-mechanical affected zone (Fig. 2b). The presence of such a structure proves that there is considerable plastic deformation. In addition, equiaxed grains are present in this zone. The average grain size is $5.0\pm0.5\ \mu\text{m}$. The equiaxed grains in this area are probably related to recrystallization.

The weld centre differs from all the others as it is very difficult to etch and identify structures (Fig. 2b). The grain boundaries cannot be revealed in this area. The coarse intermetallic phases (Fig. 3b), which have been observed in the parent material and in the thermo-mechanical affected zone (Fig. 3b), are not present here.

The results of measuring the microhardness across the welding zone are shown in Fig. 5. The average value of microhardness in the zone of welding line is $HV140\pm3$ and does not vary in any significant way.

In spite of significant microstructure changes as the result of LFW, the microhardness in the welding zone does not differ much from the parent material (Fig. 4). The results of tensile testing show that the weld shows high strength properties (Tab. 2).

Fig. 4. The microhardness distribution in the sample after linear friction

Table 2. Mechanical testing.

№	σ_U , MPa	HV _{mean}
1	490	143
2	493	138
3	499	140
4	504	142
5	473	140
6	501	143

The maximum tensile strength measured was $\sigma_U = 504$ MPa, while minimum was 473 MPa. During tensile testing fracture occurred along the thermo-mechanical affected zone.

4. Discussion

The experiments performed have shown that a sound weld can form with LFW of the samples from aluminum alloy D16T. Considerable changes take place in the microstructure under high temperature deformation caused by friction movement of the samples against each other. In the welding zone heating led to the development of recrystallization in the material. In the thermo-mechanically affected zone deformation was at a lower temperature, which led just to fragmentation of the initially elongated grains.

Further to these LFW has affected the phase composition of the alloy. When big particles of intermetallic phases located along the grains have been observed in the microstructure in the initial state, then following welding these phases disappear from the welding zone. It is probable that their dissolution is the result of a high temperature deformation effect.

While friction of the ingots against one another the inconsiderable heating of the narrow contact area of the

ingot material have taken place. When the frictional heat does not generate any more and the whole process is over the narrow near-contact zone of the weld centre is quenched in the air, which obviously leads to hardening. The quenching of the aluminum alloys results in lower microhardness compared to the hardened-aged state. However in our case the microhardness decrease in the weld centre has not taken place (Fig. 4).

Linear friction welding is the process related to the plastic deformation of the material, followed by work-hardening in the welding zone. The superposition of the two effects in the weld centre (the first one from the cold strain hardening during LFW and the second one from hardening the structure of the material during the follow-up quenching after the end of LFW) has probably lead to the microhardness remaining constant.

5. Conclusion

The experiments have proved linear friction welding of aluminum alloy D16T samples produces defect free welds. The following distinct zones can be identified in the weld specimens: 1 – the zone of the parent material, which corresponds to the initial state of the part; 2 – thermo-mechanical affected zone, characterized by a distinct metallographic texture; 3 – the weld centre.

It has been stated that significant microstructure changes took place in the welding zone during plastic deformation and plastic work heating.

During the thermo-mechanical treatment the dynamic recrystallization caused the development of recrystallized structures close to and in the weld line of D16T.

It has been pointed out that initial intermetallic phases coalesce during the linear friction welding of the aluminum alloy D16T in the initial quenched-aged condition.

Acknowledgment

The results of this work were produced in the joint project of USATU (Ufa State Aviation Technical University) and UMPO (Ufa Engine Industrial Association) with title “Elaboration and industrial development of high-precision shaping coordinated technologies and superficial hardening of responsible details from Al-alloys with heightened constructional energy efficiency”, implemented under the contract №40/10-30976 sponsored by the Ministry of Education and Science of the Russian Federation (contract №02.G25.31.0010 between UMPO and the Ministry of Education and Science of the Russian Federation) through the Resolution of the Russian Federation Government № 218 from April 9, 2010.

References

- [1] W.-Y. Li, T.J. Ma, S.Q. Yang, Q.Z. Xu, Y. Zhang, J.L. Li, H.L. Liao Effect of friction time on flash shape and axial shortening of linear friction welded 45 steel // Materials Letters 62 (2008) 293–296.
- [2] A.A. Zakirova, M.I. Nagimov, A.M. Khusnullin, R.M. Kashaev Structure, properties and hot deformation of steel welded joints 08Cr18Ni10Ti obtained linear friction welding (LST) // Advanced Materials 2011. p. 155-159 (in Russian).
- [3] M. Karadge, M. Preuss, C. Lovell, P.J. Withers, S. Bray Texture development in Ti-6Al-4V linear friction welds // Materials Science and Engineering A 459 (2007) 182–191.
- [4] Karavayeva M.V., Kiseleva S.K., V.M. Bychkov, A. Medvedev, Soups A.V., F.F. Musin, I.V. Aleksandrov, Latyshev V.V. Effect of precipitation on the formation of a welded joint with linear friction welding // Materials Letters vol.2 (2012) 40-44 (in Russian).
- [5] Li, W.Y., Shi, S.X., Wang, F.F., Ma, T.J., Li, J.L., Gao, D.L., Vairis, A., “Heat Reflux in Flash and Its Effect on Joint

Temperature History during Linear Friction Welding of Steel”,
International Journal of Thermal Sciences, 2013, vol.67,
pp.192-199

- [6] Livan Fratini, Gianluca Buffa, Marco Cammalleri, Davide Campanella On the linear friction welding process of aluminum alloys: Experimental insights through process monitoring // *Manufacturing Technology* 62 (2013) 295–298.
- [7] X. Song, M. Xie, F. Hofmann, T.S. Jun, T. Connolley, C. Reinhard, R.C. Atwood, L. Connor, M. Drakopoulos, S. Harding, A.M. Korsunsky Residual stresses in Linear Friction Welding of aluminium alloys // *Materials and Design* 50 (2013) 360–369.
- [8] Li Qinghua, Li Fuguo, Li Miaoquan, Wan Qiong, and Fu Li Finite Element Simulation of Deformation Behavior in Friction Welding of Al-Cu-Mg Alloy // *JMEPEG* (2006) 15:627-631. Edfors, O., M. Sandell, J.J. Van de Beek, D. Landström, and F. Sjöberg, *An Introduction to Orthogonal Frequency Division Multiplexing*, Luleå, Sweden: Luleå Tekniska Universitet, 1996.