An Effective Anticancer Nano-approach for Melanoma and Breast Cancers Using *Annona muricata* Gold Nanoparticles

Muhammad Imran¹, Ghaleb Hussein², Nahid Awad², Vinod Paul², Babiker M El-Haj³ and Heyam Saad Ali^{4*}

¹International Center for Chemical and Biological Sciences, H.E.J. Research Institute of Chemistry, University of Karachi, Pakistan

²Department of Chemical Engineering American University of Sharjah, Sharjah, UAE

³Department of Pharmaceutical Sciences, College of Pharmacy and Health Sciences, University of Science and Technology of Fujairah, Fujairah, UAE

⁴Pharmaceutics Department, Pharmacy College, University of Khartoum, Khartoum, Sudan

***Corresponding Author:** Heyam Saad Ali, Pharmaceutics Department, Pharmacy College, University of Khartoum, Khartoum, Sudan.

Received: August 08, 2021

Published: August 18, 2021

© All rights are reserved by Heyam Saad Ali, et al.

Abstract

Chemotherapy is preferred for the treatment and management of cancer; however, its efficacy is hindered by the off-target side effects of the currently used synthetic drugs. Thus, anticancer drugs with higher safety and efficacy from renewable resources are needed. Nanostructured particles can enhance the drug specificity for target tissues, thus enhancing their clinical efficacy and safety. The synthesis of *Annona muricata* gold nanoparticles is reported for enhancing its anti-cancer potential. Green nanoparticles were synthesized through reduction of gold with *Annona muricata* followed by their extensive characterization through atomic force microscope, UV-spectrophotometer, zetasizer, and FT-R. They were investigated for their anticancer activity against two melanoma and one breast cancer cell line. The nanoparticles were rounded in shape and were monodispersed with 89.34 ± 2.76 nm size and -22.41 ± 0.27 zeta potential. FT-IR study showed the hydroxyl and carbonyl groups of *Annona muricata* were involved in the stabilization of nanoparticles. The extract anticancer activity significantly improved against all cancer cells upon loading on the surfaces of the synthesized NPs. The findings suggest that *Annona muricata* gold nanoparticles can lead to promising therapeutic anticancer results, however, to reveal their anticancer effectiveness at molecular levels, further *in vivo* studies are required.

Keywords: *Annona muricata*; Gold Nanoparticles; Synthesis; Anticancer Activity

Introduction

Cancer has been a major killer for a long time, which brings a huge terror to human beings globally [1]. It is the world's second most prevalent disease with the highest mortality, after cardiac problems [2-4]. In the United Arab Emirates (UAE), cancer is the

third most common cause of death after cardiac disease and accidents [5]. The UAE Ministry of Health has reported approximately 500 deaths annually, while the world health organization reported increasing to 2079 in 2018 [6]. Millions of dirhams are currently being invested in the UAE to cure advanced cases of cancer, but the

disease still remains at an alarming state. Among the popular cancers in the UAE, breast cancer is the main form of malignancy identified in the population of the UAE [7,8]. Similarly, one of the most common male malignancies in the UAE is skin cancer, with a 14.5 percent prevalence rate [9,10].

A massive issue restricting the effectiveness of most commonly used chemotherapeutic drugs is their non-selectivity or non-specificity to tumor tissues and cells [11]. In healthy tissues and organs, this has contributed to the major side effects of these medications [12]. This non-selectivity or non-specificity against tumor tissues and cells produces toxicity that impedes successful chemotherapy [13]. Besides, the emergence of cancer cells resistant to the chemotherapy agent has posed a new challenge, resulting in unsatisfactory clinical results [14]. Thus, there is an immediate need to explore renewable resources for alternative anticancer drugs that demonstrate enhanced therapeutic efficacy with fewer side effects [15].

Plants provide animals and humans with an ongoing source of medicine; they have been used in rudimentary forms such as liniments, decoctions, infusions, ointments, syrups, and powders since ancient times. In modern times, herbal medicines are used by both advanced and developing countries to enhance their health [16,17]. Over the last three decades, natural products have gained considerable medicinal significance as innovative, secure, efficient, and affordable therapeutic agents [18-21]. Likewise, in numerous scientific articles, the potential of plant-derived compounds to inhibit different levels of tumor growth and related inflammatory processes has been documented [22]. These studies demonstrate the efficacy of natural products in the cure and control of cancer [23-25]. Although 50 percent of modern pharmaceutical medications are produced from plants in clinical practice, many of them have significant anti-cancer effects [26]. Owing to their richness in diverse phytoconstituents, versatile chemical composition, improved therapeutic efficacy, and safety, medicinal plants need to be further explored for their chemotherapeutic effects [26-29].

Annona muricata (*A. muricata*) is a species of the Annonaceae family that has been extensively studied over the past years because of its medicinal properties. The plant has been extensively reported for its anticancer activities. *A. muricata* leaves have been shown to possess anti-carcinogenic effects against colonic aberrant crypt foci induced by azoxymethane in rats [30,31]. An extract of

ethanol from *Muricata* leaves has exhibited enhanced antitumor efficacy in murine models compared to curcumin [32]. In another research, an aqueous extract of commercial powder capsules comprising *A. muricata* leaf and stem demonstrated anti-tumor and anti-metastatic function against pancreatic tumors in murine models [33,34]. Various other studies have also reported the anticancer effects of the plant or its isolated bioactive compounds and have documented its different anticancer mechanisms [35].

As an interesting innovation for the production of anticancer drug nanoparticles, nanotechnology has been introduced. Gold nanoparticles (AuNPs) have an outstanding controlled size, stability, and biocompatibility characteristics as the best drug nanocarriers, enabling them effective agents in the diagnosis and cure of cancer [36-38]. The production of nanoparticles by using a process of chemical reduction leads to the production of toxic compounds adsorbed to the surface of the particles, thus prevent their use for biomedical applications [38,39,41]. Therefore, researchers are currently employing different biological approaches to concentrate on the production of biocompatible and eco-friendly nanoparticles. Green synthesis of nanoparticles using plant extract has been highly fascinating due to their higher safety, ease of synthesis, and stability [42-44]. Furthermore, the synthesis of nanoparticles with extracts of medicinal plants enhance their pharmacological efficacy due to their smaller nano-size, increased interaction biological systems as well as their accumulation in target sites [45-47].

Purpose of the Study

The purpose of this research study is the synthesis of *A. muricata* leaves ethanolic extract stabilized AuNPs and their evaluation for anticancer activity against melanoma and breast cancer.

Experimental Methodology

Collection of plant material and identification

Fresh leaves of *A. muricata* were purchased from the Abu Dubai market, UAE, during August 2021. The plant was identified by Dr. Ibrahim Futuh. The voucher of the specimen was deposited in the herbarium of the Department of Pharmaceutical Chemistry and Natural Products, Pharmacy, University of science and technology of Al Fujairah, Al Fujairah, UAE.

Ethanolic extract preparation

After collection, the leaves of the plant were thoroughly rinsed and dried for 10 days at room temperature. The shade dried sam-

ples were then ground into a coarse powder with an electric mixer and placed in a polythene bag at room temperature. The content was then immersed in ethanol (80 percent) for 15 days. Then the extract was filtered using Whatman's No; 1 filter paper. The extract was concentrated to dryness under lower power at temperature (45°C) using a rotary evaporator.

Synthesis of gold nanoparticles (AM-AuNPs)

The synthesis of the ethanol extract *A. muricata* AuNPs (AM-AuNPs) was initially configured by combining various concentrations (0.5 - 2.5 mg/mL) of ethanol extract *A. muricata* with gold solution (1 mM) at 1: 1 v/v ratio. At the ambient temperature, the mixture was stirred at 100 rpm for 6 h. Initially, the color alters to deep purple from light yellow, suggesting the synthesis of AM-AuNPs. The NPs were further characterized by the UV-visible spectrophotometer (UV-240, Shimadzu, Kyoto, Japan) for their distinctive surface plasmon resonance (RSP) peak. For the effects of different concentrations (0.2 - 1 mM) of the gold solution, the NPs were further investigated.

Characterization surface morphology, size, zeta potential, and PDI

An atomic force microscope (AFM, Agilent 5500) was employed to examine the surface morphology of the synthesized NPs. AM-AuNPs were placed in a dust-free compartment at room temperature on a mica slide and air dried. The slide was positioned on the microscope, viewed in non-contact mode, and the images were captured. Zetasizer (ZS-90 Malvern instruments, the UK) was used to evaluate the scale, PDI, and zeta potential. Appropriately diluted samples were collected in a disposable plastic cuvette for size and PDI determination, and measurements were taken at 25°C. Diluted samples were steadily injected into capillary cells for zeta potential evaluation and observed at 25°C. Measurements with water as a dispersant were taken in triplicate.

FT-IR analysis

For the purpose to examine the participation of the functional groups of ethanolic extract of *A. muricata* in the reduction/ stabilization of AM-AuNPs, FT-IR analysis was carried out. KBr powder was combined with dried samples of ethanolic extract and AM-AuNPs and pressed for self-supporting disks. The IR spectra were obtained by an IR spectrometer (Shimadzu, Kyoto, Japan) in the range of 900 to 4000 cm⁻¹.

Anticancer activity

MCF-7, breast cancer cells, was gifted from Prof Maiweh Hamed (University of Sharjah, UAE). Metastatic melanoma [MM-138] and primary melanoma FM-55, melanoma cells were purchased from Sigma Aldrich, UK from ECACC cell lines collection. In DMEM, the MCF-7 cells were cultured, whereas the melanoma cell lines were preserved in RPMI-1640 medium with glutamine and HEPES supplementation. The media contained antibiotics (50 units/mL streptomycin and 50 units/mL penicillin) and FBS (10%). The cells were incubated in a humidified aseptic containing 5 percent CO₂ at 37°C environment. MTT assays were used to examine the cytotoxicity of ethanolic extract of *A. muricata*, and AM-AuNPs at varying concentrations (62.5, 125, 250, and 500 µg/mL) and negative control against these cells. The cells culturing was carried out in 96-well plates at a concentration of 8.0 x 10³ cells/well in a culture medium (200 µL). The initial medium was replaced after incubation for 24 hours and a new medium (200 µL) containing different concentrations (62.5 - 500 µg/mL) of test samples was introduced. Without the test sample, cells were seeded with negative regulation media. Cell cultivation was then maintained for 24h. MTT (20 µL; 5 mg/mL) solution in PBS was applied to each well. The medium containing the unreacted dye was extracted after incubating the cells for 4h. The purple formazan crystals collected were immersed in 200 µL per well of dimethyl sulphoxide (DMSO) and the absorption was assessed at 570 nm wavelength in microplate readers (ELx808, BioTek, USA). The toxicity of the cells in the test samples was measured adequately.

Statistical analysis

The data were represented as mean ± SEM. All performed tests were conducted at triplicate. To draw the graphs, the GraphPad Prism was employed. For comparison, the two-way ANOVA accompanied by the Bonferroni test was used. P values <0.05 were considered to be statistically significant. P values less than or equal to 0.05 were assumed to be statistically significant.

Results and Discussion

The AuNP synthesis is commonly achieved via the reduction of the gold atoms from a charged state to a normal state. In this research, the ethanol extract of *A. muricata* has been used both as a reducing and as a stabilizing agent. Plant-based extracts have been used for AuNP green synthesis. Such products reduce the use of

dangerous and harmful synthetic reducing agents such as sodium dimethylformamide, hydrazine hydrate, and borohydride [25]. The characteristic absorption of the extract solution is shown in figure 1A. Maximum absorbance was detected for 2.5 mg/mL of the extract solution when various concentrations (0.5 - 2.5 mg/mL) of *A. muricata* ethanol extract were blended with 1 mM gold solution in a 1:1 v/v ratio. It showed a peak of Surface Plasmon Resonance (SPR) at 538 nm with 1.45 absorbance, indicating the peak synthesis of AM-AuNPs as depicted in figure 1B. The intensity of the characteristic SPR peak dropped with a concurrent reduction of the concentration of *A. muricata* extract. As the concentration of *A. muricata* ethanolic extract reduced, the intensity of the characteristic SPR peak dropped significantly. This indicates that for adequate reduction and stabilization of NPs, lower concentrations of *A. muricata* ethanolic extract are not enough. Likewise, keeping the *A. muricata* ethanolic extract concentration at 2.5 mg/mL, the effects of gold concentration were also examined. The results indicated maximum absorbance for the highest gold concentration used, i.e. 1 mM. A distinctive SPR peak with maximum absorbance was displayed, confirming the peak synthesis of NPs as seen in figure 1C. The reducing concentration of gold triggered the intensity of the characteristic SPR to decrease. Therefore, the ideal parameters for the synthesis of AM-AuNPs with the enhanced intensity of the characteristic SPR peak were estimated to be 2.5 mg/mL of *A. muricata* ethanolic extract and 1 mM of gold mixed in a ratio of 1: 1 v/v.

Figure 1: (A) UV-visible spectrum *A. muricata* ethanolic extract, (B) and (C) UV-visible spectra showing effects of the concentrations of *A. muricata* ethanolic extract and gold on the synthesis of AM-AuNPs.

Characterization of AM-AuNPs

Surface morphology, size, PDI, and zeta potential

Surface morphology, zeta potential, PDI, and size of AM-AuNPs were explored by zetasizer and AFM respectively. AM-AuNPs showed smooth spherical surface morphologies as indicated in figure 2. As shown in figure 3A. AM-AuNPs had a mean surface charge of -22.41 ± 0.27 . AM-AuNPs indicated a mean particle size of 89.34 ± 2.76 nm as shown in figure 3B. The relatively greater size of AM-AuNPs may be due to *A. muricata* ethanol extract that induces their reduction/stabilization. The NPs showed a PDI value of 0.19 ± 0.01 , indicating that they are highly monodispersed as indicated in figure 3B. The size of NPs on the nano range scale influences the drug delivery systems' in-vivo performance as well as physical stability. When analyzed by zetasizer, AuNPs were observed to be good in nano-size. In addition, this size analysis validates spectrophotometric screening where NPs have been identified with a narrow and sharp SPR peak. In addition, nano-range particles show reduced toxicity in vivo relative to their larger counterparts [48-50]. Nano range size was shown by the synthesized NPs, predicting their better *in-vivo* efficiency and physical stability. Another significant aspect of a nano-based drug delivery system is the Zeta potential, as it maximizes the physical stability of the formulations by avoiding particle aggregation and fusion. The greater zeta potential also guarantees interactions of biological membranes with drug delivery systems and, therefore, leads to the greater therapeutic effectiveness of the loaded drugs [51,52].

The *A. muricata* ethanolic extract IR spectrum displays characteristic peaks of absorption for -OH groups at 3365 cm^{-1} and NH-

Figure 2: Surface morphological analysis of the synthesized AM-auNPs.

Figure 3: 10 (A) zeta potential and (B) the average size of the synthesized AM-AuNPs.

C=O functional groups at 1793 cm^{-1} . Likewise, it shows characteristic peaks for C=O, C=C (aromatic), and C-O-C functional groups at 1640, 1529, and 1040 cm^{-1} as shown in figure 4, respectively. At 3341 cm^{-1} for OH groups, 1715 cm^{-1} for NH-C=O functional groups, and 1608 cm^{-1} for C=O functional groups, the IR spectra of AM-AuNPs reveal their characteristic peaks. Similarly, for functional groups C=C (aromatic) and C-O-C, it also displays characteristic absorption peaks at 1528 and 1020 cm^{-1} respectively. The transition in absorption peaks from 3365.2 cm^{-1} to 3379 cm^{-1} and from 1040 cm^{-1} to 1020 cm^{-1} indicates that *A. muricata* ethanolic extract functional groups-OH and C-O-C are actively engaged in the AM-AuNP degradation and stabilization.

Anticancer activity The MTT cytotoxicity assay is widely used in vitro to determine the viability of cancer cell lines. The in vitro cytotoxicity of anticancer drugs is normally assessed by this technique [28]. In the current research, the synthesized AM-AuNPs and plant ethanolic extract were screened for their anticancer activity against two melanoma (Metastatic melanoma [MM-138] and primary melanoma [FM-55]) and one breast cancer cell lines using MTT assay. When tested against melanoma cells MM-138, the synthesized AM-AuNPs revealed improved anticancer activity as compared to the simple ethanolic extract. At the highest concentration of $500\text{ }\mu\text{g/mL}$, AM-AuNPs showed $78.98 \pm 2.52\%$ cytotoxicity as

Figure 4: FT-IR analysis of plant ethanolic extract and its stabilized NPs.

compared to $61.07 \pm 2.87\%$ cytotoxicity shown by the simple extract of the plant (Figure 5A). Similarly, the synthesized AM-AuNPs showed higher cytotoxicity against the melanoma FM-55 cells as compared to the simple extract of the plant. At the highest concentration of $500\text{ }\mu\text{g/mL}$, AM-AuNPs showed $81.33 \pm 4.81\%$ cytotoxicity as compared to $60.00 \pm 2.44\%$ cytotoxicity shown by the simple extract of the plant (Figure 5B). In MCF-7 breast cancer cells, the AM-AuNPs exhibited improved anticancer activity compared to the simple extract. 13 In the case of MCF-7 breast cancer cells, the AM-AuNPs demonstrated improved anticancer activity as compared to the simple extract. At the highest concentration of $500\text{ }\mu\text{g/mL}$, AM-AuNPs showed $87.19 \pm 3.63\%$ cytotoxicity as compared to $71.45 \pm 1.87\%$ cytotoxicity shown by the simple extract of the plant (Figure 6).

In this research, the synthesized AM-gold nanoparticles displayed substantial cytotoxicity activity towards two cancer cells of melanoma and one breast cancer cell in a dose-dependent manner. As the concentration of synthesized gold nanoparticles enhanced, the cancer cell lines' viability proportion decreased drastically. It clearly indicates the possible cytotoxic activity of the synthesized AM-gold nanoparticles against the three cancer cell lines. The function of anticancer activity of AuNPs may be recognized by the adsorbed active molecules present in *A. muricata* ethanolic extract as reported by previous researches documenting plant AuNPs for an-

ticancer activity [53-55]. Another possible reason for the improvement in the anticancer activity of the *A. muricata* ethanolic extract upon its loading on AuNPs can be the greater interaction of the synthesized NPs towards the membrane of the biological systems (the three cell lines in our case) [56-58]. Similarly, the smaller nano-size of the synthesized NPs can also increase the biological activity of the therapeutic substances adsorbed on their surfaces [59-61].

Figure 5: Anticancer activity of the synthesized NPs and the ethanolic extract against (A) MM-138 and (B) FM-55 melanoma cells.

Figure 6: Anticancer activity of the synthesized NPs and the ethanolic extract against MCF-7 breast cancer cells.

Conclusion

In conclusion, we successfully synthesized gold nanoparticle from the *A. muricata* leaves extract and screened them for anti-

cancer activity against melanoma and breast cancer cells. The synthesized NPs were highly monodispersed in the nanosized range and were spherical. Multi-functional groups of the extract were involved in the stabilization of the synthesized NPs. The extract anticancer activity significantly improved against all cancer cells upon loading on the surfaces of the synthesized NPs. However, further studies of the *A. muricata* gold nanoparticles may contribute to future anticancer therapies for breast and skin cancers.

Acknowledgment

This research was partly funded by a targeted grant from the University of Sharjah (grant no. 16010901011-P). The researcher would like to acknowledge Department of Chemical Engineering American University of Sharjah, Sharjah, UAE, for the support of the research project.

Bibliography

- Bray F, *et al.* "Global cancer statistics 2018: GLOBOCAN estimates of incidence and mortality worldwide for 36 cancers in 185 countries". *CA: A Cancer Journal for Clinicians* 68 (2018): 394-424.
- Bray F, *et al.* "Cancer Incidence in Five Continents: inclusion criteria, highlights from Volume X and the global status of cancer registration". *International Journal of Cancer* 137 (2015): 2060-2071.
- Ginsburg O, *et al.* "The global burden of women's cancers: a grand challenge in global health". *Lancet* 389 (2017): 847-860.
- Torre L A, *et al.* "Global cancer incidence and mortality rates and trends — an update". *Cancer Epidemiology, Biomarkers and Prevention* 25 (2016): 16-27.
- Loney T, *et al.* "An analysis of the health status of the United Arab Emirates: the 'Big 4' public health issues". *Global Health Action* 6 (2013): 20100.
- Harbeck N, *et al.* "Breast cancer". *Nature Reviews Disease Primers* 5 (2019): 66.
- Holt CP. "The scope of the UAE cancer problem". *Emirates Medical Journal* 3.3 (1985): 163-166.
- Al-Shamsi H and S Alrawi. "Breast cancer screening in the United Arab Emirates: is it time to call for a screening at an earlier

- age?" *Journal of Cancer Prevention and Current Research* 9.3 (2018): 123-126.
9. Radwan H., *et al.* "The epidemiology of cancer in the United Arab Emirates: Systematic Review". *Medicine* 97.50 (2018).
 10. Mahate A and Hamidi S. "Frontier efficiency of hospitals in United Arab Emirates: an application of data envelopment analysis". *Journal of Hospital Administration* 5.1 (2015): 7-17.
 11. Boumahdi S and de Sauvage FJ. "The great escape: tumour cell plasticity in resistance to targeted therapy". *Nature Reviews Drug Discovery* 19.1 (2020): 39-56.
 12. Galletti G., *et al.* "Mechanisms of resistance to systemic therapy in metastatic castration-resistant prostate cancer". *Cancer Treatment Reviews* 57 (2017): 16-27.
 13. Harrington K., *et al.* "Optimizing oncolytic virotherapy in cancer treatment". *Nature Reviews Drug Discovery* 18.9 (2019): 689-706.
 14. Riesco-Martinez M., *et al.* "Resistance to metronomic chemotherapy and ways to overcome it". *Cancer Letter* 400 (2017): 311-318.
 15. Zhang H., *et al.* "Recombinant oncolytic adenovirus expressing a soluble PVR elicits long-term antitumor immune surveillance". *Molecular Therapy - Oncolytics* 20 (2020): 12-22.
 16. Yeung KS., *et al.* "Herb-Drug Interactions in Cancer Care". *Oncology (Williston Park)* 32.10 (2018): 516-520.
 17. Singh D., *et al.* "Herbs-are they safe enough? An overview". *Critical Reviews in Food Science and Nutrition* 52.10 (2012): 876-898.
 18. Boon H and Wong J. "Botanical medicine and cancer: a review of the safety and efficacy". *Expert Opinion on Pharmacotherapy* 5.12 (2004): 2485-2501.
 19. Werneke U., *et al.* "Potential health risks of complementary alternative medicines in cancer patients". *British Journal of Cancer* 90.2 (2004): 408-413.
 20. Haefeli WE and Carls A. "Drug interactions with phytotherapeutics in oncology". *Expert Opinion on Drug Metabolism and Toxicology* 10.3 (2014): 359-377.
 21. Solowey E., *et al.* "Evaluating medicinal plants for anticancer activity". *Scientific World Journal* 2014 (2014): 721402.
 22. Yao S., *et al.* "Development and evaluation of novel tumor-targeting paclitaxel-loaded nano-carriers for ovarian cancer treatment: in vitro and in vivo". *Journal of Experimental and Clinical Cancer Research* 37 (2018): 29.
 23. Izzo AA and Ernst E. "Interactions between herbal medicines and prescribed drugs: a systematic review". *Drugs* 61.15 (2001): 2163-2175.
 24. SBM Ahmed., *et al.* "Studying the ShcD and ERK interaction under acute oxidative stress conditions in melanoma cells". *The International Journal of Biochemistry and Cell Biology* 112 (2019): 123-133.
 25. Ovadje P., *et al.* "Advances in the research and development of natural health products as main stream cancer therapeutics". *Evidence-based Complementary and Alternative Medicine* (2015): 751348.
 26. Wang Y., *et al.* "Antitumor effects of immunity-enhancing traditional Chinese medicine". *Biomed Pharmacotherapy* 121 (2020): :109570.
 27. Omara T., *et al.* "Medicinal Plants Used in Traditional Management of Cancer in Uganda: A Review of Ethnobotanical Surveys, Phytochemistry, and Anticancer Studies". *Evidence-based Complementary and Alternative Medicine* 2020 (2020): 3529081-3529081.
 28. BM El-Haj and S Ahmed. "Metabolic-Hydroxy and Carboxy Functionalization of Alkyl Moieties in Drug Molecules: Prediction of Structure Influence and Pharmacologic Activity". *Molecules* 25.8 (2020): 1937.
 29. Yuan H., *et al.* "The Traditional Medicine and Modern Medicine from Natural Products". *Molecules (Basel, Switzerland)* 21.5 (2015): 559.
 30. Zorofchian Moghadamtousi S., *et al.* "Annona muricata leaves induce G₁ cell cycle arrest and apoptosis through mitochondria-mediated pathway in human HCT-116 and HT-29 colon cancer cells". *Journal of Ethnopharmacology* 156 (2014): :277-289.

31. Siti Mariam., *et al.* "Exploring the Leaves of *Annona muricata* L. as a Source of Potential Anti-inflammatory and Anticancer Agents". *Frontiers in Pharmacology* 9 (2018): :661.
32. Syed Najmuddin SU., *et al.* "Anti-cancer effect of *Annona Muri-cata* Linn Leaves Crude Extract (AMCE) on breast cancer cell line". *BMC Complement Alternative Medicine* 16.1 (2016): 311.
33. Joo D., *et al.* "*Annona muricata* L. extracts decrease melanogenesis in B16F10 mouse melanoma cells". *Biomed Dermatology* 1 (2017): 10.
34. George VC., *et al.* "Quantitative assessment of the relative anti-neoplastic potential of the n-butanolic leaf extract of *Annona muricata* Linn. in normal and immortalized human cell lines". *Asian Pacific Journal of Cancer Prevention* 13.2 (2012): 699-704.
35. Yu-Min Koa., *et al.* "Annonacin induces cell cycle-dependent growth arrest and apoptosis in estrogen receptors- α -related pathways in MCF-7 cells". *Journal of Ethnopharmacology* 137.3 (2011): : 1283-1290.
36. Wang B., *et al.* "Novel PEG-graft-PLA nanoparticles with the potential for encapsulation and controlled release of hydrophobic and hydrophilic medications in aqueous medium". *International Journal of Nanomedicine* 6 (2011): :1443-1451.
37. Wicki A., *et al.* "Nanomedicine in cancer therapy: challenges, opportunities, and clinical applications". *Journal of Control Release* 200 (2015): 138-157.
38. Marchetti C., *et al.* "Targeted drug delivery via folate receptors in recurrent ovarian cancer: a review". *OncoTargets Therapy* 7 (2014): 1223-1236.
39. Fang J., *et al.* "The EPR effect: unique features of tumor blood vessels for drug delivery, factors involved, and limitations and augmentation of the effect". *Advanced Drug Delivery Reviews* 63 (2011): 136-151.
40. Sun XL., *et al.* "Improved tumor uptake by optimizing liposome based RES blockade strategy". *Theranostics* 7 (2017): 319-28.
41. Imran Ali., *et al.* "Advances in nanoparticles as anticancer drug delivery vector: Need of this century". *Current Pharmaceutical Design* 26 (2020): 1637-1649.
42. BM El-Haj., *et al.* "Linking Aromatic Hydroxy Metabolic Functionalization of Drug Molecules to Structure and Pharmacologic Activity". *Molecules* 23.9 (2018): 2119.
43. Zhang X., *et al.* "*Rabdosiarubescens* Linn: green synthesis of gold nanoparticles and their anticancer effects against human lung cancer cells A549". *Artificial Cells* 47.1 (2019): 2171-2178.
44. K Rao., *et al.* "Gum tragacanth stabilized green gold nanoparticles as cargos for Naringin loading: A morphological investigation through AFM". *Carbohydrate Polymer* 174 (2017): 243-252.
45. Imran M., *et al.* "Glycoside-based niosomal nanocarrier for enhanced in-vivo performance of Cefixime". *International Journal of Pharmaceutics* 505.1-2 (2016): 122-132.
46. SBM Ahmed., *et al.* "A nuclear export signal and oxidative stress regulate ShcD subcellular localisation: A potential role for ShcD in the nucleus". *Cellular Signalling* 26.1 (2014): 32-40.
47. Sun B., *et al.* "Anticancer activity of green synthesised gold nanoparticles from *Marsdeniadenacissima* inhibits A549 cell proliferation through the apoptotic pathway". *Artificial Cells* 47.1 (2019): 4012-4019.
48. Sharma D., *et al.* "Biogenic synthesis of nanoparticles: A review". *Arabian Journal* 8 (2019): 3576-3600.
49. Botteon CEA., *et al.* "Biosynthesis and characterization of gold nanoparticles using Brazilian red propolis and evaluation of its antimicrobial and anticancer activities". *Scientific Report* 11 (2021): 1974.
50. Sarvamangala D., *et al.* "Green synthesis of AgNP'S using *Alternanthera Sessilis* leaf extract [a natural source for ocular therapy]". *International Journal of Innovative Science Engineering and Technology* 3 (2014): 15000-15010.
51. Bhau BS., *et al.* "Green synthesis of gold nanoparticles from the leaf extract of *Nepenthes khasiana* and antimicrobial assay". *Advanced Materials Letters* 6 (2015): 55-58.
52. I Ali., *et al.* "Preliminary investigation of novel tetra-tailed macrocycle amphiphile based nano-vesicles for amphotericin B improved oral pharmacokinetics". *Artificial Cells, Nanomedicine, and Biotechnology* 46 (2017): S1204-S1214.

53. Sharma D., *et al.* "Biogenic synthesis of nanoparticles: a review". *Arabian Journal of Chemistry* 12.8 (2019): 3576-3600.
54. Shukla R., *et al.* "Biocompatibility of gold nanoparticles and their endocytotic fate inside the cellular compartment: a microscopic overview". *Langmuir* 21 (2005): 10644-10654.
55. Dhas TS., *et al.* "Sargassum myriocystum mediated biosynthesis of gold nanoparticles". *Spectrochimica Acta, Part A: Molecular and Biomolecular Spectroscopy* 99 (2012): 97-101.
56. Heyam Saad Ali., *et al.* "Gold nanoparticles in cancer diagnosis and therapy". Book: Metal Nanoparticles for Drug Delivery and Diagnostic Applications 43-58.
57. Vijayan R., *et al.* "Indigofera tinctoria leaf extract mediated green synthesis of silver and gold nanoparticles and assessment of their anticancer, antimicrobial, antioxidant and catalytic properties". *Artificial Cells* 46 (2018): 861-871.
58. Ahmed SBM and Prigent SA. "Insights into the Shc family of adaptor proteins". 12 (2017): 1-17.
59. Fahradyan A., *et al.* "Updates on the Management of Non-Melanoma Skin Cancer (NMSC)". *Healthcare (Basel)* 5 (2017): 82.
60. Chen JS., *et al.* "Inhibition mechanism of koji acid on polyphenol oxidase". *Journal of Agricultural and Food Chemistry* 58 (1991): 79-110.
61. Wang L., *et al.* "Green synthesis of gold nanoparticles from *Scutellaria barbata* and its anticancer activity in pancreatic cancer cell (PANC-1)". *Artificial Cells* 47.1 (2019): 1617-1627.

Volume 5 Issue 9 September 2021

© All rights are reserved by Heyam Saad Ali., *et al.*