VERTICAL PILLAR ARRAYS AS PLASMON NANOCAVITIES

Mihail Bora*, Benjamin J. Fasnfest, Elaine M. Behymer, Allan S-P Chang, Hoang T. Nguyen, Jerry A. Britten, Cindy C. Larson, Tiziana C. Bond*

Lawrence Livermore National Laboratory, Livermore CA, USA

ABSTRACT

We investigate tunable plasmon resonant cavity arrays in paired parallel nanowire waveguides. Resonances are observed when the waveguide length is an odd multiple of quarter plasmon wavelengths, consistent with boundary conditions of node and antinode at the ends. Two nanowire waveguides satisfy the dispersion relation of a planar metal-dielectric-metal waveguide of equivalent width equal to the square field average weighted gap. Confinement factors over 10^3 are possible due to plasmon focusing in the inter-wire space.

Surface plasmons, charge density waves propagating along metal-dielectric interfaces are applied in bio-molecular detection,[1-3] sub-wavelength optics[4-6] and photovoltaic technology.[7-9] Different geometries have been employed to study plasmonic structures. Horizontal layer approach provides excellent thickness control, but results in fewer plasmonic nanostructures per unit area.[10] The vertical structures provide good coverage, but require complex fabrication and are less amenable to large area substrates.[11] Here we propose fabrication of tunable plasmon resonant cavities in vertical wire arrays that combines the benefits of both approaches providing high density and good control over the cavity size over a large area (4 inch wafer) uniform plasmonic substrate. Tuning of the plasmon resonance in the 500-800 nm range is demonstrated by controlling the geometrical dimensions of the cavity. Future applications for the nano-cavities are envisioned in high sensitivity Raman spectroscopy[12,13] that requires high local electromagnetic fields and alignment between the plasmon resonance and excited and scattered light. The tunable nanocavity is of particular relevance for fabrication of plasmonic lasers which use surface plasmons instead of light to pump the lasing medium. [14,15] Since the device structure relies on vertical free standing nano-wires the plasmonic cavity region can be filled with any material of choice. In addition to the high confinement factors shown, the cavity plasmon resonance can be adjusted for maximum overlap with the absorbance of the active material.

The resonant cavity relies on paired nanowire waveguides that supports propagation of gap plasmon modes[16,17] (Figure 1a) when the separation is less than 50 nm. The cavity is delimited by a reflective metallic mirror at one side and an open end on the other for a more effective incident light-plasmon coupling. [18] Resonances occur when the cavity length is an odd multiple of quarter plasmon wavelengths due to boundary conditions of node at the mirror and anti-node at the open end. A two dimensional rectangular array of vertical resonant cavities is fabricated on a planar substrate (Figure 1b-e). Each nanowire is surrounded by four closest neighbors corresponding to two resonant cavities per nanowire, for a density of $3.85 \cdot 10^8$ cavities/cm². The vertical wire geometry enables large area fabrication (Figure 1c) and far field optical characterization. No inter-coupling between cavities is expected in these structures, since the size of the nanowires is an order of magnitude larger than the penetration depth of the electric field in the metal.

Photoresist wire arrays are patterned on a fused silica substrate using laser interference lithography under conditions described previously. [19] The pattern was transferred on the silica substrate by reactive ion etching. The silica nanowires are

coated with alumina by atomic layer deposition so that inter-wires gap is approximately 75 nm. Since the alumina deposition is self limiting, the thickness can be increased in conformal single molecule layer steps. Finally, a 20-40 nm thick gold coating was deposited by sputtering until the edge to edge distance between adjacent wires approaches 20-40 nm.

Figure 1. Vertical nanowire array substrate. (a) Single plasmon resonant cavity based on a two-nanowire waveguide. The separation medium is air of dielectric permittivity 1. Nanowire thickness is approximately 340 nm, and the height ranges from 250 to 1000 nm. The wavevector of the incident light is oriented along the waveguide in the transverse magnetic mode (b) Rectangular array of cavities on a planar substrate. Arrows indicate the lattice vectors of the array. (c) Large area fabrication of the plasmon nanocavities on a four-inch diameter substrate. (d) Side view of photoresist nanowires fabricated by laser interference lithography. (e) Top view of metallic nanowire cavity array coated with gold. The wire center-to-center distance is 360 nm and the edge to edge gap is 35 nm.

The two nanowire plasmon waveguide properties can be explained using an underlying planar metal-dielectric-metal (MDM) waveguide that is composed of two semi-infinite metal volumes separated by a dielectric of finite thickness (Figure 2, inset). The MDM waveguide is sufficiently simple to allow an analytical calculation of the dispersion curve based on the geometry and materials dielectric properties.

The two nanowire waveguide is approximated as an MDM waveguide of effective width w_{eff} that is calculated using the appropriate gap weighting metric. For example, for the optical extinction coefficient, the effective width is equal to the gap weighted with the square average of the field strength. The technique of decomposing the two nanowire waveguide into a continuum of elementary planar waveguides can be extended to other geometries providing a straightforward way to calculate the dispersion of arbitrary shape waveguides (e.g. wedges, grooves).

Figure 2. Planar MDM waveguide. Dispersion relations for the gold-air-gold (MDM) symmetric plasmon for different air thicknesses. The numbers near the curves indicate the width of the dielectric (air). For incident light along the waveguide of frequency ω_{ex} , plasmon modes of the same frequency and wavevector given by dispersion curve are excited. Inset: schematic representing the MDM waveguide. The plasmon modes are excited by light propagating with wavevector k , along the planar waveguide with the electric field vector E , perpendicular to the metal sidewall.

Dispersion relations for MDM plasmons are determined by solving for propagating modes along the waveguide under continuity conditions at metal dielectric boundaries while satisfying Maxwell's equations. [20,21] The MDM solutions degenerate into symmetric and anti-symmetric modes, defined by the parity of the electric field in the direction perpendicular to the dielectric sheet, with respect to the mid-plane. Single interface surface plasmon modes are recovered when the separation is increased beyond the evanescent decay length.

The plasmon degeneracy can be understood in the plasmon hybridization model [22] in which the MDM plasmon is decomposed into two interacting single metal interface plasmons. The low energy or “bonding” state corresponds to the symmetric mode and the high energy or “anti-bonding” state to the anti-symmetric mode.

The coupling efficiency between light and MDM plasmons is proportional with the spatial and temporal overlap of the modes [23]:

$$\eta = \frac{\langle H_{plasmon} | H_{photon} \rangle^2}{|H_{plasmon}|^2 \cdot |H_{photon}|^2} \quad (1)$$

where η is the coupling efficiency and $H_{plasmon}$ and H_{photon} are the field profiles for the plasmon and electromagnetic plane wave excitation modes. The electric field of the incident light is constant across the gap (symmetric) if the dielectric width is much smaller than the light wavelength; hence, the coupling efficiency is non-zero only for the symmetric mode.

The dispersion relation for the symmetric mode is given by the equation:[20]

$$\tanh\left(ik_{\perp}^d \frac{w}{2}\right) = -\frac{\epsilon_d k_{\perp}^m}{\epsilon_m k_{\perp}^d} \quad (2)$$

where $k_{\perp}^d$ and $k_{\perp}^m$ are the perpendicular components of the

plasmon wavevector in the dielectric and metal, ϵ_d and ϵ_m are the relative permittivities for the dielectric and metal, respectively, and w is the width of the dielectric sheet. In Figure 2, the dispersion relations for gold-air-gold waveguides of different air thicknesses are plotted. The dielectric function of gold is based on a Drude model fit for the published optical constants of gold.[24]

Figure 3. (a) Two-nanowire plasmon resonant cavity. The incident light field is oriented normal to the side surface of the wires (transverse magnetic mode). (b) Numerical simulations of the electric field as viewed from the front, top and side directions. (c) Resonances of order 2 and 3 and 4 are observed at 800, 650 and 565 nm.

Two different cavity types are analyzed. The first, the MDM slot waveguide, is a rectangular groove of height h and width w and infinite length indented in a semi-infinite metallic volume. This ideal structure allows direct comparison with the exact analytical dispersion relation calculated above for the MDM waveguide. The second case considered is a vertical wire nanocavity, composed of two metallic cylinders separated by a small distance (Figure 3a). The plasmonic features of vertical wire nanocavity are similar to those of the MDM slot waveguide, both showing resonances when the length of the cavity is an odd multiple on quarter plasmon wavelengths. Furthermore, the two nanowire waveguide satisfies the dispersion relation a modified planar MDM waveguide.

The two cavities are modeled as a waveguide of finite length, delimited by a metallic interface at the bottom and dielectric on top. Plasmon MDM type modes are excited by light normally incident on the open end side of the cavity. The photon field

overlaps with the plasmon cavity over a thin region with a thickness comparable to the skin depth of gold. The free electrons in the metal oscillate with the excitation light frequency ω_{ex} and plasmon waves with wavevector given by the dispersion relation calculated in Equation 2 propagate along the waveguide. On the closed metallic end, a reflection with a π phase shift occurs and a plasmonic standing wave forms along the waveguide.

The structure resonant features are derived from the boundary conditions at the metal mirror (anti-node) and open dielectric side (node):

$$kh = \pi \left(m + \frac{1}{2} \right) \quad (3)$$

where k is the plasmon wavevector along the inter-wire region, h is the wire height, and $m = 0, 1, 2, \dots$ is the resonance order. The plasmon states for which the wavevector satisfies the resonance condition in Equation 3 couple more strongly with the incident light and have a higher extinction coefficient, resulting in minima in the reflection spectrum.

A three-dimensional simulation of the two nanowire cavity is compared with the MDM slot model (Figure 3). Similar characteristics are observed for the electric field profile, and absorbance spectrum. As in the previous simulations the plasmon modes are excited by transverse magnetic normal incident light. Resonances are observed when the height of the wire is an odd multiple of quarter plasmon wavelengths. The plasmon modes are strongly confined to the inter-wire space where the amplitude of the electric field is two orders of magnitude larger than in the rest of the structure.

The MDM slot model predicts the optical properties of the two nanowire cavity when the equivalent spacing is taken into account. The effective distance between the wires can be calculated using coupling mode theory (Equation 1). Assuming that both photon and plasmon magnetic fields are normalized to unity and that the photon field is nearly constant across the gap, the coupling efficiency at each point along the y axis, is proportional to:

$$\eta_{(y_0)} \propto \left(\int_{y=y_0} H_{\text{plasmon}}^y dx dz \right)^2 \quad (4)$$

where H_{plasmon}^y is the y component of the plasmon magnetic field (x and z components are null). The coupling efficiency between photons and plasmons is therefore proportional to the square of the field average. Based on coupling mode theory argument presented above, we can calculate the effective separation of two adjacent cylinders as the average width weighted by the metric described earlier. This key finding allows derivation of the dispersion relation of complex plasmonic waveguides using a much simpler planar waveguide. Although outside the inter-wire region the cylindrical geometry deviates from the parallel interface model, 90% of the total electromagnetic field is concentrated in a circular sector with a ± 12 degrees opening. For the dimensions fabricated array (wire center-to-center distance of 360 nm), the effective width is approximately two times the edge to edge wire distance (15-35 nm).

The two-nanowire plasmons are confined in both lateral dimensions; along the direction normal to the wire surface the confinement is determined by the charge screening of the electric field in the metal layer. The confinement in the second orthogonal lateral direction results from the formation of a plasmon energy trap. Opposite polarity surface charges of the symmetric mode

minimize the dipole interaction energy when the distance is shortest. Since the effective MDM waveguide separation is increasing rapidly away from the inter-wire region, a strong energy gradient will focus the plasmons in the inter-wire space. This self-confinement feature makes the two wire plasmonic waveguides ideal candidates for high density plasmonic interconnects since the packaging density is increased significantly. Three dimensional sub-wavelength confinement becomes possible if the cavity length is smaller than the wavelength of the excitation light. For the 250 nm tall cavities we estimate the confinement factor to be approximately 1800.

Figure 4. Normalized reflectivity plots for wire array of height 250, 500, 750 and 1000 nm. Incident light is non-polarized and perpendicular to the substrate. The reflectivity minima correspond to nanocavity excitation of plasmon resonances labeled by their order m .

The nanowire cavity array substrates were optically characterized by measuring the wavelength dependent normal incidence reflectivity. The plots were normalized to a 100 nm thick gold film to account for material specific absorbance (Figure 4). Excitation of plasmons within the cavity increases the extinction coefficient of the substrate and resonances are observed as minima in the reflectivity data. The cavity order was identified using numerical simulations and the analytical expression of the dispersion curve.

The plasmon wavelength can be calculated from Equation 3, knowing the cavity length and cavity order. The resonances measured in the experimental reflectivity are compared with numerical simulations to determine the resonance order and to calculate the plasmon wavevector. Further, the wavevector and frequency points are plotted along the dispersion curve for the MDM waveguide (Figure 5) from the analytical expression in Equation 2, using a separation value that best fitted the data. The good agreement between the analytical calculation of dispersion relation, numerical simulation of electric field and absorbance, and experimental data reflectivity show that the two-nanowire plasmon nanocavity can be approximated using a variable width MDM waveguide. The nanowire geometry allows for a stronger confinement resulting in higher fields and quality factors.

In conclusion, we demonstrate plasmonic resonant cavities that are supported along a two nanowire waveguide. Three dimensional subwavelength confinement is realized by adjusting the longitudinal length of the cavity for lower order resonance, and by focusing the plasmon modes between two adjacent wires in an energy gradient. Confinement factors over of 10^3 are realized for the 1st order resonance of the 250 nm tall cavity considered,

however this factor can be increased to considerably larger values using smaller height and diameter wires and shorter wavelength excitation light.

Figure 5. Analytical and experimental dispersion relations. Solid blue curve: analytical calculation based on MDM infinite waveguide using an effective gap separation. Blue circles: experimental points calculated from the 1000 nm tall wire reflectivity measurements.

We have also shown that the optical properties of complex plasmonic structures (e.g. two-nanowire waveguides) can be derived from elementary structures (MDM planar waveguide) by using a squared field average weight for the effective geometrical dimensions. The high electric field in the cavity and the tunability of the plasmon resonance with height and separation make cavity based substrates promising candidates for surface enhanced Raman spectroscopy and plasmonic lasers.

ACKNOWLEDGEMENTS

This work performed under the auspices of the U.S. Department of Energy by Lawrence Livermore National Laboratory under Contract DE-AC52-07NA27344. LLNL-PROC-427303.

REFERENCES

- [1] L.R. Hirsch, J.B. Jackson, A. Lee, N.J. Halas, J. West, "A whole blood immunoassay using gold nanoshells", *Analytical Chemistry*, 75, 2377, (2003).
- [2] R.L. Rich, D.G. Myszka, "Advances in surface plasmon resonance biosensor analysis", *Current Opinion in Biotechnology*, 11, 54, (2000)
- [3] M. Bora, K. Celebi, J. Zuniga, C. Watson, K.M. Milaninia, M.A. Baldo, "Near field detector for integrated surface plasmon resonance biosensor applications", *Optics Express*, 17, 329, (2009).
- [4] W.L. Barnes, A. Dereux, T.W. Ebbesen, "Surface plasmon subwavelength optics", *Nature*, 424, 824, (2003).
- [5] H.F. Ghaemi, T. Thio, D.E. Grupp, T.W. Ebbesen, H.J. Lezec, "Surface plasmons enhance optical transmission through subwavelength holes", *Physical Review B*, 58, 6779, (1998).
- [6] H. J. Lezec, A. Degiron, E. Devaux, R.A. Linke, L. Martin-Moreno, F.J. Garcia-Vidal, T.W. Ebbesen, "Beaming light from a subwavelength aperture", *Science*, 297, 820, (2002).
- [7] A.J. Morfa, K.L. Rowlen, T.H. Reilly, M.J. Romero, J. van de Lagemaat, "Plasmon-enhanced solar energy conversion in organic bulk heterojunction photovoltaics", *Applied Physics*

- Letters, 92, (2008).
- [8] K. Tvingstedt, N.K. Persson, O. Inganas, A. Rahachou, I.V. Zozoulenko, "Surface plasmon increase absorption in polymer photovoltaic cells", *Applied Physics Letters*, 91 (2007).
- [9] M. Westphalen, U. Kreibig, J. Rostalski, H. Luth, D. Meissner, "Metal cluster enhanced organic solar cells", *Solar Energy Materials and Solar Cells*, 61, 97, (2000).
- [10] H.T. Miyazaki, Y. Kurokawa, "Controlled plasmon resonance in closed metal/insulator/metal nanocavities", *Applied Physics Letters*, 89, (2006).
- [11] C.L. Haynes, R.P. Van Duyne, "Nanosphere lithography: A versatile nanofabrication tool for studies of size-dependent nanoparticle optics", *Journal of Physical Chemistry B*, 105, 5599, (2001).
- [12] C.L. Haynes, R.P. Van Duyne, "Plasmon-sampled surface-enhanced Raman excitation spectroscopy", *Journal of Physical Chemistry B*, 107, 7426, (2003).
- [13] A.M. Michaels, M. Nirmal, L.E. Brus, "Surface enhanced Raman spectroscopy of individual rhodamine 6G molecules on large Ag nanocrystals", *Journal of the American Chemical Society*, 121, 9932, (1999).
- [14] M. Noginov, G. Zhu, A. Belgrave, R. Bakker, V. Shalaev, E. Narimanov, S. Stout, E. Herz, T. Suteewong, U. Wiesner, "Demonstration of a spaser-based nanolaser", *Nature*, 460, 1110, (2009).
- [15] R.F. Oulton, V.J. Sorger, T. Zentgraf, R.M. Ma, C. Gladden, L. Dai, G. Bartal, X. Zhang, "Plasmon lasers at deep subwavelength scale", *Nature*, 461, 629, (2009)
- [16] A. Manjavacas, F.J.G. de Abajo, "Robust Plasmon Waveguides in Strongly Interacting Nanowire Arrays", *Nano Letters*, 9, 1285, (2009).
- [17] A. Manjavacas, F.J.G. de Abajo, "Coupling of gap plasmons in multi-wire waveguides", *Optics Express*, 17, 19401 (2009).
- [18] G.I. Stegeman, R.F. Wallis, A.A. Maradudin, "Excitation of surface polaritons by end-fire coupling", *Optics Letters*, 8, 386, (1983).
- [19] A. Fernandez, H.T. Nguyen, J.A. Britten, R.D. Boyd, M.D. Perry, D.R. Kania, A.M. Hawryluk, "Use of interference lithography to pattern arrays of submicron resist structures for field emission flat panel displays", *Journal of Vacuum Science & Technology B*, 15, 729, (1997).
- [20] J.A. Dionne, L.A. Sweatlock, H.A. Atwater, A. Polman, "Plasmon slot waveguides: Towards chip-scale propagation with subwavelength-scale localization", *Physical Review B*, 73, (2006).
- [21] H.J. Lezec, J.A. Dionne, H.A. Atwater, "Negative refraction at visible frequencies", *Science*, 316, 430, (2007).
- [22] E. Prodan, C. Radloff, N.J. Halas, P. Nordlander, "A hybridization model for the plasmon response of complex nanostructures", *Science*, 302, 419, (2003).
- [23] Z.J. Sun, D.Y. Zeng, "Coupling of surface plasmon waves in metal/dielectric gap waveguides and single interface waveguides", *Journal of the Optical Society of America B-Optical Physics*, 24, 2883, (2007).
- [24] P.B. Johnson, R.W. Christy, "Optical constants of noble metals", *Physical Review B*, 6, 4370, (1972).

CONTACT

*M. Bora, tel +1-925-423-2042; bora1@llnl.gov

*T. Bond, tel +1-925-423-2205; bond7@llnl.gov