Volume 7 Issue 2 2021

ISSN 2454-3055

**INTERNATIONAL
JOURNAL OF
ZOOLOGICAL
INVESTIGATIONS**

***Forum for Biological and
Environmental Sciences***

Published by Saran Publications, India

Nanofiber Based Dressing Material Mechanism in Wound Healing Property

Ashok K.^{1*}, Babu M.¹, Sankar A.² and Anandan P.²

¹Department of Microbiology and Biotechnology, School of Basic Sciences, Bharath Institute of Higher Education and Research (BIHER), Chennai, Tamil Nadu, India

²Department of General Medicine, Sree Balaji Medical College and Hospital, Bharath Institute of Higher Education and Research (BIHER), Chennai, Tamil Nadu, India

*Corresponding Author

Received: 9th November, 2021; **Accepted:** 14th December, 2021; **Published online:** 22nd December, 2021

<https://doi.org/10.33745/ijzi.2021.v07i02.086>

Abstract: Nanofibers constitute a kind of nanostructure that may be used in wounds, and electrospinning, due to its specific properties. Wound dressings made up of electrospun nanofibers are built with a large volume to surface ratio, high wound absorption and permeabilities of high air, morphological extracellular tissue matrices and the possibility to gradually remove nanofibers. The interest in plant use is increasing because of plant adjustment to the body, poor side effects and an increase in antibiotic resistance. Because of its application in recent years in electrospinning and the manufacturing of nano-fibric plants, several plants have been utilised for extracts, essential oils and pure active chemicals.

Keywords: Nanofibers, Plant cellulose, Electrospinning, Wound healing

Citation: Ashok K. , Babu M., Sankar A. and Anandan P.: Nanofiber based dressing material mechanism in wound healing property. Intern. J. Zool. Invest. 7(2): 949-954, 2021.

<https://doi.org/10.33745/ijzi.2021.v07i02.086>

Introduction

Nanofibre may be defined in the terms "nano-" and "fibre". Fibers are defined as natural or synthetic filament by the textile industry as cotton or nylon which may be spun into yarn. A "fibre" is defined as a slim, elongated, threaded item or structure from a geometrical point of view (Leung *et al.*, 2011; Charernsriwilaiwat *et al.*, 2012; Ngygen *et al.*, 2013; Rieger *et al.*, 2013; Xie *et al.*, 2013). Technically, the term "nano" refers to the unit dimension by one billionth. Nanofiber is often a word used for fibres between 50 and 300 nanometers in diameter. Nanotechnology is the

science concerned with the study within the dimensional range of 1 – 100 nm of the phenomena and functions of matter (Bui *et al.*, 2014; Kataria *et al.*, 2014). A nano-meter abbreviated as nm, is a long-term unit in comparison to a macro material, measurements of a milliard of a metre of peculiar, unique features of nano-material (Heydary *et al.*, 2015). These materials showed novel features from the smallest dimensions that have become unique mechanical, thermal, biological, optical, magnetic, and electrical characteristics (Heydary *et al.*, 2015).

Nano materials are presently being investigated in many domains, for example self-assembling and thin films, quantum points, nanoparts, nanoparticles, nanoparticles and nanofoams (Hassiba *et al.*, 2016; Rath *et al.*, 2016; Chen *et al.*, 2017; Sarhan and Azzazy, 2017). Nano-fibre technologies included in several applications, such as cells and batteries, condensers, transistors and diodes, energy transfer systems, aerospace composites, drug delivery and tissue engineering (Liu *et al.*, 2017). Nano-fiber technology is a nanotechnology area whose main goal is to produce materials as nanoscale fibres to obtain higher functionalities (Deldar *et al.*, 2018). The unique combination of high-specific surface area, flexibility and excellent directional strength means that such fibres are the favourite materials for many applications, from apparel to aerospace structural reinforcement. It has long been understood that fibre diameter impacts on fibrous structure performance and process capability (Fayemi *et al.*, 2018). Nearly a decade ago, several experts such as Professor Parallel Reneker promoted the technology of electronic spinning (Alipour *et al.*, 2019).

Nano-fibres such as self-assembly templates, separation phases, meltdown and electro-spinning have now been created for different ways (Ajmal *et al.*, 2019). Electro-spinning is now the most promising technology for producing nano-fibers on a wide scale and can be modified from nanometers to microns in terms of their fibre diameter (Bayat *et al.*, 2019). Electrical spinning is also a reasonably simple and quick technique for nanofibre-making (Fereydouni *et al.*, 2019). Although the first electro-spinning patent was published in 1934, it was not until recently that method was properly developed (Memici *et al.*, 2019; Jatoi *et al.*, 2019; Wali *et al.*, 2019; Zhang *et al.*, 2019; He *et al.*, 2020). Electro-spinning is technically used to draw a polymer liquid into the filament by use of a strong electrical field. Although various other technologies for the production of fibres are present on a nanometer scale, the use of nano is primarily owing to the

simplicity of the electric spinning process (Jackson *et al.*, 2020; Najafiasl *et al.*, 2020; Abolghasemzade *et al.*, 2021; Agarwal *et al.*, 2021; Ahmed *et al.*, 2021; Augustine *et al.*, 2021). Polymer melt or solution allows electro-spinning. Structures and characteristics of the fibres are then checked using the electro-spinning process (Al-Wafi *et al.*, 2021; Basaran *et al.*, 2021). A large number of applications have been found, including filtration, biomedical energy storage, electronics and multi-function structure composites, recognising that the particular surfaces of fibre are increasing enormously. Chitosan is a carbohydrate produced from chitin; behind cellulose, Chitin is the second largest polysaccharide in the world. Amino group might be protonated in the structure of Chitosan (Campa-Siqueiros *et al.*, 2021; Dos santos *et al.*, 2021; Gao *et al.*, 2021; Gok *et al.*, 2021; Mistry *et al.*, 2021; Prakash *et al.*, 2021; Ramalingam *et al.*, 2021; Xuan *et al.*, 2021). A number of outstanding characteristics of chitosan presented unique potential for biomedical applications to provide solubility in acidic water diluted solution. Chitosan has been elucidated for medicinal and pharmacological interests. Chitosan's haemostasis can also be linked to positive charge for the chitosan backbone.

Wounds are serious diseases that impair everyone's quality of life. The expense and hospitalisation of an efficient, fast-training treatment can be reduced, but the intricacy of skin tissue structure still makes an optimal medication problematic. Despite the recent developments in wound management and new medicines for wound-treatment and skin-regeneration, traditional methods based on herbal and natural therapy are still well-known for their versatility, easiness of access, and limited side-effects and low cost as promising alternative treatments. Some examined the function of biomaterials of animal origin, and others focused on biomaterials based on plant, but not on nanosized scales. These researches have shown the potential of such natural compounds. In a recent review, the effectiveness of chemicals of natural origin

combined with the conventional wound dressings were revealed. In addition, in their study we have looked at the effect of herbal medicines in therapy of various wounds while the chemicals investigated are not nanoscale. This study initially dealt with the concerns of the nanosizing technique for herbal natural components and the mechanistic assessment of the existing herbal nanoformulations for wound dressing. In reality, this review offered a complete analysis of both engineering and mechanistic nanoformulations of herbal origin for wound treatment, whereas there is presently no such review paper accessible in the literature.

In the growth and appearance of nanosciences and technology, the effectiveness of various medicines and herbal items may be improved. The inconveniences of ordinary medications, a clever process of cures, the regulations of therapy release, the reductions in dosages necessary for treatment and a unique possibility to assist cures even in chronic wounds have been promised in recent years by nano-structurings and nanoformulations. In the presence or absence of synthetic materials, several methods of nanoformulation have been traditionally utilised to produce plant-based nanostructures. Electrospinning offers wound dressings successfully, which incorporate herbal components as the basis for the application. Together with many additional advantages, such as the ability of incorporating various kinds of material, the well-regulated porosity and comparable nature of the electrospun nanofibers make it suitable for wound handling. According to the literary study, the adherence, proliferation and differentiation to fibroblast and keratinocytes are largely facilitated by plant-based nanofibers. This may be because the pore shape and promising permeability and humidity conservation of those herbal nanostructures offer an excellent micro-environment. The ability to co-spin herbal compounds and other biomaterials combine the advantages of all the ingredients are another benefit of these nanostructures. A Greens and

cost-effective technique has generated a set of nanostructures with outstanding bacterial and antibiotic activity in the application of medicinal plants and their extracts to make metal-based biocompatible nanoparticles.

Different plant-mediated nanoparticles show the capacity to prevent and extend the consequences of bacterial colonisation. According to literature, the impregnation of herbal compounds in nanoparticulates, nanoemulsion, nanoliposomes, hydrogels and so on is one of the most effective methods to improve availability of these products, to control their release into the wound by means of a sustained supply system and to increase their permeability even to underlying layers of the skin. Inflammatory phase control may be done by decreasing inflammatory reactions, NF- κ B inhibition, inflammation pathways (intracellular transcription and transduction) and pro-inflammatory cytokines reduction. The most effective herbal nanostructures in the inflammation phase, which regulate levels of TNF- α , IL-10 and TGF- β 1, were discovered to be curcumin-based nanostructures. Another group of plant-based nanostructures were Biosynthesized AgNPs which play an essential role in the control of wound inflammation. A substantial amount of anti-inflammatory action ascribed to down-regulation levels of TNF- α , IL-6, IL-1 β , and IL-10 was caused by several herbal components and extracts utilised in the formulation of the AgNP. In the process of healing the wound, improved angiogenesis and vascularization depend on the activation of FGF, VEGF and PDGF. The activation of angiogenesis by controlling these growth factors is demonstrated by the use of curcumin and plant-medium metal nanoparticles. The pace of re-epithelialization is another major component in the wound healing process. Some instances of a nanostruktur such as fenugreek, curcumin and tragacanth gum can lead to a fast reepithelization of the collagen synthesis and fibroblast proliferation. While all generated herbal nanostructures were useful in treating wounds, they were discovered to be the most powerful

nanostructures based on curcumin that had a key role in controlling most wound healing stages. Metal-based nanoparticles contain, among the several techniques of creating phytochemical nanoformulations, the most pharmacological aims in the therapy process indicating their excellent treatment capacity. These results primarily show the relevance of natural chemicals as alternatives to the healing of certain wounds and the success of nanotechnology to enhance the efficiency of different medical goods. Targeted treatment and bioavailability and stabilising the effect of nanostructure techniques, natural wound healing has been improved. In regard to wound healing effects, further pharmacological studies are necessary to evaluate the intracellular goals of natural nanomedicine. Appropriately organised clinical trials are also necessary to confirm the safety and efficacy of natural nanoformulation driven by products in the treatment of wounds.

References

- Abolghasemzade S, Pourmadadi M, Rashedi H, Yazdian F, Kianbakht S and Navaei-Nigjeh M. (2021) PVA based nanofiber containing CQDs modified with silica NPs and silk fibroin accelerates wound healing in a rat model. *J Materials Chem. B* 9(3): 658-676.
- Agarwal Y, Rajinikanth PS, Ranjan S, Tiwari U, Balasubramnaia J, Pandey P, Arya DK, Anand S and Deepak P. (2021) Curcumin loaded polycaprolactone-/polyvinyl alcohol-silk fibroin based electrospun nanofibrous mat for rapid healing of diabetic wound: An in-vitro and in-vivo studies. *Int J Biol Macromol* 176: 376-386.
- Ahmed MK, Zayed MA, El-Dek SI, Hady MA, El Sherbiny DH and Uskoković V. (2021) Nanofibrous ϵ -polycaprolactone scaffolds containing Ag-doped magnetite nanoparticles: Physicochemical characterization and biological testing for wound dressing applications in vitro and in vivo. *Bioactive Materials* 6(7): 2070-2088.
- Ajmal G, Bonde GV, Thokala S, Mittal P, Khan G, Singh J, Pandey VK and Mishra B. (2019) Ciprofloxacin HCl and quercetin functionalized electrospun nanofiber membrane: Fabrication and its evaluation in full thickness wound healing. *Artif Cells Nanomed Biotechnol* 47(1): 228-240.
- Alipour R, Khorshidi A, Shojaei AF, Mashayekhi F and Moghaddam MJM. (2019) Skin wound healing acceleration by Ag nanoparticles embedded in PVA/PVP/Pectin/Mafenide acetate composite nanofibers. *Polymer Testing* 79: 106022.
- Al-Wafi R, Mansour SF, AlHammad MS and Ahmed MK. (2021) Biological response, antibacterial properties of ZrO_2 / hydroxyapatite/ grapheme oxide encapsulated into nanofibrous scaffolds of polylactic acid for wound healing applications. *Int J Pharmaceut* 601: 120517.
- Augustine G, Aarthi M, Thiagarajan H, Selvaraj S, Kamini NR, Shanmugam G and Ayyadurai N. (2021) Self-Assembly and Mechanical Properties of Engineered Protein Based Multifunctional Nanofiber for Accelerated Wound Healing. *Adv Healthcare Materials* 10(8): 2001832.
- Başaran DDA, Gündüz U, Tezcaner A and Keskin D. (2021) Topical delivery of heparin from PLGA nanoparticles entrapped in nanofibers of sericin/gelatin scaffolds for wound healing. *Int J Pharmaceut* 597: 120207.
- Bayat S, Amiri N, Pishavar E, Kalalinia F, Movaffagh J and Hashemi M. (2019) Bromelain-loaded chitosan nanofibers prepared by electrospinning method for burn wound healing in animal models. *Life Sci* 229: 57-66.
- Bui HT, Chung OH, Cruz JD and Park JS. (2014) Fabrication and characterization of electrospun curcumin-loaded polycaprolactone-polyethylene glycol nanofibers for enhanced wound healing. *Macromolec Res* 22(12): 1288-1296.
- Campa-Siqueiros PI, Madera-Santana TJ, Castillo-Ortega MM, López-Cervantes J, Ayala-Zavala JF and Ortiz-Vazquez EL. (2021) Electrospun and co-electrospun biopolymer nanofibers for skin wounds on diabetic patients: an overview. *RSC Adv* 11(25): 15340-15350.
- Charernsriwilaiwat N, Opanasopit P, Rojanarata T and Ngawhirunpat T. (2012) Lysozyme-loaded, electrospun chitosan-based nanofiber mats for wound healing. *Int J Pharmaceut* 427(2): 379-384.
- Chen S, Liu B, Carlson MA, Gombart AF, Reilly DA and Xie J. (2017) Recent advances in electrospun nanofibers for wound healing. *Nanomed* 12(11): 1335-1352.
- Deldar Y, Pilehvar-Soltanahmadi Y, Dadashpour M, Montazer Saheb S, Rahmati-Yamchi M and Zarghami N. (2018) An in vitro examination of the antioxidant, cytoprotective and anti-inflammatory properties of chrysin-loaded nanofibrous mats for potential wound healing applications. *Artif Cells Nanomed Biotechnol* 46(4): 706-716.
- Dos Santos AEA, Dos Santos FV, Freitas KM, Pimenta LPS, de Oliveira Andrade L, Marinho TA, de Avelar GF, da Silva AB and Ferreira RV. (2021) Cellulose acetate

- nanofibers loaded with crude annatto extract: Preparation, characterization, and in vivo evaluation for potential wound healing applications. *Mater Sci Eng C Mater Biol Appl*. 118: 111322.
- Fayemi OE, Ekennia AC, Katata-Seru L, Ebokaiwe AP, Ijomone OM, Onwudiwe DC and Ebenso EE. (2018) Antimicrobial and wound healing properties of polyacrylonitrile-moringa extract nanofibers. *ACS Omega* 3(5): 4791-4797.
- Fereydouni N, Darroudi M, Movaffagh J, Shahroodi A, Butler AE, Ganjali S and Sahebkar A. (2019) Curcumin nanofibers for the purpose of wound healing. *J Cellular Physiol*. 234(5): 5537-5554.
- Gao C, Zhang L, Wang J, Jin M, Tang Q, Chen Z, Cheng Y, Yang R and Zhao G. (2021) Electrospun nanofibers promote wound healing: theories, techniques, and perspectives. *J Materials Chem. B* 9(14): 3106-3130.
- Gök ZG, Yiğitoğlu M, Vargel İ, Şahin Y and Alçıgır ME. (2021) Synthesis, characterization and wound healing ability of PET based nanofiber dressing material coated with silk sericin capped-silver nanoparticles. *Materials Chem Phys*. 259: 124043.
- Hassiba AJ, El Zowalaty ME, Nasrallah GK, Webster TJ, Luyt AS, Abdullah AM and Elzatahry AA. (2016) Review of recent research on biomedical applications of electrospun polymer nanofibers for improved wound healing. *Nanomed*. 11(6): 715-737.
- He J, Liang Y, Shi M and Guo B. (2020) Anti-oxidant electroactive and antibacterial nanofibrous wound dressings based on poly (ϵ -caprolactone)/quaternized chitosan-graft-polyaniline for full-thickness skin wound healing. *Chem Engineer J*. 385: 123464.
- Heydari HA, Karamian E, Poorazizi E, Khandan A and Heydaripour J. (2015) A novel nano-fiber of Iranian gum tragacanth-polyvinyl alcohol/nanoclay composite for wound healing applications. *Procedia Materials Sci*. 11: 176-182.
- Jatoi AW, Ogasawara H, Kim IS and Ni QQ. (2019) Polyvinyl alcohol nanofiber based three phase wound dressings for sustained wound healing applications. *Materials Lett*. 241: 168-171.
- Jeckson TA, Neo YP, Sisinty SP and Gorain B. (2020) Delivery of therapeutics from layer-by-layer electrospun nanofiber matrix for wound healing: An update. *J Pharmaceut Sci*. 110(2): 635-653.
- Kataria K, Gupta A, Rath G, Mathur RB and Dhakate SR. (2014) In vivo wound healing performance of drug loaded electrospun composite nanofibers transdermal patch. *Int J Pharmaceut*. 469(1): 102-110.
- Leung V, Hartwell R, Yang H, Ghahary A and Ko F. (2011) Bioactive nanofibres for wound healing applications. *J Fiber Bioengineer Informat*. 4(1): 1-14.
- Liu M, Duan XP, Li YM, Yang DP and Long YZ. (2017) Electrospun nanofibers for wound healing. *Materials Sci Engineer. C* 76: 1413-1423.
- Memic A, Abudula T, Mohammed HS, Joshi Navare K, Colombani T and Bencherif SA. (2019) Latest progress in electrospun nanofibers for wound healing applications. *ACS Appl Bio Materials* 2(3): 952-969.
- Mistry P, Chhabra R, Muke S, Narvekar A, Sathaye S, Jain R and Dandekar P. (2021) Fabrication and characterization of starch-TPU based nanofibers for wound healing applications. *Materials Sci Engineer. C* 119: 111316.
- Najafiasl M, Osfouri S, Azin R and Zaeri S. (2020) Fabrication, characterization and in vivo evaluation of dexpanthenol sustained-release nanofibers for wound healing. *Polymer Testing* 91: 106827.
- Nguyen TTT, Ghosh C, Hwang SG, Dai Tran L and Park JS. (2013) Characteristics of curcumin-loaded poly (lactic acid) nanofibers for wound healing. *J Materials Sci*. 48(20): 7125-7133.
- Prakash J, Venkataprasanna KS, Bharath G, Banat F, Niranjana R and Venkatasubbu GD. (2021) In-vitro evaluation of electrospun cellulose acetate nanofiber containing Graphene oxide/TiO₂/Curcumin for wound healing application. *Colloids Surfaces A Physicochem Engineer Aspects* 627: 127166.
- Ramalingam R, Dhand C, Mayandi V, Leung CM, Ezhilarasu H, Karuppannan SK, Prasannan P, Ong ST, Sunderasan N, Kaliappan I, Kamruddin M, Barathi VA, Verma NK, Ramakrishna S, Lakshminarayanan R and Arunachalam KD. (2021) Core-shell structured antimicrobial nanofiber dressings containing herbal extract and antibiotics combination for the prevention of biofilms and promotion of cutaneous wound healing. *ACS Appl Mater Interfaces* 13(21): 24356-24369.
- Rath G, Hussain T, Chauhan G, Garg T and Goyal AK. (2016) Collagen nanofiber containing silver nanoparticles for improved wound-healing applications. *J Drug Target*. 24(6): 520-529.
- Rieger KA, Birch N and Schiffman JD. (2013) Designing electrospun nanofiber mats to promote wound healing—a review. *J Materials Chem. B* 1(36): 4531-4541.
- Sarhan WA and Azzazy HM. (2017) Apitherapeutics and phage-loaded nanofibers as wound dressings with

- enhanced wound healing and antibacterial activity. *Nanomed.* 12(17): 2055-2067.
- Wali A, Gorain M, Inamdar S, Kundu G and Badiger M. (2019) In vivo wound healing performance of halloysite clay and gentamicin-incorporated cellulose ether-PVA electrospun nanofiber mats. *ACS Appl Bio Materials* 2(10): 4324-4334.
- Xie Z, Paras CB, Weng H, Punnakitikashem P, Su LC, Vu K, Tang L, Yang J and Nguyen KT. (2013) Dual growth factor releasing multi-functional nanofibers for wound healing. *Acta Biomater.* 9(12): 9351-9359.
- Xuan H, Wu S, Fei S, Li B, Yang Y and Yuan H. (2021) Injectable nanofiber-polysaccharide self-healing hydrogels for wound healing. *Materials Sci Engineer. C* 128: 112264.
- Zhang K, Bai X, Yuan Z, Cao X, Jiao X, Li Y, Qin Y, Wen Y and Zhang X. (2019) Layered nanofiber sponge with an improved capacity for promoting blood coagulation and wound healing. *Biomaterials*, 204: 70-79.