CONTRIBUTION TO THE STUDY OF THE THERMOMECHANICAL PROPERTIES OF THE ADOBE. (CASE OF THE SOUTH OF ALGERIA OUARGLA)

Hachem CHAIB, Abdelouahed KRIKER, Abdessalam MEKHERMECHE

Laboratoire d'Exploitation et Valorisation des Ressources Naturelles en Zones Arides,
Ouargla 30000, Algeria

Département de Génie Civil et d'Hydraulique, Université Kasdi MERBAH Ouargla,
Ouargla 30000, Algérie

*Correspondence: chaib.hachem@univ-ouargla.dz

ABSTRACT

As part of the recovery of local materials in arid and semi-arid areas, the adobe will be chosen as a reductive object. This research topic consists of the use of clay for construction. The latter is abundant in the south of Algeria and has properties that appear to be suitable for building design. The purpose of this project is to evaluate the behaviour of clay-based Adobe by adding dune sand, gravel 8/15 and gravel 3/8 by different percentages. This technical study is based on the application of tests for the physical and mechanical characterization of the latter.

This study is launched with the aim of characterizing a clay based on local materials from the Ouargla region, namely Baldat Amor clay, sand from the dune of Sidi khouiled, gravel from Ouargla.

Keywords: Saharan Regions, Thermal Properties, Mechanical Properties, Clay, Dune sand, Gravel.

Cite this Article: Hachem CHAIB, Abdelouahed KRIKER, Abdessalam MEKHERMECHE, Contribution to the Study of the Thermomechanical Properties of the Adobe. (Case of the South of Algeria Ouargla). *International Journal of Civil Engineering and Technology*, 11(3), 2020, pp. 24-34.

<https://iaeme.com/Home/issue/IJCET?Volume=11&Issue=3>

1. INTRODUCTION

The most well-known and most often cited definition is that of F. Cointeraux in "Ecole d'architecture rurale et'économique, Paris 1790"[5] : "Adobe is a process according to which houses are built with earth, without being supported by any piece of wood, and without mixing it neither straw nor stuffing. It consists in beating, bed by bed, between boards, to the ordinary thickness of the rubble walls, the earth prepared for this purpose. Thus beaten it

binds, takes on consistency, and forms a homogeneous mass that can be "raised to the heights necessary for a dwelling."

Adobe is, therefore, a monolithic clay wall masonry technique, composed of superposed layers of compacted earth. The resulting wall is a load-bearing wall. It is 50 cm thick on average, sometimes more. The density of traditional adobe is about 1.7 to 1.9 rpm[17]. Adobe buildings commonly have two levels. Some, particularly in urban areas, may have three or even four levels.

Our research work consists in valorizing the clay and sand of the dunes of the Ouargla region by incorporating it and using it to make a Adobe. In our work we have chosen gravel to make a adobe based on these materials. The south of Algeria is an example of the hot and dry regions of our country, is also an example of a region where the past has been built of earth and local stones (Ksores); but unfortunately in recent times concrete has been built, a material not adapted to climatic conditions

To this end, this study has been launched. From a global point of view, the aim of our research is to make a Adobe based on local materials. Then proceed to its thermal and mechanical characterizations.

2. MATERIALS AND METHODS

In this section, we study the characteristics of the different materials used in the manufacture of Adobe.

2.1. Dune Sand

For our study we used the sand from the dunes of the south of Algeria (Ouargla). We performed the following tests:

- The absolute density;
- The apparent density;
- Sand equivalent;
- Chemical analysis;
- X-ray diffraction.

Figure 1 Dune sand of Ouargla.

Table 1 Physical characteristics of dune sand.

Test	Results
The absolute density	$\rho_a=2559 \text{ kg/m}^3$
The apparent density	$\rho_s=1513 \text{ kg/m}^3$
Sand equivalent	ESp=99 %

2.1.1. Chemical Analyses

The following table shows the percentages of chemical components in dune sand.

Table 2 Chemical analysis of dune sand.

Components	Percentages (%)
Fe 2O_3 - AL 2O_3	0.25
Ca SO $_4$, 2H $_2\text{O}$	2.78
SO $_4$	0.51
Ca CO $_3$	1.30
Insoluble	93.23
Na cl	Trace
Loss on Fire	1.16

We note that the percentage of (Ca SO $_4$), (SO $_4$) is below the recommended limit. As a result, the sand used is non-aggressive.

2.1.2. X-ray Diffraction

The curve represents the results obtained for dune sand.

Figure 2 Diffractometric analysis of dune sand.

Depending on the measurements made from the diffractogram, the following can be observed:

- Quartz forms a large part of the minerals with a percentage of 80%.
- Gypsum is found in the form of fine, whitish grains with a percentage of about 3%.
- Feldspar and calcite are present with low percentages in the 10% range

2.2. Clay

For our study we used Ouargla clay. We performed the following tests on this clay:

- Dry density;
- Methylene blue;
- Atterberg limit;
- Chemical analysis;
- X-ray diffraction.

Figure 3 Beldat Amor Clay

Table 3 Physical Characteristics of clay.

Characteristics	Results
Dry density (NF P 94/064)	P = 2.03 g/cm ³
Methylene blue (NF EN 933-9)	VBS = 8
Atterberg limit (NF P 94-051)	W _L = 69.58 % W _P = 24.71 % I _P = 44.87 %

According to Atterberg and Burmister, we can classify our clay by its plasticity index (IP = 44.87) the nature of the clay is a very plastic clay.

2.2.1. Analyse chimique

The main results of the chemical analysis are presented in the following table:

Table 4 Chemical analysis of clay

Chemical characteristics	Components	Percentages (%)
Insolubles (NF P 15 – 461)	Insolubles	63.18
Sulfates (BS 1377)	SO ₃	0.45
	Ca SO ₄ / 2H ₂ O	2.46
Carbonates (NF P 15 – 461)	CaCO ₃	18.0
Chlorides (MOHR method)	Cl ⁻	0.42
	NaCl	0.68

The table shows that the elements of this clay are insoluble in percentage of about 64%, the sulfate and chloride contents are very low.

2.2.2. X-ray Diffraction

The curve represents the results obtained for clay.

Figure.4 Diffractometric analyses of clay.

The sample consists essentially of associated minerals of quartz and Montmorillonite, as well as other phases that are not to be ruled out. The intensities of this diffractogram show that quartz is the dominant phase, in fact peaks 42.20, 55.02, 60.36, 76.04 (2θ), are characteristic of this material, as is Montmorillonite, its presence in the sample is determined by the main peaks at 19.76, 24.11, 35.53 and 53.87 (2θ)

2.3. Gravel

Gravel has origins similar to those of sand, it comes from the disintegration of rocks. The maximum size of the aggregates is determined, on the one hand, by the minimum distance to be achieved and, on the other hand, by the minimum distance between the various reinforcements of the structure. The 3/8 fraction is considered as crushed sand.

Figure 5 Gravel.

The results obtained are as follows:

Table 5 Physical characteristics of gravel.

Test	classe 3/8	classe 8/15
Absolute density (kg/m^3)	2613	2661
apparent density (kg/m^3)	1506	1460
Micro-Deval Test	10	11.2
Los Angeles Test	20	25

3. RESULT AND DISCUSSION

The experimental study of our work consists in determining the thermal and mechanical characteristics of the adobe based on local materials of dimensions (7x 7 x28) cm ,then different tests were carried out on the made samples.

3.1. Obtaining the Mixing Water (Proctor Tests)

The purpose of the Proctor test is to determine the optimal moisture content for a given backfill soil to which it must be compacted to obtain the maximum dry density and fixed compaction conditions, which leads to the best possible compaction or maximum bearing capacity.

Figure 6 Clay Proctor Curve.

According to Proctor's tests, the optimal amount of water for the production of Adobe based on this clay is 18%.

The compositions used are indicated in Table 6.

Table 6 Used compositions.

	C1	C2	C3	C4	C5	C6	D1	D2	D3	D4	D5
A %	25	25	25	25	25	25	25	25	25	25	25
S %	25	25	25	25	25	25	25	25	25	25	25
G %	25	30	35	40	45	50	20	15	10	5	0
g %	25	20	15	10	5	0	30	35	40	45	50

With : A: clay / S: sand / G: gravel 8/15 / g : gravel 3/8

Figure III.7 shows the variation in the density of the Adobe as a function of the different percentages of gravel.

Figure 7 Volumic Mass Results.

From the figures (7) we can see that:

- An increase in density as a function of the percentage of gravel in the compositions is due to the higher density of the gravel than the others.
- A decrease in density as a function of the decrease in the percentage of gravel in the compositions.
- The density of the composition (C6) is higher than other compositions
- The densities of the other compositions are similar.
- The results of the compressive strength test are shown in the following figure:

Figure 8 Compression results.

From figure (8) we see that:

- An increase and decrease in the first six compositions (C), This phenomenon can be explained in two Phases;

Phase 1: An increase in compressive strength in terms of an increase in the percentage of gravel to the top, which is due to the good cohesion of the mixture.

Phase 2: Decrease in compressive strength due to the increase in the percentage of gravel due to the existence of voids created by the gravel.

- A decrease in the compressive strength of the compositions (D) in terms of an increase in the percentage of gravel 3/8, which creates voids and inconsistency of the sample.
- The compressive strength of the sample (C3) is higher than that of the sample (D1) and this is due to the increase in the percentage of gravel.
- The compressive strength of sample (C6), (D5) is low by one mechanical point, and this is due to the influence of voids resulting from granular gradient is not appropriate.
- The compressive strength of samples (C3) and (D1) are acceptable.
- The results of the Flexural strength test are summarized in the following figure:

Figure 9 Flexural strength.

From figure (9) we see that:

- Compositions (C3) and (D1) give better Flexural strength and this is due to the good cohesion of the mixture.
- The Flexural strength of all compositions is similar.
- The Flexural strength of the sample (C3) is higher than that of the sample (D5) and this is due to the increase in the percentage of grivlette.
- The Flexural strength of samples (C2) and (C4) is lower than that of samples (D2) and (D3) and this is due to the fact that the gravel 8/15 is higher than the gravel 3/8, which creates voids.

The results of the Ultration test are summarized in the following figure:

Figure 10 Results of the Sound propagation speed.

- The Sound propagation speed tests confirmed the compression and Flexural strength results.
- The C3 sample gave the best result.

Figure (11) shows the variation in the thermal conductivity of the Adobe as a function of the different percentages of clay and sand in the dunes, gravel 8/15 and gravel 3/8.

Figure 11 Variation of the thermal conductivity.

From figure (11)

- Some samples were broken, it's due to transport.
- A decrease in conductivity as a function of the increase in the percentage of gravel in the mixture. This is attributed to voids left by the gravel.
- the samples (C4) and (D2) give a lower thermal conductivity, due to the presence of voids between the components of these compositions,

The results of the thermal resistance are summarized in the following figure:

Figure 12 Variation of thermal resistance

From figure (12), we see

- the thermal resistance has automatically increased because it is inversely proportional to the thermal conductivity.

- An increase in thermal resistance as a function of the increase in the percentage of gravel.
- The highest thermal resistance is that of bricks containing gravel (C6), while the sample (D5) is the lowest and this is due to the absence of gravel.
- A convergence of the thermal resistance in the sample (C2) and the sample (D2).

4. CONCLUSION

We recall the purpose of this work was to contribute to the production of a local material with good mechanical and thermal properties for which we made a mix based on local materials, after having carried out a series of thermal and mechanical tests on these mixes, we can say:

- Clay extracted from the Ouargla South Algerian deposit, which is characterized by: The nature of this clay is very plastic; and consists essentially of minerals associated with quartz and kaolinite, and is also characterized by a high proportion of silt granulometry (90%)
- The sand used is sand from the dunes extracted from Ouargla which is characterized by: A very tight granulometry; Consists essentially of minerals associated with quartz, calcite and alumina; this sand is a very fine sand After the experiment, we drew the following conclusion:
- The addition of gravel increases the density of the sample.
- The samples that have the best granular analysis give us the best result in terms of pressure resistance and bending strength.
- Economically, the use of these materials helps to reduce the amount of imported materials and reduce the energy consumption required to use the materials studied in home construction.

RÉFÉRENCES

- [1] Hachem Chaib, Techniques de production des briques de terre. Editions Universitaires Européennes, 2017.
- [2] Hachem Chaib, Contribution à l'Etude des Propriétés Thermo-Mécaniques des Briques en Terre Confectionnée par des Fibres Végétale Locale. (Cas de la ville de Ouargla). Thèse de Doctorat Université de Ouargla 2017.
- [3] Hachem Chaib and al. Thermal study of earth bricks reinforced by date palm fibers. Energy Procedia 2015 ;74 : 919 – 925.
- [4] MEKHERMECHE A, Contribution à l'étude des propriétés mécaniques et thermiques des briques en terre en vue de leur utilisation dans la restauration des Ksours sahariennes. Thèse de Magister Université de Ouargla 2012.
- [5] KRIKER A, caractérisation des fibres de palmier dattier et propriétés des bétons et mortiers renforcés par ces fibres en climat chaud et sec Thèse de Doctorat d'état ENP 2005.
- [6] Swamy RN. Vegetable fibre reinforced cement composite a false dream or a potential reality. In: Sobral H.S, editor. Proceedings of the second international RILEM symposium, vegetable plants and their fibres as building materials, Salvaor, Bahia (Brazil), Chapman and Hall; 1990: p. 139–49.
- [7] Hanifi B, Orhan A, Mehmet N, Erhan A, Selim K. Thermal isolation and mechanical properties of fibres reinforced mud bricks as wall materials. Construction and Building materials; 2007: 21: 901-906.

- [8] Abani S. Caractérisation des bétons renforcés par des fibres végétales de palmier dattier. Mémoire de magister; université de Ouargla 2003.
- [9] Ghavami K, Filho RDT, Barbosa NP. Behaviour of composite soil reinforced with natural fibres. *Cem Concr Compos* 1999; 21(1):39–48.
- [10] Coutts RSP, Ni Y. Autoclaved bamboo pulp fibre reinforced cement. *Cem Concr Compos* 1995; 17(2):99–106.
- [11] Taallah B., Guettala A., Guettala S, Kriker A. Mechanical properties and hygroscopicity behavior of compressed earth Block filled by date palm fibers. *Construction and Building Materials* 59 (2014) 161–168
- [12] Al-Harthy AS, Abdel Halim M, Taha R, Al-Jabri KS. The properties of concrete made with fine dune sand. *Constr Build Mater* 2007; 21:1803–8.
- [13] Meukam P. Thèse de doctorat Valorisation des briques de terre stabilisées en vue de l'isolation thermique de bâtiments université de Yaoundé 2004 ;
- [14] AVLISET I., Matériaux de terre cuite Technique de l'ingénieur, 1994.
- [15] Collection mémento technique Tuiles et briques de terre cuite édition le moniteur, Paris 1998.
- [16] LIVERT S., Bâtir un mur en briques de terre compressée, Février 2011.
- [17] Nguyen T.; Thèse de doctorat Etude du comportement au Feu des Maçonneries de Briques en Terre-Cuite: Approche expérimentale et Modélisation du risque d'écaillage 2009;
- [18] Coopérative des Ouvriers du Bâtiment (C.O.B) portrait des connaissances sur l'utilisation de la terre stabilisée dans le secteur du bâtiment au Sénégal 2010 ;
- [19] RICHARD P., Adobe, mémoire Maître en environnement, Université de Sherbrooke Canada, Octobre 2010.
- [20] MAKRI M.; Projet GE12 Construction en terre Technologie Compiègne, 2010.
- [21] CRA Terre EAG Bloc de terre comprimée volume I Manuel de production.
- [22] Lptr l'ESTAQUE Marseille fiche technique mur en brique de terre crue Collegiul Tecnic Buzau mai 2010
- [23] GORISSE F.; Essais et contrôle des bétons, Edition Eyrolles, vol.2, Paris ; 1978.
- [24] YVES J. Transferts Thermiques, Ecole des mines Nancy, Edition 2012.
- [25] Fiche thermique, Isolation thermique Mairie de Paris, Edition Novembre 2009.