Obtaining fulvic acid from oxidized coal of Kazakhstan

Yermagambet B.T., Kazankapova M.K., Kassenova Zh.M., Baylina G.

Institute of Coal Chemistry and Technology LLP, Nur-Sultan, Kazakhstan, coaltech@bk.ru

Keywords: oxidized coal, fulvic acid, humic acid, functional groups

DOI:10.36291/HIT.2021.068

The paper presents the results of obtaining fulvic acid (FA) from oxidized coal in Kazakhstan and the study of its functional groups.

Oxidized brown coal from the «Maikuben» deposit with the following characteristics (wt%) was used as a feedstock: A^d - 25.8; W^r - 9.3; V^d - 46.6; S^d - 0.71. The content of humic substances is 56%.

Humic acids (HA) and FA are obtained on the basis of potassium humate, by acidification with 5% hydrochloric acid solution to pH 1.0-1.5. All organic substances remaining in the acidic solution after the isolation of HA were considered as fulvic acids. HA was separated by centrifugation, transferred to a filter, washed with distilled water until neutral pH, and dried at 60-70 °C to constant weight. FA was purified by passing through ion exchangers. The functional groups of the obtained sample were studied on an IR Fourier spectrometer (Nicolet iS 10) (Fig. 1).

Figure 1. IR spectrum of fulvic acid.

According to the results of the study, a peak was found at 3372 cm^{-1} , corresponding to the vibrations of N-H/O-H groups in the structures of amide, amines, carboxyl compounds linked by hydrogen bonds. In the region of 3100–3000 cm^{-1} , vibrational vibrations of aromatic C–H bonds are observed. The less intense absorption peak at 2400 cm^{-1} is probably due to the presence of aliphatic CH bonds. An intense absorption band at 1636 cm^{-1} is characteristic of the carboxyl group. The absorption peaks at 1098 cm^{-1} and 835 cm^{-1} refer to vibrations of the -C-O bonds of phenols, polysaccharides and/or aliphatic groups. Thus, with the help of IR spectroscopy, it was found that the composition of PA contains both acidic and basic groups, which indicates the amphotericity of the sample.

Acknowledgements. The work was carried out within the framework of project No. IRN AP09260096 on the topic "Development of technology and organization of pilot production of modified organic biological products based on humic polyelectrolyte acids obtained from the coals of Kazakhstan", funded by the Science Committee of the Ministry of Education and Science of the Republic of Kazakhstan.