Improvement of Mechanical Properties of Polymer Materials by the Nanosized Ceramic Particles

O. V. EGOROVA¹, THANT ZIN HEIN²,

¹Moscow Aviation Institute (National Research University), Moscow, Volokolamskoe shosse, 4, 125993, RUSSIA

²Defense Services Technological Academy (DSTA), Mandalay Lashio Highway, Pyin Oo Lwin, Mandalay Division, MYANMAR

Abstract—As a result of the experiments, epoxy nanocomposites based on titanium dioxide nanoparticles in the form of opaque blue-gray films were obtained. The composition and structure of epoxy nanocomposites were studied by scanning electron microscopy and infrared spectroscopy. The properties of the obtained film nanocomposites were investigated to determine the glass transition temperature, and the mechanical properties of the films were tested in tension, where the tensile strength, elastic modulus, and relative deformation were determined.

Keywords—Composites, mechanical properties, polymers, nanoparticles.

Received: April 27, 2021. Revised: September 3, 2021. Accepted: September 10, 2021. Published: September 19, 2021.

1. Introduction

EPHOXY resins are commonly used as polymer matrices in high performance composites due to their good heat resistance, durability, electrical, chemical and mechanical properties. However, its range of applications is limited due to its fragility and poor toughness. One of the ways to overcome this problem is to change the properties of epoxy matrices by introducing a rigid filler into the polymer matrix [1]-[12]. A new approach in nanotechnology proposes the use of fillers at the nanometer scale, since nanofillers have a large surface area, which makes them chemically very reactive and helps them bind better to the matrix. Nanoparticles embedded in a polymer matrix are attracting more and more interest due to the unique mechanical, optical, electrical and magnetic properties exhibited by nanocomposites and significantly improve them [13]-[16]. These improvements depend on the volumetric content of the filler as well as the type and characteristics of the nanofillers [17]-[33]. Nanofillers of a metallic or inorganic type can be considered an excellent candidate for hardening polymer matrices [34]-[43].

The development of modern technology requires the creation of new structural materials with high elastic-strength characteristics, and, on their basis, structures with more effective weight data. The creation of polymer composites based on nano-modified binders has been one of the priority areas of research in the field of composite materials manufacturing technologies for many years [1]-[12]. Significant progress has been made in this area [13]-[21]. The development of composite materials that improve their operational limits is based on the reinforcement of two or more fibers into a single polymer matrix, which leads to an improved material system called hybrid composites with a wide variety of material properties [22]-[25].

When creating nanocomposites, the key tasks are the development of efficient, reliable, and affordable production technologies for mass production, which make it possible to obtain materials with stable characteristics. The hand lay

technique, also called wet lay, is the simplest and most widely used process for producing flat reinforced composites. The process consists of laying layers of a polymer in successive layering using an epoxy matrix. Wet-laying is a molding process that combines layers of reinforced carbon fiber with epoxy to create a high-quality laminate. Before starting the installation process, you must prepare the appropriate form. This preparation consists of cleaning the table and applying a release agent to the surface. The manual laying process can be divided into four main steps: mold preparation, epoxy coating, laying and curing. Form preparation is one of the most important steps in the installation process. This process requires dry reinforcement layers and the application of a wet epoxy matrix. They are connected together - reinforcing material, impregnated with a matrix - epoxy resin.

Titanium dioxide (TiO₂) is one of the promising materials as a nanofiller due to its optical, thermal, photocatalytic and electrophysical properties. The application potential of nanodispersed TiO₂ is very high: titanium dioxide and materials based on it can be used as an additive in plastics, an ultraviolet light blocker, an energy converter in solar batteries, an agent for photocatalytic degradation of bacteria and photochemical degradation of toxic chemicals, for wastewater treatment. Due to their chemical inertness, low toxicity, photocatalytic activity, high refractive index and other beneficial properties, titanium dioxide nanoparticles have attracted the attention of many researchers and are used in the food, paint and varnish industry, etc. Previous studies have shown that the introduction of TiO₂ nanoparticles improves some properties of epoxy resin. But the process of interaction and the mechanism of hardening of epoxy resin are not fully understood. There are few works on epoxy nanocomposites with TiO₂ nanoparticles; therefore, it is relevant to obtain new examples of such nanocomposites and study their physical and mechanical properties, since due to the presence of TiO₂, it is possible to use such nanocomposites in biomedicine, as bactericidal and photocatalytic surfaces. The aim of this work is to create an epoxy nanocomposite based on TiO₂ nanoparticles and to study its physical and mechanical

properties depending on the concentration of nanoparticles.

The matrix can be a thermosetting polymer - epoxy resin, which has already found many applications: from structural composites to adhesives and surface coatings. Epoxy resins already have a number of unique qualities among polymers: no shrinkage during curing, high adhesion to various substrates, good dielectric and other valuable properties [44]-[77]. Nanocomposites using thermoplastic polymers are well known and studied to improve mechanical, electrical, thermal and insulating properties. However, nanocomposites using thermosetting polymers have not been studied as widely, especially using TiO_2 .

Nanoparticles are usually introduced into the polymer matrix using various methods. Dispersion processes are necessary in order to transfer nanoparticles from an agglomerated state to a uniformly dispersed state [26]-[34]. The most popular are live streaming with the use of chemical methods and the use of high shear forces in the process of mechanical dispersion of the powder. Chemical methods are capable of generating individual and non-agglomerated nanoparticles within a thermosetting or thermoplastic polymer. For mechanical dispersion, ultrasonic treatment is often used, which also improves the dispersion state of nanoparticles.

The aim of this work is to create an epoxy nanocomposite based on TiO_2 nanoparticles and to study its physical and mechanical properties depending on the concentration of nanoparticles.

2. Modelling the mechanical properties of nanocomposites

We use the model of spherical inclusions to model the properties of the filled matrix, assuming that the reinforcing particles of titanium dioxide are spheres. We assume that the particles are absolutely solid and do not collapse (the upper estimate). Bulk content 0,6%. We use the Digimat - MF module, the averaging method of Mori - Tanaka. Strength criterion - according to the maximum principal stresses acting in the matrix.

If the initial volumetric content of inclusions is set to 0.6%, the model predicts that the properties of the matrix will not change, since there are too few inclusions. The effect of the interfacial layer must be taken into account. For this, we will carry out a calculation with the setting of the effective volumetric content (volumetric content of the filler + volumetric content of the interfacial layer, under the assumption that their properties are equal). Let us select the effective volumetric content that allows us to describe the obtained experimental data in relation to the elastic modulus and ultimate strength.

If we select according to ultimate strength, then the effective volumetric content of inclusions should be 50%, and the modulus of the composite should be 6 GPa according to the calculation. If we select by modulus, then the effective volumetric content of inclusions should be 11%, and the ultimate strength of the composite according to the calculation

should be 23 MPa.

To describe the experiment, we can assume that the effective volumetric content of inclusions is 11% (we obtain the coincidence of the calculation and experiment in modulus), and the strength of the matrix increases when a filler is added up to 30 MPa (we obtain a coincidence of the calculation and experiment in strength).

Fig. 1 Diagram of $\sigma - \epsilon$ samples with different volumetric content of inclusions (in "DIGMAT-MF"), (green-50%, blue-11%, red-0%).

For the found volumetric content of inclusions, by selection, we determine what the volumetric content of inclusions should be, so that the calculation and the experiment on measuring the CTE of the composite coincide. For 11%, we find that the CTE of the filler (and the surrounding interfacial layer) should be $85 \cdot 10^{-6} \text{ s}^{-1}$. The obtained high value of the CTE of the filler and the experimentally established phenomenon of an increase in the CTE of composites with a nanomodified matrix may be associated with a change in the structure of the polymer matrix or may be a consequence of the ongoing chemical reactions between the filler and the matrix.

The initial data for modeling the process of degradation of the mechanical properties of the test samples are the characteristics of the monolayer.

"DIGMAT" program is designed for fast and highly accurate prediction of the nonlinear behavior of multicomponent materials, such as plastics, polymers, carbon and fiberglass, nanomaterials, etc., for accurate assessment of the local and global behavior of multicomponent structures using the finite element method, for preparing storage and confidential exchange of material models, for easy and highly efficient design of honeycomb sandwich panels. Also "DIGMAT" presents to the user a number of interfaces for finite element software systems of computer engineering ("ANSYS", "LS DYN", "SIMULIA / Abaqus", etc.), intended for computer modeling and research of problems of mechanics of a deformable solid body, mechanics of structures and software systems for finite element modeling of plastic molding processes ("MOLDEX3D", "MOLDFLOW", etc.).

Fig. 3 shows the $\sigma - \epsilon$ diagrams obtained as a result of finite element analysis in conjunction with "DIGMAT".

Fig. 2 Diagram of stress-strain for unidirectional specimen and specimen with packing in «DIGMAT MF».

Two analyzes were given: a unidirectional sample and a sample with longitudinal transverse packing. These diagrams exactly matched the diagrams obtained when testing these two types of samples.

3. Investigation of the physical and mechanical properties of nanocomposites

Tests carried out by the method of differential scanning calorimetry with an increase in temperature from 20 to 200 °C and a test speed of 5 °C/min in a nitrogen atmosphere gave the result shown in Figure 3. As it follows from Fig. 3, the glass transition temperature of the obtained epoxy nanocomposites weakly depends on the TiO₂ concentration, however, there is a tendency to a slight decrease: at concentrations less than 1 wt. % the glass transition temperature decreases to 167 °C, and at concentrations up to 5 wt. % rises and reaches 173 °C. Such a decrease in the glass transition temperature may indicate a change in the viscosity and elasticity of the system, an increase in the flexibility of molecules and their mobility, and a further increase in the concentration of nanoparticles leads to an increase in the rigidity and, consequently, to an increase in the glass transition temperature of the system.

Fig. 3 Dependence of the glass transition temperature of TiO₂/EP nanocomposites on the concentration of TiO₂.

Based on the results obtained, it can be concluded that the presence of titanium dioxide nanoparticles in the system leads to a slight decrease in the glass transition temperature at a concentration of 1% TiO₂.

In physical and mechanical tensile tests, the efficiency of filling the composite with TiO₂ nanoparticles was monitored according to the following parameters: tensile strength (R_m, MPa), elastic modulus (E, GPa), relative deformation (ε, %). The test included control samples not modified with titanium dioxide and samples of nanocomposites with different contents of TiO₂ nanoparticles. The size of the samples was 10×90 mm, the thickness was 0,08 mm. The tensile test speed was 2 mm/min. The samples were securely fixed in rubberized clamps and a load was applied until complete destruction. Fracture occurred in the middle of the sample. After carrying out all the necessary tests and calculations, diagrams of the dependence of strength, modulus, and deformation on the concentration of TiO₂ nanoparticles were obtained. As shown in Figure 4, tensile strength drops sharply at n-TiO₂ concentrations greater than 3 wt. %, which is possibly associated with secondary processes of agglomeration of n-TiO₂. Therefore, the working concentration should not exceed 3 mass. % n-TiO₂.

Fig. 4 Dependence of the tensile strength of n-TiO₂/EP nanocomposite on the concentration of TiO₂.

The dependence of the modulus of elasticity on the concentration of TiO₂ is given in Figure 5. At concentrations above 1 wt. % increase in the modulus of elasticity is 20-25%, which indicates the effect of antiplasticization of the nanocomposite.

Fig. 5 Dependence of the modulus of elasticity of TiO₂/EP nanocomposite on the concentration of TiO₂.

The change in the relative deformation with varying nanofiller content is complex: the deformation increases at TiO₂ concentrations less than 1 wt. %, and decreases at TiO₂ concentrations above 1 wt. %.

Fig. 6 Dependence of the relative deformation of the TiO₂/EP nanocomposite on the TiO₂ concentration.

Thus, the mechanical properties depend on the concentration of TiO₂ nanoparticles. The values of the modulus of elasticity and tensile strength are maximum at a nanoparticle concentration of 3 wt. %. The relative deformation increases with increasing concentration up to 1 wt. %.

4. Discussion of the results obtained

The obtained value of the average Young's modulus of the packet differs from the test. It is known that when using test data for a unidirectional material in the calculation of the properties of a layered package, errors can occur, therefore, it is usually necessary to use data on the stiffness of several versions of packages with different layering of layers. If using the values of the modules, then it is not possible to describe

the test data. In this work, for the properties of a monolayer, we will use an overestimated value of the transverse modulus equal to 28 GPa, which is higher than the experimental data obtained for unidirectional samples (6,5 GPa). In this case, it is possible to reliably describe the obtained experimental data on Young's modulus of composite samples with symmetric packing.

The conducted studies allowed to investigate residual deformations in panels with an asymmetric reinforcement scheme based on the obtained analytical solution, as well as numerical modeling. Comparison of the results of analytical and numerical solutions with the obtained experimental data confirms the reliability and validity of the developed mathematical models and research methods for effective thermomechanical characteristics and residual stress-strain state of panels made of layered nanomodified materials.

5. Conclusion

Nanocomposites based on ED-20 epoxy resin and titanium dioxide nanoparticles have been obtained by introducing finished nanoparticles into epoxy resin at the stage of its curing, and the effect of nanoparticle concentration on physical and mechanical properties has been investigated. The physical and mechanical properties of epoxy nanocomposites have been investigated. It is shown that the introduction of 1 mass. % TiO₂ nanoparticles leads to an increase in the relative deformation by 35-40%. The maximum tensile strength values are achieved at a concentration of 3 wt. % TiO₂. The increase in the elastic modulus is 20-25% at TiO₂ concentrations above 1%. Improved mechanical properties indicate the formation of strong interfacial interactions.

This opens new prospective for tailored fabrication of polymer nanocomposites with desired structure and properties. Further research can be aimed toward the development of nanocomposites with advanced mechanical properties.

To determine the structure of the obtained nanocomposite, the method of IR spectroscopy can be further used. IR spectroscopy allows first to get evidences of the interaction between nanoparticles and polymer matrix and, second, get the information about the structure of the resulting nanocomposite. For the details of the IR characterization of the polymer nanocomposites, it is referred to the literature [59]-[61].

This study was funded by RFBR, project number 19-01-00675.

References

- [1] L. N. Rabinskiy, S. A. Sitnikov, "Development of technologies for obtaining composite material based on silicone binder for its further use in space electric rocket engines," *Periodico Tche Quimica*, 15(Special Issue 1), pp. 390–395, 2018.
- [2] V. A. Pogodin, L. N. Rabinskii, S. A. Sitnikov, "3D Printing of Components for the Gas-Discharge Chamber

- of Electric Rocket Engines," Russian Engineering Research, vol. 39, no. 9, pp. 797-799, 2019.
- [3] Y. K. Kyaw, E. L. Kuznetsova, A. V. Makarenko "Complex mathematical modelling of mechatronic modules of promising mobile objects," INCAS Bulletin, 12(Special Issue), pp. 91-98, 2020.
- [4] L. E. Kuznetsova, V. F. Fedotenkov, "Dynamics of a spherical enclosure in a liquid during ultrasonic cavitation," Journal of Applied Engineering Science, 18(4), pp. 681 – 686, 2020.
- [5] A. V. Makarenko, E. L. Kuznetsova, "Energy-Efficient Actuator for the Control System of Promising Vehicles," Russian Engineering Research, 39(9), pp. 776-779, 2019.
- [6] N. A. Kucheva, V. Kohlert, "Analytical solution of the problem of thermoelasticity for a plate heated by a source with a constant heat supply on one surface," Turkish Journal of Computer and Mathematics Education (TURCOMAT), vol. 12, no. 10, pp. 1622-1633, 2021.
- [7] E. L. Kuznetsova, A. V. Makarenko, "Mathematic simulation of energy-efficient power supply sources for mechatronic modules of promising mobile objects," Periodico Tche Quimica, 15(Special Issue 1), pp. 330-338, 2018.
- [8] Y. Li, A. M. Arutiunian, E. L. Kuznetsova, G. V. Fedotenkov, "Method for solving plane unsteady contact problems for rigid stamp and elastic half-space with a cavity of arbitrary geometry and location," INCAS Bulletin, 12(Special Issue), pp. 99–113, 2020.
- [9] E. L. Kuznetsova, G. V. Fedotenkov, E. I. Starovoirov, "Methods of diagnostic of pipe mechanical damage using functional analysis, neural networks and method of finite elements," INCAS Bulletin, 12(Special Issue), pp. 79–90, 2020.
- [10] Y. K. Kyaw, P. F. Pronina, P. O. Polyakov, "Mathematical modelling of the effect of heat fluxes from external sources on the surface of spacecraft," Journal of Applied Engineering Science, 18(4), pp. 732–736, 2020.
- [11] V. F. Formalev, S. A. Kolesnik, B. A. Garibyan, "Mathematical modeling of heat transfer in anisotropic plate with internal sinks," AIP Conference Proceedings, 2181, 020003, 2019.
- [12] N. A. Kucheva, V. Kohlert, "Mathematical modeling methods for estimation the thermophysical properties of heat-protective composite materials," Turkish Journal of Computer and Mathematics Education (TURCOMAT), vol. 12, no. 10, pp. 1606-1612, 2021.
- [13] N. A. Kucheva, "Investigation of the mechanical properties of heat-protective highly porous composite materials using the effective medium model," Turkish Journal of Computer and Mathematics Education (TURCOMAT), vol. 12, no. 10, pp. 1613-1621, 2021.
- [14] V. F. Formalev, S. A. Kolesnik, B. A. Garibyan, "Heat transfer with absorption in anisotropic thermal protection of high-temperature products," Herald of the Bauman Moscow State Technical University, Series Natural Sciences, (5), pp. 35–49, 2019.
- [15] S. A. Kolesnik, N. A. Bulychev, "Numerical analytic method for solving the inverse coefficient problem of heat conduction in anisotropic half-space," Journal of Physics: Conference Series, 1474(1), 012024, 2020.
- [16] V. F. Formalev, N. A. Bulychev, S. A. Kolesnik, M. A. Kazaryan, "Thermal state of the package of cooled gas-dynamic microlasers," Proceedings of SPIE - The International Society for Optical Engineering, 11322, article number 113221B, 2019.
- [17] O. A. Butusova, "Surface Modification of Titanium Dioxide Microparticles Under Ultrasonic Treatment," International Journal of Pharmaceutical Research, vol. 12, i. 4, pp. 2292-2296, 2020.
- [18] O. A. Butusova, "Stabilization of Carbon Microparticles by High-Molecular Surfactants," International Journal of Pharmaceutical Research, vol. 12, Supplementary Issue 2, pp. 1147-1151, 2020.
- [19] Yu. V. Ioni, A. Ethiraj, "New Tailor-Made Polymer Stabilizers for Aqueous Dispersions of Hydrophobic Carbon Nanoparticles," International Journal of Pharmaceutical Research, vol. 12, i. 4, pp. 3443-3446, 2020.
- [20] Yu. V. Ioni, "Nanoparticles of noble metals on the surface of graphene flakes," Periodico Tche Quimica, vol. 17, no. 36, pp. 1199-1211, 2020.
- [21] O. A. Butusova, "Vinyl Ether Copolymers as Stabilizers of Carbon Black Suspensions," International Journal of Pharmaceutical Research, vol. 12, Supplementary Issue 2, pp. 1152-1155, 2020.
- [22] M. O. Kaptakov, "Catalytic Desulfuration of Oil Products under Ultrasonic Treatment," International Journal of Pharmaceutical Research, vol. 12, Supplementary Issue 2, pp. 1838-1843, 2020.
- [23] B. A. Garibyan, "Enhancement of Mechanical Properties of Inorganic Glass under Ultrasonic Treatment," International Journal of Pharmaceutical Research, vol. 12, Supplementary Issue 2, pp. 1829-1832, 2020.
- [24] M. O. Kaptakov, "Enhancement of Quality of Oil Products under Ultrasonic Treatment," International Journal of Pharmaceutical Research, vol. 12, Supplementary Issue 2, pp. 1851-1855, 2020.
- [25] O. A. Butusova, "Adsorption Behaviour of Ethylhydroxyethyl Cellulose on the Surface of Microparticles of Titanium and Ferrous Oxides," International Journal of Pharmaceutical Research, vol. 12, Supplementary Issue 2, pp. 1156-1159, 2020.
- [26] A. N. Tarasova, "Vibration-based Method for Mechanochemical Coating Metallic Surfaces," International Journal of Pharmaceutical Research, vol. 12, Supplementary Issue 2, pp. 1160-1168, 2020.
- [27] B. A. Garibyan, "Mechanical Properties of Electroconductive Ceramics," International Journal of Pharmaceutical Research, vol. 12, Supplementary Issue 2, pp. 1825-1828, 2020.
- [28] M. O. Kaptakov, "Effect of Ultrasonic Treatment on Stability of TiO₂ Aqueous Dispersions in Presence of Water-Soluble Polymers," International Journal of Pharmaceutical Research, vol. 12, Supplementary Issue 2, pp. 1821-1824, 2020.

- [29] Yu. V. Ioni, "Synthesis of Metal Oxide Nanoparticles and Formation of Nanostructured Layers on Surfaces under Ultrasonic Vibrations," *International Journal of Pharmaceutical Research*, vol. 12, i. 4, pp. 3432-3435, 2020.
- [30] A. N. Tarasova, "Effect of Reagent Concentrations on Equilibria in Water-Soluble Complexes," *International Journal of Pharmaceutical Research*, vol. 12, Supplementary Issue 2, pp. 1169-1172, 2020.
- [31] A. N. Tarasova, "Effect of Vibration on Physical Properties of Polymeric Latexes," *International Journal of Pharmaceutical Research*, vol. 12, Supplementary Issue 2, pp. 1173-1180, 2020.
- [32] Yu. V. Ioni, A. Ethiraj, "Study of Microparticles Surface Modification by Electrokinetic Potential Measuring," *International Journal of Pharmaceutical Research*, vol. 12, i. 4, pp. 3436-3439, 2020.
- [33] Yu. V. Ioni, "Effect of Ultrasonic Treatment on Properties of Aqueous Dispersions of Inorganic and Organic Particles in Presence of Water-Soluble Polymers," *International Journal of Pharmaceutical Research*, vol. 12, i. 4, pp. 3440-3442, 2020.
- [34] O. A. Butusova, "Design and Properties of Magnetically Controlled Sorbents," *Turkish Journal of Computer and Mathematics Education (TURCOMAT)*, vol. 12, no. 5, pp. 515-519, 2021.
- [35] O. A. Butusova, "Application of Magnetically Controlled Sorbents for Detoxication," *Turkish Journal of Computer and Mathematics Education (TURCOMAT)*, vol. 12, no. 5, pp. 520-524, 2021.
- [36] M. O. Kaptakov, "Effect of Thin Polymer Layers on Mechanical Properties of Metal Surfaces," *Turkish Journal of Computer and Mathematics Education (TURCOMAT)*, vol. 12, no. 5, pp. 525-529, 2021.
- [37] B. A. Garibyan, "Determination of the Elastic Modulus of the Coating Using a Spherical Indenter," *Turkish Journal of Computer and Mathematics Education (TURCOMAT)*, vol. 12, no. 10, pp. 1594-1600, 2021.
- [38] M. O. Kaptakov, "Modelling of Mechanical Properties of Metal Plates with Polymer Coatings," *Turkish Journal of Computer and Mathematics Education (TURCOMAT)*, vol. 12, no. 5, pp. 530-534, 2021.
- [39] B. A. Garibyan, "Theoretical Estimations of Influence of Polymer Coatings on the Elastic Modulus and Ultimate Strength of Steel Samples," *Turkish Journal of Computer and Mathematics Education (TURCOMAT)*, vol. 12, no. 10, pp. 1651-1656, 2021.
- [40] M. O. Kaptakov, "Investigation of Effective Mechanical Characteristics of Nanomodified Carbon-Epoxy Composite by Numerical and Analytical Methods," *Turkish Journal of Computer and Mathematics Education (TURCOMAT)*, vol. 12, no. 5, pp. 535-541, 2021.
- [41] M. O. Kaptakov, "Obtaining of Carbon Fibers Based Composite Materials and Study of Their Mechanical Properties," *Turkish Journal of Computer and Mathematics Education (TURCOMAT)*, vol. 12, no. 10, pp. 1601-1605, 2021.
- [42] V. F. Formalev, S. A. Kolesnik, B. A. Garibyan, "Analytical solution of the problem of conjugate heat transfer between a gasdynamic boundary layer and anisotropic strip," *Herald of the Bauman Moscow State Technical University, Series Natural Sciences*, 5(92), pp. 44-59, 2020.
- [43] Y. Sun, S. A. Kolesnik, E. L. Kuznetsova, "Mathematical modeling of coupled heat transfer on cooled gas turbine blades," *INCAS Bulletin*, 12(Special Issue), pp. 193-200, 2020.
- [44] I. Kurchatov, N. Bulychev, S. Kolesnik, E. Muravev, "Application of the direct matrix analysis method for calculating the parameters of the luminescence spectra of the iron ion in zinc sulfide crystals," *AIP Conference Proceedings*, 2181, 020015, 2019.
- [45] B. A. Antufev, E. L. Kuznetsova, L. N. Rabinskiy, O. V. Tushavina, "Investigation of a complex stress-strain state of a cylindrical shell with a dynamically collapsing internal elastic base under the influence of temperature fields of various physical nature," *Asia Life Sciences*, (2), pp. 689-696, 2019.
- [46] G. A. Kalugina, A. V. Ryapukhin, "Impact of the 2020 Pandemic on Russian Aviation," *Russian Engineering Research*, vol. 41, no. 7, pp. 627-630, 2021.
- [47] R. N. Zaripov, I. M. Murakaev, A. V. Ryapukhin, "Development of the Organization's Key Performance Indicators System in Order to Improve the Effectiveness of Its Human Capital and Risk Management," *TEM Journal*, vol. 10, no. 1, pp. 298-302, 2021.
- [48] A. A. Kalugin, G. A. Kalugina, A. V. Ryapukhin, "Informational Support for the Sale of Passenger Aircraft," *Russian Engineering Research*, vol. 41, no. 2, pp. 183-187, 2021.
- [49] R. N. Zaripov, I. M. Murakaev, S. V. Novikov, A. V. Ryapukhin, "Corporate Structure for Innovative Enterprises," *Russian Engineering Research*, vol. 40, no. 2, pp. 137-139, 2020.
- [50] A. Y. Burova, "Concept of multistage discrete fourier transform without performing multiplications" *Journal of Physics: Conference Series*, vol. 1889, no. 2, 022003, 2021.
- [51] A. Burova, "Reducing the Error of Digital Algorithms for Deductive Signal Processing Based on Their Multi-Stage Discrete Fourier Transform by the Difference Digital Filters," *22th International Conference on Digital Signal Processing and its Applications, DSPA 2020*, no. 9213275, 2020.
- [52] A. Y. Burova, "Minimization of asymmetry of thrust of dual-flow turbojet engines of airliner in accordance with the results of system analysis of thrust parameters," *Asia Life Sciences*, no. 2, pp. 629-643, 2019.
- [53] N. V. Britvin, E. O. Karpukhin, "Determining the linear network code parameters to minimize the destructive factors influence in telecommunications systems and networks," *Journal of Physics: Conference Series*, vol. 1889, no. 3, 032016, 2021.

- [54] S. V. Grazion, M. V. Mukomela, M. N. Erofeev, V. V. Spiriyagin, S. S. Amelin, "Experimental Estimation of the Waveguide Effect on the Acoustic Emission Signal Parameters in Monitoring Facilities with a Long Surface Radius of Curvature," *Journal of Machinery Manufacture and Reliability*, vol. 49, no. 11, pp. 971-979, 2020.
- [55] M. I. Gordeeva, "Methods for forecasting and control of the phase composition and residual voltage in Al-Cu-Li alloys in friction mixing welding" *Journal of Physics: Conference Series*, vol. 1713, no. 1, 012017, 2020.
- [56] N. A. Bulychev, E. L. Kuznetsova, "Ultrasonic Application of Nanostructured Coatings on Metals," *Russian Engineering Research*, 39 (9), pp. 809–812, 2019.
- [57] N. A. Bulychev, V. V. Bodryshev, L. N. Rabinskiy, "Analysis of geometric characteristics of two-phase polymer-solvent systems during the separation of solutions according to the intensity of the image of micrographs," *Periodico Tche Quimica*, 16(32), pp. 551–559, 2019.
- [58] S. A. Kolesnik, N. A. Bulychev, "Numerical analytic method for solving the inverse coefficient problem of heat conduction in anisotropic half-space," *Journal of Physics: Conference Series*, 1474(1), 012024, 2020.
- [59] N. A. Bulychev, A. V. Ivanov, "Effect of vibration on structure and properties of polymeric membranes," *International Journal of Nanotechnology*, vol. 16, nos. 6/7/8/9/10, pp. 334 – 343, 2019.
- [60] N. A. Bulychev, A. V. Ivanov, "Nanostructure of Organic-Inorganic Composite Materials Based on Polymer Hydrogels," *International Journal of Nanotechnology*, vol. 16, nos. 6/7/8/9/10, pp. 344 – 355, 2019.
- [61] N. A. Bulychev, A. V. Ivanov, "Study of Nanostructure of Polymer Adsorption Layers on the Particles Surface of Titanium Dioxide," *International Journal of Nanotechnology*, vol. 16, nos. 6/7/8/9/10, pp. 356 – 365, 2019.
- [62] N. A. Bulychev, L. N. Rabinskiy, O. V. Tushavina, "Effect of intense mechanical vibration of ultrasonic frequency on thermal unstable low-temperature plasma," *Nanoscience and Technology: An International Journal*, 11 (1), pp. 15–21, 2020.
- [63] N. A. Bulychev, L. N. Rabinskiy, "Ceramic Nanostructures Obtained by Acoustoplasma Technique," *Nanoscience and Technology: An International Journal*, 10 (3), pp. 279–286, 2019.
- [64] O. A. Pashkov, "Influence of Polymer Coatings on the Mechanical Properties of Steel Samples in Tensile and Bending Tests," *Turkish Journal of Computer and Mathematics Education (TURCOMAT)*, vol. 12, no. 5, pp. 542-548, 2021.
- [65] O. A. Pashkov, "Investigation of the Effect of Steel Plate Size and Elevated Temperature on Critical Load in Stability Tests," *Turkish Journal of Computer and Mathematics Education (TURCOMAT)*, vol. 12, no. 10, pp. 1657-1663, 2021.
- [66] B. A. Antufev, E. L. Kuznetsova, L. N. Rabinskiy, O. V. Tushavina, "Complex stressed deformed state of a cylindrical shell with a dynamically destructive internal elastic base under the action of temperature fields of various physical nature," *Asia Life Sciences*, (2), pp. 775–782, 2019.
- [67] L. N. Rabinskiy, O. V. Tushavina, "Problems of land reclamation and heat protection of biological objects against contamination by the aviation and rocket launch site," *Journal of Environmental Management and Tourism*, 10(5), pp. 967–973, 2019.
- [68] A. N. Astapov, I. P. Lifanov, L. N. Rabinskiy, "Perspective Heat-Resistant Coating for Protection of Cf/SiC Composites in Air Plasma Hypersonic Flow," *High Temperature*, 57(5), pp. 744–752, 2019.
- [69] V. N. Dobryanskiy, L. N. Rabinskiy, O. V. Tushavina, "Validation of methodology for modeling effects of loss of stability in thin-walled parts manufactured using SLM technology," *Periodico Tche Quimica*, 16(33), pp. 650–656, 2019.
- [70] M. Sha, Y. A. Utkin, O. V. Tushavina, P. F. Pronina, "Experimental studies of heat and mass transfer from tip models made of carbon-carbon composite material (cccm) under conditions of high-intensity thermal load," *Periodico Tche Quimica*, vol.17, i. 35, pp 988-997, 2020.
- [71] O. A. Pashkov, "Theoretical calculation of the thickness of interphase zones in the Al-Al₂O₃ composite," *Turkish Journal of Computer and Mathematics Education (TURCOMAT)*, vol. 12, no. 10, pp. 1672-1677, 2021.
- [72] O. A. Pashkov, "Experimental and Theoretical Study of Mechanical Properties of Matrix Composite Materials," *Turkish Journal of Computer and Mathematics Education (TURCOMAT)*, vol. 12, no. 10, pp. 1678-1684, 2021.
- [73] P. F. Pronina, O. V. Tushavina, E. I. Starovoitov, "Study of the radiation situation in moscow by investigating elastoplastic bodies in a neutron flux taking into account thermal effects," *Periodico Tche Quimica*, 17(35), pp. 753–764, 2020.
- [74] A. A. Orekhov, Y. A. Utkin, P. F. Pronina, "Determination of deformation in mesh composite structure under the action of compressive loads," *Periodico Tche Quimica*, 17(35), pp. 599–608, 2020.
- [75] A. V. Babaytsev, L. N. Rabinskiy, K. T. Aung, "Investigation of the contact zone of a cylindrical shell located between two parallel rigid plates with a gap," *INCAS Bulletin*, 12(Special Issue), pp. 43–52, 2020.
- [76] O. V. Tushavina, "Coupled heat transfer between a viscous shock gasdynamic layer and a transversely streamlined anisotropic half-space," *INCAS Bulletin*, 12 (Special Issue), pp. 211–220, 2020.
- [77] S. Vakhneev, E. Starovoitov, "Damping of circular composite viscoelastic plate vibration under neutron irradiation," *Journal of Applied Engineering Science*, 18(4), pp. 699–704, 2020.

Sources of Funding for Research Presented in a Scientific Article or Scientific Article Itself

This study was funded by RFBR, project number 19-01-00675.

**Creative Commons Attribution License 4.0
(Attribution 4.0 International, CC BY 4.0)**

This article is published under the terms of the Creative Commons Attribution License 4.0

https://creativecommons.org/licenses/by/4.0/deed.en_US