Investigating electrical and optical properties of low energy ion irradiated α -Fe₂O₃ (Hematite) thin films for solar cell applications

Indra Sulania^{1*}, Jyoti Kaswan², Vinesh Attatappa², Ranjeet Karn³, D C Agarwal⁴
 and D Kanjilal¹

¹Inter University Accelerator Centre, New Delhi, Delhi, India

²Department of physics, Amity University, Manesar, Haryana, India

³Jamshedpur Cooperative College, Jamshedpur, Jharkhand, India

⁴Sant Longowal Institute of Engineering and Technology, Sangrur, Punjab, India

*Email: indra.sulaniya@gmail.com

Iron oxide is an important transition metal oxides and can exist in different phases such as FeO, α -Fe₂O₃, γ -Fe₂O₃, β -Fe₂O₃ and Fe₃O₄. Hematite or α -Fe₂O₃ is the most stable iron oxide under normal ambient conditions. It is a low cost, non-toxic and environment friendly material which is easily available in nature [1].

Thin films of α -Fe₂O₃ or Hematite with thickness ~ 100 nm were synthesized on crystalline Si (100) and glass substrates by resistive heating method at a pressure of 3×10^{-6} torr. The as-deposited films were annealed at 400 °C in Oxygen environment for 2 hours to obtain the desired phase. The annealed films found to be polycrystalline in nature with an average crystallite size ~ 7 nm. The optical measurements of the thin films were performed with UV-Vis. spectrometer from Hitachi. The direct and indirect band gaps were found to be 2.2 and 1.5 eV respectively for annealed α -Fe₂O₃ thin films [2, 3]. Figure 1 shows I-V characteristics of annealed thin films with a current generated in μ A.

Figure 1: I-V characteristic of annealed α -Fe₂O₃ thin film

The film shows a good IV response in the presence of light where the current increase from μ A to mA regime. I-V characteristics and Hall-effect measurement of annealed films showed n-type semiconducting behavior. Further, films

were irradiated with nitrogen ions of energy 10 keV at ion fluence of 1×10^{18} ions/cm².

Figure 2 shows I-V characteristics of irradiated α -Fe₂O₃ thin film at fluence of 1×10^{18} ions/cm² from -6 V to 6 V, which is found to be semiconducting in nature. Current generated is found to be in mA. Current shows saturation after 5V, as current generated at higher voltages is too high for measuring device used for I-V characterization.

Figure 2: I-V characteristic of irradiated α -Fe₂O₃ thin film

After irradiation, a decrease in both direct as well as indirect band gap was observed, from 2.2 to 2.1 eV and 1.5 to 1.3 eV respectively.

I-V characteristic and Hall effect measurement confirmed change in conductivity of the films from n-type to p-type after irradiation, which can have possible applications in semiconducting device fabrications [4]. Further, tuning of the bandgap and study of transport properties is needed to have possible applications in solar cells.

References

1. A.A. Ziabari, F.E. Ghodsi, J. Alloy. Compd. 509 (2011) 8748e8755.
2. X.L. Huang, Y. Yang, J. Ding, Acta Mater. 61 (2013) 548e557
3. J.A. Glasscock, P.R.F. Barnes, I.C. Plumb, A. Bendavid, P.J.Martin, Thin Solid Films 516 (2008) 1716e1724.
4. S. Wang, W. Wang, W. Wang, Z. Jiao, J. Liu, Y. Qian, Sens. Actuators B-Chem. 69 (2000) 22e27.