Deep Traps and Parasitic Effects in $\text{Al}_{0.25}\text{Ga}_{0.75}\text{N}/\text{GaN}/\text{SiC}$ Heterostructures with Different Schottky Contact Surfaces

Salah Saadaoui^{1,2}, Olfa Fathallah¹, Mohamed Mongi Ben Salem¹, Christophe Gaquière³, Hassen Maaref¹

¹Laboratoire de Micro-Optoélectronique et Nanostructures, Faculté des Sciences de Monastir, Université de Monastir, Monastir, Tunisie

²Faculty of Sciences and Arts (Mohail Asir Campus-Males), King Khalid University, Abha, Kingdom of Saudi Arabia

³Institut d'Electronique de Microélectronique et de Nanotechnologie IEMN, Département Hyperfréquences et Semiconducteurs, Université des Sciences et Technologies de Lille, Villeneuve d'Ascq Cedex, France

Email: salahaadaoui_22@yahoo.fr

Received 5 August 2015; accepted 24 August 2015; published 27 August 2015

Copyright © 2015 by authors and OALib.

This work is licensed under the Creative Commons Attribution International License (CC BY).

<http://creativecommons.org/licenses/by/4.0/>

Open Access

Abstract

Hysteresis phenomenon in the capacitance-voltage characteristics under reverse-biased Schottky gate has been investigated for $\text{Al}_{0.25}\text{Ga}_{0.75}\text{N}/\text{GaN}/\text{SiC}$ structures having three different gate surfaces. This parasitic effect was correlated with the presence of deep levels in our samples. Indeed, we have noticed the presence of two traps named H1 and A1; their respective activation energies, which are determined using capacitance deep level transient spectroscopy (DLTS) are respectively 0.74 and 0.16 eV. The H1 hole trap was associated to extended defect in the $\text{Al}_{0.25}\text{Ga}_{0.75}\text{N}/\text{GaN}$ heterostructure such as threading dislocations and was responsible of capacitance hysteresis phenomenon. The A1 electron trap appears only in the HEMT (1), which has the smaller Schottky contact area. This trap was related to a punctual defect and attributed to free surface states in the access region between the gate and the source.

Keywords

AlGaN/GaN HEMT, Capacitance Hysteresis, Deep Traps, Gate Surface Effect

Subject Areas: Applied Physics

1. Introduction

GaN high electron mobility transistors (HEMT's) have revolutionized power amplification from RF to millimeter-wave regime. At 4 GHz, a power density in excess of 40 W/mm has been demonstrated [1] [2]. However, the degradation and the reliability problem of GaN-based HEMT's, caused by the trap-related effects, has been a critical problem that was widely discussed in recent years [3]-[12]. These defects may result from surface states and threading dislocations in the AlGaN/GaN heterostructures [6]-[12]. The well-known phenomena are capacitance hysteresis [7] [10] [11], high leakage current [10]-[13], Kink effect [3]-[6] and drain current collapse [3] [5] [6] [9]. In this context, as a preliminary study of parasitic effects, we had started by examining the electrical behavior on the AlGaN/GaN heterostructures by the use of a variety of electrical techniques $C(V)$, $I_g(V_g)$, $I_{ds}(V_{ds})$, capacitance DLTS and drain-current DLTS [6] [10] [11]. This study enabled us to locate certain anomalies in the electrical characteristics of these components which seem to be caused by trapping mechanisms of the carriers by defects. In particular, capacitance DLTS measurements carried out for three samples with different Schottky contact surfaces [(200 $\mu\text{m} \times 200 \mu\text{m}$), (2 $\mu\text{m} \times 100 \mu\text{m}$) and (1 $\mu\text{m} \times 100 \mu\text{m}$)] revealed the presence of two defects; one negative peak corresponding to a hole trap labeled H1 having an activation energy of 0.74 eV, associated to an extended defect in the AlGaN/GaN heterostructures, and one positive peak corresponding to an electron trap labeled A₁ observed only in the transistor having the smaller Schottky contact surface. The possible explanations of its origin will be established in this work.

2. Experimental

The components under test have been grown by metal organic chemical vapor deposition (MOCVD) on SiC substrate. The device structure growth and its fabrication details were reported elsewhere [6] [10], see Figure 1. For this study, the devices have different Schottky contact surfaces of 200 $\mu\text{m} \times 200 \mu\text{m}$, 2 $\mu\text{m} \times 100 \mu\text{m}$ and 1 $\mu\text{m} \times 100 \mu\text{m}$ for diode, HEMT (2) and HEMT (1) respectively. The $C(V)$ and Capacitance DLTS measurements were done using experimental setups described in detail elsewhere [10].

3. Results and Discussions

3.1. Capacitance-Voltage Measurements

Capacitance-voltage (C-V) measurements of the three (Ni/Au)/Al_{0.25}Ga_{0.75}N/GaN/SiC structures were performed at a frequency of 1 MHz and a temperature between 50 and 320 K (an example is given in Figure 2) by sweeping voltage successively down (V_g from 1 to -10 V) and up (V_g from -10 to 1 V); the voltage sweep directions are shown in Figure 2.

Figure 1. Cross-sectional schematic of an (Ni/Au)/AlGaN/GaN/SiC structure adopted for this work (not to scale).

Figure 2. C (V) characteristics, for (a) diode and (b) HEMT (1) and HEMT (2).

A hysteresis phenomenon, expressed by a shift towards lower reverse bias during the return sweep, has been observed. Saadaoui *et al.* [10] [11] have claimed that the hysteresis curve can be explained as follow: A) emission of electrons, B) total depletion of electrons, C) injection and trapping of electrons and D) accumulation of electrons.

This phenomenon indicates a built-in negative charge increase either in the AlGa_N barrier or in the Ga_N buffer layer. This accumulated negative charge is very possibly due to the electron injection from the gate into the AlGa_N barrier layer through a trap-assisted tunneling mechanism at high reverse bias [10].

To better understand the hysteresis phenomenon dependence with the temperature, we have determined the hysteresis area at each temperature for the three samples (see the Figure 3). We note that the evolution of this phenomenon presents a maximum at ~290 K, for the three samples, whereas it is absent at low temperatures ($T \leq 200$ K). This behavior is practically identical to that observed in the (Ni/Au)/Al_{0.25}Ga_{0.75}N/GaN/SiC Schottky barrier diode [10], which reflects the thermal activation of deep traps. In Figure 3, We remarked that, the hysteresis area at ~290 K in C (V) characteristics is twice higher in the case of HEMT (2), which is in good agreement with the amplitude of the H1 peak observed by DLTS measurements. So, it is reasonable to suggest that H1 trap is responsible of hysteresis phenomenon [10].

3.2. Capacitance DLTS Measurements

In order to clarify the origin of this anomaly, DLTS measurements have been carried out in the temperature range from 50 to 320 K for different rate windows (e_n) and a filling pulse time of 0.5 ms. The DLTS spectra for diode, HEMT (1) and HEMT (2) at $e_n = 213$ s⁻¹, presented in the Figure 4, reveal the presence of one negative peak corresponding to a hole trap labeled H₁ and one positive peak corresponding to an electron trap labeled A₁.

The activation energies were deduced from the Arrhenius diagram of $\ln(T^2/e_n)$ versus $1000/T$, as shown in Figure 5. The Capture cross section (σ_n) and trap density (N_t) of each observed levels on the DLTS spectrum are summarized in Figure 5.

The H₁ trap, observed in the three samples, and the A₁ trap observed only in the HEMT (1), have an activation energy of 0.73 - 0.75 eV and 0.16 eV, respectively. We remarked that, the DLTS spectra of these samples show that the H₁ peak amplitude is higher in the case of diode, which is in good agreement with the hysteresis area in C (V) characteristics. So, it's reasonable to suggest that H₁ trap is responsible of hysteresis phenomenon appearance and leakage current, as demonstrated in our previously work [10] [11]. The H₁ is probably a threading dislocation in the Al_{0.25}Ga_{0.75}N/GaN heterostructure [11].

The A₁ trap is related to a punctual defect [11] which appears in the HEMT (1) and is completely disappeared when the gate area becomes important; thus, it seems to be reasonable that this trap ought to be attributed to free surface states in the access region between the gate and the source. Indeed, the gate area increase results a decrease in the free surface between gate and source, which minimize the surface defects [11].

Figure 3. The temperature dependence of the Hysteresis area, for the three samples.

Figure 4. DLTS spectra at reverse voltage $V_r = -6$ V for the three samples. In the inset, a schematic section of the HEMT structure showing the analysis region (not to scale).

	Trap	Ea (eV)	σ (cm²)	N_t (cm⁻³)
Diode	H_1	0.75	1.09×10^{-13}	4.72×10^{16}
HEMT (2)	H_1	0.73	6.59×10^{-13}	8.13×10^{15}
HEMT (1)	H_1	0.74	1.32×10^{-13}	3.07×10^{15}
	A_1	0.16	1.61×10^{-15}	1.64×10^{15}

Figure 5. Arrhenius diagrams plotted for each observed level. The extracted activation energy (Ea), Capture cross section (σ_n) and trap density (N_t) values are summed up in the table.

4. Conclusion

In conclusion, $\text{Al}_{0.25}\text{Ga}_{0.75}\text{N}/\text{GaN}/\text{SiC}$ structures with three different gate areas have been characterized by temperature-dependent $C(V)$. We have marked a capacitance hysteresis phenomenon more significant around the room temperature. This effect is explained by defect-assisted tunneling. This mechanism was assisted by some extended defects as threading dislocations. Using Capacitance DLTS measurements, we have identified two trap levels H_1 and A_1 . The H_1 hole trap was associated to extended defect in the $\text{Al}_{0.25}\text{Ga}_{0.75}\text{N}/\text{GaN}$ heterostructure such as threading dislocations and was responsible of capacitance hysteresis phenomenon. The A_1 electron trap appears only in the HEMT (1), which has the smaller Schottky contact area. This trap was related to a punctual defect and attributed to free surface states in the access region between the gate and the source. These defects that were already found in our previous works should have an impact on the transport mechanisms though the Schottky contacts which is the aim of future works.

Acknowledgements

This work has been supported by “Comité Mixte de Coopération Universitaire (CMCU) France-Tunisie” under the project “08G1305” between the IEMN-Lille and the LMON Monastir University.

References

- [1] Wu, Y.-F., Moore, M., Saxler, A., Wisleder, T. and Parikh, P. (2006) 40-W/mm Double Field-Plated GaN HEMTs. *DRC Proc*, 151-152.
- [2] Joh, J. and del Alamo, J.A. (2012) Impact of Gate Placement on RF Power Degradation in GaN High Electron Mobility Transistors. *Microelectronics Reliability*, **52**, 33-38.
- [3] Sun, H.F. and Bolognesi, C.R. (2007) Anomalous Behavior of AlGaIn/GaN Heterostructure Field-Effect Transistors at Cryogenic Temperatures: From Current Collapse to Current Enhancement with Cooling. *Applied Physics Letters*, **90**, 123505-123507.
- [4] Meneghesso, G., Rossi, F., Salviati, G., Uren, M.J., Muñoz, E. and Zanoni, E. (2010) Correlation between Kink and Cathodoluminescence Spectra in AlGaIn/GaN High Electron Mobility Transistors. *Applied Physics Letters*, **96**, 263512-263514. <http://dx.doi.org/10.1063/1.3459968>
- [5] Fu, L., Lu, H., Chen, D., Zhang, R., Zheng, Y., Chen, T., Wei, K. and Liu, X. (2011) Field-Dependent Carrier Trapping Induced Kink Effect in AlGaIn/GaN High Electron Mobility Transistors. *Applied Physics Letters*, **98**, 173508-173510. <http://dx.doi.org/10.1063/1.3584861>
- [6] Saadaoui, S., Ben Salem, M.M., Gassoumi, M., Maaref, H. and Gaquière, C. (2012) Anomaly and Defects Characterization by I-V and Current Deep Level Transient Spectroscopy of $\text{Al}_{0.25}\text{Ga}_{0.75}\text{N}/\text{GaN}/\text{SiC}$ High Electron-Mobility Transistors. *Journal of Applied Physics*, **111**, 073713-073718.
- [7] Polyakov, A.Y., Smirnov, N.B., Govorkov, A.V., Markov, A.V., Dabiran, A.M., Wowchak, A.M., Osinsky, A.V., Cui, B., Chow, P.P. and Pearton, S.J. (2007) Deep Traps responsible for Hysteresis in Capacitance-Voltage Characteristics of AlGaIn/GaN Heterostructure Transistors. *Applied Physics Letters*, **91**, 232116-232118. <http://dx.doi.org/10.1063/1.2823607>
- [8] Fang, Z.-Q., Claflin, B., Look, D.C., Green, D.S. and Vetury, R. (2010) Deep Traps in AlGaIn/GaN Heterostructures Studied by Deep Level Transient Spectroscopy: Effect of Carbon Concentration in GaN Buffer Layers. *Journal of Applied Physics*, **108**, 063706-063711. <http://dx.doi.org/10.1063/1.3488610>
- [9] Joh, J. and del Alamo, J.A. (2011) A Current-Transient Methodology for Trap Analysis for GaN High Electron Mobility Transistors. *IEEE Transactions on Electron Devices*, **58**, 132-140. <http://dx.doi.org/10.1109/TED.2010.2087339>
- [10] Saadaoui, S., Ben Salem, M.M., Gassoumi, M., Maaref, H. and Gaquière, C. (2011) Electrical Characterization of (Ni/Au)/ $\text{Al}_{0.25}\text{Ga}_{0.75}\text{N}/\text{GaN}/\text{SiC}$ Schottky Barrier Diode. *Journal of Applied Physics*, **110**, 013701-013706. <http://dx.doi.org/10.1063/1.3600229>
- [11] Saadaoui, S., Ben Salem, M.M., Fathallah, O., Gassoumi, M., Gaquière, C. and Maaref, H. (2013) Leakage Current, Capacitance Hysteresis and Deep Traps in $\text{Al}_{0.25}\text{Ga}_{0.75}\text{N}/\text{GaN}/\text{SiC}$ High-Electron-Mobility Transistors. *Physica B: Condensed Matter*, **412**, 126-129. <http://dx.doi.org/10.1016/j.physb.2012.11.031>
- [12] Park, Y.S., Lee, M., Jeon, K., Yoon, I.T., Shon, Y., Im, H., Park, C.J., Cho, H.Y. and Han, M.-S. (2010) Deep Level Transient Spectroscopy in Plasma-Assisted Molecular Beam Epitaxy Grown $\text{Al}_{0.2}\text{Ga}_{0.8}\text{N}/\text{GaN}$ Interface and the Rapid Thermal Annealing Effect. *Applied Physics Letters*, **97**, 112110-112112. <http://dx.doi.org/10.1063/1.3491798>

- [13] Huang, S., Shen, B., Xu, F.-J., Lin, F., Miao, Z.-L., Song, J., Lu, L., Cen, L.-B., Sang, L.-W., Qin, Z.-X., Yang, Z.-J. and Zhang, G.-Y. (2009) Study of the Leakage Current Mechanism in Schottky Contacts to $\text{Al}_{0.25}\text{Ga}_{0.75}\text{N}/\text{GaN}$ Heterostructures with AlN Interlayers. *Semiconductor Science and Technology*, **24**, 055005-055009.
<http://dx.doi.org/10.1088/0268-1242/24/5/055005>