Determination of Trace Metallic Constituents in Nuclear-grade BeO Matrix by D.C. Arc Carrier Distillation and ICP-AES: A Comparative Evaluation

S. Pathak^a, Sk. Jayabun^a, B. Rajeswari^a, N. Pathak^a, M. Mohapatra^{a,b}, Arijit Sengupta^{*a}, and R.M. Kadam^{a,b}

^a Radiochemistry Division, Bhabha Atomic Research Centre, Mumbai, India

^b Homi Bhabha National Institute, Mumbai, India

INTRODUCTION

Chemical quality control is an essential part for the characterization of nuclear materials and includes trace metal assay of base materials, intermediate and final products (1-3). Beryllium oxide (BeO) crystallizes in the hexagonal wurtzite structure and is used in rocket engines and as a transparent protective over-coating on aluminized telescope mirrors (4-6). The high thermal conductivity blended with an electrical insulator makes BeO useful in many high-performance semiconductor parts. BeO has extensively been used as structural ceramic for high-performance microwave devices, vacuum tubes, magnetrons, and gas lasers. BeO is also carcinogenic and can lead to chronic beryllium disease. However, the ceramic form is not a hazardous waste under U.S. federal law. In the nuclear reactor, BeO has been used as a neutron reflector (7-8). In view of such technological importance, stringent chemical quality control of BeO is essential to achieve its desired performance either in the nuclear, semiconductor, and thermo-electric industries.

In general, D.C. arc carrier distillation is routinely applied for trace characterization of nuclear materials (9-12). This is a solid state route involving the least handling of the samples, which is highly important in order to avoid process pickup and radio-toxicity of the nuclear materials. In the carrier distillation approach, suitable material is used

ABSTRACT

A comparative evaluation was carried out to determine the trace metallic constituents in nuclear-grade BeO by D.C. arc carrier distillation and inductively coupled plasma atomic emission spectrometry. D.C. arc carrier distillation is accomplished by physical separation of the major matrix to avoid interference, while ICP-AES employs the solution route because chemical separation of the major matrix is preferred. The method was optimized for Ca, Fe, Mg, Mn, Si, Na, Li, Al, B, Cd, Cr, Cu, Ni, and Zn at minor and trace levels and was optimized using multiple standards and validated using synthetic samples. The analytical performance for both techniques, including detection limits, sensitivity, linear dynamic range, etc., was compared. Though both techniques were found to be suitable for analysis of nuclear-grade BeO samples, some differences were observed. ICP-AES provides better analytical performance, while D.C. arc requires less sample handling, minimizes process pickup, and results in less toxic exposure in the laboratory.

to physically separate the analytes from the refractory matrix on the basis of volatilization. This separation is a prerequisite for emission-rich nuclear materials to avoid matrix effects pertaining to spectral interference (13-16). Though this technique is advantageous in some cases, limitations do exist. The arc not being an optically thin source, self-absorption is one of the predominating factors in reducing the linear dynamic range of the

analysis; hence, the sigmoid curve is expected. Each replicate measurement is associated with a different arc and independent arc characteristics. Arc wandering is another major issue resulting in the reduction of poor precision of the analysis. In the case of rare earth element analysis, d.c. arc suffers a major issue since the rare earth elements form refractory oxides. Therefore, not sufficient amount of these analytes can reach the arc and as a result, it is practically impossible to achieve very low detection limits using this arrangement.

On the other hand, ICP-AES offers simultaneous multi-element determination of the analytes with a wide range of concentrations (17-20). ICP-AES is known for its analytical merits such as wide linear dynamic range, high sensitivity, very low detection limits, and high degree of precision. Since the radio frequency plasma is optically thin and a stable source, self-absorption and precision are higher in comparison to D.C. arc carrier distillation. The high temperature (6000 - 6500 K) of the plasma in the analytical zone provides more energy for excitation and atomization of the analytes, resulting in more emission lines compared to D.C. arc carrier distillation. In ICP-AES, the atomic as well as the ionic lines can be observed. This provides the option for choosing multiple analytical lines for the determination of the analytes; however, it would also lead to spectral interference mainly from emission-rich elements. Preferential separation of these elements from the actual analytes/samples is a prerequisite and is

*Corresponding author.
E-mail: arijita@barc.gov.in
Tel: +91 22 25590630

achieved by chemical separation and using solvent extraction or solid phase chromatographic separation.

In view of these differences of methods, a comparative evaluation was carried out for the chemical quality control of nuclear-grade BeO and its trace metallic impurities by D.C. arc carrier distillation and by ICP-AES.

EXPERIMENTAL

Reagents and Standard Solutions

The standard solutions for the individual elements were prepared from CertiPUR® ICP standard reference material solutions (E-Merck, Germany). Suprapur® HNO₃ (E-Merck, Germany) and quartz double-distilled water were used throughout this study. Multi-point standardization was carried out for ICP-AES analysis. The optimized ICP-AES conditions are listed in Table I.

ICP-AES Instrumental Operating Conditions for BeO Sample Analysis

An atomic emission spectrometer (SpectroArcos, Germany) with ICP source and coupled with a D.C. arc system with a charge coupled device (CCD) as the detector was used for the impurity analyses (21). Unlike a photomultiplier tube, different pixels present in the CCD detector give a 2D image of the spectra. The cartridge associated with the detection can provide the detection in a vacuum or in an Ar atmosphere to avoid interference from the environment. Ar flushing is a prerequisite to open the slit for any detection, resulting in reduction of background as well as keeping the detector safe. The detector system, consisting of linear arrays of CCD detectors (3648 pixels/array), thermally stabilized, provides the ability to choose the alternate analytical lines. High purity argon plasma was used for the excitation

source. To establish the calibration curves for the analytes, the solution standards in the concentration range of 1 -100 ppm were prepared from Specpure solutions. Since ICP-AES has a large dynamic range, linear correlations between concentrations and intensity were obtained to establish the calibration curves. Triplicate measurements were carried out to report each data. The dilution was done using 1 M HNO₃ and the same solution was also used as a blank.

Sample Preparation for ICP-AES Analysis

For the ICP-AES analysis of actual BeO samples, the solid powder was allowed to dissolve in concentrated HNO₃ under an infrared lamp. After repeated evaporation to dryness, the medium was kept 1 M HNO₃. This will lead to complete dissolution of the matrix along with the metallic impurities mainly in nitrate form.

D.C. Arc Carrier Distillation Technique for BeO Sample Analysis

For d.c. arc carrier distillation, the same detector system was used. However, the sample introduction and the power supply differed. The

ASTM designation E-130-66 type S-2 on a S-1 pedestal was used as the anode, while pointed electrode of ASTM designation E-130-66 type C-1 was used as the cathode. Since BeO has a lower density, a 40 mg charge was used for the carrier distillation technique. AgCl of 10% composition was used as the carrier to physically separate the analytes from the matrix elements. The sample charge was put on anode after complete homogenization of the samples with the carrier having almost similar particle size. Subsequently, the charge was tapped for proper packing of the samples inside the anode, while venting was done to keep the passage of any gas, if generated, during arcing. This also helped to avoid any sample charge going directly to the arc. After the arc is generated by the appropriate current and arc gap (as specified in Table II), the electrons from the pointed cathode collimated towards the sample charge on the anode. This impact can lead to excitation of the analytes into the arc. The arc temperature achieved is ~2500 K and is sufficient only for excitation of the atomic lines of the analytes. The analytes in the d.c. arc can be divided into different groups depending on the volatility

TABLE I
Optimized Instrumental Parameters for ICP-AES

Optical design	750 mm and P-R mounting
Grating	Holographic, ion-etched optical grating
Groove density	1800 and 3600 grooves/mm
Grating size	110 x 110 mm
Wavelength range	120-800 nm
Bandpass	0.0023 nm from 120 to 340 nm 0.0046 nm from 340 to 800 nm
Thermal regulation	Controlled to 30 ± 1 °C
Frequency	27.12 MHz
Pump	Dual channel (12 roller)
Nebulizer	Pneumatic concentric
Ar plasma flow	12 L/min
Integration time	11 s
Sample rate	1 mL/min

characteristics. It should be noted that the intensity response with respect to the concentration is sigmoid in nature, not linear. Therefore, the calibration curve must be in logarithmic scale to establish the linear dynamic range. Table II summarizes the arc characteristics.

For D.C. arc standard preparation, a master impurity mixture was prepared by grinding the metallic elements, mostly in their oxide form. An intermediate range concentration standard was prepared synthetically by homogeneous mixing of a certain portion of the master impurity mixture, base material (Specpure BeO), and 10% AgCl as the carrier. These two standards were arced for finalizing the pre-burn and exposure time for each analyte and using the experimental procedure adopted earlier for other matrices. A series of five analytical standards were prepared by grinding a mixture of graded portions of the master impurity mixture, 10% AgCl, and the balance amount of base material. A blank standard was also prepared in a similar manner but without any master impurity mixture. Repetitive analyses of all standards using optimized experimental parameters were carried out, and the data obtained were used to get the best fit for the calibration curve for each analytical channel. The data were stored in the computer in the form of a slope, intercept, curvature, and exponent of each analytical curve

TABLE II
D.C. Arc-AES Experimental
Parameters for
Determination of the Analytes

Standard/sample charge on electrode	40 mg
Carrier	10% AgCl
D.C. arc current	12.5 A
Arc gap	4 mm
Pre-burn time	10 sec
Exposure time	30 sec

for subsequent use in the two-point standardization procedure for the analysis of the samples. The intermediate concentration standard was arced repeatedly using optimized parameters to obtain the precision data. Table III summarizes the concentrations of different analytes in the prepared standards.

For optimization of the methodologies, synthetic solid standards were used in D.C. arc carrier distillation and the same standards were used for ICP-AES analysis after dissolution. The detection limits for the analytes in the BeO matrix were calculated based on the expression $\langle x \rangle + 3\sigma$, where, $\langle x \rangle$ is the average of the blank values for replicate measurements, and σ is the standard deviation of that measurement. The slope of the calibration curves were used as the sensitivity, which physically meant the response corresponds to the unit concentration.

RESULTS AND DISCUSSION

Especially in the nuclear industries, each BeO batch has to pass through stringent quality control before being put into the reactor. This is essential not only to achieve the desired performance, but also for safe nuclear operations. Different metallic impurities were found to have detrimental effects in the thermo-physical, mechanical, and chemical properties of BeO. To cite a few examples, certain trace metals with a high neutron absorption cross-section, such as B, Cd, and the rare earth elements Eu, Sm, Gd, and Dy, have to be well below their

maximum permissible concentrations, since the neutron economy is of utmost importance to sustain the nuclear reaction in the reactor in a controllable manner. Refractory elements, i.e., W, Mo, etc., can result in creep resistance (22), while low melting elements, such as Zn, can lead to liquid-metal embrittlement. The presence of common metallic analytes (Fe, Cr, Ni, etc.) cannot only indicate the possibility of process pickup but also can lead to problems during sintering. Thus, the fuel designer has prescribed the limits of tolerance of these analytes for BeO samples, also known as specification limits. As seen from Table IV, the specification limits for B, Cd, and Li were found to be very low. The elements Mn, Cr, and Cu were found to have specification limits below 100 ppm, whereas for Ca, Fe, Mg, Si, Na, Ni, and Zn the specification limits are below 650 ppm. In case of Al, more than 1000 ppm was allowed in the BeO matrix.

The analytical performance of the analytes in d.c. arc carrier distillation and ICP-AES are shown in Table V. The detection limits for ICP-AES were found to be almost an order of magnitude better compared to the D.C. arc carrier distillation technique, which can be attributed to the higher temperature in the analytical zone of the ICP-AES leading to more excitation and emission. The sensitivity for the d.c. arc was also found to be poorer than that of ICP-AES, mainly attributed to the same reason. The linear dynamic range for d.c. arc is also poorer due to the self-absorp-

TABLE III
Concentration of the Analytes in the Standards

Elements	Std. 1	Std. 2	Std. 3 (ppm)	Std. 4	Std. 5
B, Cd, Li	0.1	0.4	1	4	10
Ca, Fe, Mg, Mn, Si, Na, Al, Cr, Cu, Ni, Zn	5	20	50	200	500

TABLE IV
Specification Limits for the Analytes in BeO Matrix

Element	Specification Limit (ppm)
Ca	500
Fe	600
Mg	600
Mn	36
Si	600
Na	360
Li	7
Al	1100
B	1
Cd	1.5
Cr	90
Cu	36
Ni	360

tion caused by the optically non-thin source.

Table VI shows the analytical results for two synthetic samples, one in the lower concentration range and the other in higher concentration range. Both the D.C. arc and the ICP-AES techniques were found to be successful in analyzing the synthetic samples. However, the ICP-AES results were more precise in comparison to the d.c. arc carrier distillation technique. All of the values listed are the average of five replicate measurements and the values were reported based on the 99% confidence interval, i.e., $\sim 3\sigma$, where σ is the relative standard deviation associated with the measurement. It should also be noted that the precision values calculated from the analyses were found to be $\sim 20\%$ for D.C. arc, while $\sim 5\%$ for ICP-AES. Source stability and arc wandering are responsible factors for this difference (as discussed earlier).

Table VII summarizes the comparative characterization of the

TABLE V
Comparative Evaluation of Analytical Performance of D.C. Arc Carrier Distillation and the ICP-AES for BeO Samples

Element	D.C. Arc Carrier Distillation				ICP-AES		
	Anal. Line (nm)	D.L. (ppm)	Sensitivity (counts/ppm)	Linear Dynamic Range (ppm)	D.L. (ppm)	Sensitivity (counts/ppm)	Linear Dynamic Range (ppm)
Ca	396.8	2	7.6	10-400	0.1	41	0.1-500
Fe	261.7	4	8.3	5-450	0.08	32	0.08-500
Mg	280.2	3	11	7-350	0.06	45	0.06-500
Mn	257.6	4	14	5-500	0.05	29	0.05-500
Si	288.1	5	2.9	10-400	0.5	24	0.5-500
Na	588.9	5	4.1	5-450	0.08	39	0.08-500
Li	670.7	0.2	11	0.2-8	0.05	31	0.05-500
Al	308.2	5	14	10-400	0.08	49	0.08-500
B	249.7	0.1	12	0.15-10	0.04	40	0.04-500
Cd	228.8	0.1	9	0.1-10	0.04	38	0.04-500
Cr	357.8	6	8.7	10-350	0.1	28	0.1-500
Cu	324.7	5	10	10-500	0.2	29	0.2-500
Ni	231.6	4	9.1	10-450	0.09	27	0.09-500
Zn	213.8	6	7.7	10-400	0.08	30	0.08-500

Table VI
Comparison of Analytical Results for Synthetic Samples by D.C. Arc and ICP-AES (in ppm)

Element	Actual	D.C. Arc Estimated	ICP-AES Estimated	Actual	D.C. Arc Estimated	ICP-AES Estimated
Ca	20	18 $\pm$ 4	19.5 $\pm$ 0.5	200	220 $\pm$ 31	195 $\pm$ 9
Fe	20	19 $\pm$ 3	20.1 $\pm$ 0.4	200	213 $\pm$ 24	207 $\pm$ 8
Mg	20	22 $\pm$ 4	18.7 $\pm$ 0.7	200	170 $\pm$ 41	192 $\pm$ 8
Mn	20	20 $\pm$ 4	19.0 $\pm$ 0.5	200	250 $\pm$ 40	195 $\pm$ 9
Si	20	19 $\pm$ 3	20.3 $\pm$ 0.5	200	162 $\pm$ 32	201 $\pm$ 10
Na	20	17 $\pm$ 4	19.7 $\pm$ 0.8	200	178 $\pm$ 29	206 $\pm$ 9
Li	0.4	0.29 $\pm$ 0.05	0.37 $\pm$ 0.02	4	4.2 $\pm$ 0.4	3.9 $\pm$ 0.2
Al	20	16 $\pm$ 4	19.4 $\pm$ 0.7	200	233 $\pm$ 38	190 $\pm$ 9
B	0.4	0.50 $\pm$ 0.09	0.41 $\pm$ 0.02	4	3.4 $\pm$ 0.5	4.3 $\pm$ 0.2
Cd	0.4	0.47 $\pm$ 0.09	0.38 $\pm$ 0.01	4	3.8 $\pm$ 0.6	4.0 $\pm$ 0.1
Cr	20	18 $\pm$ 4	21.0 $\pm$ 0.9	200	177 $\pm$ 27	204 $\pm$ 6
Cu	20	22 $\pm$ 4	19.1 $\pm$ 0.5	200	190 $\pm$ 30	197 $\pm$ 8
Ni	20	23 $\pm$ 4	19.6 $\pm$ 0.5	200	220 $\pm$ 25	192 $\pm$ 8
Zn	20	18 $\pm$ 3	20.4 $\pm$ 0.6	200	197 $\pm$ 20	204 $\pm$ 7

actual BeO samples by d.c.arc and ICP-AES. In the first two samples, B and Cd were found to be less than 0.3 ppm, while for the 3rd sample, these two elements are less than 1 ppm. The Li values for these samples are less than 6 ppm. These three elements are described separately, since their specification limits are very low. S1 and S2 were found to be of similar purity. Mg, Mn, Al, Cr, Ni, and Zn were present in the range 10-15 ppm, while Si, Fe, and Ca were present in the range 20-30 ppm. However, S3 was found to have more metallic impurities. Si, Na, and Al were found to be in the range of 150-250 ppm. These three samples were found to have impurities lower than the specification limits of the individual elements as seen from both the D.C. arc and ICP-AES techniques. Apart from the precision, the analytical results from both methods were in good agreement.

CONCLUSION

A comparative evaluation was carried out for the determination of Ca, Fe, Mg, Mn, Si, Na, Li, Al, B, Cd, Cr, Cu, Ni, and Zn at minor and trace level in a nuclear-grade BeO matrix by D.C. arc carrier distillation and ICP-AES. The former method used solid samples and 10% AgCl as the carrier gas to sweep away the analytes into the arc, while the latter method requires dissolution of the samples. The d.c. arc is associated with less sample handling, resulting in less process pickup and less chemical as well as radio-toxic exposure to individuals. However, the linear dynamic range of the d.c.arc is less wide compared to ICP-AES due to the self-absorption phenomena pertaining to the non-optical thin source. The arc wandering and stability of the plasma were found to be responsible for poorer precision in the d.c.arc carrier distillation technique. The analytical results

Element	S1		S2		S3	
	D.C. Arc	ICP	D.C. Arc	ICP	D.C. Arc	ICP
Ca	25±4	26±1	22±3	20±1	60±9	53±2
Fe	32±5	30±1	28±5	23±1	81±9	88±3
Mg	12±2	11.6±0.3	15±3	16±1	47±9	40±2
Mn	10±2	10.4±0.3	10±3	8.4±0.3	25±5	30±1
Si	30±5	25±1	28±4	30±1	154±20	140±8
Na	5.0±0.9	6.1±0.2	4.2±0.7	3.5±0.1	200±31	210±8
Li	4.2±0.7	5.0±0.2	5.1±0.8	4.5±0.2	6±1	5.3±0.3
Al	10±2	9.8±0.3	14±3	13±1	240±30	210±10
B	0.15±0.02	0.11±0.01	0.25±0.05	0.22±0.01	0.80±0.06	0.71±0.02
Cd	0.10±0.02	0.15±0.01	0.2±0.04	0.21±0.01	0.91±0.04	0.87±0.03
Cr	10±2	9.8±0.5	12±3	10±1	73±9	80±3
Cu	5.1±0.8	6.0±0.2	5.9±0.7	6.4±0.2	9.0±1.6	8.5±0.3
Ni	12±3	11±1	10±2	11±1	38±6	33±3
Zn	10±2	8.9±0.3	15±3	13±1	28±4	30±1

obtained from both methods were found to be in good agreement.

ACKNOWLEDGMENT

The authors wish to acknowledge the constant support of Dr. P.K. Pujari, Head, and AD RC & IG, Bhabha Atomic Research Centre, Mumbai, India.

Received July 25, 2019.

REFERENCES

1. A. Sengupta, B. Rajeswari, R. M. Kadam, and S. V. Godbole, *At. Spectrosc.* 33(2), 48 (2012).
2. P.S. Somayajulu, A. Sengupta, A.K. Karande, R. Malav, D.K. Das and Mohd. Afzal, *J. Radioanal. Nucl. Chem.* 308(2), 495 (2016).
3. N. Pathak, V.C. Adya, S.K. Thulasidas, A. Sengupta, T.K. Seshagiri, and S.V. Godbole, *At. Spectrosc.* 35(1), 17 (2014).
4. G. A. Day, A. B. Stefaniak, A. Weston and S. S. Tinkle, *Int. Archives Occupational Environ. Health* 79(2), 161 (2006).
5. T. M. Sabine, A. W. Pryor and B. S.

- Hickman, *Nature* 191, 1385 (1961).
6. O. F. Schirmer, K. A. Müller and J. Schneider, *Physik der kondensierten Materie* 3(4), 323 (1965).
7. I.V. Dulera and R.K. Sinha, *J. Nucl. Matr.* 383(1-2), 183 (2008).
8. W.D. Manly, *J. Nucl. Matr.* 14, 3 (1964).
9. A. Sengupta, V.C. Adya, T.K. Seshagiri, S.K. Thulasidas, S.V. Godbole, and V. Natarajan, *J. Res. Spectrosc.* DOI: 10.5171/2014.757111, 2014, 757111(2014)
10. B. F. Scribner and H. R. Mullin, *J. Res. Nat. Bureau Standards* 37, RPI 753 (1946).
11. T. R. Bangia, V. C. Adya, B. A. Dhawale, B. Rajeswari, M. D. Sasstry and P.R. Natarajan, *Anal. Lett.* 23(1), 147 (1990).
12. N. K. Porwal, A. A. Argekar, P. J. Purohit, A. G. Page and M. D. Sasstry, *Fresenius' J. Anal. Chem.* 338(3), 255 (1990).
13. A. Sengupta, N. K. Gupta and Y. Airan, *At. Spectrosc.* 38(2), 48 (2017).
14. A. Sengupta, Y. Airan, S.K. Thulasidas and V. Natarajan, *At. Spectrosc.* 37(2), 50(2016).

15. P.W.J.M. Boumans, *Anal. Chem.* 66(8), 459 (1994).
16. E.H. van Veen, F.J. Oukes and M.T.C. de Loos-Vollebregt, *Spectrochim. Acta* 45 (10), 1109 (1990).
17. K. Satyanarayana and S. Durani, *J. Radioanal. Nucl. Chem.* 285(3), 659-665 (2010).
18. A. Sengupta, S. K. Thulasidas and V. Natarajan, *J. Radioanal. Nucl. Chem.* 303, 2421 (2015).
19. A. Sengupta, M. J. Kulkarni, S.V. Godbole, V.Natarajan and P.N. Pathak, *At. Spectrosc.* 35(2), 60(2014).
20. J. L. Todolí, L. Gras , V. Hernandis and J. Mora, *J. Anal. At. Spectrom.* 17, 142 (2002).
21. V.C. Adya, A. Sengupta and S.V. Godbole, *At. Spectrosc.* 35(1), 25(2014).
22. V. Venugopal, *Ind. Assoc. Nucl. Chem. Allied Sci. Bull.* 4, 205 (2005).