CLINICAL AND LABORATORY TESTING OF A NEW MODIFICATION OF TWO-LAYER "SILEP" DENTURES USED IN PROSTHETIC DENTISTRY

TIMOSHIN, Anton¹; MITIN, Nikolay²; OLEYNIKOV, Alexander²; TIMOSHINA, Maria¹; MITINA, Evgeniya²

¹ I.M. Sechenov First Moscow State Medical University (Sechenov University)

² Ryazan State Medical University named after academician I.P. Pavlov

* Correspondence author
e-mail: sbjchem@gmail.com

Received 13 March 2020; received in revised form 16 June 2020; accepted 23 June 2020

ABSTRACT

Dentistry is a part of medicine, where various polymer materials were used for the first time. Many factors forced researchers to find more stable, versatile, and hygienic materials for the manufacture of dental products. It is important to note that the search for the ideal polymer dental material is still ongoing. This is because modern polymers, in some cases, do not meet the specified requirements for chemical, physical, strength, and elastic properties. Based on the data on the method of creating and using silicone material for the base of the removable prosthesis "Gossil", an improved silicone material for two-layer dentures "Silep" was developed, as well as a special primer for better connection of the lining with the rigid acrylic base of the prosthesis. To evaluate the most suitable compound, materials were tested for several parameters, such as tensile strength, elongation, and shore hardness. In addition to selecting a suitable material for modification, the selection and testing of an adhesive that allows the chemical bonding of the acrylate surface to the siloxane surface were carried out.

Keywords: *GosSil, Silep, polymeric material, prosthetic dentistry.*

1. INTRODUCTION

Dentistry is a part of medicine, where various polymer materials were used for the first time. One of these materials was rubber, as the most convenient in terms of molding and elastic properties. However, this natural material had significant disadvantages in the form of porosity and chemical instability (Evstratenko *et al.*, 2018; Mazzeo *et al.*, 2013). These and many other factors forced researchers to find more stable, versatile, and hygienic materials for the manufacture of dental products. It is important to note that the search for the ideal polymer dental material is still ongoing.

This is because modern polymers, in some cases, do not meet the specified requirements for chemical, physical, strength, and elastic properties. The first artificial polymer materials appeared in the XIX century.

The chemical structure of acrylates consists of molecules of polymer compounds constructed from repeated links and connected by covalent bonds that form macromolecules (Voloshina *et al.*, 2018; Silva *et al.*, 2019). The chemical formula of acrylate can be represented by the example of methylacrylate (Figure 1) and methyl methacrylate (Figure 2).

Figure 1. The chemical formula of methyl acrylate

Figure 2. The chemical formula of methyl methacrylate

Currently, polymers are used for dental, orthopedic structures that are macromolecules with a molecular weight of several thousand to several million, consisting of two or more different components (Dukić *et al.*, 2013; Vehkalahti *et al.*, 1996).

The synthesis of polymers takes place using a polymerization or polycondensation reaction. The essence of this reaction is that molecules of low-molecular substances that are monomers by nature join the active centers of polymers that are high-molecular substances (Girardin *et al.*, 2019; Timoshin *et al.*, 2018, 2019). In the course of this reaction, the above-mentioned macromolecular links are formed, which differ in composition from the original monomers and are formed by their sequential "cross-linking" with the release of low-molecular-weight by-products (Sevbitov *et al.*, 2018). An example of a polymerization reaction is a reaction from monomers that do not include an aromatic ring. For example, obtaining acrylic or methacrylic acids by polymerization (Figures 3a and 3b).

Figure 3. Polymerization of acrylic acid (A) and methacrylic acid (B)

Knowledge of the physical and chemical nature of polymer synthesis allows us to identify the positive and negative properties of materials-

acrylates used to create acrylic dental plastics.

The positive properties include the existing high modulus of elasticity, which allows some dental polymer materials to have the ability to reverse deformations at a relatively low load, as well as a favorable factor for dental production and operation is the low brittleness of crystalline polymers, which allows dental plastic to withstand chewing load and physical and mechanical impact during processing and fitting (Kolodkina *et al.*, 2018; Gozha *et al.*, 2010).

Positive features of polymer solutions and their chemical nature provide high manipulative qualities in plastic molding and the ability to dramatically change their physical and mechanical properties when using catalysts and initiators (Zholudev *et al.*, 2004, 2005) of the polymerization reaction, which speeds up and simplifies the process of manufacturing orthopedic structures.

Despite the high level of physical and chemical indicators that characterize the resistance of polymers to various destructive factors, for use in dentistry, in particular in dental and maxillofacial prosthetics using partially removable or full removable plate acrylic prostheses, the structure of polymers needs to be embedded in various components (Kasatkina, 2010; Kalyvradzhiyan *et al.*, 2010). This is due to the fact the operation of the polymer prosthesis occurs under constant physical and mechanical stress in an aggressive, constantly changing chemical environment. The combination of these factors actively affects the structure and properties of polymers, causing the so-called "aging" of the prosthesis, in which there is a loss of the complex of useful properties of the product material (Lepilin *et al.*, 2003).

Additional components embedded in the chemical composition of the polymer that improves its natural properties and slows down the process of operational wear include fillers, plasticizers, stabilizers, dyes, cross-agents, etc. (Nartikova *et al.*, 1977; Paschina *et al.*, 1968). The arrangement of additional substances with polymers allows us today to produce bioinert and technological dentures that meet high performance, quality, medical and technical characteristics, aesthetic and functional requirements.

However, despite the fact that modern manufacturing methods allow you to achieve high-quality polymer prosthesis, they are not ideal, and the positive properties have a number of disadvantages. Primary negative qualities of

dental polymers occur already during the polymerization reaction and are characterized by a part of the original monomer that is not embedded in the polymer molecules, which determines the degree of biocompatibility of the material and affects the allergization factors when using a polymer prosthesis (Kuznetsova *et al.*, 2018; Platonova *et al.*, 2018). Another physical and chemical disadvantage of polymers is their water absorption. It can be assumed that this process is associated with the uncompensated polarity of the dipole links of the polymer, which characterizes their hydrophilic properties (Sevbitov *et al.*, 1999; 2004).

From a physical point of view, this property of affinity for water molecules is more obvious because the free hypothetical space in the polymer structure is saturated with water during a prolonged stay in a humid environment (Mamedov *et al.*, 2019; Yumashev *et al.*, 2019). This effect of water absorption adversely affects the geometry of the polymer prosthesis base, as well as its optical and mechanical parameters. To the changes in optical properties, we can also add that in addition to saturation with water, the porous micro-surface of the polymer is able to accumulate molecules of various substances, including those that are dyed by their chemical nature, which leads to a deterioration in the aesthetic properties of the polymer orthopedic product. In addition to physical and chemical changes within the polymer structure, polymer prostheses themselves are a factor of influence, in particular on the surrounding tissue natural formations of the prosthetic bed, which is subjected to mechanical pressure due to a much higher modulus of polymer hardness than that of the oral mucosa.

Long-term use of a removable prosthesis leads to a number of changes in trophic processes, physiology, and microcirculation of the soft tissues of the mucous membrane, as well as the underlying bone tissue of the jaw (Saxena *et al.*, 2019; Rech-Ortega *et al.*, 2019).

The rigidity of the polymeric denture base has a significant impact on the usability of this orthopedic designs, so, if you have to thin of the mucous membrane in the oral cavity, natural and abnormal bony prominences in the area of prosthetic bed dental patients do not have the ability to comfortable use of the prosthesis, are faced with painful sensations and also the difficult phase of adaptation to the prosthesis.

These disadvantages of removable polymer prostheses, in particular those made of acrylates, were a prerequisite for the use of other

polymer compounds that can be used in medicine. The leading factor in the medical scientific and technical search for a suitable material is obtaining the safest, technologically accessible, acceptable material in the manufacture and operation, from which it is possible to create an anatomical orthopedic structure that meets the physiological requirements as much as possible.

It is important to understand that synthetic polymer compounds that do not contain carbon atoms in the main chain are inherently inorganic and foreign to the body (Utyuzh *et al.*, 2019; Mironov *et al.*, 2020). In this regard, when creating dental products made of polymers, it is necessary to observe all the maximum possible technological conditions and physiological restrictions that allow full and effective use of plastic prostheses in the treatment of dental patients without harming them.

Acrylic polymer prostheses containing in their chemical composition acrylic resin, which is a derivative of the product of polymerization of acrylic and methacrylic acids (Enina *et al.*, 2019; Turgaeva *et al.*, 2020), have various restrictions on use. First of all, they are due to the extreme rigidity of this material, which exerts mechanical pressure on the soft tissues of the oral cavity, also included in the composition of acrylate acids, esters and their derivatives with the content of a low-molecular compound (monomer) that is not embedded in the structure can cause an allergic reaction or be intolerant for the patient. An alternative to this group of polymers can serve as other synthetic materials-elastomers, such as silicones, copolymers of polychlorinated vinyl and butylacrylate, nylons, polyoxymethylenes, polypropylene, ethylene-vinyl acetate (Sevbitov *et al.*, 2005; Ergesheva *et al.*, 2018).

These materials are mostly elastic plastics, and this is not provided by the acrylic base of their chemical composition. During prosthetics, orthopedic prostheses made entirely of elastomers, thermoplastic masses, or acrylic prostheses created in combination with elastic-plastic, for example, an acrylic prosthesis with a rubber or polymethylmethacrylate, plasticized with salicylic acid, are the most common (Sevbitov *et al.*, 2018; 2019).

However, early developments on creating two-layer acrylic removable prostheses with lining materials were not widely used in practice. For example, rubber linings in the base of the prosthesis due to the porosity of their structure had a high level of water absorption, quickly polluted, and had low adhesion to acrylates. Polymethylmethacrylates, which are close to them

in chemical nature, had a stronger bond with acrylates, but the content of a low-molecular plasticizer in their composition was actively subjected to washing out, which caused the porosity of the lining, which made the latter hard (Sevbitov *et al.*, 2018; 2019; 2020).

Various other materials, such as PVC, silicone, and others, were used to create linings, but most of these elastomers did not meet the necessary requirements for strength and adhesion to the acrylic base of the prosthesis (Sevbitov *et al.*, 2019; 2020).

The decrease in adhesion, as the most common lack of linings, is due to the fact that the surfaces of the two materials are uneven at the atomic level, and if they come into contact with each other during loading, the contacts will appear only in the places of the largest protrusion, which will lead to frictional wear of the material. Thus, only the densest intermolecular contact of materials of different phases can cause optimal adhesion.

As an alternative to the two-layer bases of removable polymer prostheses, prostheses made of thermoplastic masses can be used. The creation of this material involves the use of biologically neutral thermoplastics with a crystalline linear or branched structure. The characteristic difference from inorganic polymers is that this group of materials does not have a three-dimensional cross-linked structure and contains tertiary carbon atoms (Sevbitov *et al.*, 2018; 2019, 2020).

Another important difference is the ability of the thermoplastic to reversibly transition to a highly elastic or viscous state when the temperature increases, which favorably affects the plasticity and shape change of the material in accordance with the anatomy of the prosthetic bed when using thermoplastic removable prostheses.

The competitive advantage of this material over acrylates is the absence of a monomer, which eliminates the toxic effect on the body and allows the use of thermoplastic prostheses in patients with hyper sensibilization or allergic reactions. This group of materials includes nylon, polypropylene, polyurethane, and others. Thus, removable prostheses made of nylon have high flexibility, allow you to optimize the load on the soft tissues of the prosthetic bed, and are more durable in comparison with acrylic polymer prostheses (Sevbitov *et al.*, 2018; 2019, 2020).

However, this group of materials for the manufacture of dental, orthopedic products has its

own disadvantages, for example, the rapid occurrence of micro-scratches, where a plaque is formed when coloring products are ingested, which reduces the aesthetic appearance of the prosthesis. A more important adverse factor, in this case, is the higher contamination of the micro-rough surface of the prosthesis by microorganisms, which potentially reduces the level of oral hygiene, complicates hygienic measures for cleaning the prosthesis, and creates prerequisites for the development of infectious agents.

Another negative technological property of thermoplastics is the lack of chemical compatibility with acrylic polymer materials. This is reflected in the increased probability of breaking off artificial teeth of the prosthesis, made mainly from acrylic plastics. But, despite these disadvantages, the creation of prostheses made of thermoplastic materials is an actual and promising direction in the development of dental, orthopedic removable prosthetics, which is confirmed by the works of a number of authors of modern research in this area, and indicates that the positive qualities of polymer materials made of thermoplastic offset the negative ones (Sevbitov *et al.*, 2018; 2019, 2020).

In addition to polymer materials for the manufacture of solid bases of orthopedic removable prostheses that do not carry acrylate molecular substances in their structure, the development of the direction of combining acrylate or other materials with materials for linings is also continuing. So, in the last decade, prostheses with pads made of various modern materials have been introduced into clinical practice. Polymer elastic plastics and silicones are used as such linings.

One of the promising developments is the use of silicone material for elastic linings "GosSil". This material is based on monolithic silicon, which in its chemical structure, is an oxygen-containing high-molecular-weight organosilicon compound. The synthesis of this compound is carried out by standard methods of polymer chemistry, including the polymerization reaction. The issue of adhesion to acrylates in this material is resolved by adding a special adhesive that can be chemically bonded to both components in a two-phase connection.

According to the results of the author's research, this material is acceptable and effective in use in combination with the polymer acrylic base of a removable orthopedic prosthesis, since silicone polymers are chemically stable substances and do not undergo destruction in their molecular structure when exposed to a humid environment. The presence of a soft silicone pad

in the prosthesis provides a more reliable fixation of the prosthesis in the oral cavity, precisely corresponds to the anatomical structures, and significantly reduces the pain sensitivity of areas with developed bone formations.

All these indicators may indicate an improvement in the quality of life of patients using this two-phase combination of dental, orthopedic polymer materials.

2. MATERIALS AND METHODS

Based on the above advantages of the silicone lining technology in a removable acrylic orthopedic prosthesis, we give an example of manufacturing and using a soft silicone rubber lining combined with an acrylic prosthesis.

Based on the data on the method of creating and using silicone material for the base of the removable prosthesis "GosSil", an improved silicone material for two-layer dentures "SilEP" was developed, as well as a special primer for better connection of the lining with the rigid acrylic base of the prosthesis.

The essence of this material for creating a lining is that it is created from high-elasticity silicone rubber and is chemically inert. The chemical composition of this polymer is characterized by the fact that it is obtained from organic substances containing silicon, by its nature it is a high-molecular substance: silicone rubber combines the structure of carbon and silicon high-molecular compounds. The chemical formula of this compound is presented below:

Figure 4. Structure of carbon and silicon

where R - is hydrocarbon radicals, for example - CH₃, - C₂H₅. The synthesis of this substance occurs through a polycondensation reaction, and this reaction is shown in Figure 5.

Thus, from a chemical point of view, this polymer is a compound of a linear structure that can combine the property of elasticity with heat resistance, which has found application in clinical practice when creating a lining for a removable denture. From the point of view of the practical

application of this material in an environment with constant mechanical and physical stress, as well as under the action of various chemically aggressive substances, silicone rubber, which is the main component of the material for the elastic lining of "SilEP", provides acceptable results for long-term use in combination with an acrylic denture.

The physical and chemical characteristics of silicone rubber allow us to predict its qualitative state during operation. The most significant characteristics of the material, when used in dentistry, are presented in Table 1.

For the visual application of these values for practical use, you can compare the characteristics of silicone rubber with the characteristics of rubber, which was also used for linings for the basis of a removable prosthesis. The most significant characteristics of the rubber material, when used in dentistry, are presented in Table 2.

Based on these characteristics, we can conclude that the rubber is superior in some respects to those found in silicone rubber, but the most critical indicators for operation in the oral cavity, indicated earlier in the list of disadvantages of pads for the basis of the prosthesis, such as water resistance and tear resistance, are higher in silicones. Thus, silicone rubber, used as a lining for the basis of an orthopedic prosthetic product, is a more suitable polymer material from a practical point of view.

In addition to selecting a suitable polymer material, the necessary criterion for the quality of its use is the selection of the optimal adhesive technology and filler, which allow for reliable "bonding" in the two-phase connection of the surface of the acrylic with the surface of siloxane (silicone). To solve this problem, the filler was chemically modified in the "GosSil" material by treating the surface of the Aerosil with substances that can chemically interact with reactive groups on the surface of the filler. When developing a modification to improve the strength characteristics of a two-phase connection, the creators of the "SilEP" material selected several different compounds:

1. Amyltrimethylchlorosilane
CH₃(CH₂)₄Si(OC₂H₅) (APEC)
2. Chloropropyltrimethoxysilane
Cl(CH₂)₃Si(OCH₃)₃ (HPTMS)

3. Vinyltriethoxysilane
 $\text{CH}_2=\text{CHSi}(\text{OC}_2\text{H}_5)_3$ (VTES)

4. Dimethyldimethoxysilane
 $(\text{CH}_3)_2\text{Si}(\text{OCH}_3)_2$ (DMLS)

To evaluate the most suitable compound, materials were tested for several parameters, such as tensile strength, elongation, and shore hardness. The test results obtained are shown in table 3. In addition to selecting a suitable material for modification, the selection and testing of an adhesive that allows the chemical bonding of the acrylate surface to the siloxane surface were carried out. The following compounds were studied as adhesives:

1. Tetrabutoxide (TBT)
2. Tetraethoxysilane (TEOS)
3. γ -aminopropyltriethoxysilane (as)
4. Vinyltriethoxysilane (VTES)
5. γ -glycidopropyltrimethoxysilane (GTS)
6. The product of the interaction of vinyltriethoxysilane with 1,6 hexamethylene diisocyanate (VHC).

The test evaluated the bond strength of the materials during peeling. The data obtained are presented in the "Results and discussions" in Table 5.

3. RESULTS AND DISCUSSION

The greatest effect in improving the strength characteristics of the resulting vulcanizates is achieved when using vinyltriethoxysilane as a modifier. Based on the research, the authors developed a composition based on siloxane rubber to produce vulcanizates with low hardness and high physical and mechanical properties (utility model patent No. 71249 of 13.06.2007). Thus, the results obtained indicate a high level of strength of the two-phase connection of materials when using vinyl triethoxysilane in the "SilEP" material, which is superior to the "GosSil" material in these indicators. The comparative characteristics of "SilEP" and "GosSil" for these indicators are presented in table 4 below.

Based on the data in table 4, you should pay attention to the index of resistance to tearing,

which is significantly higher in the material "SilEP" in comparison with the material "GosSil". As it was established earlier, siloxanes themselves have a fairly high level of this indicator in comparison with rubber, and the use of a modifier allows you to increase the level of this characteristic almost 4 times in conjunction with a material of another physical and chemical phase, which potentially improves the strength properties of the product created using this technology.

Based on the table 5 data, it is noted that the use of an adhesive (primer) can significantly increase the adhesion of the silicone lining to the acrylate base. In this case, the most effective product in this combination was the interaction of vinyltriethoxysilane with 1,6-hexamethylene diisocyanate. From the point of view of chemical analysis, the obtained high strength of the compound is provided by the presence in VHC of active functional groups that interact with unreacted active groups in the siloxane polymer, the functional groups on the surface of the acrylate react in the same way. It was found that this combination of a primer to improve the connection of the silicone lining "SilEP" with acrylate allows for a 14-fold increase in the degree of adhesion to the base of the denture.

4. CONCLUSIONS

Thus, based on the above review, can conclude that all methods of using polymer compounds in orthopedic dentistry are still relevant, and the development of modern technologies and approaches to dental materials allows us to successfully combine traditional methods of using acrylate polymers with other newer polymers for successful orthopedic treatment.

The most relevant and promising methods are the use of advanced silicone material for two-layer dentures "Silep" as a lining for the acrylic base of the prosthesis, as well as a special primer of vinyltriethoxysilane in combination with 1,6 hexamethylene diisocyanate for better connection of the silicone lining with a rigid acrylic base of the prosthesis.

This composition allows to increase the degree of adhesion to the basis of the denture by 14 times, thereby extending the service life and increasing the comfort of using the denture.

5. ACKNOWLEDGMENTS:

This work was done at Sechenov University with supported by the "Russian Academic Excellence Project 5-100".

6. REFERENCES

1. Evstratenko, V., Sevbitov, A., Platonova, V., Selifanova, E., Dorofeev, A. The characteristics of crystallization of mixed saliva in patients using heroin and methadone. *Klin. Lab. Diagn*, **2018**, 63(4), 223.
2. Mazzeo, M., Linares, J., López, M. Analysis of saliva samples from oncological patients treated with 5-fluorouracil and leucovorin calcium by scanning electron microscopy with energy dispersive system. *J. Oral Pathol. Med*, **2013**, 42(10), 788.
3. Voloshina, I., Borisov, V., Sevbitov, A., Davidiants, A., Mironov, S., Kuznetsova, M., Ergesheva, E. Distinctive features of microcrystallization of mixed saliva in children with different levels of activity of carious process. *Asian J. Pharm*, **2018**, 12(3), S1017.
4. Silva, P., Santos, B., Soares, G. Anti-Candida albicans activity of the association of citronelal with anfotericin B or with cetoconazole. *Periodico Tche Química*, **2019**, 16(31), 223.
5. Dukić, W., Dobrijević, T., Katunarić, M. Caries prevalence in chronic alcoholics and the relationship to salivary flow rate and pH. *Cent. Eur. J. Public Health*, **2013**, 21(1), 43.
6. Vehkalahti, M., Nikula-Sarakorpi, E., Paunio, I. Evaluation of salivary tests and dental status in the prediction of caries increment in caries-susceptible teenagers. *Caries Res*, **1996**, 30(1), 22.
7. Girardin, F., Hearmon, N., Negro, F. Increasing hepatitis C virus screening in people who inject drugs in Switzerland using rapid antibody saliva and dried blood spot testing: A cost-effectiveness analysis. *J. Viral Hepat*, **2019**, 26(2), 236.
8. Timoshin, A., Sevbitov, A., Ergesheva, E., Mironov, S., Kozhemov, S., Pustokhina, I., Danshina, S. Experience in the use of collagen phytoplates in the treatment of gingivitis. *Opcion*, **2019**, 35(21), 582.
9. Timoshin, A., Sevbitov, A., Drobot, G., Yumashev, A., Timoshina, M. Use of bioresorbable plates on the basis of collagen and digestase for treatment of diseases of oral mucosa (review of clinical cases). *Int. J. Green Pharm*, **2018**, 12(1), 290.
10. Sevbitov, A., Dorofeev, A., Davidiants, A., Ershov, K., Timoshin, A. Assessment of pain perception of elderly patients with different levels of dentophobia during surgical dental appointment. *Asian J. Pharm*, **2018**, 12(3), S1012.
11. Timoshin, A., Sevbitov, A., Ergesheva, E., Boichuk, A., Sevbitova, M. Experience of treatment of aphthous lesions of oral mucosa by preparations on the basis of collagen and digestase. *Asian J. Pharm*, **2018**, 12(1), 284.
12. Kolodkina, V., Arutyunov, A., Sirak, S., Andriutsa, N., Tsymbalov, O. Cytological characteristics of oral cavity tissues of experimental animals when using photo polymeric material. *Med. News North Cauc*, **2018**, 13(4), 637.
13. Gozha, L., Talalai, T., Arunov, T. Functional disorders of saliva in toxic-chemical stomatitis caused by metal prostheses. *Dentistry for all*, **2010**, 3, 53.
14. Zholudev, S., Zhmakin, I. Treatment and prevention of prosthetic stomatitis in persons older than 55 years, that use removable plate prostheses. *Dentist*, **2004**, 9, 21.
15. Zholudev, S. Ways to improve the adaptation in people with problems of tolerability of removable denture materials. *Maes. Dent*, **2005**, 19, 5.
16. Kasatkina, E. Iodine deficiency diseases in children and adolescents. *Eligible Doctor*, **2010**, 10, 14.
17. Kalyvradzhiyan, E., Podoprighora, A., Komarova, Yu. Clinical and experimental substantiation of the use of modified adhesive composition based on polysaccharides to improve the period of adaptation to removable denture plate prosthesis. *Modern Orthop. Dentistry*, **2010**, 13, 31.
18. Lepilin, A., Rubin, V., Proshin, N. The effect of removable plate prostheses made of acrylic plastics on the structural and functional properties of the cellular membranes of the oral mucosa. *Stomatology*, **2003**, 1, 51.
19. Nartikova, V., Oglobina, O. Modern methods in biochemistry, M. **1977**.
20. Paschina, T., Egorova, G. Modern methods in biochemistry, M. **1968**.

21. Kuznetsova, M., Nevdakh, A., Platonova, V., Sevbitov, A., Dorofeev, A. Evaluation of effectiveness of a preparation on the basis of phytoecdysteroids for treatment of traumatic injuries of oral mucosa in orthodontic patients. *Int. J. Green Pharm*, **2018**, 12(S1), 297.
22. Platonova, V., Sevbitov, A., Shakaryants, A., Dorofeev, A. Experimental and clinical justification for the treatment of patients with odontogenic phlegmon of the maxillofacial region using dalargin in the complex therapy. *Clin. lab. diagn*, **2018**, 63(5), 293.
23. Sevbitov, A., Persin, L., Slabkobskaia, A., Pankratova, N. The morphological status of the maxillofacial system in children living in an area contaminated by radionuclides as a result of the accident at the chernobyl atomic electric power station. *Stomatologiya*, **1999**, 78(6), 41.
24. Sevbitov, A. V. Remote effects of the Chernobyl accident: evaluation of the maxillofacial status of the children. *Stomatologiya*, **2004**, 83(1), 44.
25. Mamedov, A., Morozova, N., Yumashev, A., Dybov, A., Nikolenko, D. Criteria for provisional restorations used in preparation for comprehensive orthodontic and orthopedic rehabilitation. *Periodico Tche Quimica*, **2019**, 16(32), 647.
26. Yumashev, A., Semenycheva, I., Rakhadilov, B. Development of biocompatible coatings for dental implants based on transition metal nitrides. *J. Global Pharma Technol*, **2019**, 11(5), 22.
27. Yumashev, A., Koneva, E., Borodina, M. Electronic apps in assessing risk and monitoring of patients with arterial hypertension. *Prensa Medica Argentina*, **2019**, 105(4), 235.
28. Saxena, N., Habelitz, S., Marshall, G. Remineralization of demineralized dentin using a dual analog system. *Orthodon. Craniofac. Res*, **2019**, 22(S1), 76.
29. Rech-Ortega, C., Fernández-Estevan, L., Solá-Ruiz, M. Comparative in vitro study of the accuracy of impression techniques for dental implants: Direct technique with an elastomeric impression material versus intraoral scanner. *Med. Oral Patol. Oral Cir. Bucal*, **2019**, 24(1), 89.
30. Utyuzh, A., Nikolenko, D., Yumashev, A., Volchkova, I., Samusenkov, V. Adhesion of periodontal pathogens to materials used for long-term temporary crowns. *Periodico Tche Quimica*, **2019**, 16(33), 60.
31. Sevbitov, A., Kuznetsova, M., Dorofeev, A., Borisov, V., Mironov, S., Iusupova, I. Dental anomalies in people living in radionuclide-contaminated regions. *J. Environ. Radioact*, **2020**, 216, 106190.
32. Sevbitov, A., Davidyants, A., Kuznetsova, M., Dorofeev, A., Mironov, S. Analysis of electronic microscopy results based on combining the infiltration method with different restoration technologies and in vitro investigation of enamel focal demineralization treatment at the defect stage. *Periodico Tche Quimica*, **2019**, 16(33), 53.
33. Sevbitov, A., Brago, A., Enina, Y., Dorofeev, A., Mironov, S. Experience in the application of hybrid ceramic restorations in the cervical region. *Asian J. Pharm*, **2018**, 12(3), S1106.
34. Sevbitov, A., Dorofeev, A., Kuznetsova, M., Timoshin, A., Ershov, K. Comparative characteristics of the crystallogram of the oral fluid in patients who use heroin and methadone. *Periodico Tche Quimica*, **2019**, 16(33), 94.
35. Sevbitov, A., Timoshin, A., Dorofeev, A., Davidyants, A., Ershov, K., Kuznetsova, M. Comparative characteristics of the state of hard dental tissues in drug-dependent patients who use heroin, and methadone as replacement therapy. *Periodico Tche Quimica*, **2020**, 17(34), 135.
36. Sevbitov, A., Ergesheva, E., Sirak, S., Enina, Yu., Mallkov, S., Kuznetsova, M. Clinical and laboratory analysis of the efficiency of hirudotherapy in complex treatment of endodontal diseases. *J. Global Pharma Technol*, **2020**, 12(1), 253.
37. Mironov, S., Emelina, E., Troitskii, V., Yablokova, N., Kuznetsov, I. The Impact of Smoking, Including Hookah, on the Human Body. *J. Global Pharma Technol*, **2020**, 12(1), 211.
38. Enina, Yu., Sevbitov, A., Dorofeev, A., & Pustokhina, I. Experimental substantiation of the choice of the restoration method in the cervical area of teeth with abfraction defects. *Int. J. Mechan. Eng. Technol*, **2019**, 10(5), 41.
39. Sevbitov, A., Mitin, N., Kuznetsova, M., Dorofeev, A., Ershov, K. A new modification of the dental prosthesis in the postoperative restoration of chewing function. *Opcion*, **2020**, 36(S26), 864.
40. Sevbitov, A., Zhadko, S., Dorofeev, A., Ershov, K., Enina, Yu., Pustokhina, I. Rationale for the preservation of vital pulp

- in the use of fixed dentures in the experiment. *Opcion*, **2020**, 36(S26), 953.
41. Sevbitov, A., Danshina, S., Platonova, V., Usatova, G., Borisov, V., Kuznetsova, M. Icon as a method of choice for injectable treatment of initial caries in patients with fibrodysplasia ossificans progressive: a clinical case. *J. Global Pharma Technol*, **2020**, 12(2), 270.
 42. Sevbitov, A., Ershov, K., Dorofeev, A., Borisov, V., Mironov, S., Enina, Yu. Analysis of the quality of life of elderly patients with removable orthopedic constructions during rehabilitation. *Prensa Medica Argentina*, **2020**, 106(4), 226.
 43. Turgaeva, A., Kashirskaya, L., Zurnadzhlyants, Yu., Latysheva, O., Pustokhina, I., Sevbitov, A. Assessment of the financial security of insurance companies in the organization of internal control. *Ent. Sust Issues*, **2020**, 7(3), 2243.
 44. Sevbitov, A., Emelina, G., Kuznetsova, M., Dorofeev, A., Emelina, E. A study of the prevalence of non-carious dental lesions related to production factors in residents of the city of penza. *Georgian Med News*, **2019**, 295, 42.
 45. Sevbitov, A., Borisov, V., Davidyants, A., Timoshin, A., Ershov, K., Enina, Yu., Pustokhina, I. Prevention of injuries of the maxillofacial area in contact sports using sports caps. *Indo Am. J. Pharm. Sci*, **2018**, 5(11), 12322.
 46. Sevbitov, A., Enina, Yu., Dorofeev, A., Kamenskov, P., Kozhemov, S., Nikonova, A. Study of the impact of various abrasive factors on the microrelief of the surface of hybrid ceramic orthopedic structures. *Opcion*, **2019**, 35(S24), 598.
 47. Sevbitov, A., Zhadko, S., Ershov, K., Borisov, V., Mironov, S. Rationale for the use of therapeutic and prophylactic complex to prevent intolerance to acrylates in patients with hyperfunction of the thyroid glands. *Periodico Tche Quimica*, **2019**, 16(33), 266.
 48. Sevbitov, A. Dental characteristics of clinical manifestations of delayed effects of radiation exposure. Abstract of the dissertation for the degree of doctor of medicine. *Central research Institute of dentistry of the Ministry of health of the Russian Federation*. Moscow, **2005**.
 49. Ergesheva, E., Davidiants, A., Dorofeev, A., Sevbitova, M., Timoshina, M. Evaluation of effectiveness of an alternative method in complex treatment of diseases of endodont. *Asian J. Pharm*, **2018**, 12(3), S933.
 50. Sevbitov, A., Kuznetsova, M., Dorofeev, A., Borisov, V., Davidyants, A., Mironov, S., Timoshin, A., Paperno, A., Limonjan V. Introduction to Cariology and Periodontology, **2020**, 120.

Table 1. Physical characteristics of silicone rubber.

Specifications	Values
Density, kg/m ³	960-980
Glass transition temperature, °C	130
Thermal conductivity, W/m.K	1,32
Water resistance, %	<1
Tear resistance, kgf/cm	20

Table 2. Physical characteristics of rubber.

Specifications	Values
Density, kg/m ³	1200
Glass transition temperature, 0°C	73
Thermal conductivity, W/m.K	0,368
Water resistance, %	>1
Tear resistance, kgf/cm	8

Table 3. Influence of the modifier nature on the physical and mechanical properties of vulcanizates.

№	Indicators	Symbol modifier				
		APEC	HPTMS	VTES	DMLS	Unmodified
1	TS ^a (MPa)	4,0±0.2	4,2±0.21	5,6±0.28	3,2±0.16	3,8±0.19
2	Elongation (%)	220±11	360±18	550±27.5	360±18	200±10
3	Hardness ^b	30±1.5	28±1.4	22±1.1	32±1.6	42±2.1

^a Tensile strength

^b by Shore A, conventional unit

Table 4. The physical and mechanical properties of siloxane compositions.

№	Indicators	Method (SS ^c)	Value of the index	
			SiIEP	GosSil
1	CTS ^a (MPa)	270-75	5.6	5.1
2	Elongation at break (%)	270-75	550	436
3	Hardness ^b	263-75	22	32
4	Tear resistance (kN/m)	262-93	31	12
5	Permanent elongation (%)	270-75	3	3.6

^a Conditional Tensile Strength

^b by Shore A, conventional unit

^c State Standard

Table 5. The effect of the primer on the strength of the connection of the "SiIEP" lining with the acrylic base of the prosthesis.

№	Primer	Bond strength during exfoliation (M±m)
1	WP ^a	0.3±0.05
2	TBT	1.3±0.03
3	TEOS	1.8±0.06
4	AS	1.7±0.04
5	VTES	1.3±0.05
6	VHC	4.3±0.04

^a Without a primer

Figure 5. The chemical structure of the synthesized silicone rubber.