CRYOGENIC PROPERTIES OF SILVER

Chart Prepared by:
David R. Smith and F.R. Fickett
National Institute of Standards and
Technology
Boulder, Colorado

Change in Resistivity of Ag, per Atomic Percent of Alloying Element 18° C, nΩ·m/(at.%)							
As	Au	Bi	Cd	Cu	Ga	Ge	Hg
84.6	3.8	73	3.82	0.68	55.2	55.2	7.9
In	Pb	Pd	Pt	Sn	Sn	Ti	Zn
17.8	46.4	4.36	15.9	72.6	43.2	22.7	6.2

J.O. Linde, Annalen der Physik, 5 Folge, 15, 239 (1932)

CONVERSION FACTORS and CONSTANTS			
K	= °C + 273.15	= (°F - 32)/1.8 + 273.15	
1 J	= 0.239 cal	= 9.480 × 10 ⁻⁴ Btu	
1 W/(m·K)	= 2.39 × 10 ⁻³ cal/(s·cm·°C)	= 0.578 Btu/(h·ft·°F)	
1 J/(kg·K)	= 2.39 × 10 ⁻⁴ cal/(g·°C)	= 2.39 × 10 ⁻⁴ Btu/(lb _m ·°F)	
1 m ² /s	= 10 ⁴ cm ² /s	= 10.76 ft ² /s	
1 Pa	= 10 dyne/cm ²	= 1.45 × 10 ⁻⁴ lb _f /in ²	
1 T	= 10 ⁴ G		
μ ₀	= 4π × 10 ⁻⁷ H/m		
1 m ³ /kg	= 79.58 emu/g	(Magnetic Susceptibility)	
1 (SI)	= 7.958 × 10 ⁻² emu/cm ³	(Magnetic Susceptibility)

PHYSICAL and CHEMICAL PROPERTIES of SILVER (Ag; Argentum)			
Atomic Number, Z	47	Melting Point	961.93°C
Atomic Mass, A	107.8682 u	Density (20°C)	10.492 g/cm ³
Isotopes (A = 107)	106.9051 u (51.84%)	(0 K)	10.63 g/cm ³
(A = 109)	108.9048 u (48.16%)	Debye Temperature	215 K (20°C)
Atomic Diameter	0.2883 nm	Thermoelec. pwr.	1.35 μV/K (20°C)
Electron. Structure	[Kr] 4d ¹⁰ 5s ¹	Elec. Resistivity	0.0147 μΩ·m (0°C)
Valence States	1, 2	Elastic Constants (0°C)	C ₁₁ = 131.5 GPa
Crystal Structure	face-centered cubic, Fm3m	C ₁₂ = 97.33 GPa	C ₄₄ = 51.1 GPa
Lattice spacing, a ₀	0.4078 nm (20°C)	Elastic Modulus	78.89 GPa (293 K)
Electrochemical Potential	0.798 V (Ag ⁺ + e ⁻ = Ag)	(0 K)	87.02 GPa
Ionization Potentials	7.574 V (I)	Poisson Ratio	0.37 (293 K)
	21.960 V (II)	Hall Coefficient:	-9.0 × 10 ⁻¹¹ m ³ /(A·s)
	36.10 V (III)	(290 K)	-10.2 × 10 ⁻¹¹ m ³ /(A·s)
Cohesive Energy (25°C)	2.96 eV/atom, 285.8 kJ/mol	Fermi Energy	5.52 eV = 8.84 × 10 ⁻¹⁹ J
Magnetic (mass) Susceptibility	-2.300 × 10 ⁻⁹ m ³ /kg (4.2 K)	Fermi Surface	Spherical, with necks at {111}
	-2.27 × 10 ⁻⁹ m ³ /kg (295 K)		

Constants: u = ¹²C/12 = 1.66 × 10⁻²⁷ kg
 1 eV = 1.602 × 10⁻¹⁹ J
 N_A = 6.023 × 10²³ molecules per mole

PROPERTIES OF CRYOGENIC FLUIDS									
FLUID	Atomic mass u	Liquid at normal b.p.				Vapor at 10 ⁵ Pa (1 atm)			
		Temp. K	Density mol/L	Enthalpy J/mol	Spec. Ht. J/(mol·K)	Temp. K	Density mol/L	Enthalpy J/mol	Spec. Ht. J/(mol·K)
Helium	4.0026	4.227	31.20	-21.0	21.10	4.227	4.226	62	36.73
		20.77				20.77	0.601	419	21.01
		27.09				27.09	0.449	562	20.91
		77.36				77.36	0.157	1609	20.80
		90.20				90.20	0.135	1876	20.79
Hydrogen (para)	2.0159	273.15				273.15	0.045	5679	20.79
		20.77	35.12	-516	19.49	20.77	0.664	382	24.68
		27.09				27.09	0.470	539	22.14
		77.36				77.36	0.158	1632	23.36
		90.20				90.20	0.135	1944	25.38
Neon	20.180	273.15				273.15	0.045	5679	30.36
		27.09	59.71	-1703	36.63	27.09	0.475	527	28.5
		77.36				77.36	0.156	1602	20.9
		90.20				90.20	0.135	1870	20.9
		273.15				273.15	0.045	5678	20.8
Nitrogen	28.134	77.36	28.66	-3401	57.79	77.36	0.165	2164	31.45
		90.20				90.20	0.139	2559	30.43
		273.15				273.15	0.045	7934	29.15
Oxygen	31.999	90.20	35.66	-4263	54.22	90.20	0.140	2535	31.35
		273.15				273.15	0.045	7937	29.33

NIST Standard Database 12: "NIST Thermophysical Properties of Pure Fluids" (Version 3.0), D.G. Friend INIST, Gaithersburg, MD, 1992